Rare-earth-doped Calcium Carbonate exposed to X-ray to induce Reactive Oxygen Species for Tumor Treatment

Chun-Chen Yang^a, Wei-Yun Wang^a, Feng-Huei Lin^{b, c,*}, Chun-Han Hou^{d,*}

- ^a Department of Materials Science and Engineering, National Taiwan University, Taipei 10617, Taiwan
- ^b Institute of Biomedical Engineering, National Taiwan University, Taipei 10617, Taiwan
- ^c Institute of Biomedical Engineering and Nanomedicine, National Health Research Institutes, Miaoli 35053, Taiwan
- ^d Department of Orthopedic Surgery, National Taiwan University, Taipei 10617, Taiwan

Corresponding Author

- * Chun-Han Hou: phone, +886-2-23123456#65274; fax, +886-2-23971266; Email, chhou@ntu.edu.tw.
- * Feng-Huei Lin: phone, +886-2-27327474; fax, +886-2-27327474; Email, double@ntu.edu.tw.

Table S1. CaCO₃:Ce measured by BET.

CaCO ₃ :Ce	BET Surface Area:
	$35.8875\pm0.1818 \text{ m}^2/\text{g}$
	Correlation Coefficient: 0.9999237
	Langmuir Surface Area: 48.6989±0.6808
	m^2/g

Correlation Coefficient: 0.9996093
BJH Adsorption Average Pore Diameter :
1295.3808 Å
BJH Desorption Average Pore Diameter:
1228.4492Å