

Cristina Grijalva


Author: administrator
Creation: 9/13/2017
Sample Name: SN05

Added Spectra

9/13/2017 10:59:59 AM

kV: 15 Mag: 300 Takeoff: 34.8 Live Time(s): 48.3 Amp Time(μs): 7.68 Resolution:(eV)130.4

9/13/2017 10:59:59 AM



Lsec: 48.3 0 Cnts 0.000 keV Det: Octane Super Det

Element	Weight %	Atomic %	Net Int.	Error %
SmL	58.3	34.18	156.02	7.97
FeK	41.7	65.82	206.7	4.66

Cristina Grijalva


Author: administrator
Creation: 9/13/2017
Sample Name: SN05

Added Spectra

9/13/2017 11:06:40 AM

kV: 15 Mag: 300 Takeoff: 34.8 Live Time(s): 48.2 Amp Time(μs): 7.68 Resolution:(eV)130.4

9/13/2017 11:06:40 AM



Lsec: 48.2 0 Cnts 0.000 keV Det: Octane Super Det

Element	Weight %	Atomic %	Net Int.	Error %
SmL	56.65	32.68	153.11	8.03
FeK	43.35	67.32	216.8	4.65

Cristina Grijalva


Author: administrator
Creation: 9/13/2017
Sample Name: SN05

Added Spectra

9/13/2017 11:09:48 AM

kV: 15 Mag: 300 Takeoff: 34.8 Live Time(s): 48.3 Amp Time(μs): 7.68 Resolution:(eV)130.4

9/13/2017 11:09:48 AM



Lsec: 48.3 0 Cnts 0.000 keV Det: Octane Super Det

Element	Weight %	Atomic %	Net Int.	Error %
SmL	57.91	33.82	156.84	8.08
FeK	42.09	66.18	211.13	4.59

Cristina Grijalva


Author: administrator
Creation: 9/13/2017
Sample Name: SN05

Added Spectra

9/13/2017 11:12:57 AM

kV: 15 Mag: 300 Takeoff: 34.8 Live Time(s): 48.1 Amp Time(μs): 7.68 Resolution:(eV)130.4

9/13/2017 11:12:57 AM



Lsec: 48.1 0 Cnts 0.000 keV Det: Octane Super Det

Element	Weight %	Atomic %	Net Int.	Error %
SmL	58.77	34.62	175.68	7.25
FeK	41.23	65.38	228.4	4.54