	5	
Properties	Value	
Standard Filament Size	1.7 dtex	
Standard Cut Lengths	4 mm	
Cross-section	Round	
Luster	Bright, uncrimped	
Specific Gravity	1.53 g/cm <sup>3</sup>	
Whiteness	63 CIE	
Finish level	0.22%	
Dry Tenacity	4.5 - 5.0 g/den	
Elongation at break, dry	24% - 26%	
Wet Tenacity	3.9 - 4.3 g/den	
Elongation at break, wet	16% - 18%	
Degree of polymerization	550 - 600	
Initial Moisture Content	10%	
Dispersibility in water	Very good	

 Table S1.
 Technical data sheet of Lyocell fiber