

Article

Miniaturized Near-Infrared (MicroNIR) Spectrometer in Plastic Waste Sorting

Monika Rani ^{1,2,†}, **Claudio Marchesi** ^{1,2,†}, **Stefania Federici** ^{1,2,*}, **Gianluca Rovelli** ³, **Ivano Alessandri** ^{2,4,5}, **Irene Vassalini** ^{2,4,5}, **Serena Ducoli** ^{2,4}, **Laura Borgese** ^{1,2}, **Annalisa Zacco** ^{1,2}, **Fabjola Bilo** ^{1,2}, **Elza Bontempi** ^{1,2} and **Laura E. Depero** ^{1,2}

¹ Department of Mechanical and Industrial Engineering, University of Brescia, via Branze, 38-25123, Brescia, Italy

² Consorzio Interuniversitario Nazionale per la Scienza e Tecnologia dei Materiali (INSTM), 50121 Firenze, Italy

³ ABCS Srl-Scientific Instruments & Materials Science, viale Regina Giovanna, 37-20129 Milan, Italy

⁴ Department of Information Engineering, University of Brescia, via Branze, 38–25123, Brescia, Italy

⁵ CNR-INO, Unit of Brescia, 25123 Brescia, Italy

† these authors are equally contributed.

* Correspondence: stefania.federici@unibs.it

Supplementary Materials



Figure S1. Systematic organization of the collected urban plastic waste for laboratory measurements.




Figure S2. Error rate as a function of latent variables calculated in the PLS-DA model for HDPE and LDPE classification. 6 LVs is the optimal number.

Table S1. Confusion matrices obtained from PLS-DA model, both in fitting and in cross-validation (based on venetian blinds with 10 groups) restricted to PE class.

Experimental Class	Calculated Class		
	HDPE	LDPE	Not Assigned
Fitting	-	-	-
HDPE	125	0	0
LDPE	0	131	0
Cross-Validation	-	-	-
HDPE	125	0	0
LDPE	0	131	0