
Magnetic Properties and Magnetocaloric Effect in Gd100-xCox Thin Films

Mohamed Tadout, Charles-Henri Lambert, Mohammed Salah El Hadri, Abdelilah Benyoussef, Mohammed Hamedoun, Mohammed Benaissa, Omar Mounkachi and Stephane Mangin

Supplementary information



Supplemental figure 1: XRD patterns of the Gd100-xCox alloys, where x = 52 and 44. Only one broad hump was observed between 30° and 40° 20 on each pattern, which indicates that the studied Gd100-xCox alloys primarily consist of an amorphous phase.