

**Supporting Information for**

**Fluorescence Resonance Energy Transfer Properties  
and Auger Recombination Suppression in  
Supraparticles Self-Assembled from Colloidal  
Quantum Dots**

**Xinhua Tian <sup>1,2,†</sup>, Hao Chang <sup>1,†</sup>, Hongxing Dong <sup>1,3,4,\*</sup>, Chi Zhang <sup>3,5,\*</sup> and Long Zhang <sup>1,2,3,4,\*</sup>**

1 Key Laboratory of Materials for High-Power Laser, Shanghai Institute of Optics and Fine Mechanics,  
Chinese Academy of Sciences, Shanghai 201800, China

2 School of Physical and Technology, ShanghaiTech University, Shanghai 201210, China


3 School of Physics and Optoelectronic Engineering, Hangzhou Institute for Advanced Study,  
University of Chinese Academy of Sciences, Hangzhou 310024, China

4 CAS Center for Excellence in Ultra-intense Laser Science, Shanghai 201800, China

5 Department of Mechanical and Aerospace Engineering, University of Missouri, Columbia, MO 65211, USA

\* Correspondence: hongxingd@siom.ac.cn (H.D.); chizhang@ucas.ac.cn (C.Z.); lzhang@siom.ac.cn (L.Z.)

† These authors contributed equally to this work.



**Figure S1.** High resolution transmission electron microscopy image of SPs.




Figure S2. Fourier transform infrared spectroscopy spectra of OctA-SPs and OA-SPs.

**Table S1** Life decay curve fitting parameters at different wavelengths of 595-620 nm

Wavelength(nm)	A <sub>1</sub> (%)	$\tau_1$ (ps)	A <sub>2</sub> (%)	$\tau_2$ (ps)
595	58.891	52.49663	38.854	308.6004
600	52.399	53.41224	44.405	301.9325
605	45.166	54.65532	50.797	301.9542
610	39.077	57.93251	55.774	315.5416
615	34.66	61.97879	59.648	330.6701
620	33.457	64.7552	61.16	355.4469