

Supplementary Materials

The Effects of Catalyst Support and Temperature on the Hydrotreating of Waste Cooking Oil (WCO) over CoMo Sulfided Catalysts

Hui Wang ^{1,2,*}, Kyle Rogers ², Haiping Zhang ^{2,3}, Guoliang Li ², Jianglong Pu ¹, Haoxuan Zheng ², Hongfei Lin ², Ying Zheng ^{2,4,*} and Siau Ng ⁵

¹ College of Biological, Chemical Sciences and Engineering, Jiaying University, 118 Jiahang Road, Jiaying 314001, China

² Department of Chemical Engineering, University of New Brunswick, 15 Dineen Drive, Fredericton, NB E3B 5A3, Canada

³ Department of Chemical Engineering & Technology, Tianjin University, Tianjin 300072, China

⁴ Department of Chemical and Biochemical Engineering, Western University, 1151 Richmond Street, London, ON N6A 3K7, Canada

⁵ National Centre for Upgrading Technology, Canmet ENERGY-Devon, 1 Oil Patch Drive, Edmonton, AB T9G 1A8, Canada

* Correspondence: huiwang@zjxu.edu.cn or hui.wang@unb.ca (H.W.); ying.zheng@uwo.ca (Y.Z.)




Figure S1. BJH pore size distribution of the supported and unsupported catalyst

Table S1. The amount of active sites on the supported and unsupported catalyst ^[a]

Catalysts	H ₂ consumption		H ₂ S production	
	Temperature (°C)	Amount (mmol g ⁻¹)	Temperature (°C)	Amount (mmol g ⁻¹)
Supported	175-275	0.55	175-610	0.13
Unsupported	230-430	2.56	402-510	1.26

^[a] Calculation based on the first peak