


# Structural insights into new Bi(III) coordination polymers with pyridine-2,3-dicarboxylic acid: Photoluminescence properties and anti-*Helicobacter pylori* activity

**Mateusz Kowalik, Joanna Masternak, Iwona Łakomska, Katarzyna Kazimierczuk,  
Anna Zawilak-Pawlak, Piotr Szczepanowski, Oleksiy V. Khavryuchenko, Barbara  
Barszcz**

**Table S1.** Selected bands of the most important bonds in the FT-IR spectra of pyridine-2,3-dicarboxylic acid and Bi(III) polymers **1** and **2** ( $\text{cm}^{-1}$ ).

Assignments	2,3pydcH <sub>2</sub>	1	2
$\nu(\text{O}-\text{H})_{\text{H}_2\text{O}}$	—	3600–3200 <i>br</i>	—
$\nu(\text{N}-\text{H})_{\text{pyH}}$	3103	—	—
$\nu(\text{N}-\text{H})_{\text{Et}_3\text{NH}}$	—	—	2712, 2511 <i>br</i>
$\nu(\text{C}=\text{O})_{\text{COOH}}$	—	1727	1708
$\nu_{\text{as}}(\text{COO})$	1581	1618, 1574, 1537	1618, 1563
$\nu_{\text{s}}(\text{COO})$	1361	1372	1381, 1369
$\Delta\nu$	220	246, 202, 165	249, 182
$\nu(\text{C}=\text{C}/\text{N})$	1600, 1469, 1408	1605, 1449	1573, 1479, 1441
$\nu(\text{C}-\text{N})_{\text{Et}_3\text{NH}}$	—	—	1272

$\Delta\nu = \nu_{\text{as}}(\text{COO}) - \nu_{\text{s}}(\text{COO})$ ; *br* – broad; pyH – pyridinium cation; Et<sub>3</sub>NH – triethylammonium cation.



**Fig. S1.** The UV-Vis spectrum of the product of the reaction of BiCl<sub>3</sub> with H<sub>2</sub>O in 1M HCl solution.