OPEN ACCESS marine drugs ISSN 1660-3397 www.mdpi.com/journal/marinedrugs

Review

# **Understanding Nanocalcification: A Role Suggested for Crystal Ghosts**

# Ermanno Bonucci

La Sapienza University, Policlinico Umberto I, Viale Regina Elena 324, Rome 00161, Italy; E-Mail: ermanno.bonucci@uniroma1.it; Tel.: +39-064-957-685

Received: 19 June 2014; in revised form: 7 July 2014 / Accepted: 8 July 2014 / Published: 23 July 2014

Abstract: The present survey deals with the initial stage of the calcification process in bone and other hard tissues, with special reference to the organic-inorganic relationship and the transformation that the early inorganic particles undergo as the process moves towards completion. Electron microscope studies clearly exclude the possibility that these particles might be crystalline structures, as often believed, by showing that they are, instead, organic-inorganic hybrids, each comprising a filamentous organic component (the crystal ghost) made up of acidic proteins. The hypothesis is suggested that the crystal ghosts bind and stabilize amorphous calcium phosphate and that their subsequent degradation allows the calcium phosphate, once released, to acquire a hydroxyapatite, crystal-like organization. A conclusive view of the mechanism of biological calcification cannot yet be proposed; even so, however, the role of crystal ghosts as a template of the structures usually called "crystallites" is a concept that has gathered increasing support and can no longer be disregarded.

**Keywords:** biomineralization; bone; calcification; crystal ghosts; crystallites; electron microscopy; organic-inorganic relationships; templates

## 1. Introduction

In the course of 1926, using X-ray diffraction, De Jong [1] showed that the inorganic fraction of bone consists of very small particles, whose diffractograms are similar to those of poorly crystalline carbonated apatite. These findings were confirmed a few years later by Roseberry *et al.* [2] and subsequently by a number of investigators using the same or different physical techniques in a number of hard tissues. In addition, studies with the polarizing microscope suggested that, in accordance with

Wiener's law, the inorganic particles in bone are structured like rods [3], and the electron microscope confirmed that they are needle- or platelet-like nanostructures [4,5]. Similar results were drawn from studies on other calcified tissues of both terrestrial and marine vertebrates, such as epiphyseal cartilage, dentine and enamel, and were extended to invertebrates, whose shells and spicules consist of aragonite and calcite plates (reviewed by [6]). These and other observations led to the conclusion that the inorganic structures of vertebrate hard tissues are rod-, needle- or platelet-like nanoparticles consisting of polycrystalline hydroxyapatite; they therefore came to be called "crystals" or "crystallites" and were thought to respond to the rules of mineralogy, although, as stressed by Arnott and Pautard [7], there were no proofs that, in developing bone, any portion of the area where they occur is specifically crystalline.

The conviction that the inorganic structures of bone are "crystals" led to attempts to explain their formation and properties according to the rules of mineralogy. On the other hand, there has been an increasing awareness that the biomineralization process occurs in the context of an organic matrix and that this plays a conditioning role in mineralization, by promoting or by inhibiting the deposition of the inorganic substance. A number of theories based on prevalently mineralogical or on prevalently biological concepts have therefore been put forward; in neither case has any definitive explanation of the mechanism of biomineralization emerged. As a result, the whole topic is still widely debated.

The main obstacle to finding a definitive solution to the controversial issue of the mechanism of biomineralization seems to be the widespread, deeply rooted conviction that, first, the inorganic substance has, from the outset, a crystalline organization, which then persists unchanged until the tissue is eventually reabsorbed, whereas the actual evidence is that the earliest mineral particles are non-crystalline; second, that the bone "crystals" (the terms "crystal" and "crystallite", as well as "mineralization" and "biomineralization" are retained here from force of habit) are considered stable, permanent structures, when they actually undergo deep, although poorly known, changes during their lifespan. These are not only the well-known changes in crystal chemistry that occur during the aging of animals, as already described for bone by Posner et al. [8] in 1965 and then confirmed by X-ray diffraction in the same type of tissue [9–12], as well as by nuclear magnetic resonance in bone and enamel [13], but also other structural modifications that take place as the earliest inorganic particles evolve into the definitive needle-shaped, crystal-like structures. These changes imply the acquisition of a more apatite-like configuration and a higher degree of crystallinity [9,12,14], which, in turn, imply an increase in crystallite size, an attenuation in lattice imperfections, or both [14]. They take the form of a sort of crystal "maturation" that is usually overlooked, although it cannot be ignored without damaging our understanding of the mechanism of calcification.

#### 1.1. "Maturation" of Crystals

Morphological studies carried out on both marine and terrestrial organisms have shown that the earliest inorganic particles are non-crystalline and that they undergo a sort of maturation that gradually leads to their becoming hydroxyapatite-like structures. As early as 1977, X-ray studies on oriented bone sections by Wheeler and Lewis [15] had shown that bone apatite has a paracrystalline structure (*i.e.*, no long range order). Electron diffraction studies on different types of hard tissue (bone, dentine, enamel) confirmed that the crystallites that are formed at an early stage have a paracrystalline

character comparable to that of biopolymers and that the lattice fluctuations decrease with age and maturation, so allowing the acquisition of a typical crystalline organization [16]. In dentine, the fluctuation of the lattice plane distances in the c-axis direction decreases in proceeding from the region near the dentine/predentine border to the dentine/enamel border [17]. In line with these observations, Landis and Glimcher [18] reported that no electron diffraction pattern of a specific calcium phosphate solid phase is generated from the early mineral deposits of newly synthesized bone, whereas the more heavily calcified, older regions of the bone show the reflections and characteristics of poorly crystalline hydroxyapatite. These results are in agreement with the finding that the Ca/P molar ratio changes with the age of the crystals: Wergedal and Baylink [19] found that the earliest mineral deposits (*i.e.*, calcification nodules) in osteoid tissue have a mean Ca/P ratio value of 1.35, which increases to 1.60 in the fully-calcified areas; in the same areas, Landis and Glimcher [18] reported ratio ranges of 1.60–1.70 and 1.81–1.97, respectively.

An evident example of "crystal maturation" is given by enamel formation (reviewed by Nanci, [20]). The earliest enamel crystals are thin, very long, filament- and ribbon-like structures, which reveal a poor hydroxyapatite electron diffraction and whose electron probe analysis shows a low Ca/P molar ratio (mean value: 1.24 [21]). It is only through a process of "maturation" that enamel crystals acquire their typical hexagonal shape, a Ca/P molar ratio of about 1.40 and give hydroxyapatite electron diffractograms. Several reports pointed to the early enamel mineral as being amorphous calcium phosphate (ACP) that later fuses to become hydroxyapatite [22–24], and the same results were reported by Mahamid *et al.* [25] in bones of zebrafish. In addition, Beniash *et al.* [22] made the interesting observation that the size, shape and spatial organization of the early, non-crystalline mineral particles are essentially the same as those of the older crystals; they suggested that the mineral morphology and organization are determined prior to the formation of definitive crystalline structures. This topic was considered also by Simmer *et al.* [24], who agreed that the early enamel consists of non-crystalline ACP and that the mineral in the early enamel ribbons is not yet crystalline and has no shape of its own.

The existence of a phase of maturation, which leads to the gradual development of apatite-like crystals, implies that studies on the mechanism of biomineralization cannot be carried out on the bulk of mature hard tissue, but must be concentrated on the inorganic structures that are formed early and on their evolution.

#### 1.2. Early Inorganic Structures

The early inorganic structures of vertebrate hard tissues show various aggregation states that can be recognized under the electron microscope: whether in bone, dentin or cartilage, the early recognizable mineralized areas correspond to the so-called "calcification nodules", which are small, roundish aggregates of filament-like crystallites (Figure 1). In bone, especially compact secondary bone, the inorganic substance shows, in addition, a unique relationship with the periodic banding of the collagen fibrils, whose pattern is reinforced, leading to the ultrastructural picture known as "mineral substance in bands". In enamel, the early ribbon- and filament-like crystals are oriented almost perpendicularly to the ameloblast plasma membrane and are organized into rod and inter-rod structures. In spite of the different arrangements that are found in different tissues, at the outset, the single crystal units are all

rather similar: they are long (or very long, in the case of enamel), thin nanostructures (thickness ranging from 1.0 to 7.7 nm in bone and around 1.5 nm in immature enamel [6]) that are usually compared to needles or rods, or threads and ribbons in enamel, but should, rather, be considered filamentous structures, because of their frequently bent and winding appearance (Figure 2). Only with maturation do they increase in size, acquire a more definite pattern, similar to rigid, inorganic structures, and, as discussed above, give the diffraction pattern of hydroxyapatite. They develop in an organic matrix and, therefore, maintain a close relationship with the organic components.

**Figure 1.** An area of early calcification in bone: the calcification nodules consist of roundish aggregates of filament-like, intrinsically electron-dense structures. Unstained,  $\times$ 90,000. Scale bar: 0.9 mm = 0.1 µm.



Figure 2. Detail of the inorganic structures that are components of the calcification nodules in bone; note that they have a filament-like appearance. Unstained,  $\times 220,000$ . Scale bar: 22 mm = 0.1  $\mu$ m.



#### 1.3. Organic-Inorganic Relationships

A number of investigations have been carried out in marine and terrestrial organisms to establish the location of the crystals in bone and their relationships with organic structures. The excessive importance attached to collagen fibrils as being responsible for the heterogeneous nucleation of bone crystals and the finding of the "mineral substance in bands" that reinforces the collagen period favored the idea that the bone crystals are nucleated in the hole zone of the collagen fibrils and that they therefore come to be located within the fibrils [26]. It is now clear that the inorganic substance in bone is organized in two different, relatively independent patterns, corresponding in the first case to the "mineral substance in bands", which is actually contained in the hole zones of the collagen fibrils, and in the second to the filament-like crystals, which are located in the extrafibrillar space [27,28]. This double organization is recognizable in bone, but is hard to identify in dentin, where filament-like crystals predominate; it is completely absent in cartilage and enamel, where only filament-like crystals are recognizable.

The mineral substance in bands and the filament-like crystals may basically be formed through the same process, the differences in mineral organization being exclusively due to the structure (collagenous or not) of the matrix (discussed by Bonucci [28]). The crystals located in the extrafibrillar space are obviously in contact with non-collagenous components of the organic matrix; the recognition of the ultrastructural relationships between organic and inorganic components is, however, a demanding task, not only because of the heterogeneity of the former, but also, and primarily, because of the masking effect of the latter. The inorganic substance is, in fact, electron-dense, and this fact makes it difficult (or impossible) to distinguish it from the organic structures with which it is associated. The practical consequence is that the electron microscope study of the organic components of the calcified matrix requires their unmasking by decalcification.

#### 1.4. Decalcification Procedures

The removal of the inorganic substance by decalcification is not without consequences on the components of the organic matrix and may be responsible for a number of artifacts. Two methods can be used to avoid them or to keep them to a minimum and to preserve the ultrastructural morphology of the decalcified tissue: the PEDS (post-embedding decalcification and staining) method and the CDS (cationic dye stabilization) method.

The PEDS method implies that the decalcification is carried out after the tissue has been embedded in a resin, either by flotation of the ultrathin sections on, or the soaking of whole embedded specimens in, the decalcified solution, followed by "staining" with a heavy metal [29,30]. In both cases, the embedding resin stabilizes the organic components, which are retained unaltered in the sections in spite of the complete removal of inorganic substance (discussed by [29]). The CDS method is based on the stabilization of anionic molecules by cationic dyes (Alcian blue, acridine orange, cupromeronic blue, *etc.*) that are added to the fixative solutions [31]. The PEDS method gives the best results: the ultrastructure of the sections decalcified and stained with this method is practically indistinguishable from that of a non-decalcified section. Surprisingly, this similarity also applies to the areas of initial calcification: in spite of the decalcification procedure, the previously calcified areas (which appear as empty areas after decalcification alone, *i.e.*, after the first PEDS step) appear electron-dense after the whole PEDS procedure (decalcification and staining; Figure 3). This finding was initially interpreted as being due to the persistence of inorganic crystals, because of the failure of the decalcification process; it is actually due to the deep staining of decalcified, crystal-like, organic structures that were previously masked by the inorganic substance (Figure 4). This result is common to the calcification nodules of bone, dentin, cartilage and, again, to the early, immature enamel, but is particularly conspicuous in calcifying cartilage: the aggregates of filament-like inorganic crystals are replaced by aggregates of filament-like organic structures (crystal ghosts [29]). In contrast, the fully-calcified matrix appears faintly stained and has an amorphous appearance.

**Figure 3.** A series of three sections of the same area of epiphyseal cartilage, showing: (A) a zone of early calcification (untreated; the calcified matrix is electron-dense); (B) a corresponding area after decalcification (decalcified with formic acid and unstained; the previously calcified area is electron-transparent); and (C) another corresponding area after decalcification and staining (decalcified with formic acid and stained with uranium and lead; the previously calcified area is electron-dense; compare with Figure 3A). Post-embedding decalcification and staining (PEDS) method, ×16,000. Scale bar: 16 mm = 1  $\mu$ m.



### 1.5. Crystal Ghosts

Crystal ghosts are organic, filament-like structures that become manifest under the electron microscope when the early calcification areas (calcification nodules) are treated with the PEDS method, *i.e.*, are decalcified after embedding and are then "stained" with uranyl acetate and lead citrate (Figure 4), phosphotungstic acid or other heavy metals (reviewed by [32]). Their name derives from their only becoming manifest when the inorganic crystals are dissolved by decalcification and, above all, from their close morphological similarity with untreated crystals. Structures analogous to crystal ghosts are shown by the CDS method (Figure 5).

**Figure 4.** Area of early cartilage calcification after treatment with the PEDS method: the calcification nodules are replaced by similar aggregates of crystal ghosts. Decalcified with formic acid and stained with uranium and lead,  $\times 80,000$ . Scale bar: 8 mm = 0.1 µm.



Most of the studies on the relationship between the organic and inorganic components during the early stages of calcification have been carried out in calcifying cartilage (reviewed by [33]); however, crystal ghosts have also been recognized in bone [34], dentin [35,36] and enamel [37–41], as well as in non-skeletal tissues [42,43]. The crystal ghosts of the cartilage, which can be considered paradigms of the crystal ghosts in all other hard tissues, are thin (mean: 9 nm), straight or, more often, irregularly wavy structures of variable length; those of early enamel differ above all in their length, which is hard to measure, but in any case considerable (reviewed by [6]). The crystal ghosts have no intrinsic electron-density and become recognizable under the electron microscope only after their staining with heavy metals. Before further considering these structures and in view of the role that they may play in the mineralization process, it is mandatory to exclude any possible artifact that might affect their nature.

First, the similarity of crystal ghosts with untreated crystals is so close, that it might be thought that they are just residual crystals left in the sections, because of incomplete decalcification. This possibility can easily be excluded: the decalcification of ultrathin sections is easy and rapid, even by simple flotation of sections on distilled water [44]; moreover, direct electron microscope examination (Figure 3B) and the electron diffraction of the decalcified areas [37] both confirm the complete dissolution of the inorganic substance.

**Figure 5.** Area of early cartilage calcification after treatment with the cationic dye stabilization (CDS) method: the calcification nodules are replaced by similar aggregates of filament-like structures resembling crystal ghosts. Glutaraldehyde-acridine orange fixation, EDTA decalcification, ruthenium red staining,  $\times 24,000$ . Scale bar: 24 mm = 1  $\mu$ m.



Second, one possibility that has been put forward is that crystal ghosts may be produced by stain penetration in holes left in the section when crystallites have been extracted [45]. This hypothesis is in conflict with the observation that crystal ghosts are recognizable in sections that were re-embedded after decalcification, so much so, that every space produced and left by decalcification should have been occluded. Moreover, structures similar to crystal ghosts can be demonstrated using the CDS method in which, as reported above, decalcification occurs before embedding.

Third, adsorption of organic material on the crystal surface during the fixation procedure has been considered a possible cause of the formation of crystal ghosts. However, the thickness of the crystal ghosts in cartilage is approximately the same as that of untreated crystals, whereas it would inevitably be greater if they were located around the latter; moreover, on accepting the envelope hypothesis, their cross-section should display them as rings, whereas the image that appears shows them as small dots.

Fourth, the concept that crystal ghosts are organic components of crystals has been considered to be inconsistent, because crystals cannot accommodate proteins, and these are not compatible with the crystal structure [46,47]. This view derives from the deep-rooted opinion that the inorganic structures of hard tissues are true crystals and that, as such, they must be strictly adherent to the laws of mineralogy. As discussed above, the nanostructures that give rise to calcification nodules and that are called "crystals" are not true crystals, do not give crystalline electron diffractograms and only become

crystalline with aging and maturation; it should also be noted that they have these properties just because of their link with crystal ghosts. It must be added, anyway, that the location of organic material in the crystals is not necessarily in contrast with their organization: intracrystalline organic material has been reported several times in biological hard tissues, and it can even strengthen the mechanical properties of crystals [48–52].

The considerations set out above point to crystal ghosts as being true organic components of early crystals; histochemical investigations confirm their organic nature. The crystal ghosts of cartilage are, in fact, stained by acidic phosphotungstic acid, periodic acid-silver methenamine and periodic acid thiosemicarbazide-osmium and are reactive with cations and with colloidal iron at pH 2.0, but become unreactive after methylation and saponification [53]. These results point to crystal ghosts in cartilage as pertaining to, or deriving from, acid proteoglycans, a conclusion strengthened by the observation that they react with CS-56, an antibody specific to the glycosaminoglycan portion of chondroitin sulfate [54]. Results reported by Appleton [55] and Davis *et al.* [56] also point to cartilage crystal ghosts as protein-carbohydrate complexes. Studies of early mantle dentin with soybean agglutinin-gold complexes [36] and with cetylpyridinium chloride-glutaraldehyde as a fixative [57] have shown filament- and needle-like structures similar to crystal ghosts reacting as proteoglycans. Similar results have been reported in bone [58] and in developing enamel [59].

Independently of their structure and composition, crystal ghosts are components of the organic matrix and must therefore pre-exist before the matrix begins to calcify. In this connection, the incubation of epiphyseal cartilage in lanthanum chloride shows in the still uncalcified matrix "focal filament aggregates", which have a close resemblance with aggregates of crystal ghosts [60]. The reaction with lanthanum seems to reveal the same sites as those that react with calcium ions.

#### 1.6. Supposed Function of Crystal Ghosts

The striking similarity between crystal ghosts and untreated early crystals leads to the supposition, first, that they are different morphological expressions of the same nanostructures or, in other words, that the early crystals are organic-inorganic, hybrid structures and, second, that their organic component functions as a reacting substrate that links the inorganic ions and behaves as a template: the filament-like shape of the crystals would then simply reflect the filament-like shape of the organic substrate. This shape is shared with the crystal ghosts of all vertebrate hard tissues; there are, however, ultrastructural differences (for instance, the crystal ghosts in enamel are much longer than those in bone and in cartilage), suggesting that molecules sharing the same general properties, but having a different composition, may be active in different tissues. The histochemical results show that crystal ghosts correspond to polymeric anionic molecules, which include the acid proteoglycans of epiphyseal cartilage, the phosphoproteins of dentin and the acidic glycoproteins of bone and enamel.

A number of reports have stressed the primary role that acidic molecules can play in the calcification of vertebrates and invertebrates [48,61–68]: they are generally thought to play a role in the nucleation process of hydroxyapatite (see [69]) and to control mineral formation and growth, not only through their high calcium ion binding capacity, but also by interacting with specific faces of crystals and by permitting or preventing their growth [70,71]. The finding of crystal ghosts as components of the early crystals suggests that their function is, rather (or in addition to), that of

templates that link and stabilize mineral ions, giving rise to the early organic-inorganic structures and forcing them to acquire a filament-like shape. This would, incidentally, explain the observation of Beniash *et al.* [22] and Simmer *et al.* [24] (reported above) that the mineral morphology of enamel is determined prior to the formation of definitive crystalline structures. It also appears to be in line with the finding of Fang *et al.* [72] that the native and recombinant porcine amelogenins, P173 and rP172, stabilize initial mineral clusters and that, more importantly, rP172 regulates the organization of initial mineral clusters into linear chains. This suggested mechanism does not exclude other substances from playing a role in biocalcification: hydroxyapatite can be grown in gelatin [73], as well as in collagen type I fibrils [74]. Biomineralization is a complex process than may include complementary mechanisms.

The formation of the organic-inorganic, crystal-like, hybrid structures would function as an initial phase of the biocalcification process. As discussed above, a second, often neglected phase appears to follow, leading to the "maturation" of the crystals and to the removal of all crystal ghosts. This is documented by the fact that crystal ghosts become unrecognizable under the electron microscope as the degree of calcification rises: they do, in fact, gradually disappear from the central zone of the calcification nodules, where the calcification process is completed and is at its highest, final degree, and only remain recognizable at the periphery of the nodules, where the formation of crystals continues (Figure 6; see also [56]). At the same time, the Ca/P ratio increases in the central area of the nodules, and the electron diffractograms acquire the reflections and characteristics of poorly crystalline hydroxyapatite.

**Figure 6.** Cartilage calcification nodules after treatment with the PEDS method: crystal ghosts are recognizable at the border of the nodules, whose central zone appears empty. Formic acid-uranyl acetate and lead citrate,  $\times 75,000$ . Scale bar: 7.5 mm = 0.1  $\mu$ m.



The disappearance of crystal ghosts implies their proteolysis. Actually, the loss of organic material has often been described during calcification. It typically occurs in enamel (reviewed by [75]), whose protein content falls from an initial value of 15%–20% by weight in immature enamel to 0.1% or less in the most mature enamel [76]. Proteolysis also occurs in bone, where a dramatic decrease

in non-collagenous nitrogen takes place as incompletely calcified osteons reach the highest degree of calcification [77], and in epiphyseal cartilage, which loses about half of its content of proteoglycans [78] and 0.3% of sulfur [79] and whose proteoglycan aggregates undergo partial disaggregation and degradation and decrease in size during calcification [80–83].

The removal of the organic component from the early calcified particles may permit the amorphous inorganic substance, previously stabilized by crystal ghosts, to acquire an organized crystalline pattern. In this connection, it is of interest that a transient precursor phase has been described both in vertebrate and invertebrate hard tissues; this phase consists of amorphous calcium phosphate or carbonate and is stabilized by proteic molecules before becoming transformed into a crystalline phase [22,84–89]. *In vitro* surface-induced formation of apatite from simulated body fluid shows that the aggregation of prenucleation clusters leading to the nucleation of ACP precedes the development of oriented apatite crystals [90]. The removal of the organic stabilization molecules might be the factor that triggers the phase transformation. The proteolytic processing of P173 (full-length phosphorylated amelogenin) is required, for instance, to induce the transformation of amorphous calcium phosphate into apatitic enamel crystals, according to Kwak *et al.* [91].

## 2. Conclusions

An attempt to provide a definitive explanation of the mechanism of biological calcification would still be premature. An outline of the early phases of the calcification process should, in any case, include the crucial role of crystal ghosts as acidic organic molecules that link inorganic ions and give rise to organic-inorganic hybrids, whose organic constituent is subsequently removed, so allowing the inorganic component to acquire a crystalline organization.

# **Conflicts of Interest**

The authors declare no conflict of interest.

# References

- 1. De Jong, W.F. La substance minérale dans les os. Rec. Trav. Chim. 1926, 45, 445-446.
- Roseberry, H.H.; Hastings, A.B.; Morse, J.K. X-ray analysis of bone and teeth. J. Biol. Chem. 1931, 90, 335–407.
- 3. Ascenzi, A.; Bonucci, E. A quantitative investigation of the birefringence of the osteon. *Acta Anat.* **1961**, *44*, 236–262.
- 4. Ascenzi, A.; Bonucci, E.; Bocciarelli, S.D. An electron microscope study of osteon calcification. *J. Ultrastruct. Res.* **1965**, *12*, 287–303.
- 5. Ascenzi, A.; Bonucci, E.; Bocciarelli, S.D. An electron microscope study on primary periosteal bone. *J. Ultrastruct. Res.* **1967**, *18*, 605–618.
- 6. Bonucci, E. Biological calcification. In *Normal and Pathological Processes in the Early Stages*; Springer-Verlag: Berlin, Heidelberg, Germany, 2007.
- 7. Arnott, H.J.; Pautard, F.G.E. Osteoblast function and fine structure. *Israel J. Med. Sci.* 1967, *3*, 657–670.

- 8. Posner, A.S.; Harper, R.A.; Muller, S.A.; Menczel, J. Age changes in the crystal chemistry of bone apatite. *Ann. N. Y. Acad. Sci.* **1965**, *131*, 737–742.
- Bonar, L.C.; Roufosse, A.H.; Sabine, W.K.; Grynpas, M.D.; Glimcher, M.J. X-ray diffraction studies of the crystallinity of bone mineral in newly synthesized and density fractionated bone. *Calcif. Tissue Int.* 1983, 35, 202–209.
- 10. Burnell, J.M.; Teubner, E.J.; Miller, A.G. Normal maturation changes in bone matrix, mineral, and crystal size in the rat. *Calcif. Tissue Int.* **1980**, *31*, 13–19.
- 11. Legros, R.; Balmain, N.; Bonel, G. Age-related changes in mineral of rat and bovine cortical bone. *Calcif. Tissue Int.* **1987**, *41*, 137–144.
- 12. Smith, C.B.; Smith, D.A. An X-ray diffraction investigation of age-related changes in the crystal structure of bone apatite. *Calcif. Tissue Res.* **1976**, *22*, 219–226.
- Wu, Y.; Ackerman, J.L.; Kim, H.-M.; Rey, C.; Barroug, A.; Glimcher, M.J. Nuclear magnetic resonance spin-spin relaxation of the crystals of bone, dental enamel, and synthetic hydroxyapatites. *J. Bone Miner. Res.* 2002, *17*, 472–480.
- 14. Matsushima, N.; Hikichi, K. Age changes in the crystallinity of bone mineral and in the disorder of its crystal. *Biochim. Biophys. Acta* **1989**, *992*, 155–159.
- 15. Wheeler, E.J.; Lewis, D. An X-ray study of the paracrystalline nature of bone apatite. *Calcif. Tissue Res.* **1977**, *24*, 243–248.
- 16. Arnold, S.; Plate, U.; Wiesmann, H.P.; Stratmann, U.; Kohl, H.; Höhling, H.J. Quantitative analyses of the biomineralization of different hard tissues. *J. Microsc.* **2001**, *202*, 488–494.
- Arnold, S.; Plate, U.; Wiesmann, H.P.; Stratmann, U.; Kohl, H.; Höhling, H.J. Quantitative electron spectroscopic diffraction analyses of the crystal formation in dentine. *J. Microsc.* 1999, 195, 58–63.
- 18. Landis, W.J.; Glimcher, M.J. Electron diffraction and electron probe microanalysis of the mineral phase of bone tissue prepared by anhydrous techniques. *J. Ultrastruct. Res.* **1978**, *63*, 188–223.
- 19. Wergedal, J.E.; Baylink, D.J. Electron microprobe measurements of bone mineralization rate *in vivo. Am. J. Physiol.* **1974**, *226*, 345–352.
- 20. Nanci, A. Ten Cate's Oral Histology: Development, Structure, and Function, 6th ed.; Mosby: St. Louis, MO, USA, 2003.
- Landis, W.J.; Burke, G.Y.; Neuringer, J.R.; Paine, M.C.; Nanci, A.; Bai, P.; Warshawsky, H. Earliest enamel deposits of the rat incisor examined by electron microscopy, electron diffraction, and electron probe microanalysis. *Anat. Record* 1988, 220, 233–238.
- 22. Beniash, E.; Metzler, R.A.; Lam, R.S.; Gilbert, P.U. Transient amorphous calcium phosphate in forming enamel. *J. Struct. Biol.* **2009**, *166*, 133–143.
- Diekwisch, T.G.H. Subunit compartments of secretory stage enamel matrix. *Connect. Tissue Res.* 1998, 38, 101–111.
- 24. Simmer, J.P.; Richardson, A.S.; Hu, Y.Y.; Smith, C.E.; Ching-Chun Hu, J. A post-classical theory of enamel biomineralization and why we need one. *Int. J. Oral. Sci.* **2012**, *4*, 129–134.
- Mahamid, J.; Sharir, A.; Addadi, L.; Weiner, S. Amorphous calcium phosphate is a major component of the forming fin bones of zebrafish: Indications for an amorphous precursor phase. *Proc. Natl. Acad. Sci. USA* 2008, 105, 12748–12753.

- Glimcher, M.J. The nature of the mineral component of bone and the mechanism of calcification. In *Disorders of Bone and Mineral Metabolism*; Coe, F.L., Favus, M.J., Eds.; Raven Press: New York, NY, USA, 1992; pp. 265–286.
- 27. Bonucci, E. Bone mineralization. Front. Biosci. 2012, 17, 100-128.
- 28. Bonucci, E. The mineralization of bone and its analogies with other hard tissues. In *Advanced Topics in Crystal Growth*; Ferreira, S.O., Ed.; InTech: Rijeka, Croazia, 2013; pp. 145–184.
- 29. Bonucci, E. Fine structure of early cartilage calcification. J. Ultrastruct. Res. 1967, 20, 33-50.
- Bonucci, E.; Reurink, J. The fine structure of decalcified cartilage and bone: A comparison between decalcification procedures performed before and after embedding. *Calcif. Tissue Res.* 1978, 25, 179–190.
- Shepard, N. Role of proteoglycans in calcification. In *Calcification in Biological Systems*; Bonucci, E., Ed.; CRC Press: Boca Raton, FL, USA, 1992; pp. 41–58.
- Bonucci, E. Crystal ghosts and biological mineralization: Fancy spectres in an old castle, or neglected structures worthy of belief? J. Bone Miner. Metab. 2002, 20, 249–265.
- Bonucci, E.; Gomez, S. Cartilage calcification. In *Advanced Topics in Biomineralization*; Seto, J., Ed.; InTech: Rijeka, Croazia, 2012; pp. 85–110.
- Prostak, K.S.; Lees, S. Visualization of crystal-matrix structure. *In situ* demineralization of mineralized turkey leg tendon and bone. *Calcif. Tissue Int.* 1996, 59, 474–479.
- Goldberg, M.; Noblot, M.M.; Septier, D. Effets de deux méthodes de démineralisation sur la préservation des glycoprotéines et des protéoglycanes dans les dentines intercanaliculaires et péricanaliculaires chez le cheval. *J. Biol. Buccale* 1980, *8*, 315–330.
- 36. Hayashi, Y. Ultrastructural demonstration of the carbohydrate in developing mantle dentine with soybean agglutinin-gold complexes. *J. Electron. Microsc.* **1988**, *37*, 150–154.
- Bishop, M.A.; Warshawsky, H. Electron microscopic studies on the potential loss of crystallites from routinely processed sections of young enamel in the rat incisor. *Anat. Record* 1982, 202, 177–186.
- Hayashi, Y.; Bianco, P.; Shimokawa, H.; Termine, J.D.; Bonucci, E. Organic-inorganic relationships, and immunohistochemical localization of amelogenins and enamelins in developing enamel. *Basic Appl. Histochem.* **1986**, *30*, 291–299.
- Kallenbach, E. Crystal-associated matrix components in rat incisor enamel. An electron-microscopic study. *Cell Tissue Res.* 1986, 246, 455–461.
- 40. Nanci, A.; Bai, P.; Warshawsky, H. The effect of osmium postfixation and uranyl and lead staining on the ultrastructure of young enamel in the rat incisor. *Anat. Record* **1983**, *207*, 1–16.
- 41. Smales, F.C. Structural subunit in prisms of immature rat enamel. Nature 1975, 258, 772–774.
- 42. Davis, W.L.; Jones, R.G.; Hagler, H.K. An electron microscopic histochemical and analytical X-ray microprobe study of calcification in Bruch's membrane from human eyes. *J. Histochem. Cytochem.* **1981**, *29*, 601–608.
- 43. Kuhar, K.J.; Eisenmann, D.R. Fluoride-induced mineralization within vacuoles in maturative ameloblasts of the rat. *Anat. Record* **1978**, *191*, 91–102.
- 44. Boothroyd, B. The problem of demineralisation in thin sections of fully calcified bone. *J. Cell Biol.* **1964**, *20*, 165–173.

- 45. Dong, W.; Warshawsky, H. Failure to demonstrate a protein coat on enamel crystallites by morphological means. *Archs Oral Biol.* **1995**, *40*, 321–330.
- 46. Warshawsky, H. External shape of enamel crystals. Scann. Microsc. 1987, 1, 1913–1923.
- 47. Warshawsky, H. Organization of crystals in enamel. Anat. Record 1989, 224, 242-262.
- 48. Albeck, S.; Addadi, L.; Weiner, S. Regulation of calcite crystal morphology by intracrystalline acidic proteins and glycoproteins. *Connect. Tissue Res.* **1996**, *35*, 365–370.
- 49. Berman, A.; Addadi, L.; Kvick, Å.; Leiserowitz, L.; Nelson, M.; Weiner, S. Intercalation of sea urchin proteins in calcite: Study of a crystalline composite material. *Science* **1990**, *250*, 664–667.
- 50. Berman, A.; Addadi, L.; Weiner, S. Interactions of sea-urchin skeleton macromolecules with growing calcite crystals—A study of intracrystalline proteins. *Nature* **1988**, *331*, 546–548.
- Pokroy, B.; Fitch, A.N.; Lee, P.L.; Quintana, J.P.; Caspi, E.N.; Zolotoyabko, E. Anisotropic lattice distortions in the mollusk-made aragonite: A widespread phenomenon. *J. Struct. Biol.* 2006, 153, 145–150.
- 52. Tong, H.; Hu, J.; Ma, W.; Zhong, G.; Yao, S.; Cao, N. *In situ* analysis of the organic framework in the prismatic layer of mollusc shell. *Biomaterials* **2002**, *23*, 2593–2598.
- 53. Bonucci, E.; Silvestrini, G.; Di Grezia, R. Histochemical properties of the "crystal ghosts" of calcifying epiphyseal cartilage. *Connect. Tissue Res.* **1989**, *22*, 43–50.
- 54. Bonucci, E.; Silvestrini, G. Immunohistochemical investigation on the presence of chondroitin sulfate in calcification nodules of epiphyseal cartilage. *Eur. J. Histochem.* **1992**, *36*, 407–422.
- 55. Appleton, J. Ultrastructural observations on the inorganic/organic relationships in early cartilage calcification. *Calcif. Tissue Res.* **1971**, *7*, 307–317.
- 56. Davis, W.L.; Jones, R.G.; Knight, J.P.; Hagler, H.K. Cartilage calcification: An ultrastructural, histochemical, and analytical X-ray microprobe study of the zone of calcification in normal avian epiphyseal growth plate. *J. Histochem. Cytochem.* **1982**, *30*, 221–234.
- Chardin, H.; Septier, D.; Goldberg, M. Visualization of glycosaminoglycans in rat incisor predentin and dentin with cetylpyridinium chloride-glutaraldehyde as fixative. *J. Histochem. Cytochem.* 1990, 38, 885–894.
- 58. Sauren, Y.M.H.F.; Mieremet, R.H.P.; Groot, C.G.; Scherft, J.P. An electron microscopical study on the presence of proteoglycans in the calcified bone matrix by use of cuprolinic blue. *Bone* **1989**, *10*, 287–294.
- 59. Hayashi, Y. Ultrastructural demonstration of the carbohydrate in developing rat enamel using soybean agglutinin-gold complexes. *Arch. Oral Biol.* **1989**, *34*, 517–522.
- Gomez, S.; Lopez-Cepero, J.M.; Silvestrini, G.; Mocetti, P.; Bonucci, E. Matrix vesicles and focal proteoglycan aggregates are the nucleation sites revealed by the lanthanum incubation method: A correlated study on the hypertrophic zone of the rat epiphyseal cartilage. *Calcif. Tissue Int.* 1996, 58, 273–282.
- 61. Butler, W.T. Matrix macromolecules of bone and dentin. Collagen Rel. Res. 1984, 4, 297–307.
- 62. Deutsch, D.; Catalano-Sherman, J.; Dafni, L.; David, S.; Palmon, A. Enamel matrix proteins and ameloblast biology. *Connect. Tissue Res.* **1995**, *32*, 97–107.
- 63. Gorski, J.P. Biomineralization of bone: A fresh view of the roles of non-collagenous proteins. *Front. Biosci.* **2011**, *17*, 2598–2621.

- 64. Gotliv, B.A.; Addadi, L.; Weiner, S. Mollusk shell acidic proteins: In search of individual functions. *Chembiochem* **2003**, *4*, 522–529.
- 65. Marin, F.; Narayanappa, P.; Motreuil, S. Acidic shell proteins of the mediterranean fan mussel *Pinna nobilis. Progr. Mol. Subcell Biol.* **2011**, *52*, 353–395.
- 66. Rahman, M.A.; Oomori, T. *In vitro* regulation of CaCO<sub>3</sub> crystal growth by the highly acidic proteins of calcitic sclerites in soft coral, *Sinularia polydactyla*. *Connect. Tissue Res.* **2010**, *50*, 285–293.
- 67. Veis, A. Mineral-matrix interactions in bone and dentin. *J. Bone Miner. Res.* **1993**, 8 (suppl. 2), S493–S497.
- 68. Weiner, S. Aspartic acid-rich proteins: Major components of the soluble organic matrix of mollusk shells. *Calcif. Tissue Int.* **1979**, *29*, 163–167.
- 69. Mann, S. Biomineralization: Principles and Concepts. In *Bioinorganic Materials Chemistry*, 1st ed.; Oxford University Press: Oxford, UK, 2001.
- 70. Addadi, L.; Weiner, S. Interactions between acidic proteins and crystals: Stereochemical requirements in biomineralization. *Proc. Natl. Acad. Sci. USA* **1985**, *82*, 4110–4114.
- Aizenberg, J.; Hanson, J.; Ilan, M.; Leiserowitz, L.; Koetzle, T.F.; Addadi, L.; Weiner, S. Morphogenesis of calcitic sponge spicules: A role for specialized proteins interacting with growing crystals. *FASEB J.* 1995, *9*, 262–268.
- Fang, P.A.; Margolis, H.C.; Conway, J.F.; Simmer, J.P.; Beniash, E. CryoTEM study of effects of phosphorylation on the hierarchical assembly of porcine amelogenin and its regulation of mineralization *in vitro*. J. Struct. Biol. 2013, 183, 250–257.
- Kawska, A.; Hochrein, O.; Brickmann, J.; Kniep, D.; Zahn, D. The nucleation mechanism of fluorapatite-collagen composites: Ion association and motif control by collagen proteins. *Angew. Chem. Int. Ed.* 2008, 47, 4982–4985.
- Wang, Y.; Azaïs, T.; Robin, M.; Vallée, A.; Catania, C.; Legriel, P.; Pehau-Arnaudet, G.; Babonneau, F.; Giraud-Guille, M.M.; Nassif, N. The predominant role of collagen in the nucleation, growth, structure and orientation of bone apatite. *Nat. Mat.* 2012, *11*, 724–733.
- 75. Moradian-Oldak, J. Protein-mediated enamel mineralization. Front. Biosci. 2012, 17, 1996–2023.
- Glimcher, M.J.; Brickley-Parsons, D.; Levine, P.T. Studies of enamel proteins during maturation. *Calcif. Tissue Res.* 1977, 24, 259–270.
- 77. Pugliarello, M.C.; Vittur, F.; de Bernard, B.; Bonucci, E.; Ascenzi, A. Chemical modifications in osteones during calcification. *Calcif. Tissue Res.* **1970**, *5*, 108–114.
- 78. Lohmander, S.; Hjerpe, A. Proteoglycans of mineralizing rib and epiphyseal cartilage. *Biochim. Biophys. Acta* **1975**, *404*, 93–109.
- Althoff, J.; Quint, P.; Krefting, E.R.; Höhling, H.J. Morphological studies on the epiphyseal growth plate combined with biochemical and X-ray microprobe analyses. *Histochemistry* 1982, 74, 541–552.
- 80. Campo, R.D.; Dziewiatkowski, D.D. Turnover of the organic matrix of cartilage and bone as visualized by autoradiography. *J. Cell Biol.* **1963**, *18*, 19–29.
- 81. Campo, R.D.; Romano, J.E. Changes in cartilage proteoglycans associated with calcification. *Calcif. Tissue Int.* **1986**, *39*, 175–184.

- 82. Hirschman, A.; Dziewiatkowski, D.D. Protein-polysaccharide loss during endochondral ossification: Immunochemical evidence. *Science* **1966**, *154*, 393–395.
- 83. Matukas, V.J.; Krikos, G.A. Evidence for changes in protein polysaccharide associated with the onset of calcification in cartilage. *J. Cell Biol.* **1968**, *39*, 43–48.
- 84. Aizenberg, J.; Lambert, G.; Addadi, L.; Weiner, S. Stabilization of amorphous calcium carbonate by specialized macromolecules in biological and synthetic precipitates. *Adv. Mater.* **1996**, *8*, 222–226.
- Bentov, S.; Weil, S.; Glazer, L.; Sagi, A.; Berman, A. Stabilization of amorphous calcium carbonate by phosphate rich organic matrix proteins and by single phosphoamino acids. *J. Struct. Biol.* 2010, *171*, 207–215.
- Gajjeraman, S.; Narayanan, K.; Hao, J.; George, A. Matrix macromolecules in hard tissues controls the nucleation and hierarchical assembly of hydroxyapatite. *J. Biol. Chem.* 2007, 282, 1193–1204.
- 87. Politi, Y.; Arad, T.; Klein, E.; Weiner, S.; Addadi, L. Sea urchin spine calcite forms via a transient amorphous calcium carbonate phase. *Science* **2004**, *306*, 1161–1164.
- 88. Weiner, S.; Levi-Kalisman, Y.; Raz, S.; Addadi, L. Biologically formed amorphous calcium carbonate. *Connect. Tissue Res.* **2003**, *44* (suppl. 1), 214–218.
- 89. Zhang, G.; Xu, J. From colloidal nanoparticles to a single crystal: New insights into the formation of nacre's aragonite tablets. *J. Struct. Biol.* **2013**, *182*, 36–43.
- Dey, A.; Bomans, P.H.; Müller, F.A.; Will, J.; Frederik, P.M.; de With, G.; Sommerdijk, N.A. The role of prenucleation clusters in surface-induced calcium phosphate crystallization. *Nat. Mater.* 2010, *9*, 1010–1014.
- Kwak, S.Y.; Green, S.; Wiedemann-Bidlack, F.B.; Beniash, E.; Yamakoshi, Y.; Simmer, J.P.; Margolis, H.C. Regulation of calcium phosphate formation by amelogenins under physiological conditions. *Eur. J. Oral Sci.* 2011, *119* (suppl. 1), 103–111.

© 2014 by the authors; licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution license (http://creativecommons.org/licenses/by/3.0/).