

## Article

# Effect of Various Parameters on the Thermal Stability and Corrosion of CO<sub>2</sub>-Loaded Tertiary Amine Blends

Usman Shoukat  and Hanna Katariina Knuutila \* 

Department of Chemical Engineering, Norwegian University of Science and Technology (NTNU),  
7491 Trondheim, Norway; usman.shoukat@ntnu.no

\* Correspondence: hanna.knuutila@ntnu.no

Received: 26 April 2020; Accepted: 19 May 2020; Published: 21 May 2020



**Abstract:** In this study, the thermal stability and corrosivity of various CO<sub>2</sub>-loaded tertiary amine blends in both aqueous and non-aqueous form in stainless steel cylinders were studied for combined acid gas and water removal. The thermal stability was measured from the remaining amine concentration and the corrosivity was measured from the amount of various metals in blends using titration and inductively coupled plasma mass spectrometry (ICP-MS), respectively. The experimental data were used to calculate the rate constants of amine group loss. The developed model represented the experimental data very well. Solvent change from H<sub>2</sub>O to triethylene glycol (TEG) in blends decreased the thermal stability and vice versa for corrosivity. The amine stability was increased when contact with stainless steel was reduced. An increase in the amine concentration or CO<sub>2</sub> loading at constant temperature decreased the thermal stability and vice versa for corrosivity.

**Keywords:** thermal stability; corrosivity; tertiary amines; amine concentration; CO<sub>2</sub> loading; CO<sub>2</sub> capture

## 1. Introduction

Acid gas impurities such as carbon dioxide (CO<sub>2</sub>) and hydrogen sulfide (H<sub>2</sub>S) are typically present in natural gas. Energy production from natural gas also produces large quantities of CO<sub>2</sub> during combustion [1]. H<sub>2</sub>S is naturally present with methane, water vapor, CO<sub>2</sub>, and other impurities in many natural gas reservoirs [2]. Water vapor can cause corrosion in the pipelines and can also form hydrates in the presence of methane at suitable temperatures and pressures. These hydrates can plug manifolds, pipelines, and various accessories, such as valves and fittings [3]. Absorption-based acid gas capture processes are the most versatile processes for the removal of CO<sub>2</sub> and H<sub>2</sub>S from natural gas [4]. Amine solutions are generally used for this type of process, and glycols such as monoethylene glycol (MEG) and triethylene glycol (TEG) are typically used to remove H<sub>2</sub>O and inhibit hydrate formation [5].

A process that can remove acid gases and water simultaneously from the natural gas stream can be beneficial and using this process for subsea applications will reduce the environmental footprint. Simultaneous acid gas and water removal was discussed as early as 1939 by Hutchinson [6] and later by McCartney [7] and Chapin [8]. An ethanolamine (MEA) and diethylene glycol blend was the first used blend, but it was discontinued due to higher amine degradation and severe corrosivity [4]. MEA is mostly used for CO<sub>2</sub> absorption processes, but tertiary amines are alternatives for CO<sub>2</sub> absorption due to their higher theoretical CO<sub>2</sub> loading capacity and low energy requirement during the regeneration process [9]. Additionally, tertiary amine increases the thermal stability and reduces corrosivity [10].

CO<sub>2</sub> is absorbed in the presence of water in tertiary amines, and they form an unstable carbamate, subsequently producing bicarbonate ions, as shown in Equation (1) [9,11,12]:



The thermal stability and corrosivity of amine solutions are major problems in amine-based acid gas capture processes. High temperatures cause thermal degradation and the presence of oxygen can cause oxidative degradation [13,14]. Degradation can create various problems during the acid gas capture process, for example, solvent loss, by-product formation, fouling, foaming, corrosion, and a reduction in the absorption capacity [15–21].

Corrosion and thermal stability are interconnected since by-products can increase corrosion, while heat-stable amine salts, water vapor, organic acids, oxygen, and acid gas can also increase the corrosion rates [22–24]. Therefore, for a combined acid gas removal and water control process, it is essential to consider the corrosivity by checking the metal ion concentration in degraded blends. Corrosion can also be controlled by injecting film formation corrosion inhibitors (FFCIs) or pH stabilizers [25]. An example of a pH stabilizer used is *N*-methyl diethanolamine (MDEA), which is added to a lean MEG solution to lower the corrosion rate. The effect is based on the formation of a protective layer of FeCO<sub>3</sub> on the pipeline wall in the presence of CO<sub>2</sub> [25–27]. Corrosion inhibition by an FeCO<sub>3</sub> protection layer has been observed on mild steel, carbon steel, and stainless steel surfaces [28–30]. Thermally degraded solutions (MDEA-MEG-FFCI) decrease the hydrate inhibition, which is still less than the reduction caused by pure thermally degraded MEG [31]. Therefore, combining amine with MEG/TEG can reduce corrosion in comparison to using pure MEG/TEG.


The thermal stability of aqueous MDEA has been studied by various authors for concentrations ranging from 20 to 83.4 wt.% at temperatures from 100 to 230 °C [10,32–38], and it has been concluded that aqueous MDEA is more thermally stable in the absence of CO<sub>2</sub>. In the presence of CO<sub>2</sub>, minimal degradation was observed until 120 °C, but above this temperature, it started degrading rapidly. Moreover, an increase in the initial amine concentration and CO<sub>2</sub> loading decreased the amine stability. The thermal stability of 2-(diethylamino)ethanol (DEEA) was studied in the presence of CO<sub>2</sub> with 20–35.1 wt.% aqueous solutions at ≥135 °C [35,37,39], and it was concluded that, at temperatures >135 °C, the stability of aqueous DEEA was also reduced by an increase in the initial CO<sub>2</sub> loading and amine concentration, like an aqueous MDEA solution.

Only three published works are available for the thermal stability of non-aqueous amines. Al Harooni et al. [25] studied an MDEA-MEG-H<sub>2</sub>O solution (6.7 wt.% MDEA, 74.64 wt.% MEG, and 18.66 wt.% H<sub>2</sub>O) at 135–200 °C. The other two studies are our previously published works, where we studied MDEA blends (30 wt.% MDEA and 70 wt.% MEG/TEG) and both MDEA and DEEA blends (20 wt.% amine, 20 wt.% H<sub>2</sub>O, and 60 wt.% MEG/TEG) at 135 °C for seven weeks in the presence of CO<sub>2</sub> [10,37]. It was concluded that the thermal stability of amine was decreased with the addition of MEG in aqueous MDEA and DEEA solutions. Generally, tertiary amines first degrade into primary and secondary amines, and later, these primary and secondary amines make other by-products [33]. This was confirmed by Gouedard et al. [16] by studying aqueous MDEA thermal degradation kinetics and mechanisms. No data are available for the thermal stability of both aqueous and non-aqueous blends of 3-dimethylamino-1-propanol (3DMA-1P) and 3-diethylamino-1-propanol (3DEA-1P). MEG and TEG remained thermally stable up to 157 and 210 °C, respectively, in the absence of oxygen [40,41].

Corrosivity by amine solutions at a high temperature was studied by Grimstvedt et al. [42] in metal cylinders. Solutions were analyzed for the total Fe, Cr, Ni, and Mo, and these metal concentrations were compared to pilot data. The higher the amount of metals in solution, the higher the corrosion rate, and vice versa. Later, a similar approach was used in numerous studies [10,28,35,37]. Eide-Haugmo [35] found that metal concentrations in aqueous MDEA solutions are higher than aqueous DEEA solutions at 135 °C after five weeks of an experiment in 30 wt.% solutions. A similar trend was also observed in our previous work [37] for all aqueous and non-aqueous MDEA and DEEA solutions. According to

our other previous work, for 30 wt.% MDEA blends, the metal concentrations were in the order of MDEA.TEG > MDEA.H<sub>2</sub>O > MDEA.MEG [10].

The stability and corrosivity of amine are important factors to consider while selecting a blend for a combined acid gas and water removal process. In our previous work [43], we identified various potential blends for combined H<sub>2</sub>S and water removal. Among others, DEEA, 3DMA-1P, and 3DEA-1P showed good acid gas absorption, while MDEA is currently used as an industrial standard amine for H<sub>2</sub>S removal. As mentioned previously, most investigations of thermal stability in amine solutions have been conducted for aqueous and water lean solutions. There are very little data available for the thermal stability of amine blends in glycols without any water present in blends. Similarly, the effects of the initial amine concentration and CO<sub>2</sub> loading were previously only investigated for the thermal stability of amine, and no data are available for their effects on corrosion. Hence, in the current work, four tertiary amine blends in water, MEG, and TEG were studied to investigate their thermal stability and corrosivity. The effects of solvent type, amine concentration, and CO<sub>2</sub> loading were investigated. Finally, the impact of metal on MDEA blends' thermal stability was investigated by running thermal degradation experiments in glass tubes and stainless steel cylinders. The chemical structures of all the chemicals used in this study are shown in Figure 1.



**Figure 1.** Chemical structures of all chemicals used in this study.

## 2. Materials and Methods

### 2.1. Materials

All chemicals used in this study were purchased from Sigma-Aldrich (Oslo, Norway), except for 3DEA1P and CO<sub>2</sub>. 3DEA1P was bought from TCI Europe (Zwijndrecht, Belgium) and CO<sub>2</sub> was obtained from AGA AB (Oslo, Norway). All the chemicals used are listed in Table 1 and were used without further purification.

**Table 1.** Full name, CAS, and purity of all chemicals.

Chemical	CAS	Purity	Molecular Weight (g/mol)
N-Methyldiethanolamine (MDEA)	105-59-9	≥99.0%	119.16
2-(Diethylamino)ethanol (DEEA)	100-37-8	≥99.5%	117.19
3-Dimethylamino-1-propanol (3DMA-1P)	3179-63-3	≥99.0%	103.16
3-Diethylamino-1-propanol (3DEA-1P)	622-93-5	≥95.0%	131.22
Monoethylene glycol (MEG)	107-21-1	≥99.5%	62.07
Triethylene glycol (TEG)	112-27-6	≥99.8%	150.17
Carbon dioxide (CO <sub>2</sub> )	124-38-9	≥99.9%	44.01

Amine solutions were prepared gravimetrically in flasks using the Mettler Toledo scale, model MS6002S/01 (Oslo, Norway) ( $\pm 0.01$  g). Solutions were loaded with CO<sub>2</sub> by using a continuously weighted gas wash bottle in an isolated environment to achieve the required CO<sub>2</sub> concentration. All solutions were titrated for amine and CO<sub>2</sub> concentration to verify the CO<sub>2</sub> loading prior to the start of the experiment [10,44,45]. The unloaded amine wt.% and CO<sub>2</sub> loading at the beginning of the experiment for all solutions are given in Table 2.

**Table 2.** Rate constants (k) and correlation factor (R<sup>2</sup>) of all solutions, along with the experimental duration (time), CO<sub>2</sub> loading ( $\alpha$ ), and unloaded amine weight %.

Name	Unloaded Amine wt. %	$\alpha$ (mol CO <sub>2</sub> /mol amine)	Time (days)	$k \times 10^{-4}$ (day <sup>-1</sup> )	R <sup>2</sup>
DEEA.H <sub>2</sub> O	30	0.1	49	3.792	0.910
3DMA-1P.H <sub>2</sub> O	30	0.1	49	2.933	0.945
3DEA-1P.H <sub>2</sub> O	30	0.1	49	2.659	0.981
MDEA.H <sub>2</sub> O	30	0.1	49	3.960	0.908
MDEA.H <sub>2</sub> O (Glass)	30	0.1	35	4.546	0.904
DEEA.MEG	30	0.1	49	7.998	0.938
3DMA-1P.MEG	30	0.1	49	0.362	0.981
3DEA-1P.MEG	30	0.1	49	6.634	0.930
MDEA.MEG	30	0.1	49	22.910	0.919
MDEA.MEG (Glass)	30	0.1	49	17.390	0.900
DEEA.TEG	30	0.1	49	3.853	0.974
3DMA-1P.TEG	30	0.1	49	4.505	0.928
3DEA-1P.TEG	30	0.1	49	4.043	0.914
MDEA.TEG	30	0.1	49	19.450	0.988
MDEA.TEG (Glass)	30	0.1	49	11.920	0.939
DEEA.H <sub>2</sub> O	10	0.4	49	5.483	0.916
DEEA.H <sub>2</sub> O	30	0.4	49	9.473	0.941
DEEA.H <sub>2</sub> O	50	0.4	49	11.561	0.935
MDEA.H <sub>2</sub> O	10	0.4	49	3.058	0.974
MDEA.H <sub>2</sub> O	30	0.4	49	7.061	0.990
MDEA.H <sub>2</sub> O	50	0.4	49	16.520	0.998
MDEA.H <sub>2</sub> O	70	0.4	49	32.810	0.986

## 2.2. Methodology

Both stirred cell reactors [32,33,36,39] and metal cylinders [10,21,28,37] have been used to study amine solutions' thermal stability. In this work, metal cylinders were selected, as various amine solutions at different concentrations could be tested in multiple cylinders at the same time, consequently reducing the overall experimental duration. The corrosivity of the blends can be studied by analyzing the solutions for the total Fe, Cr, Ni, and Mo. The metal concentrations in the solution can be used as an indicator of corrosivity [42]. Therefore, multiple cylinders were made by using 10 cm long and 1.3 cm

diameter 316 stainless steel tubes, with both ends closed with Swagelok® end caps (Stavanger, Norway). Pre-loaded CO<sub>2</sub> amine solutions were added in cylinders, leaving around 1 cm gaps between the solution surface and cap. Additionally, glass tubes were used inside metal cylinders to study the effect of metal on the thermal stability of amine solutions for 30 wt.% MDEA solutions (both aqueous and non-aqueous). A replica of each cylinder was made to attain more precise results. Cylinders were stored vertically in a forced convection oven at 135 °C, in order to enhance the degradation and shorten the experimental time. Since several studies using these conditions have been performed previously, the current data can be easily compared with literature data [10,28,35,37]. The experiment was run for seven weeks, and one cylinder, along with a replica of each solution, were taken out from the oven after 1, 3, 5, and 7 weeks at the same time of day. Cylinders were cooled down to room temperature before opening in the fume cabinet and were stored in the fridge to prevent any further decomposition. Cylinders were weighed before and after the experiment to identify any leakages. All cylinders, except for aqueous MDEA solutions in glass tubes for week 3 and week 5, showed less than a 2% difference in weight. The cylinders that leaked, including aqueous MDEA solutions in glass tubes for week 3 and week 5, were not used in the calculations of results.

All solutions were titrated with 0.1 M H<sub>2</sub>SO<sub>4</sub> to measure the amine group in the solutions [37,44]. For all samples, the average difference in amine concentrations was less than ±2% between the solution and its replica in all non-leaking cylinders. In this paper, the average concentrations between the replicates are reported. At the end of the experiment, cation ionized chromatography (IC) was also used to determine the amine concentration of 30 wt.% solutions ( $\alpha = 0.1$ ) and the difference between the amine group concentration calculated by titration and cation IC was less than ±2.5 percentage points. The average of the total amine group concentration measured by titration was used in Equation (2) to calculate the experimental values of the remaining amine group (%). In this equation,  $C_i$  is the amine group concentration at time =  $t$  (days), and  $C_o$  is the amine group concentration in fresh solution at the start of the experiment. Metal concentrations (Fe, Cr, Ni, and Mo) were measured using inductively coupled plasma mass spectrometry (ICP-MS) for only week five solutions and used as an indicator of the relative corrosivity caused by amine solutions on the stainless steel [10,28,37,42]. The primary focus of the current work was to study the effect of TEG/MEG in the absence of water, amine concentration, and CO<sub>2</sub> loading on the stability and corrosivity of amine. Therefore, by-products produced due to amine loss were not studied.

$$\text{Remaining amine group (\%)} = 100 \times \frac{C_i}{C_o} \quad (2)$$

## Modeling

Rate constants of amine group loss can be calculated with a linear regression model by using Equations (3) and (4) while assuming first-order reactions concerning amine and integrated over time “ $t$ ” [37,46].

$$\frac{dC}{dt} = r = kC \quad (3)$$

$$\ln \frac{C_o}{C_i} = k.t \quad (4)$$

$$\frac{C_i}{C_o} = \frac{1}{e^{k.t}} \quad (5)$$


Plotting  $\ln (C_o/C_i)$  as a function of time from Equation (4) provided the first-order rate constants ( $k$ ) as the slope in linear regression, while the correlation coefficient ( $R^2$ ) gave the accuracy of the model. Rate constants were used in Equation (5) to calculate  $(C_i/C_o)$ , which were subsequently used to predict the remaining amine group (%) from Equation (2). First-order rate constants ( $k$ ), the experimental duration (time “ $t$ ”), and  $R^2$  are given in Table 2.

### 3. Results and Discussion

#### 3.1. Comparison with Literature Data

##### 3.1.1. Thermal Stability

The validation of degradation results is not simple. In the laboratory, the degradation is accelerated to shorten the experimental time and small differences in solvent compositions or experimental conditions can give large differences in the results. Of the solutions studied in this work, the thermal degradation of aqueous DEEA and MDEA has previously been studied and there is adequate agreement found between the current study and published data, as shown in Figure 2. For aqueous DEEA solutions, Gao et al. [39] (35 wt.% DEEA with  $\alpha = 0.5$ ) showed 4 percentage points and 7 percentage points higher amine loss after 12.5 and 20 days, respectively, probably due to the higher amine concentration and higher CO<sub>2</sub> loading. Eide-Haugmo [35] (30 wt.% DEEA with  $\alpha = 0.5$ ) showed 11 percentage points higher amine loss after five weeks at 135 °C in comparison to our current data, which can be partly explained by the higher loading. Finally, the new data are in good agreement with our previous data, showing a good reproducibility [10]. Figure 2 also presents a comparison of this work (30 wt.% MDEA in H<sub>2</sub>O, MEG, and TEG with  $\alpha = 0.1$ ) and our previous work (34 wt.% MDEA in H<sub>2</sub>O with  $\alpha = 0.19$ , 30 wt.% MDEA in MEG with  $\alpha = 0.19$ , and 30 wt.% MDEA in TEG with  $\alpha = 0.11$ ) [10]. The agreement is good and both studies show the same trend in the thermal stability of MDEA blends after seven weeks, which is in the order of MDEA.H<sub>2</sub>O > MDEA.TEG > MDEA.MEG. It can be concluded that there is a good overall agreement between the published literature data and degradation data reported in this paper.




**Figure 2.** Comparison with the literature in terms of the remaining amine group concentration in 30 wt.% amine–H<sub>2</sub>O solutions (Eide-Haugmo 2011 [35], Gao et al. 2015 [39], Shoukat et al. 2016 [10]).



### 3.1.2. Corrosion

The corrosion results are in agreement with previously published data from various authors, as shown in Figure 3. Shoukat et al. [10] also found similar total metal concentrations and a similar order for MDEA blends as the current work. Furthermore, the new aqueous MDEA and DEEA data are also in acceptable agreement with Eide-Haugmo [35]. Individual metal ion concentrations display very small quantities (<67 mg/L), both in our current data set and previously published data sets. It can be concluded that the current data set is in good agreement with the literature data.




**Figure 3.** Total metal concentrations in 30 wt.% amine blends (Eide-Haugmo 2011 [35], Shoukat et al. 2016 [10]).

### 3.2. Thermal Stability


The thermal stability of amines is presented by the remaining amine group (%) (total remaining alkalinity) as a function of experimental days. The remaining experimental amine group % for each solution is shown as markers, while the solid lines are the values calculated from linear regression. All the experimental data of amine group concentrations is given in Table A1. Rate constants were computed for all solutions until 49 days, except MDEA.H<sub>2</sub>O (Glass) solutions, where the solutions leaked after week one. The week one results of 50 wt.% DEEA.H<sub>2</sub>O were also not included in linear regression. Unloaded amine wt.% and CO<sub>2</sub> loading at the start of an experiment for all solutions, along with the experimental duration, rate constants (k), and correlation coefficients (R<sup>2</sup>) for all blends, are given in Table 2. The rate constant increased with the increase in amine concentration and CO<sub>2</sub> loading in aqueous solutions. The change of solvent had a different effect on each amine solution rate constant. The correlation factor (R<sup>2</sup>) value was higher than 0.9 in all solutions, showing the good accuracy of the model, and is visible in the thermal stability results (Figures 4–6 & 10–12).

Figure 4 shows the thermal stability results of 30 wt.% aqueous amine solutions with CO<sub>2</sub> loading of 0.1. After seven weeks, the maximum thermal stability was observed in 3DMA-1P. Overall, the thermal stability was quite high, as less than 2 percentage points of amine were lost during the whole set of experiments. No significant difference in thermal stability was observed when the methyl group was swapped with an ethyl group in solutions, i.e., 3DMA-1P to 3DEA-1P.




**Figure 4.** Remaining amine group concentration in aqueous amine solutions, with solid lines representing the model results; unloaded amine wt.% = 30; CO<sub>2</sub> loading  $\approx$  0.1.

Figures 5 and 6 represent the 30 wt.% amine blends in MEG and TEG with CO<sub>2</sub> loading  $\approx$  0.1, respectively. In both cases, MDEA blends showed the least thermal stability compared to others. Installing a glass tube in between the metal cylinder and blend increased the thermal stability of MDEA blends. In both MEG and TEG blends of MDEA, the glass tube increased the thermal stability by 2 percentage points after seven weeks, which might be due to the absence of metal ions. An increase in the alkyl group in amine from 3DMA-1P to 3DEA-1P decreased the thermal stability in amine–MEG blends and the opposite trend was seen with amine–TEG blends. Eide-Haugmo [35] and Shoukat et al. [37] also found that an increase in the carbon number or alkyl group length reduced the thermal stability in aqueous amine solutions, and vice versa, for amine–water–glycol solutions. 3DMA-1P and DEEA showed the highest thermal stability among MEG and TEG blends, respectively, after 49 days.




**Figure 5.** Remaining amine group concentration in amine monoethylene glycol (MEG) blends, with solid lines representing the model results; unloaded amine wt.% = 30; CO<sub>2</sub> loading  $\approx$  0.1.






**Figure 6.** Remaining amine group concentration in amine triethylene glycol (TEG) blends, with solid lines representing the model results; unloaded amine wt.% = 30; CO<sub>2</sub> loading  $\approx$  0.1.


Figure 7 presents the effect of a change of solvent from water to MEG on the thermal stability of amine for 30 wt.% amine blends at 0.1 CO<sub>2</sub> loadings. MEG usage instead of water replacement decreased the thermal stability of all solutions, except 3DMA-1P. The thermal stability of MDEA was decreased by 8 percentage points, which was more than three times that of other blends. Similarly, Figure 8 shows the results for the change of solvent from water to TEG. TEG decreased the thermal stability of all blends. Again, like the effect of MEG, the maximum thermal stability decrease was observed in the MDEA.TEG blend. Figure 9 represents the results of changing the solvent from MEG to TEG. Apart from 3DMA-1P, the thermal stability was increased for all blends. The maximum increase (3 percentage points) in thermal stability was observed in the MDEA (Glass) week five blend.



**Figure 7.** Difference between the remaining amine group (percentage points) of aqueous amine solutions vs. the amine–MEG blend; unloaded amine wt.% = 30; CO<sub>2</sub> loading  $\approx$  0.1.



**Figure 8.** Difference between the remaining amine group (percentage points) of aqueous amine solution vs. the amine–TEG blends; unloaded amine wt.% = 30; CO<sub>2</sub> loading  $\approx$  0.1.




**Figure 9.** Difference between the remaining amine group (percentage points) of amine–MEG blends vs. amine–TEG blends; unloaded amine wt.% = 30; CO<sub>2</sub> loading  $\approx$  0.1.


### 3.2.1. Effect of the Initial Amine Concentration

Figures 10 and 11 present the results of 10–70 wt.% MDEA.H<sub>2</sub>O solutions and 10–50 wt.% DEEA.H<sub>2</sub>O solutions, respectively, with initial CO<sub>2</sub> loading of 0.4. An increase in the amine concentration decreased the thermal stability of amine in all solutions. The thermal stability of amine was decreased more rapidly in MDEA solutions with an increase in the amine concentration in comparison to DEEA solutions. Every increase of 20 wt.% MDEA concentration in aqueous solution doubled the amine loss in each step. The results are in good agreement with the literature. Chakma and Meisen [32] found that an increase in the initial MDEA concentration increased the amine loss rates due to the higher solubility of CO<sub>2</sub> in the solutions achieving constant CO<sub>2</sub> loading at higher amine concentrations. Similarly, Gao et al. [39] concluded that an increase in the initial concentration of DEEA

significantly decreased the stability of amine due to the availability of a more reactive DEEA molecule for CO<sub>2</sub> absorption.




**Figure 10.** Remaining amine group (%) in various aqueous *N*-methyl diethanolamine (MDEA) solutions, with solid lines representing the model results at CO<sub>2</sub> loading  $\approx 0.4$ .



**Figure 11.** Remaining amine group (%) in various aqueous 2-(diethylamino) ethanol (DEEA) solutions, with solid lines representing the model results at CO<sub>2</sub> loading  $\approx 0.4$ .

### 3.2.2. Effect of Initial CO<sub>2</sub> Loading


The effect of CO<sub>2</sub> loading on the thermal stability in the initial 30 wt.% MDEA and DEEA aqueous solutions is presented in Figure 12. After 49 experimental days, the thermal stability was reduced with an increase in CO<sub>2</sub> loading from 0.1 to 0.4 for both amines. Aqueous DEEA solution exhibited a greater reduction in the thermal stability compared to aqueous MDEA. Again, our data agree with the published literature. Chakma and Meisen [32] and Gao et al. [39] found that an increase in the CO<sub>2</sub> concentration in solutions decreased the thermal stability of aqueous MDEA and DEEA solutions, respectively. Lepaumier et al. [33] and Eide-Haugmo [35] also concluded that the addition of CO<sub>2</sub> reduced the thermal stability of amines.



**Figure 12.** Remaining amine group (%) in various aqueous amine solutions, with solid lines representing the model results; unloaded amine wt.% = 30.

### 3.3. Corrosion


Week 5 blends were analyzed for individual metal components (iron (Fe), nickel (Ni), chromium (Cr), and molybdenum (Mo)) using ICP-MS, and the results as a sum of all of these metals for 30 wt.% amine blends with initial 0.1 CO<sub>2</sub> loadings are given in Figure 13. A higher corrosivity of a blend was indicated by a higher metal concentration. Each solution and its replica were analyzed and the average was used for result calculations. The average deviation in the replicas was  $\pm 0.1$  mg/L. Various metal concentrations (mg/L) in all solutions after five weeks are given in Table A2. Iron contributed most to the total metal concentration in all amine blends in MEG and TEG. In aqueous amine solutions, Mo showed the highest contribution, except for aqueous MDEA solutions, where Cr contributed the most. In all amine blends except the DEEA blend, the total metal concentration was highest in amine–TEG blends, followed by amine–H<sub>2</sub>O blends. The lowest metal concentrations were found in amine–MEG blends. The total metal concentration in DEEA blends was in the order of DEEA.H<sub>2</sub>O < DEEA.MEG < DEEA.TEG.



**Figure 13.** Metal concentrations of amine solutions after five weeks; unloaded amine wt.% = 30; CO<sub>2</sub> loading  $\approx 0.1$ .

### 3.3.1. Effect of the initial amine concentration


The results for the effects of the amine concentration on corrosivity at a constant initial CO<sub>2</sub> loading of 0.4 are presented in Figure 14. An increase in the amine concentration increased the corrosivity, mainly due to higher amine loss. The maximum metal concentration (534 mg/L) was found with 70 wt.% MDEA aqueous solution, whereas the minimum value (1 mg/L) was found with 10 wt.% DEEA aqueous solution. The total metal concentration in aqueous MDEA increased exponentially, whereas in aqueous DEEA it increased quite linearly.



**Figure 14.** Metal concentrations of various aqueous MDEA and DEEA solutions after five weeks at CO<sub>2</sub> loading  $\approx 0.4$ .

### 3.3.2. Effect of Initial CO<sub>2</sub> Loading

CO<sub>2</sub> loading affected the corrosivity caused by amine solutions. The total metal concentrations for 30 wt.% aqueous MDEA and DEEA solutions with CO<sub>2</sub> loadings of 0.1 and 0.4 after week five are shown in Figure 15. An increase in CO<sub>2</sub> loading increased the total metal concentration in both solutions. The aqueous MDEA solution with 0.4 CO<sub>2</sub> loading contained the highest amount of metals compared to other solutions. Eide-Haugmo [35] also found that CO<sub>2</sub>-loaded amine solutions corroded more in comparison to their unloaded counterpart.



**Figure 15.** Metal concentrations of 30 wt.% aqueous MDEA and DEEA solutions after week five at various CO<sub>2</sub> loadings.

#### 4. Conclusions

In this work, the thermal stability and corrosivity of four tertiary amine blends in water, MEG, and TEG, loaded with CO<sub>2</sub>, were studied in stainless steel cylinders at 135 °C for seven weeks. The effects of direct metal contact with the blend, the initial amine concentration, and the initial CO<sub>2</sub> loading were discussed. An increase in the initial amine concentration, CO<sub>2</sub> loading, and direct contact between the cylinder and blends decreased the thermal stability, and vice versa, for corrosivity. Amine blends with TEG displayed a higher thermal stability, except for 3DMA-1P, and higher corrosion, in comparison to MEG. 3DEA-1P blends showed a good combination of low corrosion and a higher thermal stability in comparison to other solutions.

**Author Contributions:** Conceptualization, H.K.K. and U.S.; methodology, U.S.; writing—original draft preparation, U.S.; writing—review and editing, H.K.K.; supervision, H.K.K. All authors have read and agreed to the published version of the manuscript.

**Funding:** This work was carried out under funding provided by the NTNU-SINTEF Gas Technology Centre (GTS) and the Faculty of Natural Sciences, Norwegian University of Science and Technology (NTNU), Trondheim, Norway.

**Acknowledgments:** We would like to thank the Department of Chemical Engineering (IKP) at the Faculty of Natural Sciences and Technology, Norwegian University of Science and Technology (NTNU), Trondheim, Norway, for their support.

**Conflicts of Interest:** The authors declare no conflict of interest.

#### Appendix A

**Table A1.** Amine group concentrations in all solutions.

Name	CO <sub>2</sub> Loading (α)	Remaining Amine Group Concentration (mole/L) after Time (days)				
		0	7	21	35	49
DEEA.H <sub>2</sub> O	0.1	2.5005	2.4999	2.4886	2.4594	2.4561
3DMA-1P.H <sub>2</sub> O	0.1	2.9098	2.8992	2.8935	2.8755	2.8716
3DEA-1P.H <sub>2</sub> O	0.1	2.1932	2.1871	2.1833	2.1730	2.1641
MDEA.H <sub>2</sub> O	0.1	2.4178	2.4051	2.3942	2.3796	2.3772
MDEA.H <sub>2</sub> O(Glass)	0.1	2.4178	2.4022	-	2.3812	-
DEEA.MEG	0.1	2.5044	2.4871	2.4761	2.4212	2.4130
3DMA-1P.MEG	0.1	2.9063	2.9052	2.9038	2.9025	2.9014
3DEA-1P.MEG	0.1	2.2519	2.2318	2.2209	2.1922	2.1869
MDEA.MEG	0.1	2.4167	2.3426	2.2768	2.2162	2.1854
MDEA.MEG(Glass)	0.1	2.4167	2.3497	2.3161	2.2639	2.2371
DEEA.TEG	0.1	2.4816	2.4714	2.4628	2.4447	2.4378
3DMA-1P.TEG	0.1	2.8995	2.8876	2.8856	2.8562	2.8295
3DEA-1P.TEG	0.1	2.2387	2.2254	2.2153	2.2058	2.1987
MDEA.TEG	0.1	2.4297	2.3973	2.3367	2.2537	2.2183
MDEA.TEG(Glass)	0.1	2.4297	2.4121	2.3697	2.3543	2.2748
DEEA.H <sub>2</sub> O	0.4	0.8141	0.8068	0.8031	0.7992	0.7933

Table A1. Cont.

Name	CO <sub>2</sub> Loading ( $\alpha$ )	Remaining Amine Group Concentration (mole/L) after Time (days)				
		0	7	21	35	49
DEEA.H <sub>2</sub> O	0.4	2.4062	2.3737	2.3574	2.3390	2.2919
DEEA.H <sub>2</sub> O	0.4	3.9907	-	3.9392	3.8226	3.7596
MDEA.H <sub>2</sub> O	0.4	0.7779	0.7756	0.7743	0.7697	0.7658
MDEA.H <sub>2</sub> O	0.4	2.3081	2.2970	2.2802	2.2522	2.2266
MDEA.H <sub>2</sub> O	0.4	3.8348	3.8001	3.7076	3.6184	3.5348
MDEA.H <sub>2</sub> O	0.4	5.3424	5.2131	4.9166	4.7757	4.5688

Table A2. Various metal concentrations (mg/L) in all solutions after five weeks.

Name	Unloaded Amine Weight (%)	CO <sub>2</sub> Loading ( $\alpha$ )	Fe (mg/L)	Ni (mg/L)	Cr (mg/L)	Mo (mg/L)
DEEA.H <sub>2</sub> O	30	0.1	1.55	0.62	0.62	4.17
3DMA-1P.H <sub>2</sub> O	30	0.1	1.13	0.66	0.07	12.36
3DEA-1P.H <sub>2</sub> O	30	0.1	1.15	0.06	0.11	3.15
MDEA.H <sub>2</sub> O	30	0.1	3.24	8.08	10.53	1.49
DEEA.MEG	30	0.1	15.11	0.44	0.44	0.56
3DMA-1P.MEG	30	0.1	3.06	0.53	0.14	0.74
3DEA-1P.MEG	30	0.1	3.70	0.22	0.03	0.36
MDEA.MEG	30	0.1	3.99	0.16	0.51	0.10
DEEA.TEG	30	0.1	36.21	2.48	2.48	0.76
3DMA-1P.TEG	30	0.1	27.28	0.98	0.08	0.22
3DEA-1P.TEG	30	0.1	8.18	0.46	0.07	0.12
MDEA.TEG	30	0.1	66.64	11.25	17.53	2.12
DEEA.H <sub>2</sub> O	10	0.4	0.33	0.01	0.26	0.37
DEEA.H <sub>2</sub> O	30	0.4	5.06	0.91	5.69	0.64
DEEA.H <sub>2</sub> O	50	0.4	9.11	1.46	6.91	0.84
MDEA.H <sub>2</sub> O	10	0.4	1.13	3.54	4.83	0.82
MDEA.H <sub>2</sub> O	30	0.4	5.42	33.24	52.27	6.31
MDEA.H <sub>2</sub> O	50	0.4	14.10	79.80	130.50	16.07
MDEA.H <sub>2</sub> O	70	0.4	34.48	174.17	290.49	34.39

## References

1. Amosa, M.; Mohammed, I.; Yaro, S. Sulphide scavengers in oil and gas industry—A review. *Nafta* **2010**, *61*, 85–92.
2. Jalili, A.H.; Shokouhi, M.; Maurer, G.; Zoghi, A.T.; Ahari, J.; Forsat, K. Measuring and modelling the absorption and volumetric properties of CO<sub>2</sub> and H<sub>2</sub>S in the ionic liquid 1-ethyl-3-methylimidazolium tetrafluoroborate. *J. Chem. Thermodyn.* **2019**, *131*, 544–556. [[CrossRef](#)]
3. Kohl, A.L.; Nielsen, R.B. Chapter 11—Absorption of Water Vapor by Dehydrating Solutions. In *Gas Purification*, 5th ed.; Kohl, A.L., Nielsen, R.B., Eds.; Gulf Professional Publishing: Houston, TX, USA, 1997; pp. 946–1021.
4. Kohl, A.L.; Nielsen, R.B. Chapter 2—Alkanolamines for Hydrogen Sulfide and Carbon Dioxide Removal. In *Gas Purification*, 5th ed.; Gulf Professional Publishing: Houston, TX, USA, 1997; pp. 40–186.
5. Netusil, M.; Dittl, P. Comparison of three methods for natural gas dehydration. *J. Nat. Gas Chem.* **2011**, *20*, 471–476. [[CrossRef](#)]
6. Hutchinson, A.J. Process for Treating Gases. U.S. Patent US2177068 A, 1939.
7. McCartney, E.R. Gas Purification and Dehydration Process. U.S. Patent US2435089 A, 28 June 1948.
8. Chapin, W.F. Purification and Dehydration of Gases. U.S. Patent US2518752 A, 28 June 1950.



9. Chowdhury, F.A.; Yamada, H.; Higashii, T.; Goto, K.; Onoda, M. CO<sub>2</sub> capture by tertiary amine absorbents: A performance comparison study. *Ind. Eng. Chem. Res.* **2013**, *52*, 8323–8331. [\[CrossRef\]](#)
10. Shoukat, U.; Fytianos, G.; Knuutila, H.K. Thermal stability and corrosion studies of amines for combined acid gas removal and hydrate control for subsea gas treatment systems. In *Techno-Ocean 2016: Return to the Oceans*; IEEE: Kobe, Japan, 2016; pp. 176–180.
11. Barth, D.; Tondre, C.; Delpuech, J.J. Kinetics and mechanisms of the reactions of carbon dioxide with alkanolamines: A discussion concerning the cases of MDEA and DEA. *Chem. Eng. Sci.* **1984**, *39*, 1753–1757. [\[CrossRef\]](#)
12. Vaidya, P.D.; Kenig, E.Y. CO<sub>2</sub>-Alkanolamine Reaction Kinetics: A Review of Recent Studies. *Chem. Eng. Technol.* **2007**, *30*, 1467–1474. [\[CrossRef\]](#)
13. Chi, S.; Rochelle, G.T. Oxidative degradation of monoethanolamine. *Ind. Eng. Chem. Res.* **2002**, *41*, 4178–4186. [\[CrossRef\]](#)
14. Vevelstad, S.J.; Grimstvedt, A.; Elnan, J.; da Silva, E.F.; Svendsen, H.F. Oxidative degradation of 2-ethanolamine: The effect of oxygen concentration and temperature on product formation. *Int. J. Greenh. Gas Control* **2013**, *18* (Suppl. SC), 88–100. [\[CrossRef\]](#)
15. Islam, M.S.; Yusoff, R.; Si Ali, B.; Islam, M.N.; Chakrabarti, M.H. Degradation studies of amines and alkanolamines during sour gas treatment process. *Int. J. Phys. Sci.* **2011**, *6*, 5883–5896.
16. Gouedard, C.; Picq, D.; Launay, F.; Carrette, P.L. Amine degradation in CO<sub>2</sub> capture. I. A review. *Int. J. Greenh. Gas Control* **2012**, *10*, 244–270. [\[CrossRef\]](#)
17. Da Silva, E.F.; Lepaumier, H.; Grimstvedt, A.; Vevelstad, S.J.; Einbu, A.; Vernstad, K.; Svendsen, H.F.; Zahlsen, K. Understanding 2-ethanolamine degradation in postcombustion CO<sub>2</sub> capture. *Ind. Eng. Chem. Res.* **2012**, *51*, 13329–13338. [\[CrossRef\]](#)
18. Zhou, S.; Wang, S.; Chen, C. Thermal degradation of monoethanolamine in CO<sub>2</sub> capture with acidic impurities in flue gas. *Ind. Eng. Chem. Res.* **2012**, *51*, 2539–2547. [\[CrossRef\]](#)
19. Zoannou, K.S.; Sapsford, D.J.; Griffiths, A.J. Thermal degradation of monoethanolamine and its effect on CO<sub>2</sub> capture capacity. *Int. J. Greenh. Gas Control* **2013**, *17*, 423–430. [\[CrossRef\]](#)
20. Rao, A.B.; Rubin, E.S. A technical, economic, and environmental assessment of amine-based CO<sub>2</sub> capture technology for power plant greenhouse gas control. *Environ. Sci. Technol.* **2002**, *36*, 4467–4475. [\[CrossRef\]](#)
21. Freeman, S.A.; Davis, J.; Rochelle, G.T. Degradation of aqueous piperazine in carbon dioxide capture. *Int. J. Greenh. Gas Control* **2010**, *4*, 756–761. [\[CrossRef\]](#)
22. Davoudi, M.; Safadoost, A.R.; Akbar Mansoori, S.A.; Mottaghi, H.R. The impurities effect on thermal degradation and corrosivity of amine solution in South Pars gas sweetening plants. *J. Nat. Gas Sci. Eng.* **2014**, *19*, 116–124. [\[CrossRef\]](#)
23. Sandengen, K.; Kaasa, B.; Østvold, T. pH Measurements in Monoethylene Glycol (MEG) + Water Solutions. *Ind. Eng. Chem. Res.* **2007**, *46*, 4734. [\[CrossRef\]](#)
24. Davoudi, M.; Heidari, Y.; Safadoost, A.; Samieirad, S. Chemical injection policy for internal corrosion prevention of South Pars sea-pipeline: A case study. *J. Nat. Gas Sci. Eng.* **2014**, *21*, 592. [\[CrossRef\]](#)
25. AlHarooni, K.; Pack, D.; Iglaue, S.; Gubner, R.; Ghodkay, V.; Barifcani, A. Analytical Techniques for Analyzing Thermally Degraded Monoethylene Glycol with Methyl Diethanolamine and Film Formation Corrosion Inhibitor. *Energy Fuels* **2016**, *30*, 10937–10949. [\[CrossRef\]](#)
26. Khorrami, M.R.; Raeissi, K.; Shahban, H.; Torkan, M.A.; Saatchi, A. Corrosion behavior of carbon steel in carbon dioxide-loaded activated methyl diethanol amine solution. *Corrosion* **2008**, *64*, 124–130. [\[CrossRef\]](#)
27. Zheng, L.; Landon, J.; Matin, N.S.; Thomas, G.A.; Liu, K. Corrosion mitigation via a pH stabilization method in monoethanolamine-based solutions for post-combustion CO<sub>2</sub> capture. *Corros. Sci.* **2016**, *106*, 281. [\[CrossRef\]](#)
28. Fytianos, G.; Ucar, S.; Grimstvedt, A.; Hyldbakk, A.; Svendsen, H.F.; Knuutila, H.K. Corrosion and degradation in MEA based post-combustion CO<sub>2</sub> capture. *Int. J. Greenh. Gas Control* **2016**, *46*, 48–56. [\[CrossRef\]](#)
29. Xiang, Y.; Yan, M.; Choi, Y.-S.; Young, D.; Nesic, S. Time-dependent electrochemical behavior of carbon steel in MEA-based CO<sub>2</sub> capture process. *Int. J. Greenh. Gas Control* **2014**, *30* (Suppl. SC), 125–132.
30. Nordsveen, M.; Nešić, S.; Nyborg, R.; Stangeland, A. A Mechanistic Model for Carbon Dioxide Corrosion of Mild Steel in the Presence of Protective Iron Carbonate Films—Part 1: Theory and Verification. *Corrosion* **2003**, *59*, 443–456. [\[CrossRef\]](#)

31. AlHarooni, K.; Pack, D.; Iglaier, S.; Gubner, R.; Ghodkay, V.; Barifcani, A. Effects of Thermally Degraded Monoethylene Glycol with Methyl Diethanolamine and Film-Forming Corrosion Inhibitor on Gas Hydrate Kinetics. *Energy Fuels* **2017**, *31*, 6397–6412. [\[CrossRef\]](#)
32. Chakma, A.; Meisen, A. Methyl-Diethanolamine Degradation - Mechanism and Kinetics. *Can. J. Chem. Eng.* **1997**, *75*, 861–871. [\[CrossRef\]](#)
33. Lepaumier, H.; Picq, D.; Carrette, P.L. New amines for CO<sub>2</sub> Capture. I. mechanisms of amine degradation in the presence of CO<sub>2</sub>. *Ind. Eng. Chem. Res.* **2009**, *48*, 9061–9067. [\[CrossRef\]](#)
34. Closmann, F.; Rochelle, G.T. Degradation of aqueous methyldiethanolamine by temperature and oxygen Cycling. *Energy Procedia* **2011**, *4*, 23–28. [\[CrossRef\]](#)
35. Eide-Haugmo, I. Environmental Impacts and Aspects of Absorbents Used for CO<sub>2</sub> Capture. Ph.D. Thesis, Norwegian Univeristy of Science and Technology, Trondheim, Norway, 2011.
36. Handojo, L.; Yudianto, M.D.; Susanti, R.F.; Yaswari, Y.; Raksajati, A.; Indarto, A. Non-oxidative thermal degradation of amines: GCMS/FTIR spectra analysis and molecular modeling. *Sep. Sci. Technol.* **2018**, *53*, 2259–2266. [\[CrossRef\]](#)
37. Shoukat, U.; Baumeister, E.; Pinto, D.D.; Knuutila, H.K. Thermal stability and corrosion of tertiary amines in aqueous amine and amine-glycol-water solutions for combined acid gas and water removal. *J. Nat. Gas Sci. Eng.* **2019**, *62*, 26–37. [\[CrossRef\]](#)
38. Shoukat, U.; Baumeister, E.; Knuutila, H.K. ATR-FTIR Model Development and Verification for Qualitative and Quantitative Analysis in MDEA–H<sub>2</sub>O–MEG/TEG–CO<sub>2</sub> Blends. *Energies* **2019**, *12*, 3285. [\[CrossRef\]](#)
39. Gao, H.; Liang, Z.; Liao, H.; Idem, R.O. Thermal degradation of aqueous DEEA solution at stripper conditions for post-combustion CO<sub>2</sub> capture. *Chem. Eng. Sci.* **2015**, *135*, 330–342. [\[CrossRef\]](#)
40. Rossiter, W.J.; Brown, P.W.; Godette, M. The determination of acidic degradation products in aqueous ethylene glycol and propylene glycol solutions using ion chromatography. *Sol. Energy Mater.* **1983**, *9*, 267–279. [\[CrossRef\]](#)
41. Campbell, J.M. *Gas Conditioning and Processing*; Campbell Petroleum Series: Norman, OK, USA, 1982.
42. Grimstedt, A.; da Silva, E.F.; Hoff, K.A. Thermal degradation of MEA, effect of temperature and CO<sub>2</sub> loading. *TCCS7 SINTEF Mater. Chem.* **2013**, 7465.
43. Shoukat, U.; Pinto, D.D.D.; Knuutila, H.K. Study of Various Aqueous and Non-Aqueous Amine Blends for Hydrogen Sulfide Removal from Natural Gas. *Processes* **2019**, *7*, 160. [\[CrossRef\]](#)
44. Ma'mun, S.; Svendsen, H.F.; Hoff, K.A.; Juliussen, O. Selection of new absorbents for carbon dioxide capture. *Energy Convers. Manag.* **2007**, *48*, 251–258. [\[CrossRef\]](#)
45. Monteiro, J.G.M.S.; Pinto, D.D.D.; Zaidy, S.A.H.; Hartono, A.; Svendsen, H.F. VLE data and modelling of aqueous N,N-diethylethanolamine (DEEA) solutions. *Int. J. Greenh. Gas Control* **2013**, *19*, 432–440. [\[CrossRef\]](#)
46. Vevelstad, S.J.; Johansen, M.T.; Knuutila, H.; Svendsen, H.F. Oxygen and Temperature Effect on Formation of Degradation Compounds from MEA. *Energy Procedia* **2014**, *63*, 957–975. [\[CrossRef\]](#)

