

Article

Thermal stability and thermoelectric properties of NaZnSb

Volodymyr Gvozdetskyi ¹, Bryan Owens-Baird ^{1,2}, Sangki Hong¹ and Julia V. Zaikina ^{1,*}

¹ Department of Chemistry, Iowa State University, Ames, IA 50011, United States; volodya@iastate.edu (V.G.); skhong@iastate.edu (S.H.)

² Ames Laboratory, U.S. Department of Energy, Ames, IA 50011 United States; bowens@iastate.edu (B.O-B.)

* Correspondence: yzaikina@iastate.edu; Tel.: +1-515-294-3125




Figure S1. Scanning electron microscopy (SEM) images obtained in back-scattered electrons (BSE, left) and secondary electrons (SE, right) modes for the sample of NaZnSb prepared via hydride route and further densified by SPS. The composition determined by EDXS is $\text{Na}_{1.3(1)}\text{Zn}_{1.0(1)}\text{Sb}_{1.0(1)}$. The standard deviation in composition is calculated for the data collected in 8 different areas of each sample. The combined error of EDXS analysis is $\pm 5\%$.