

The Effect of Crystalline Waterproofing Admixtures on the Self-Healing and Permeability of Concrete

Firstname Lastname ¹, Firstname Anita Gojević ¹, Vilma Ducman ², Ivanka Netinger Grubeša ^{1,*}, Ana Baričević ³ and Ivana Banjad Pecur ³

¹ Faculty of Civil Engineering and Architecture Osijek, University Josip Juraj Strossmayer of Osijek, Vladimir Prelog Street 3, 31000 Osijek, Croatia; anitagojevic@gmail.com

² Slovenian National Building and Civil Engineering Institute, Dimičeva 12, 1000 Ljubljana, Slovenia; vilma.ducman@zag.si

³ Faculty of Civil Engineering, University of Zagreb, Andrija Kačić Miošić Street 26, 10000 Zagreb, Croatia; ana.baricevic@grad.unizg.hr (A.B.); ivana.banjad.pecur@grad.unizg.hr (I.B.P.)

* Correspondence: nivanka@gfos.hr; Tel.: +38531540070

Table S1. Crack width before and after self-healing

Mix ID	Specimen number	Crack ID	Initial crack width [mm]	Initial crack pattern	Crack width after selfhealing [mm]	Reduction in crack width (%)	Crack reduction pattern
M-0.45-R	1	1	0.25	0.1 mm ≤ width <0.2 mm – 9 cracks	0.2	20	0% ≤ width reduction <20 % - 7 cracks 20% ≤ width reduction <90 % - 5 cracks 90% ≤ width reduction <100 % - 6 cracks
		2	0.55		0.45	18	
		3	0.1		0.1	0	
		4	0.2		0.2	0	
		5	0.3		0.2	33	
		6	0.2		0.2	0	
	2	1	0.5	0.2 mm ≤ width <0.3 mm – 6 cracks 0.3 mm ≤ width <0.4 mm – 1 crack 0.4 mm ≤ width <0.5 mm – 0 crack 0.5 mm ≤ width – 2 cracks	0.45	10	
		2	0.25		0.25	0	
		3	0.1		0	100	
		4	0.1		0	100	
		5	0.1		0.1	0	
		6	0.1		0	100	
	3	1	0.15		0.1	33	
		2	0.1		0	100	
		3	0.25		0.1	60	
		4	0.15		0	100	
		5	0.1		0	100	
		6	0.25		0.15	40	
M-0.45-CWA	1	1	0.1	0.1 mm ≤ width <0.2 mm – 10 cracks 0.2 mm ≤ width <0.3 mm – 4 cracks 0.3 mm ≤ width <0.4 mm – 3 cracks 0.4 mm ≤ width <0.5 mm – 0 crack 0.5 mm ≤ width – 1 crack	0	100	0% ≤ width reduction <20 % - 4 cracks 20% ≤ width reduction <90 % - 4 cracks 90% ≤ width reduction <100 % - 10 cracks
		2	0.3		0.3	0	
		3	0.1		0	100	
		4	0.2		0.2	0	
		5	0.25		0.2	20	
		6	0.5		0.5	0	
	2	1	0.1		0	100	
		2	0.1		0	100	
		3	0.15		0	100	
		4	0.25		0.1	60	
		5	0.3		0.25	17	
		6	0.15		0	100	
	3	1	0.15		0	100	
		2	0.3		0.15	50	
		3	0.1		0	100	
		4	0.1		0	100	
		5	0.2		0.15	25	
		6	0.1		0	100	

M-0.55 - R	1	1	0.3		0.2	33	
		2	0.6		0.5	17	
		3	0.1		0.1	0	
		4	0.15		0.1	33	
		5	0.2		0.1	50	
		6	0.15	0.1 mm ≤ width < 0.2 mm – 12 cracks	0.1	33	
	2	1	0.1	0.2 mm ≤ width < 0.3 mm – 4 cracks	0	100	0% ≤ width reduction < 20 % - 2 cracks
		2	0.2	0.3 mm ≤ width < 0.4 mm – 1 crack	0.15	25	20% ≤ width reduction < 90 % - 9 cracks
		3	0.1	0.4 mm ≤ width < 0.5 mm – 0 crack	0	100	90% ≤ width reduction < 100 % - 7 cracks
		4	0.1		0	100	
		5	0.1		0	100	
		6	0.15		0.1	33	
	3	1	0.2	0.5 mm ≤ width – 1 crack	0.1	50	
		2	0.1		0	100	
		3	0.25		0.2	20	
		4	0.15		0	100	
		5	0.15		0.1	33	
		6	0.1		0	100	
M-0.55-CWA	1	1	0.1		0	100	
		2	0.3		0.15	50	
		3	0.35		0.2	43	
		4	0.45		0.35	22	
		5	0.15	0.1 mm ≤ width < 0.2 mm – 11 cracks	0.1	33	
		6	0.3		0.25	17	
	2	1	0.15	0.2 mm ≤ width < 0.3 mm – 2 cracks	0	100	0% ≤ width reduction < 20 % - 1 cracks
		2	0.15	0.3 mm ≤ width < 0.4 mm – 4 cracks	0	100	20% ≤ width reduction < 90 % - 7 cracks
		3	0.1	0.4 mm ≤ width < 0.5 mm – 1 crack	0	100	90% ≤ width reduction < 100 % - 10 cracks
		4	0.15		0.15	40	
		5	0.25		0	100	
		6	0.1		0	100	
	3	1	0.1	0.5 mm > width – 0 crack	0	100	
		2	0.3		0.1	67	
		3	0.1		0	100	
		4	0.2		0.15	25	
		5	0.1		0	100	
		6	0.1		0	100	

Citation: Gojević, A.; Ducman, V.; Netinger Grubeša, I.; Baričević, A.; Banjad Pečur, I. The Effect of Crystalline Waterproofing Admixtures on the Self-Healing and Permeability of Concrete. *Materials* **2021**, *14*, 1860. <https://doi.org/10.3390/10.3390/ma14081860>

Academic Editor: Angelo Marcello Tarantino

Received: 9 March 2021

Accepted: 7 April 2021

Published: 9 April 2021

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2021 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).