

Communication

# Vinyl-Functionalized Janus Ring Siloxane: Potential Precursors to Hybrid Functional Materials

Thanawat Chaiprasert, Yujia Liu , Nobuhiro Takeda  and Masafumi Unno \* 

Department of Chemistry and Chemical Biology, Graduate School of Science and Technology, Gunma University, Kiryu 376-8515, Japan; t182a007@gunma-u.ac.jp (T.C.); yliu@gunma-u.ac.jp (Y.L.); ntakeda@gunma-u.ac.jp (N.T.)

\* Correspondence: unno@gunma-u.ac.jp

**Abstract:** A vinyl-functionalized all-*cis*-tetrasiloxycyclotetrasiloxane  $[ViSi(OSiMe_2H)O]_4$  ( $Vi =$  vinyl group) Janus precursor was prepared from potassium cyclotetrasiloxane silanolate. The Janus precursor was selectively modified at its dimethylhydrosilyl groups  $[-SiMe_2H]$  via the Piers–Rubinsztajn reaction to obtain a family of new tetravinyl-substituted Janus rings  $[ViSi(OR')O]_4$  containing various functional groups in moderate yields. Remarkably, the tetravinyl groups on the structure remained intact after modification by the Piers–Rubinsztajn reaction. Since these synthesized compounds possess multiple functional groups (up to eight per molecule), they are potential precursors for advanced hybrid organic-inorganic functional materials.

**Keywords:** Janus ring; silsesquioxane; hybrid organic-inorganic; vinyl monomer; Piers–Rubinsztajn reaction; cyclotetrasiloxane



**Citation:** Chaiprasert, T.; Liu, Y.; Takeda, N.; Unno, M. Vinyl-Functionalized Janus Ring Siloxane: Potential Precursors to Hybrid Functional Materials. *Materials* **2021**, *14*, 2014. <https://doi.org/10.3390/ma14082014>

Academic Editor: Barbara Gawdzik

Received: 27 February 2021

Accepted: 14 April 2021

Published: 16 April 2021

**Publisher's Note:** MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



**Copyright:** © 2021 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).


## 1. Introduction

Hybrid organic-inorganic silsesquioxane precursors play an important role in the development of new materials and have a high potential for industrial applications [1–3]. Among them, vinyl-functionalized silsesquioxanes are interesting precursors because the vinyl groups can be modified by various methods, e.g., C–C coupling reaction [4–7], cross-metathesis [8,9], hydrosilylation [10], thiol-ene reaction [11–14], and polymerization [15–17]. In contrast to silica compounds that have high crystallinity and poor solubility, silsesquioxane compounds typically have an adjustable solubility and good dispersion in organic solvents or organic materials [18–20]. This is a desirable characteristic for their use as a nanofiller to improve the thermal properties of materials instead of harmful transition metal compounds [21–24].

The cyclotetrasiloxane  $T_4$  ring, a silsesquioxane compound with a core structure containing four silicon and four oxygen atoms connected with adjustable organic substituents  $((RSi(OR')O)_4$ , shows promising characteristics like high thermal durability and a high refractive index with good solubility [25–28]. Furthermore, there are four possible isomeric structures of cyclotetrasiloxanes with two different substituents. Among them, all-*cis*-cyclotetrasiloxanes can be recognized as Janus molecules [29] because they have two different faces [30,31]. These Janus compounds have been used in the synthesis of well-defined nano-precursors [32–35], cubic silsesquioxanes  $T_8$  [30,36–38], copolymers [39,40], cyclic polymers [41–43], highly porous materials [4,11,12,44], semiconducting materials [45], protective coating molecules [46], and catalysts [47–49].

Although the synthesis of all-*cis*-cyclotetrasiloxanes with various substituents has been previously reported by several groups [30,36,50–59], there are only a few reported examples of modification, further functionalization, or bond extension of these compounds in the literature. For example, Makarova et al. [60] successfully modified the different stereoisomers of  $[PhSi(OSiMe_2H)O]_4$  by hydrosilylation with  $H_2C=CH(CH_2)_8COOC_6H_4C_6H_4CN$ . Previously, Marciniec et al. [61] synthesized various silsesquioxanes and demonstrated

a proficient selective cross-metathesis reaction catalyzed by the ruthenium-hydride complex  $[\text{RuHCl}(\text{CO})(\text{PCy}_3)_2]$  between olefins and tetramethyltetravinylcyclotetrasiloxane  $\text{D}_4$ , which has a cyclic ring structure similar to that of  $\text{T}_4$ . In 2012, Panisch et al. [29] reported the functionalization of all-*cis*-cyclotetrasiloxanes via the Heck and Sonogashira coupling reactions. The Piers–Rubinsztajn reaction, an efficient route for constructing the C–O–Si or Si–O–Si bonds [40,45,62–67], can also be used for the modification of hydrosilanes and hydrosilyl-functionalized linear, hyperbranched, cage  $\text{T}_8$ , and double-decker silsesquioxanes [40,45,62–64,66,68–84]. In the case of all-*cis*-cyclotetrasiloxanes, we recently synthesized and characterized Janus-type phenyl-substituted all-*cis*-cyclotetrasiloxanes, as shown in Scheme 1 [35]. The isomerization reaction was not observed when using the Piers–Rubinsztajn reaction. In the presence of excess water,  $[\text{PhSi}(\text{OSiMe}_2\text{H})\text{O}]_4$  underwent an intramolecular cyclization reaction to form a six- or eight-membered side ring [85].



**Scheme 1.** Previous work: (A) The synthesis of the Janus ring  $[\text{PhSi}(\text{OSiMe}_2\text{R})\text{O}]_4$  ( $\text{R} = 4$ -methylphenyl, phenyl, 4-bromophenyl, 4-chlorophenyl, 4-(chloromethyl)phenyl, and 4-allylphenyl) by the Piers–Rubinsztajn reaction. (B) The synthesis of a tricyclic laddersiloxane by the intramolecular cyclization mediated by  $\text{B}(\text{C}_6\text{F}_5)_3$ .

In continuation of our previous studies, herein we report the synthesis of various vinyl-functionalized Janus-type all-*cis*-cyclotetrasiloxanes  $[\text{ViSi}(\text{OSiMe}_2\text{OR})\text{O}]_4$ . Remarkably, only the hydrosilyl group ( $-\text{SiMe}_2\text{H}$ ) of the starting material  $[\text{ViSi}(\text{OSiMe}_2\text{H})\text{O}]_4$  was transformed selectively in the Piers–Rubinsztajn reaction, and the vinyl groups ( $\text{Vi}$ ) remained unreacted after the reaction. Furthermore, these compounds have high functional densities because they have four or eight functional groups per molecule.

## 2. Materials and Methods


### 2.1. General

All reactions in this study were conducted under an argon atmosphere (G2 grade (purity > 99.9995%, JAPAN FINE PRODUCTS (JFP), Kawasaki, Kanagawa, Japan) and stirred using Magnetic stirrer (PTFE stirrer, football type, As one, Osaka, Japan). All substrates were purchased from Tokyo Chemical Industry Co., Ltd., (Kawaguchi, Saitama, Japan) and used as received. The Janus precursor  $[\text{ViSi}(\text{OSiMe}_2\text{H})\text{O}]_4$  and potassium all-*cis*-tetravinylcyclotetrasiloxanolate were stored under anhydrous and argon atmospheres. All solvents were distilled and stored on anhydrous molecular sieves (Wako Pure Chemical Industries, Ltd., Osaka, Japan). Catalyst  $\text{B}(\text{C}_6\text{F}_5)_3$  was stored under an argon atmosphere. LC-5000 recycle-type preparative liquid chromatography was performed using a combination of a JAIGEL 1HR + 2HR (20 mm × 600 mm) GPC column (Japan Analytical Industry Co., Ltd., Tokyo, Japan) (eluent:  $\text{CHCl}_3$ ). Fourier-transform NMR spectra were obtained on a JEOL JNM-ECS 600 NMR spectrometer (JEOL Ltd., Akishima, Tokyo, Japan),  $^1\text{H}$  at

600 MHz,  $^{13}\text{C}$  at 150.91 MHz, and  $^{29}\text{Si}$  at 119.24 MHz). MALDI-TOF mass spectrometry was performed on a Shimadzu MALDI-TOF AXIMA<sup>®</sup> instrument (Shimadzu Corporation, Kyoto, Japan). IR spectra were measured with a Shimadzu FTIR-8400S instrument (Shimadzu Corporation, Kyoto, Japan).

## 2.2. Synthesis of Potassium All-Cis-Tetravinylcyclotetrasiloxanolate


As shown in Scheme 2, triethoxyvinylsilane (14.9 g, 88 mmol) was added dropwise to a round-bottom flask containing KOH (4.9 g, 88 mmol), water (1.6 g, 88 mmol), and hexane (90 mL) at room temperature. After stirring (RCT basic, IKA Japan K. K., Higashi-Osaka, Osaka, Japan) for 3.5 h, a white precipitate was formed. The precipitate was collected, washed with hexane, and dried using a high vacuum pump (G-20DA, ULVAC, Inc., Chigasaki, Kanagawa, Japan) for 1 day to yield potassium all-*cis*-tetravinylcyclotetrasiloxanolate as a white solid (5.00 g, 50% yield). Please note that this compound is highly hygroscopic and should be kept under an anhydrous atmosphere. In our study, it was used immediately after its preparation. Spectral data:  $^{29}\text{Si}$  NMR (methanol-d<sub>4</sub>)  $\delta = -42.06$  ppm.



**Scheme 2.** Synthesis of all-*cis*-tetravinylcyclotetrasiloxanolate by alkaline-direct condensation reaction.

## 2.3. Synthesis of Hydrido-Functionalized Janus Precursor $[\text{ViSi(OSiMe}_2\text{H})\text{O}]_4$

As shown in Scheme 3, in a 250 mL two-necked round-bottom flask equipped with a magnetic stirrer, the white solid of potassium all-*cis*-tetravinylcyclotetrasiloxanolate (molecular weight 504.91, 5.00 g, 9.09 mmol) was added and evacuated for 1 day before use. Subsequently, the flask was refilled with argon. Then, anhydrous hexane (100 mL) and distilled  $\text{NEt}_3$  (7.6 mL, 54.54 mmol, 6 equiv.) were added to the reaction flask, and the mixture was vigorously stirred at  $-5^\circ\text{C}$  for 60 min. Next,  $\text{SiMe}_2\text{HCl}$  (54.54 mmol, 6 equiv.) was added dropwise (1–2 drops per second) into the reaction flask via a glass syringe (Hamilton Company Inc., Reno, NV, USA). Water (200 mL) was then added to the reaction mixture, which was extracted with hexane (100 mL  $\times$  3). The combined organic layer was washed with water (200 mL  $\times$  3) and saturated  $\text{NaCl}$  solution once, dried over anhydrous  $\text{Na}_2\text{SO}_4$ , and concentrated using a high vacuum pump (G-20DA, ULVAC, Inc., Chigasaki, Kanagawa, Japan) for 1 day. After 1 day of evacuation, the pure product was obtained as a colorless liquid in 90% yield without purification.



**Scheme 3.** Synthesis of Janus precursor by condensation reaction.

Spectral data:  $^1\text{H}$  NMR of Janus precursor ( $\text{CDCl}_3$ )  $\delta = 0.26$ –0.26 ppm of  $\text{CH}_3$  (s); total H = 24H, 4.76–4.80 ppm of Si–H (m); 4H, 5.87–5.89 ppm for  $\text{CH}=\text{CH}_2$  (m); 8H, and 5.98–6.01 ppm (m) for  $\text{CH}=\text{CH}_2$ ; 4H),  $^{29}\text{Si}$  NMR of in  $\text{CDCl}_3$  ( $\delta = -4.06$  and  $-79.63$  ppm).

## 2.4. Synthesis of Vinyl-Functionalized Janus Rings $[\text{ViSi(OSiMe}_2\text{R})\text{O}]_4$

In a 25 mL two-necked round-bottom flask equipped with a magnetic stirrer, Janus precursor  $[\text{ViSi(OSiMe}_2\text{H})\text{O}]_4$  (200 mg, 0.34 mmol) was mixed with a solution of aryl

anisole (2.05 mmol, 6 equiv.) in anhydrous toluene (4 mL). Then, 5 mol%  $B(C_6F_5)_3$  (8.7 mg) was added to the reaction in an open system with an argon flow. After the addition of the catalyst, we observed that a gas was released spontaneously. The mixture was stirred at room temperature and subsequently quenched with water. Finally, the product was extracted using hexane, and the organic layer was washed with brine (CGC JAPAN CO., Ltd., Tokyo, Japan.) and dried over anhydrous  $Na_2SO_4$ . After solvent evaporation, the crude product was purified by GPC ( $CHCl_3$ ) (product yield and  $^{29}Si$ -NMR data are summarized in Table 1 and Supplementary Materials Table S1).

**Table 1.** The synthesis of Janus rings  $[ViSi(OSiMe_2OR)O]_4$  Vi-JR-01 to Vi-JR-08 by Piers–Rubinsztajn reaction from the Janus precursor  $[ViSi(OSiMe_2H)O]_4$  with an excess amount of aryl anisole.


Entry	Janus Rings	R	Isolated Yield <sup>1</sup> (%)
1	Vi-JR-01		60
2	Vi-JR-02		55
3	Vi-JR-03		42
4	Vi-JR-04		46
5	Vi-JR-05		39
6	Vi-JR-06		38
7	Vi-JR-07		50
8	Vi-JR-08		53

<sup>1</sup> The yield was determined after purification using GPC (eluent =  $CHCl_3$ ). All products are colorless viscous liquids.

### 3. Results

The Janus precursor  $[ViSi(OSiMe_2H)O]_4$  was prepared by the condensation of vinyl-functionalized potassium cyclotetrasiloxane silanolate all-*cis*- $[ViSi(OK)O]_4$  with chlorodimethylthysilane ( $Me_2SiHCl$ ) according to our previous report [27], as shown in Scheme 4. The


reaction was conducted under argon atmosphere at low temperature ( $-5\text{ }^{\circ}\text{C}$ ) with the slow addition of  $\text{Me}_2\text{SiHCl}$  in the presence of triethylamine ( $\text{NEt}_3$ ) to avoid side reactions such as acid-catalyzed isomerization and polymerization. These reaction conditions provided a 90% yield of the pure product ( $[\text{ViSi}(\text{OSiMe}_2\text{H})\text{O}]_4$ ), which was confirmed by Fourier transform infrared spectroscopy (FTIR) and nuclear magnetic resonance (NMR) spectroscopy (Supplementary Materials, Figures S1–S51).




**Scheme 4.** The synthesis of Janus precursors  $[\text{ViSi}(\text{OSiMe}_2\text{H})\text{O}]_4$  by the condensation of  $[\text{ViSi}(\text{OK})\text{O}]_4$  with  $\text{Me}_2\text{SiHCl}$  in the presence of  $\text{NEt}_3$ .

Further, reaction screening of the Janus precursor  $[\text{ViSi}(\text{OSiMe}_2\text{H})\text{O}]_4$  was conducted. It revealed that the Pier–Rubinsztajn reaction conditions enabled selective transformation of dimethylhydrosilyl groups with various aryl anisoles (Table 1). Vinyl-functionalized Janus ring products Vi-JR-01 to Vi-JR-08 were successfully synthesized in the presence of 5 mol%  $\text{B}(\text{C}_6\text{F}_5)_3$  using an excess of the aryl anisole derivatives (1.5 equivalents per Vi) at room temperature for 1 day. Anhydrous toluene was used as the solvent because all the starting materials displayed good solubility in this solvent. It is worth noting that the reactions were conducted using an open system with an argon flow because the catalyst liberated flammable methane gas. Purification by gel permeation chromatography (GPC) provided the desired Janus rings in moderate yields (Table 1).

In these reactions, the yields were affected by the purification methods because several byproducts formed as a result of partial intramolecular cyclization, intermolecular reaction, and polymerization, as shown in Figure 1. Owing to the interference of water or hydride migration, intramolecular cyclization took place competitively to partially form 6- or 8-membered cyclic or tricyclic laddersiloxanes as byproducts as shown in Scheme 5 [35,70–74,84,85].



**Figure 1.** The structure of target product and possible by-products, including the partial intramolecular cyclization product, intramolecular cyclization product (tricyclic laddersiloxane), and crosslinked product.



Scheme 5. Proposed reaction mechanism [35].

$^1\text{H}$ ,  $^{13}\text{C}$ , and  $^{29}\text{Si}$  NMR spectroscopy and matrix-assisted laser-desorption-ionization time-of-flight (MALDI-TOF) mass spectrometry were used to characterize the product structures. Similar results have been reported previously [35,59];  $^{29}\text{Si}$  NMR spectra for Vi-JR-01 to Vi-JR-08 exhibited two peaks in the region from  $-11.7$  to  $-12.3$  ppm, corresponding to the D unit of Si in the  $-\text{OSiMe}_2\text{OAr}$  arms, and in the region from  $-80.0$  to  $-80.7$  ppm, corresponding to the T unit Si atoms on the  $\text{T}_4$  ring of all-*cis*-cyclotetrasiloxanes. The disappearance of the signal at  $-4.08$  ppm confirmed that all the Si–H in the starting material was transformed to  $-\text{OSiMe}_2\text{OAr}$ . In the  $^1\text{H}$  NMR spectra, all the isolated products exhibited similar signals for the vinyl groups ( $\text{CH}=\text{CH}_2$ ) at  $5.90$ – $6.07$  ppm, confirming that these groups were intact after the reaction. The lone signal of the T unit Si in the  $^{29}\text{Si}$  NMR spectrum of each product confirmed the conservation of the all-*cis* structure. All target Janus ring products are colorless viscous liquids with lower thermal properties (e.g., glass transition temperature or melting temperature) and lower crystallinity than previously reported tricyclic laddersiloxanes, double-decker, or octahedral oligomeric silsesquioxanes  $\text{T}_8$  [25,26,86–91].

Further investigations of the application of these vinyl-functionalized Janus rings as ion recognition molecules and porous materials are underway in our group. These products can be considered highly functionalized precursors because they have either four vinyl groups in each molecule (Vi-JR-01 to Vi-JR-03, and Vi-JR-08) or eight functional groups per unit (Vi-JR-04 to Vi-JR-07). Since they can be prepared more easily than octahedral oligomeric silsesquioxanes, vinyl-functionalized Janus rings can be used for the construction of advanced materials, such as well-defined cage silsesquioxanes, Janus-type nanomaterials, new polymers, and porous materials.

#### 4. Conclusions

In this study, we successfully synthesized new vinyl-functionalized Janus-type all-*cis*-cyclotetrasiloxanes,  $[\text{ViSi}(\text{OSiMe}_2\text{OR})\text{O}]_4$  ( $\text{R} = 4\text{-methylphenyl}$  (Vi-JR-01), 2-methylphenyl (Vi-JR-02), phenyl (Vi-JR-03), 4-chlorophenyl (Vi-JR-04), 4-bromophenyl (Vi-JR-05), 4-iodophenyl (Vi-JR-06), 4-allylphenyl (Vi-JR-07), and naphthyl (Vi-JR-08)), by the Piers-Rubinsztajn reaction from the prepared Janus precursor. Currently, further investigations on the application of these compounds, e.g., as porous materials and ion-recognition-responsive materials, are underway in our group. Moreover, since these compounds have a high number of functional groups per unit, they are potential monomers of well-defined cage silsesquioxanes, Janus-type nanomolecules, and new polymers and porous materials.

**Supplementary Materials:** The following are available online at <https://www.mdpi.com/article/10.3390/ma14082014/s1>, including  $^1\text{H}$ ,  $^{13}\text{C}$ , and  $^{29}\text{Si}$  NMRs, MALDI-TOF-MS (Table S1, Figures S1 to S42), and FTIR spectra (Figures S43 to S51).

**Author Contributions:** Conceptualization, M.U. and T.C.; methodology, T.C. and Y.L.; X-ray structure analysis, N.T.; writing—original draft preparation, T.C.; writing—review and editing, Y.L.; supervision, M.U.; project administration, M.U.; funding acquisition, M.U., N.T., and Y.L. All authors have read and agreed to the published version of the manuscript.

**Funding:** This research is supported by the “Development of Innovative Catalytic Processes for Organosilicon Functional Materials” project (PL: K. Sato) from the New Energy and Industrial Technology Development Organization (NEDO).

**Institutional Review Board Statement:** Not applicable.

**Informed Consent Statement:** Not applicable.

**Data Availability Statement:** Data is contained within the article.

**Conflicts of Interest:** The authors declare no conflict of interest.

## References

1. Tanaka, K.; Chujo, Y. Advanced functional materials based on polyhedral oligomeric silsesquioxane (POSS). *J. Mater. Chem.* **2012**, *22*, 1733–1746. [[CrossRef](#)]
2. Foorginezhad, S.; Zerafat, M.M. Fabrication of superhydrophobic coatings with self-cleaning properties on cotton fabric based on Octa vinyl polyhedral oligomeric silsesquioxane/polydimethylsiloxane (OV-POSS/PDMS) nanocomposite. *J. Colloid Interface Sci.* **2019**, *540*, 78–87. [[CrossRef](#)]
3. Chan, K.L.; Sonar, P.; Sellinger, A. Cubic silsesquioxanes for use in solution processable organic light emitting diodes (OLED). *J. Mater. Chem.* **2009**, *19*, 9103–9120. [[CrossRef](#)]
4. Wang, D.; Xue, L.; Li, L.; Deng, B.; Feng, S.; Liu, H.; Zhao, X. Rational Design and Synthesis of Hybrid Porous Polymers Derived from Polyhedral Oligomeric Silsesquioxanes via Heck Coupling Reactions. *Macromol. Rapid Commun.* **2013**, *34*, 861–866. [[CrossRef](#)]
5. Chanmungkalakul, S.; Ervithayasuporn, V.; Hanprasit, S.; Masik, M.; Prigyai, N.; Kiatkamjornwong, S. Silsesquioxane cages as fluoride sensors. *Chem. Commun.* **2017**, *53*, 12108–12111. [[CrossRef](#)]
6. Chanmungkalakul, S.; Ervithayasuporn, V.; Boonkitti, P.; Phuekphong, A.; Prigyai, N.; Kladsomboon, S.; Kiatkamjornwong, S. Anion identification using silsesquioxane cages. *Chem. Sci.* **2018**, *9*, 7753–7765. [[CrossRef](#)]
7. Prigyai, N.; Chanmungkalakul, S.; Thanyalax, S.; Sukwattanasinitt, M.; Ervithayasuporn, V. Cyclic siloxanes conjugated with fluorescent aromatic compounds as fluoride sensors. *Mater. Adv.* **2020**, *1*, 3358–3368. [[CrossRef](#)]
8. Žak, P.; Pietraszuk, C. Application of olefin metathesis in the synthesis of functionalized polyhedral oligomeric silsesquioxanes (POSS) and POSS-containing polymeric materials. *Beilstein J. Org. Chem.* **2019**, *15*, 310–332. [[CrossRef](#)] [[PubMed](#)]
9. Itami, Y.; Marciniec, B.; Kubicki, M. Functionalization of Octavinylsilsesquioxane by Ruthenium-Catalyzed Silylative Coupling versus Cross-Metathesis. *Chem. A Eur. J.* **2004**, *10*, 1239–1248. [[CrossRef](#)]
10. Grzelak, M.; Januszewski, R.; Marciniec, B. Synthesis and Hydrosilylation of Vinyl-Substituted Open-Cage Silsesquioxanes with Phenylsilanes: Regioselective Synthesis of Trifunctional Silsesquioxanes. *Inorg. Chem.* **2020**, *59*, 7830–7840. [[CrossRef](#)]
11. Scholderer, P.; Nischang, I. Miniaturized catalysis: Monolithic, highly porous, large surface area capillary flow reactors constructed in situ from polyhedral oligomeric silsesquioxanes (POSS). *Catal. Sci. Technol.* **2015**, *5*, 3917–3921. [[CrossRef](#)] [[PubMed](#)]
12. Alves, F.; Nischang, I. Tailor-Made Hybrid Organic–Inorganic Porous Materials Based on Polyhedral Oligomeric Silsesquioxanes (POSS) by the Step-Growth Mechanism of Thiol-Ene “Click” Chemistry. *Chem. Eur. J.* **2013**, *19*, 17310–17313. [[CrossRef](#)] [[PubMed](#)]
13. Li, Y.; Guo, K.; Su, H.; Li, X.; Feng, X.; Wang, Z.; Zhang, W.; Zhu, S.; Wesdemiotis, C.; Cheng, S.Z.D.; et al. Tuning “thiolene” reactions toward controlled symmetry breaking in polyhedral oligomeric silsesquioxanes. *Chem. Sci.* **2014**, *5*, 1046–1053. [[CrossRef](#)]
14. Li, Y.; Dong, X.-H.; Guo, K.; Wang, Z.; Chen, Z.; Wesdemiotis, C.; Quirk, R.P.; Zhang, W.-B.; Cheng, S.Z.D. Synthesis of Shape Amphiphiles Based on POSS Tethered with Two Symmetric/Asymmetric Polymer Tails via Sequential “Grafting-from” and Thiol-Ene “Click” Chemistry. *ACS Macro Lett.* **2012**, *1*, 834–839. [[CrossRef](#)]
15. Li, G.; Wang, L.; Ni, H., Jr.; Pittman, C.U. Polyhedral Oligomeric Silsesquioxane (POSS) Polymers and Copolymers: A Review. *J. Inorg. Organomet. Polym. Mater.* **2001**, *11*, 123–154. [[CrossRef](#)]
16. Sangtrirutnugul, P.; Chaiprasert, T.; Hunsiri, W.; Jitjaroendee, T.; Songkhum, P.; Laohhasurayotin, K.; Osotchan, T.; Ervithayasuporn, V. Tunable Porosity of Cross-Linked-Polyhedral Oligomeric Silsesquioxane Supports for Palladium-Catalyzed Aerobic Alcohol Oxidation in Water. *ACS Appl. Mater. Interfaces* **2017**, *9*, 12812–12822. [[CrossRef](#)] [[PubMed](#)]
17. Dudziec, B.; Žak, P.; Marciniec, B. Synthetic Routes to Silsesquioxane-Based Systems as Photoactive Materials and Their Precursors. *Polymers* **2019**, *11*, 504. [[CrossRef](#)]
18. Baney, R.H.; Itoh, M.; Sakakibara, A.; Suzuki, T. Silsesquioxanes. *Chem. Rev.* **1995**, *95*, 1409–1430. [[CrossRef](#)]
19. Feher, F.J.; Newman, D.A.; Walzer, J.F. Silsesquioxanes as models for silica surfaces. *J. Am. Chem. Soc.* **1989**, *111*, 1741–1748. [[CrossRef](#)]

20. Cordes, D.B.; Lickiss, P.D.; Rataboul, F. Recent Developments in the Chemistry of Cubic Polyhedral Oligosilsesquioxanes. *Chem. Rev.* **2010**, *110*, 2081–2173. [CrossRef] [PubMed]
21. Zhao, J.; Fu, Y.; Liu, S. Polyhedral Oligomeric Silsesquioxane (POSS)-Modified Thermoplastic and Thermosetting Nanocomposites: A Review. *Polym. Polym. Compos.* **2008**, *16*, 483–500.
22. Dong, F.; Lu, L.; Ha, C.-S. Silsesquioxane-Containing Hybrid Nanomaterials: Fascinating Platforms for Advanced Applications. *Macromol. Chem. Phys.* **2019**, *220*, 1800324. [CrossRef]
23. Qian, Y.; Wei, P.; Zhao, X.; Jiang, P.; Yu, H. Flame retardancy and thermal stability of polyhedral oligomeric silsesquioxane nanocomposites. *Fire Mater.* **2011**, *37*, 1–16. [CrossRef]
24. Scapini, P.; Figueroa, C.A.; Amorim, C.L.; Machado, G.; Mauler, R.S.; Crespo, J.S.; Oliveira, R.V. Thermal and morphological properties of high-density polyethylene/ethylene-vinyl acetate copolymer composites with polyhedral oligomeric silsesquioxane nanostructure. *Polym. Int.* **2010**, *59*, 175–180.
25. Endo, H.; Takeda, N.; Takanashi, M.; Imai, T.; Unno, M. Refractive Indices of Silsesquioxanes with Various Structures. *Silicon* **2014**, *7*, 127–132. [CrossRef]
26. Endo, H.; Takeda, N.; Unno, M. Synthesis and Properties of Phenylsilsesquioxanes with Ladder and Double-Decker Structures. *Organometallics* **2014**, *33*, 4148–4151. [CrossRef]
27. Unno, M.; Endo, H.; Takeda, N. Synthesis and Structures of Extended Cyclic Siloxanes. *Heteroat. Chem.* **2014**, *25*, 525–532. [CrossRef]
28. Endo, H.; Takeda, N.; Unno, M. Stereoisomerization of Cyclic Silanols. *Chem. Asian J.* **2017**, *12*, 1224–1233. [CrossRef] [PubMed]
29. Panisch, R.; Bassindale, A.R.; Korlyukov, A.A.; Pitak, M.B.; Coles, S.J.; Taylor, P.G. Selective Derivatization and Characterization of Bifunctional “Janus-Type” Cyclotetrasiloxanes. *Organometallics* **2013**, *32*, 1732–1742. [CrossRef]
30. Yagihashi, F.; Igarashi, M.; Nakajima, Y.; Sato, K.; Yumoto, Y.; Matsui, C.; Shimada, S. Unexpected Selectivity in Cyclotetra-siloxane Formation by the Hydrolytic Condensation Reaction of Trichloro(phenyl)silane. *Eur. J. Inorg. Chem.* **2016**, *2016*, 2882–2886. [CrossRef]
31. Ryuichi, I.; Yuriko, K.; Yusuke, K. Cyclic Tetrasiloxanetetraols: Formation, Isolation, and Characterization. *Chem. Lett.* **2009**, *38*, 364–365.
32. Shankar, R.; Chaudhary, M.; Molloy, K.C.; Kociok-Kohn, G. New cyclotetrasiloxanes bearing sila-alkyl substituted side chains and their applications as templates for gold nanowires. *Dalton Trans.* **2013**, *42*, 7768–7774. [CrossRef] [PubMed]
33. Uchida, T.; Egawa, Y.; Adachi, T.; Oguri, N.; Kobayashi, M.; Kudo, T.; Takeda, N.; Unno, M.; Tanaka, R. Synthesis, Structures, and Thermal Properties of Symmetric and Janus “Lantern Cage” Siloxanes. *Chem. A Eur. J.* **2019**, *25*, 1683–1686. [CrossRef]
34. Liu, Y.; Onodera, K.; Takeda, N.; Ouali, A.; Unno, M. Synthesis and Characterization of Functionalizable Silsesquioxanes with Ladder-type Structures. *Organometallics* **2019**, *38*, 4373–4376. [CrossRef]
35. Chaiprasert, T.; Liu, Y.; Takeda, N.; Unno, M. Janus ring siloxane: A versatile precursor of the extended Janus ring and tricyclic laddersiloxanes. *Dalton Trans.* **2020**, *49*, 13533–13537. [CrossRef]
36. Asuncion, M.Z.; Ronchi, M.; Abu-Seir, H.; Laine, R.M. Synthesis, functionalization and properties of incompletely condensed “half cube” silsesquioxanes as a potential route to nanoscale Janus particles. *Comptes Rendus Chim.* **2010**, *13*, 270–281. [CrossRef]
37. Oguri, N.; Egawa, Y.; Takeda, N.; Unno, M. Janus-Cube Octasilsesquioxane: Facile Synthesis and Structure Elucidation. *Angewandte Chem. Int. Ed.* **2016**, *55*, 9336–9339. [CrossRef]
38. Tateyama, S.; Kakihana, Y.; Kawakami, Y. Cage octaphenylsilsesquioxane from cyclic tetrasiloxanetetraol and its sodium salt. *J. Organomet. Chem.* **2010**, *695*, 898–902. [CrossRef]
39. Inoue, H.; Matsukawa, K. Synthesis and Gas Permeability of Cyclotetrasiloxane-Containing Methacrylate Copolymers. *J. Macromol. Sci. Part A* **1992**, *29*, 415–440. [CrossRef]
40. Gretton, M.J.; Kamino, B.A.; Bender, T.P. Extension of the Application of Piers-Rubinsztajn Conditions to Produce Tri-arylamine Pendant Dimethylsiloxane Copolymers. *Macromol. Symp.* **2013**, *324*, 82–94. [CrossRef]
41. Wu, C.; Yu, J.; Li, Q.; Liu, Y. High molecular weight cyclic polysiloxanes from organocatalytic zwitterionic polymerization of constrained spirocyclosiloxanes. *Polym. Chem.* **2017**, *8*, 7301–7306. [CrossRef]
42. Frampton, M.B.; Marquardt, D.; Jones, T.R.B.; Harroun, T.A.; Zelisko, P.M. Macroyclic Oligoesters Incorporating a Cyclotetrasiloxane Ring. *Biomacromolecules* **2015**, *16*, 2091–2100. [CrossRef]
43. Casado, C.M.; Cuadrado, I.; Morán, M.; Alonso, B.; Barranco, M.; Losada, J. Cyclic siloxanes and silsesquioxanes as cores and frameworks for the construction of ferrocenyl dendrimers and polymers. *Appl. Organomet. Chem.* **1999**, *13*, 245–259. [CrossRef]
44. Du, Y.; Unno, M.; Liu, H. Hybrid Nanoporous Materials Derived from Ladder- and Cage-Type Silsesquioxanes for Water Treatment. *ACS Appl. Nano Mater.* **2020**, *3*, 1535–1541. [CrossRef]
45. Kamino, B.A.; Bender, T.P. The use of siloxanes, silsesquioxanes, and silicones in organic semiconducting materials. *Chem. Soc. Rev.* **2013**, *42*, 5119–5130. [CrossRef] [PubMed]
46. Rodošek, M.; Koželj, M.; Slemenik Perše, L.; Cerc Korošec, R.; Gaberšček, M.; Surca, A.K. Protective coatings for AA 2024 based on cyclotetrasiloxane and various alkoxysilanes. *Corros. Sci.* **2017**, *126*, 55–68. [CrossRef]
47. Bilyachenko, A.N.; Kulakova, A.N.; Levitsky, M.M.; Petrov, A.A.; Korlyukov, A.A.; Shul’Pina, L.S.; Khrustalev, V.N.; Dorovatovskii, P.V.; Vologzhanina, A.V.; Tsareva, U.S.; et al. Unusual Tri-, Hexa-, and Nonanuclear Cu(II) Cage Methylsilsesquioxanes: Synthesis, Structures, and Catalytic Activity in Oxidations with Peroxides. *Inorg. Chem.* **2017**, *56*, 4093–4103. [CrossRef]

48. Kulakova, A.N.; Bilyachenko, A.N.; Levitsky, M.M.; Khrustalev, V.N.; Korlyukov, A.A.; Zubavichus, Y.V.; Dorovatovskii, P.V.; Lamaty, F.; Bantrel, X.; Villeméjeanne, B.; et al.  $\text{Si}_{10}\text{Cu}_6\text{N}_4$  Cage Hexacoppersilsesquioxanes Containing N Ligands: Synthesis, Structure, and High Catalytic Activity in Peroxide Oxidations. *Inorg. Chem.* **2017**, *56*, 15026–15040. [[CrossRef](#)]
49. Bilyachenko, A.N.; Khrustalev, V.N.; Zubavichus, Y.V.; Shul’Pina, L.S.; Kulakova, A.N.; Bantrel, X.; Lamaty, F.; Levitsky, M.M.; Gutsul, E.I.; Shubina, E.S.; et al. Heptanuclear  $\text{Fe}_5\text{Cu}_2$ -Phenylgermsesquioxane containing 2,2'-Bipyridine: Synthesis, Structure, and Catalytic Activity in Oxidation of C–H Compounds. *Inorg. Chem.* **2017**, *57*, 528–534. [[CrossRef](#)]
50. Brown, J.F.; Vogt, L.H. The Polycondensation of Cyclohexylsilanetriol. *J. Am. Chem. Soc.* **1965**, *87*, 4313–4317. [[CrossRef](#)]
51. Brown, J.F. The Polycondensation of Phenylsilanetriol. *J. Am. Chem. Soc.* **1965**, *87*, 4317–4324. [[CrossRef](#)]
52. Vysochinskaya, Y.S.; Anisimov, A.A.; Milenin, S.A.; Korlyukov, A.A.; Dolgushin, F.M.; Kononova, E.G.; Peregudov, A.S.; Buzin, M.I.; Shchegolikhina, O.I.; Muzaferov, A.M. New all-cis-tetra(p-tolyl)cyclotetrasiloxanetetraol and its functionalization. *Mendeleev Commun.* **2018**, *28*, 418–420. [[CrossRef](#)]
53. Molodtsova, Y.; Pozdniakova, Y.; Lyssenko, K.; Blagodatskikh, I.; Katsoulis, D.; Shchegolikhina, O. A new approach to the synthesis of cage-like metallasiloxanes. *J. Organomet. Chem.* **1998**, *571*, 31–36. [[CrossRef](#)]
54. Molodtsova, Y.A.; Shchegolikhina, O.I.; Peregudov, A.S.; Buzin, M.I.; Matukhina, E.V. Synthesis and mesomorphic properties of cis-penta[(phenyl)(trimethylsiloxy)]cyclopentasiloxane. *Russ. Chem. Bull.* **2007**, *56*, 1402–1407. [[CrossRef](#)]
55. Shchegolikhina, O.; Pozdniakova, Y.; Antipin, M.; Katsoulis, D.; Auner, N.; Herrschaft, B. Synthesis and Structure of Sodium Phenylsiloxanolate. *Organometallics* **2000**, *19*, 1077–1082. [[CrossRef](#)]
56. Matukhina, E.V.; Shchegolikhina, O.I.; Makarova, N.N.; Pozdniakova, Y.A.; Katsoulis, D.E.; Godovsky, Y.K. New mesomorphic organocyclosiloxanes I. Thermal behaviour and mesophase structure of organocyclotetrasiloxanes. *Liq. Cryst.* **2001**, *28*, 869–879. [[CrossRef](#)]
57. Pozdniakova, Y.A.; Lyssenko, K.A.; Korlyukov, A.A.; Blagodatskikh, I.V.; Auner, N.; Katsoulis, D.; Shchegolikhina, O.I. Alkali-Metal-Directed Hydrolytic Condensation of Trifunctional Phenylalkoxysilanes. *Eur. J. Inorg. Chem.* **2004**, *2004*, 1253–1261. [[CrossRef](#)]
58. Shchegolikhina, O.I.; Pozdnyakova, Y.A.; Chetverikov, A.A.; Peregudov, A.S.; Buzin, M.I.; Matukhina, E.V. cis-Tetra[(organo)(trimethylsiloxy)]cyclotetrasiloxanes: Synthesis and mesomorphic properties. *Russ. Chem. Bull.* **2007**, *56*, 83–90. [[CrossRef](#)]
59. Ronchi, M.; Pizzotti, M.; Birol, A.O.; Macchi, P.; Lucenti, E.; Zucchi, C. Synthesis and structural characterization of functionalized cyclotetrasiloxane rings [4- $\text{RC}_6\text{H}_4\text{Si}(\text{O})\text{OR}'_4$ ] ( $\text{R} = \text{Cl}, \text{Br}, \text{CHCH}_2, \text{CH}_2\text{Cl}$ ;  $\text{R}' = \text{Na}, \text{SiMe}_3$ ) as scaffolds for the synthesis of models of a silica bound monolayer of fluorescent or second order NLO active organic chromophores. *J. Organomet. Chem.* **2007**, *692*, 1788–1798. [[CrossRef](#)]
60. Makarova, N.N.; Petrova, I.M.; Petrovskii, P.V.; Kaznacheev, A.V.; Volkova, L.M.; Shcherbina, M.A.; Bessonova, N.P.; Chvalun, S.N.; Godovskii, Y.K. Synthesis of new stereoregular 2,4,6,8-tetraphenylcyclotetrasiloxanes with mesogenic groups and the influence of spatial isomerism on the phase state of individual isomers and their mixtures. *Russ. Chem. Bull.* **2004**, *53*, 1983–1992. [[CrossRef](#)]
61. Marciniec, B.; Waehner, J.; Pawluc, P.; Kubicki, M. Highly stereoselective synthesis and application of functionalized tetra-vinylcyclotetrasiloxanes via catalytic reactions. *J. Mol. Catal. A Chem.* **2007**, *265*, 25–31. [[CrossRef](#)]
62. Kamino, B.A.; Mills, B.; Reali, C.; Gretton, M.J.; Brook, M.A.; Bender, T.P. Liquid Triarylamines: The Scope and Limitations of Piers–Rubinsztajn Conditions for Obtaining Triarylamine–Siloxane Hybrid Materials. *J. Org. Chem.* **2012**, *77*, 1663–1674. [[CrossRef](#)] [[PubMed](#)]
63. Brook, M.A.; Grande, J.B.; Ganachaud, F. New Synthetic Strategies for Structured Silicones Using  $\text{B}(\text{C}_6\text{F}_5)$ . In *Silicon Polymers*; Muzaferov, A.M., Ed.; Springer: Berlin/Heidelberg, Germany, 2011; pp. 161–183.
64. Brook, M.A. New Control Over Silicone Synthesis using SiH Chemistry: The Piers–Rubinsztajn Reaction. *Chem. A Eur. J.* **2018**, *24*, 8458–8469. [[CrossRef](#)] [[PubMed](#)]
65. Yoshikawa, M.; Shiba, H.; Wada, H.; Shimojima, A.; Kuroda, K. Polymerization of Cyclododecasiloxanes with Si–H and Si–OEt Side Groups by the Piers–Rubinsztajn Reaction. *Bull. Chem. Soc. Jpn.* **2018**, *91*, 747–753. [[CrossRef](#)]
66. Kamino, B.A.; Grande, J.B.; Brook, M.A.; Bender, T.P. Siloxane–Triarylamine Hybrids: Discrete Room Temperature Liquid Triarylamines via the Piers–Rubinsztajn Reaction. *Org. Lett.* **2011**, *13*, 154–157. [[CrossRef](#)] [[PubMed](#)]
67. Shinke, S.; Tsuchimoto, T.; Kawakami, Y. Stereochemistry in Lewis acid-catalyzed silylation of alcohols, silanols, and methoxysilanes with optically active methyl(1-naphthyl)phenylsilane. *Silicon Chem.* **2007**, *3*, 243–249. [[CrossRef](#)]
68. Grande, J.B.; Thompson, D.B.; Gonzaga, F.; Brook, M.A. Testing the functional tolerance of the Piers–Rubinsztajn reaction: A new strategy for functional silicones. *Chem. Commun.* **2010**, *46*, 4988–4990. [[CrossRef](#)] [[PubMed](#)]
69. Morgan, J.; Chen, T.; Hayes, R.; Dickie, T.; Urlich, T.; Brook, M.A. Facile synthesis of dendron-branched silicone polymers. *Polym. Chem.* **2017**, *8*, 2743–2746. [[CrossRef](#)]
70. Schneider, A.F.; Chen, Y.; Brook, M.A. Trace water affects tris(pentafluorophenyl)borane catalytic activity in the Piers–Rubinsztajn reaction. *Dalton Trans.* **2019**, *48*, 13599–13606. [[CrossRef](#)]
71. Chojnowski, J.; Rubinsztajn, S.; Cell, J.A.; Fortuniak, W.; Cypryk, M.; Kurjata, J.; Kaźmierski, K. Mechanism of the  $\text{B}(\text{C}_6\text{F}_5)_3$ -Catalyzed Reaction of Silyl Hydrides with Alkoxy silanes. Kinetic and Spectroscopic Studies. *Organometallics* **2005**, *24*, 6077–6084. [[CrossRef](#)]
72. Chojnowski, J.; Fortuniak, W.; Kurjata, J.; Rubinsztajn, S.; Cell, J.A. Oligomerization of Hydrosiloxanes in the Presence of Tris(pentafluorophenyl)borane. *Macromolecules* **2006**, *39*, 3802–3807. [[CrossRef](#)]

73. Chojnowski, J.; Rubinsztajn, S.; Fortuniak, W.; Kurjata, J. Oligomer and Polymer Formation in Hexamethylcyclotrisiloxane (D<sub>3</sub>)-Hydrosilane Systems Under Catalysis by tris(pentafluorophenyl)borane. *J. Inorg. Organomet. Polym. Mater.* **2007**, *17*, 173–187. [[CrossRef](#)]
74. Chojnowski, J.; Kurjata, J.; Fortuniak, W.; Rubinsztajn, S.; Trzebicka, B. Hydride Transfer Ring-Opening Polymerization of a Cyclic Oligomethylhydrosiloxane. Route to a Polymer of Closed Multicyclic Structure. *Macromolecules* **2012**, *45*, 2654–2661. [[CrossRef](#)]
75. Zhou, D.; Kawakami, Y. Tris(pentafluorophenyl)borane as a Superior Catalyst in the Synthesis of Optically Active SiO-Containing Polymers. *Macromolecules* **2005**, *38*, 6902–6908. [[CrossRef](#)]
76. Kawakami, Y.; Li, Y.; Liu, Y.; Seino, M.; Pakjamsai, C.; Oishi, M.; Cho, Y.H.; Imae, I. Control of molecular weight, stereo-chemistry and higher order structure of siloxane-containing polymers and their functional design. *Macromol. Res.* **2004**, *12*, 156–171. [[CrossRef](#)]
77. Hoque, A.; Kakihana, Y.; Shinke, S.; Kawakami, Y. Polysiloxanes with Periodically Distributed Isomeric Double-Decker Silsesquioxane in the Main Chain. *Macromolecules* **2009**, *42*, 3309–3315. [[CrossRef](#)]
78. Sodkhamkhum, R.; Ervithayasuporn, V. Synthesis of poly(siloxane/double-decker silsesquioxane) via dehydrocarbonative condensation reaction and its functionalization. *Polymers* **2016**, *86*, 113–119. [[CrossRef](#)]
79. Rubinsztajn, S.; Cellia, J.A. A New Polycondensation Process for the Preparation of Polysiloxane Copolymers. *Macromolecules* **2005**, *38*, 1061–1063. [[CrossRef](#)]
80. Cellia, J.; Rubinsztajn, S. Preparation of Polyaryloxysilanes and Polyaryloxysiloxanes by B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub> Catalyzed Polyetherification of Dihydrosilanes and Bis-Phenols. *Macromolecules* **2008**, *41*, 6965–6971. [[CrossRef](#)]
81. Blackwell, J.M.; Foster, K.L.; Beck, V.H.; Piers, W.E. B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub>-Catalyzed Silation of Alcohols: A Mild, General Method for Synthesis of Silyl Ethers. *J. Org. Chem.* **1999**, *64*, 4887–4892. [[CrossRef](#)]
82. Kaźmierczak, J.; Lewandowski, D.; Hreczycho, G. B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub>-Catalyzed Dehydrocoupling of POSS Silanols with Hydrosilanes: A Metal-Free Strategy for Effecting Functionalization of Silsesquioxanes. *Inorg. Chem.* **2020**, *59*, 9206–9214. [[CrossRef](#)]
83. Matsumoto, K.; Oba, Y.; Nakajima, Y.; Shimada, S.; Sato, K. One-Pot Sequence-Controlled Synthesis of Oligosiloxanes. *Angewandte Chem. Int. Ed.* **2018**, *57*, 4637–4641. [[CrossRef](#)]
84. Yang, W.; Gao, L.; Lu, J.; Song, Z.; Ji, L. Chemoselective deoxygenation of ether-substituted alcohols and carbonyl compounds by B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub>-catalyzed reduction with (HMe<sub>2</sub>SiCH<sub>2</sub>). *Chem. Commun.* **2018**, *54*, 4834–4837. [[CrossRef](#)] [[PubMed](#)]
85. Chaiprasert, T.; Liu, Y.; Intaraprecha, P.-k.; Kunthom, R.; Takeda, N.; Unno, M. Synthesis of Tricyclic Laddersiloxane with Various Ring Sizes (Bat Siloxane). *Macromol. Rapid Commun.* **2021**, *42*, 2000608. [[CrossRef](#)]
86. Unno, M.; Suto, A.; Matsumoto, H. Pentacyclic Laddersiloxane. *J. Am. Chem. Soc.* **2002**, *124*, 1574–1575. [[CrossRef](#)]
87. Chang, S.; Matsumoto, T.; Matsumoto, H.; Unno, M. Synthesis and characterization of heptacyclic laddersiloxanes and ladder polysilsesquioxane. *Appl. Organomet. Chem.* **2010**, *24*, 241–246. [[CrossRef](#)]
88. Unno, M.; Matsumoto, T.; Matsumoto, H. Nonacyclic Ladder Silsesquioxanes and Spectral Features of Ladder Polysilsesquioxanes. *Int. J. Polym. Sci.* **2012**, *2012*, 723892. [[CrossRef](#)]
89. Unno, M.; Suto, A.; Matsumoto, T. Laddersiloxanes—Silsesquioxanes with defined ladder structure. *Russ. Chem. Rev.* **2013**, *82*, 289–302. [[CrossRef](#)]
90. Kunthom, R.; Adachi, T.; Liu, Y.; Takeda, N.; Unno, M.; Tanaka, R. Synthesis of a “Butterfly Cage” Based on a Double-Decker Silsesquioxane. *Chem. Asian J.* **2019**, *14*, 4179–4182. [[CrossRef](#)]
91. Kunthom, R.; Takeda, N.; Unno, M. Synthesis and Characterization of Unsymmetrical Double-Decker Siloxane (Basket Cage). *Molecules* **2019**, *24*, 4252. [[CrossRef](#)] [[PubMed](#)]