



Purevdulam Namkhai and Kiwan Jang \*

Department of Physics, Changwon National University, Changwon 51140, Korea \* Correspondence: kwjang@changwon.ac.kr

**Abstract:** To investigate the effect of co-doping on the optical properties of  $Eu^{(2+/3+)}$  doped in  $Ba_{0.98}SiO_3:0.02Eu$ , the series of  $Ba_{0.96}SiO_3:0.02Eu$ ,  $0.02R^{+/3+}$  ( $R^+ = Li^+$ ,  $K^+$  or  $Na^+$ ,  $R^{3+} = La^{3+}$  or  $Y^{3+}$ ) phosphors were synthesized using a solid-state reaction method. The excitation efficiency due to the charge transfer band (CTB) was enhanced via co-doping of  $R^+$  and the emission intensity due to  $Eu^{3+}$  was thus increased by 3.7 times compared with that of the single-doped  $Ba_{0.98}SiO_3:0.02Eu^{3+}$ . However, the co-doping of  $R^+$  does not increase the emission intensity of  $Eu^{3+}$  via the direct  ${}^7F_0 \rightarrow {}^5L_6$  excitation of  $Eu^{3+}$ , but rather decreases it. On the other hand, the emission intensities due to  $Eu^{2+}$  were decreased via the co-doping of  $R^+$  but increased via the co-doping of  $La^{3+}$ . The present work reveals that the optical properties of  $Eu^{3+}$  or  $Eu^{2+}$  doped in  $BaSiO_3$  depend not on the charge state (+ or 3+) of the co-doped ions, but on the co-doped element itself.

**Keywords:** BaSiO<sub>3</sub>; photoluminescence; emission efficiency; pc-white LED phosphor; divalent europium



**Citation:** Namkhai, P.; Jang, K. Co-Doping Effect on the Optical Properties of Eu<sup>(2+/3+)</sup> Doped in BaSiO<sub>3</sub>. *Materials* **2022**, *15*, 6559. https://doi.org/10.3390/ ma15196559

Academic Editors: Dirk Poelman, Antonio Polimeni and Dominique de Caro

Received: 14 August 2022 Accepted: 19 September 2022 Published: 21 September 2022

**Publisher's Note:** MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



**Copyright:** © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/).

# 1. Introduction

The photoluminescent properties of rare-earth (RE) ions have attracted considerable interest because of their potential applications as phosphors, white light-emitting diodes (WLEDs), and lasers, etc. When doped in inorganic host materials, RE ions energetically prefer the trivalent state in hosts. Some RE ions, such as Eu, Sm, and Yb, where Yb<sup>2+</sup> is more stable than Yb<sup>3+</sup>, are doped with divalent atoms in some hosts. Specifically, Eu<sup>2+</sup>-doped phosphors exhibit a broad emission band that varies from ultra-violet to red, depending on the host lattice, and some of Eu<sup>3+</sup>-doped phosphors are used as a typical red phosphor. Thus, europium-based luminescence materials are extensively used in solid-state lighting, solar cells, red phosphors, and WLEDs.

Silicates are widely used as phosphor hosts due to their merits, such as their high thermal stability, the high energy efficiency of the silicate phosphors, and the inexpensive nature of the raw materials. Most often, the europium ions in a host are substituted into alkaline earth metals such as  $Ba^{2+}$ ,  $Sr^{2+}$ , or  $Ca^{2+}$ . When  $Eu^{3+}$  ions are doped in silicate hosts such as BaSiO<sub>3</sub>, Ca<sub>2</sub>SiO<sub>4</sub>, and Sr<sub>2</sub>SiO<sub>4</sub> through heat-treatment in air, there should be a charge balance mechanism involved in replacing  $A^{2+}(A^{2+} = Ba^{2+}, Ca^{2+}, and Sr^{2+})$  with  $Eu^{3+}$ . In the case of BaSiO<sub>3</sub>, in which  $Eu^{3+}$  replaces the Ba<sup>2+</sup> site based on the ionic radius, negatively charged barium ion vacancies (V<sub>ba</sub>) are created for charge compensation. It is known that the creation of such defects leads to a deterioration in the optical performance of the synthesized phosphors. Jiang et al. have investigated the influence of Li<sup>+</sup> co-doping on the photoluminescence of Eu<sup>3+</sup> doped in an SrWO<sub>4</sub> host [1]. Li et al. also studied the effect of Li<sup>+</sup>, Na<sup>+</sup>, and K<sup>+</sup> on the PL enhancement of Tb<sup>3+</sup> doped in CaMoO<sub>4</sub> [2]. In many cases, it has been reported that the co-doping of alkali-metal ions or  $Y^{3+}$  or  $La^{3+}$ enhances the emission intensity of RE ions doped in host materials [3–7]. However, it has also been reported that the emission intensity decreased in ZnTa<sub>2</sub>O<sub>6</sub>:Pr<sup>3+</sup> co-doped with alkali-metal ions [8]. The Eu<sup>3+</sup> ions doped in a BaSiO<sub>3</sub> host will be located along with

the Ba<sup>2+</sup> site because the ionic radius of Eu<sup>3+</sup> is similar to that of Ba<sup>2+</sup>. Meanwhile, the BaSiO<sub>3</sub>:Eu<sup>2+</sup> phosphors are mostly prepared via the heat-treatment of BaSiO<sub>3</sub>:Eu<sup>3+</sup> in a reducing atmosphere at high temperature. In this reduction process, the V<sub>ba</sub> defect created for charge compensation in BaSiO<sub>3</sub>:Eu<sup>3+</sup> will lose its charge compensation function. To date, to the best of the authors' knowledge, there have been no reports on the effect of V<sub>ba</sub> on the optical properties of Eu<sup>2+</sup> doped in BaSiO<sub>3</sub>.

In this article, we report on the co-doping effects of alkali metal ions and  $La^{3+}$  (or  $Y^{3+}$ ) on the optical properties of BaSiO<sub>3</sub>:Eu<sup>(2+/3+)</sup> fabricated via a solid-state reaction (SSR) method. The effects of Li<sup>+</sup>, K<sup>+</sup>, Na<sup>+</sup>, La<sup>3+</sup>, and Y<sup>3+</sup> co-doped with Eu<sup>(2+/3+)</sup> on the crystalline phase and the optical properties of BaSiO<sub>3</sub>:Eu<sup>(2+/3+)</sup> are discussed. The results showed that the doping of Li<sup>+</sup>, K<sup>+</sup>, Na<sup>+</sup>, La<sup>3+</sup>, and Y<sup>3+</sup> can significantly affect the optical properties of Eu<sup>(2+/3+)</sup> but the element used for the co-doping ion has a greater effect on the optical properties of Eu<sup>(2+/3+)</sup> than the charge state (+ or 3+) of the co-doping ion.

#### 2. Materials and Methods

A series of Ba<sub>0.98</sub>SiO<sub>3</sub>:0.02Eu, Ba<sub>0.96</sub>SiO<sub>3</sub>:0.02Eu, and 0.02R (R = Li, K, Na, La, and Y) phosphors were prepared using a conventional solid-state reaction. The BaCO<sub>3</sub> (99+%), SiO<sub>2</sub> (particle size 5~20 nm, 99.5%), Eu<sub>2</sub>O<sub>3</sub> (99.99%), K<sub>2</sub>CO<sub>3</sub> (99+%), Li<sub>2</sub>CO<sub>3</sub> (99+%), Li<sub>2</sub>O (97%), Na<sub>2</sub>CO<sub>3</sub> (99+%), LaCl<sub>3</sub> (99.99%), and Y<sub>2</sub>O<sub>3</sub> (99.99%), purchased from Merck, were used as a raw materials but SiO<sub>2</sub> was used 20% more to obtain a single-phase BaSiO<sub>3</sub> sample. The raw materials were thoroughly mixed in an agate mortar and subsequently fired in air at 1100 °C for 4 h to synthesize the Eu<sup>3+</sup>-doped BaSiO<sub>3</sub>. The BaSiO<sub>3</sub>:Eu<sup>2+</sup> samples were prepared by sintering the BaSiO<sub>3</sub>:Eu<sup>3+</sup> samples again under a reduction atmosphere (95% N<sub>2</sub> + 5% H<sub>2</sub>) at 1200 °C for 6 h. The specific formulations of the studied samples are shown in Table 1.

Sample No	Eu <sup>(3+/2+)</sup> (2%)	R	Remark
1	Eu <sup>3+</sup>	0	1st heat treated in air
2	Eu <sup>3+</sup>	0.02 Li <sup>+</sup>	$R = Li$ , $Li_2O$ used as co-doping material, 1st heat treated in air
3	Eu <sup>3+</sup>	0.02 Li <sup>+</sup>	$R = Li, Li_2CO_3$ used as co-doping material, 1st heat treated in air
4	Eu <sup>3+</sup>	0.02 K <sup>+</sup>	$R = K, K_2CO_3$ used as co-doping material, 1st heat treated in air
5	2 Eu <sup>3+</sup>	0.02 Na <sup>+</sup>	$R = Na$ , $Na_2CO_3$ used as co-doping material, 1st heat treated in air
6	Eu <sup>3+</sup>	0.02 La <sup>3+</sup>	$R = La, LaCl_3$ used as co-doping material, 1st heat treated in air
7	Eu <sup>3+</sup>	0.02 Y <sup>3+</sup>	$R = Y$ , $Y_2O_3$ used as co-doping material, 1st heat treated in air
8	Eu <sup>2+</sup>	0	same as sample 1 except 2nd heat treated in a reducing atmosphere
9	0 Eu <sup>2+</sup>	0.02 Li <sup>+</sup>	same as sample 2 except 2nd heat treated in a reducing atmosphere
10	Eu <sup>2+</sup>	0.02 Li <sup>+</sup>	same as sample 3 except 2nd heat treated in a reducing atmosphere
11	Eu <sup>2+</sup>	0.02 K <sup>+</sup>	same as sample 4 except 2nd heat treated in a reducing atmosphere
12	Eu <sup>2+</sup>	0.02 Na <sup>+</sup>	same as sample 5 except 2nd heat treated in a reducing atmosphere
13	Eu <sup>2+</sup>	0.02 La <sup>3+</sup>	same as sample 6 except 2nd heat treated in a reducing atmosphere
14	Eu <sup>2+</sup>	0.02 Y <sup>3+</sup>	same as sample 7 except 2nd heat treated in a reducing atmosphere

Table 1. Studied samples.

The crystal phase of the obtained samples was identified using an X-ray diffractometer (X'Pert PRO MPD-3040, Malvern Panalytical, Malvern, UK, CuK<sub> $\alpha$ 1</sub>,  $\lambda$  = 1.5406 Å) operating at 40 kV and 30 mA with a scan speed of 0.02°/sec. The photoluminescence excitation (PLE) and emission (PL) spectra were measured using a fluorescent spectrofluorometer (JASCO FP-8500, JASCO, Tokyo, Japan) equipped with an integrating sphere (ISF-834, JASCO, Tokyo, Japan). All measurements were performed at room temperature.

# 3. Results and Discussion

Figure 1 shows the X-ray powder diffraction (XRD) patterns of the studied samples. The XRD patterns of all samples were relatively well matched with pure BaSiO<sub>3</sub> (JCPDS-702112) within the accuracy of our XRD equipment, indicating that the studied samples were single-phased BaSiO<sub>3</sub>, which crystallizes in an orthorhombic structure and has a space group of P2<sub>1</sub>2<sub>1</sub>2<sub>1</sub> with lattice constants of a = 0.4580 nm, b = 0.5611 nm, and c = 1.2431 nm,  $\alpha = \beta = \gamma = 90^{\circ}$  [7]. This also means that the activator Eu<sup>(2+/3+)</sup> ions and co-doping ions R<sup>+/3+</sup> which were small-doped in the samples, did not cause any significant changes in the crystal phase of BaSiO<sub>3</sub>. Miscellaneous minor peaks were marked with a plus (+) and an asterisk (\*). The XRD patterns of samples 8–14, prepared under a reducing atmosphere, were identical to those of samples 1–7 because there was no change in crystallinity even if the secondary heat treatment was performed under a reducing atmosphere. The XRD patterns of the samples prepared under a reducing atmosphere. The XRD patterns of the samples prepared under a reducing atmosphere. The XRD patterns of the samples prepared under a reducing atmosphere. The XRD patterns of the samples prepared under a reducing atmosphere.



Figure 1. XRD patterns of Ba<sub>0.98</sub>SiO<sub>3</sub>:0.02Eu<sup>3+</sup>, 0.02R (R = Li<sup>+</sup>, K<sup>+</sup> and Na<sup>+</sup>).

Based on the data provided by the Cambridge Crystallographic Data Center, Si<sup>4+</sup> ions are located at the center of a tetrahedron coordinated with four  $O_2^-$  ions. The  $[SiO_4]^{2-}$  tetrahedrons form a chain running parallel to the *c*-axis by sharing corners and the Ba<sup>2+</sup> ions are accommodated in the tunnels between chains [9,10].

In our previous work [11], the crystal structure of  $BaSiO_3$  was found to be highly dependent on the particle size of the  $SiO_2$  used as a raw material. Even though this result was not presented in this paper, it was not possible to fabricate samples not having the minor second phase with  $SiO_2$ , the particle size of which was greater than 500 nm. This means that the characteristics of raw materials having the same molecular formula can highly affect the crystal structures of the samples prepared under the same preparation conditions. Specially, the optical properties of  $BaSiO_3:Eu^{2+}$  are highly sensitive to the presence or absence of the minor second phase in the crystal structure, even though this is not true of other materials. The main reason that previously reported results are slightly different may be due to the difficulties involved in achieving single-phase  $BaSiO_3:Eu^{2+}$  fabrication without having some minor peaks [10,12,13].

The crystal structure of BaSiO<sub>3</sub> has been detailed in other works [10,14], where a Ba site and six oxygen atoms bond together in the BaSiO<sub>3</sub> unit cell. Since Ba<sup>2+</sup> ions (0.135 nm) are closer to Eu<sup>3+</sup> ions (0.0947 nm) than Si<sup>4+</sup> ions (0.0400 nm) in terms of their ionic radius, Ba<sup>2+</sup> is expected to be replaced by Eu<sup>3+</sup> [7]. Assuming that Ba<sup>2+</sup> is expected to be replaced by Eu<sup>3+</sup>, an imbalance of charges is generated in the sample, resulting in the creation of a negatively charged defect, V<sub>Ba</sub>. To solve this problem, charge compensators such as Li<sup>+</sup>, K<sup>+</sup>,

or Na<sup>+</sup> were co-doped with Eu<sup>3+</sup> and the effect of charge compensation on the emission of Eu<sup>3+</sup> has been reported [7]. Yang et al. reported that doping with Na<sup>+</sup> and K<sup>+</sup> ions has a drastic effect on the improvement of the excitation and emission of Eu<sup>3+</sup> [7]. However, through this work, we found that doping with Y<sup>3+</sup> ions also has the same effect as that obtained with Na<sup>+</sup> and K<sup>+</sup> ions. This result means that the improvement of the excitation and emission of Eu<sup>3+</sup> could be determined by the species of co-doping ions, rather than the charge state of the co-doping ions, and also shows that this process may not be explained with charge compensation alone, as described so far.

Figure 2 illustrates the excitation and emission spectra of  $Ba_{0.96}SiO_3:0.02Eu^{3+}$ ,  $0.02R^{+/3+}$  samples. The PLE, measured by monitoring the strongest  $Eu^{3+}$  emission at 612 nm, is shown in Figure 2a. When  $Eu_2O_3$ , which is an optical active material, was mixed with other host materials and then heat-treated in air, the Eu ions were doped into  $Eu^{3+}$  in the host material due to its chemical stability. The PLE spectra exhibit a wide band known as a charge transfer band (CTB), where the electrons come from the entirely filled 2p orbitals of  $O^{2-}$  ions and are transferred to the partially filled 4f orbitals of  $Eu^{3+}$ . The CTB ranged from 200 nm to 290 nm, with the highest peak centered around 228 nm. Lingxiang Yang et al. reported that the CTB peaked around 246 nm [14]. This 18 nm difference in the CTB peak position may be attributed to the crystallinity of the studied samples. The sample studied by Lingxiang Yang et al. exhibited relatively many miscellaneous peaks, which were ascribed to the BaSi<sub>2</sub>O<sub>5</sub> phase (JCPDS#26-0176), compared with our samples.



**Figure 2.** Excitation spectra (**a**) obtained by monitoring the emission at 612 nm, emission spectra at an excitation wavelength of (**b**) 230 nm and (**c**) 393 nm for  $Ba_{0.96}SiO_3:0.02Eu^{3+}$ ,  $0.02R^{+/3+}$  phosphors (samples 1–7).

Based on our previous study, we knew that the optical properties of  $Eu^{(2+/3+)}$  doped in BaSiO<sub>3</sub> were more highly dependent upon the crystallinity of the host materials, compared to other host materials. Several narrow bands from 300 nm to 550 nm, due to the intra-4f transitions of  $Eu^{3+}$  ions, were also observed. Since the transitions of  $Eu^{3+}$  were very stable, and are almost certainly not affected by the lattice structure or neighboring anion ligands of  $Eu^{3+}$ , the excitation peaks were almost same for all samples. However, in the case of the CTB, things were quite different. It has been reported in the literature that the CTB depends greatly on the lattice structure of the matrix in which  $Eu^{3+}$  was introduced [15]. For example, the CTB peak position for  $Sr_2SiO_4:Eu^{3+}$  is 293 nm and it was 250 nm for the  $Gd_2O_3$  [16]. It is thus reasonable to assume that the 18 nm difference in the CTB peak position may be attributed to the crystallinity of the studied samples.

One interesting aspect of our results is that the excitation efficiency due to the CTB in sample 5, co-doped with Na<sup>+</sup> ions, was enhanced by 3.7 times compared with that of the single-doped sample 1. The CTB excitation efficiency of sample 7, co-doped with  $Y^{3+}$ , was two times higher than that of sample 6, co-doped with La<sup>3+</sup>. Furthermore, The CTB excitation efficiency of samples co-doped with Li<sup>+</sup> or K<sup>+</sup> was twice as high as that of the single-doped sample 1. These results mean that the co-doped R<sup>+/3+</sup> ions act as a sensitizer and can thus contribute to the enhancement of the emission intensity due to Eu<sup>3+</sup>. It is thus

relatively reasonable to conclude that the CTB excitation efficiency does not depend greatly on the charge state of the co-doping element, but rather on the species of co-doping ions.

Upon the excitation of CTB's 230 nm region, as shown in Figure 2a, the  ${}^{5}D_{0}\rightarrow{}^{7}F_{2}$  maximum transition intensity of Eu<sup>3+</sup> for sample 5, co-doped with Na<sup>+</sup>, was enhanced by a factor of 3.7 times compared with sample 1. In the case of samples 2 and 3, which were co-doped with the same Li<sup>+</sup>, the  ${}^{5}D_{0}\rightarrow{}^{7}F_{2}$  transition intensity of sample 2 was stronger than that of sample 3. We have thus shown through this study, for the first time, that the emission efficiency of Eu<sup>3+</sup> is dependent upon the raw material of the co-doping ions, rather than the charge state of the co-doping ions. Figure 2c shows the emission spectra obtained at an excitation wavelength of 393 nm, which represents a  ${}^{7}F_{0}\rightarrow{}^{5}L_{6}$  excitation of Eu<sup>3+</sup>. The emission intensities of samples 2, 3, and 6, co-doped with Li<sup>+</sup> or La<sup>3+</sup> ions, were stronger than that of sample 1 but that of sample 4, co-doped with K<sup>+</sup>, Na<sup>+</sup> and K<sup>+</sup>, was much weaker than that of sample 1.

Figure 3 shows the strongest Eu<sup>3+</sup> emission intensity that was obtained at 612 nm when excited by 230 nm and 393 nm, and it also shows the difference in the excitation efficiency through the CTB and the direct  ${}^{7}F_{0} \rightarrow {}^{5}L_{6}$  excitation of Eu<sup>3+</sup>. When excited by CTB's 230 nm region, the results clearly showed that the excitation efficiencies of sample 5, co-doped with Na<sup>+</sup>, and sample 4, co-doped with K<sup>+</sup>, were much better than those of other samples. However, the excitation efficiency of sample 4, excited by 393 nm, which represents  ${}^{7}F_{0} \rightarrow {}^{5}L_{6}$  excitation of Eu<sup>3+</sup>.



**Figure 3.** Effect of co-doping on the PL intensity of Eu<sup>3+</sup> ions excited by 230 nm and 393 nm, respectively.

Figure 4a–d shows the PLE and PL spectra of the studied BaSiO<sub>3</sub>:Eu<sup>2+</sup> phosphors (samples 8–14). The PLE spectra, measured by monitoring the 577 nm emission intensity, are shown in Figure 4a. The PLE spectra cover a very broad region, from 200 to 450 nm, with two peaks of 280 nm and 340 nm. The broad excitation covered the UV/vis range widely, which matches well with commercial LED chip emissions, so this phosphor is suitable for solid-state lighting based on an n-UV LED chip. The broad excitation band is commonly ascribed to the crystal-field split 4f<sup>6</sup>5d<sup>1</sup> configuration of Eu<sup>2+</sup> ions. It is well known that the 4f<sup>6</sup>5d<sup>1</sup> electron state is not shielded from anion ligands in the compounds. It has thus been suggested that the  $4f^{6}5d^{1}$  electron state has a strong interaction with neighboring anion ligands in the BaSiO<sub>3</sub> host, which results in a broad excitation band, as shown in Figure 4a. Since samples 8–14 were actually the same as samples 1–7, which were heat-treated in air, except for the fact that samples 8-14 were heat-treated in a reducing atmosphere, and the ionic radius of Eu<sup>3+</sup> (0.0947 nm) was smaller than that of Ba (0.135 nm), it was expected that  $Eu^{2+}$  ions in sample 8–14 would replace the Ba sites of  $BaSiO_3$ . The excitation spectrum shown in Figure 4a has two peaks at 280 nm and 340 nm, which corresponds to the crystal-field splitting of the 5d levels in the excited 4f<sup>6</sup>5d<sup>1</sup> configuration

180

160

140

120

100

80

60

40

20 0

140

120

100

80

60

40

20

0

400

450

500

550

Wavelength (nm)

PL Intensity (arb.units)

200

(C)

250

300

350

Wavelength (nm)

λ**ex** =280 nm

400

600 650 700 750

Sample 8

Sample 13

Sample 10

Sample 9

Sample 12

Sample 11

Sample 14

800

(a)

 $\lambda_{em} = 577 \text{ nm}$ 

Excitation Intensity (arb.units)



Wavelength (nm)

λ**ex** =254 nm

Sample 8

Sample 13

Sample 10

Sample 9

Sample 11

Sample 12

Sample 14

800

700 750

650

of the Eu<sup>2+</sup>. The excitation spectra for samples 8–14 show a similar pattern, even though the relative excitation intensity over the whole excitation band is slightly different.

**Figure 4.** Excitation (**a**) and emission (**b**–**d**) spectra of the  $Ba_{0.96}SiO_3:0.02Eu^{2+}$ ,  $0.02R^{+/3+}$  phosphors (samples 8–14).

100 (d)

80

60

40

20

0

400

450

500

550

600

Wavelength (nm)

PL Intensity (arb.units)

Figure 4b shows the room-temperature PL spectra of samples 8–14 excited at 340 nm, in which the PL features of  $Eu^{2+}$  showed slight changes in peak position depending on the co-doping ions. Since only one Ba site exists crystallographically in BaSiO<sub>3</sub>, a single broad emission band from 450 nm to 750 nm with the peak location at 577 nm was expected, which was attributed to the typical  $4f^{6}5d^{1} \rightarrow 4f^{7}$  transition. This single and symmetrical broad emission band indicated that the  $Eu^{2+}$  ions were replaced into the only Ba<sup>2+</sup> site in BaSiO<sub>3</sub>, as expected. The full width at half maximum (FWHM) of the emission spectrum was about 131 nm, which is broader than the common values of FWHM (50–100 nm) of  $Eu^{2+}$  in most phosphors [3,12,17] and is also broader than that (119 nm) of the well-known yellow-emitting Y<sub>3</sub>Al<sub>5</sub>O<sub>12</sub>:Ce<sup>3+</sup> phosphor [18]. This broad emission may indicate that the interaction of  $Eu^{2+}$  with the ligands of the BaSiO<sub>3</sub> host was strong and thus it may also be suitable as a warm white light source using an n-UV Led chip.

We also found the emission due to  $Eu^{3+}$  ions when samples 8–14 were excited at 280 nm was efficient in exciting  $Eu^{3+}$  ions. This implies that not the all  $Eu^{3+}$  ions present in samples 1–7 were completely reduced into  $Eu^{2+}$  via heat treatment under the mixed nitrogen (90%) and hydrogen (10%) atmosphere. Co-doping ions such as Li<sup>+</sup>, K<sup>+</sup>, and Na<sup>+</sup> were effective in enhancing the emission of  $Eu^{3+}$  via the excitation of the CTB (refer to Figure 2b) but they decreased the emission intensity of  $Eu^{2+}$  ions, as shown in Figure 4b. Based on the radii of the compound elements, all  $Eu^{3+}$  ions were expected to replace the Ba<sup>2+</sup> sites of BaSiO<sub>3</sub> due to the occurrence of the charge imbalance. To solve this charge imbalance effect, charge compensators such as Li<sup>+</sup>, K<sup>+</sup>, and Na<sup>+</sup> ions were co-doped with  $Eu^{3+}$  ions. When  $Eu^{3+}$  and

 $R^+$  ( $R^+ = Li^+$ ,  $K^+$  and  $Na^+$ ) were co-doped, two kinds of defects were created, since one  $Eu^{3+}$ and one  $R^+$  occupied two  $Ba^{2+}$  sites in  $BaSiO_3:Eu^{3+}$ ,  $R^+$  (samples 2–5). Considering that the ionic sizes of cations varied with their coordination numbers (CN), we expected that  $Eu^{3+}$ and  $R^+$  ions would prefer to replace the  $Ba^{2+}$  (CN = 8, r = 1.42Å) in  $BaSiO_3$  because the ionic radius of  $Eu^{3+}$  (CN = 6, r = 1.07~1.087 Å) was closer to that of  $Ba^{2+}$  and the  $Si^{4+}$  sites with an ionic radius of 0.42 Å were too small for  $Eu^{3+}$  to occupy [7,9,19]. The ionic radii of  $Li^+$ ,  $Na^+$ , and  $K^+$  ions are also known to be 0.9, 1.16, and 1.52 Å, respectively [19,20].

 $Ba_{0.96}SiO_3:0.02Eu^{2+}, 0.02R^{+/3+}$  (samples 8–14) phosphors were prepared by carrying out a second heat-treatment of  $Ba_{0.96}SiO_3:0.02Eu^{3+}, 0.02R^{+/3+}$  samples (samples 1–7) in a mixed nitrogen (90%) and hydrogen (10%) atmosphere to reduce  $Eu^{3+}$  into  $Eu^{2+}$ . When  $Ba_{0.96}SiO_3:0.02Eu^{3+}, 0.02R^{+/3+}$  phosphors were heated in the mixed nitrogen (90%) and hydrogen (10%) atmosphere, hydroxyl bonds were formed, which seemed to play an important role in the reduction of  $Eu^{3+}$  ions. We assume that these hydroxyl bonds may have reacted with the negatively charged barium ion vacancies ( $V_{ba}$ ) which were generated due to the charge imbalance when  $Eu^{3+}$  replaced the  $Ba^{2+}$  site in  $Ba_{0.96}SiO_3:0.02Eu^{3+}$ ,  $0.02R^{+/3+}$ , resulting in the decreased PL intensity of  $Eu^2$ . However, more experimental and theoretical studies are needed to reveal the mechanism underlying the decrease in PL intensity due to  $Eu^{2+}$ .

Figure 4d shows the room-temperature PL spectra of samples 8–14 excited at 254 nm, which belonged to the CTB and was also efficient to excite  $Eu^{3+}$  ions. As shown in Figure 4c, the PL intensity of sample 13, co-doped with La<sup>3+</sup>, was stronger than that of samples 9–12, co-doped with R<sup>+</sup>. Furthermore, the PL intensity of sample 13 was stronger than that of sample 14, which was co-doped with  $Y^{3+}$ . Figure 2 shows that the PL intensity of the  ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$  transition of Eu<sup>3+</sup> for sample 6, co-doped with La<sup>3+</sup>, was weaker than that of the  ${}^{5}D_{0} \rightarrow {}^{7}F_{4-7}$  transition but the PL intensity of the  ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$  transition of Eu<sup>3+</sup> for samples 1–7 (except for sample 6) was stronger than that of the  ${}^{5}D_{0} \rightarrow {}^{7}F_{4-7}$  transition. In general, it is known that the emission intensity due to the  ${}^{5}D_{0} \rightarrow {}^{7}F_{4-7}$  transition is weaker than the emission intensity caused by the  ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$  transition because  $\Omega_{4}$  is much smaller than  $\Omega_2$  according to the Judd–Ofelt theory [20]. However, depending on the symmetry of  $Eu^{3+}$ , it has been reported that the luminescence intensity due to the  ${}^{5}D_{0} \rightarrow {}^{7}F_{4}$  transition is stronger than that of  ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$  [21]. The results shown in Figures 2 and 4d may indicate that the PL intensity of Eu<sup>2+</sup> or Eu<sup>3+</sup> doped in BaSiO<sub>3</sub> depends on the co-doped element or the environment around the Eu<sup>2+</sup> or Eu<sup>3+</sup>, rather than the charge state of the co-doped elements such as  $R^+$ ,  $La^{3+}$ , and  $Y^{3+}$ .

### 4. Conclusions

In summary,  $Ba_{0.98+0.02R}SiO_3$ :  $0.02Eu^{(2+/3+)}$ ,  $R^{+/3+}(R = Li^+$ ,  $Na^+$ ,  $K^+$ ,  $La^{3+}$  and  $Y^{3+}$ ) phosphors were prepared by means of a solid-state reaction method and studies were carried out on the effect of co-doping with ions such as  $Li^+$ ,  $Na^+$ ,  $K^+$ ,  $La^{3+}$ , and  $Y^{3+}$  on the optical properties of the  $Ba_{0.98}SiO_3$ :  $0.02Eu^{(2+/3+)}$  phosphors.

One notable result of this work is that the excitation efficiency due to CTB was enhanced by co-doping of  $R^{+/3+}$ , which acted as a kind of sensitizer, and thus increased the emission intensity due to  $Eu^{3+}$  by 3.7 times. However, the co-doped  $R^{+/3+}$  ions did not increase the emission intensity of  $Eu^{3+}$  via direct  ${}^7F_0 \rightarrow {}^5L_6$  excitation of  $Eu^{3+}$ , but rather decreased it. On the other hand, the co-doped  $R^+$  ions did not enhance the emission intensity of  $Eu^{2+}$  via the excitation of the CTB or through a direct excitation of  $Eu^{2+}$ , but the co-doped  $La^{3+}$  did achieve this effect. The present work thus reveals for the first time that the optical properties of  $Eu^{2+}$  or  $Eu^{3+}$  doped in BaSiO<sub>3</sub> depend on the co-doped element itself, rather than the charge state of the co-doped elements such as  $R^+$ ,  $La^{3+}$ , and  $Y^{3+}$ .

**Author Contributions:** P.N.: synthesis of compounds, XRD, and luminescence measurements. K.J.: the idea of work and its planning, interpretation of results, and preparation of the paper. All authors have read and agreed to the published version of the manuscript.

**Funding:** This work was financially supported by the National Research Foundation of Korea funded by the Ministry of Education, Science and Technology (NRF-2018R1D1A1B07043099).

Informed Consent Statement: Not applicable.

Conflicts of Interest: The authors declare no conflict of interest.

## References

- Jiang, P.; Gao, W.; Cong, R.; Yang, T. Structural investigation of the A-site vacancy in scheelite and the luminescence behavior of two continuous solid solutions A<sub>1−1.5x</sub>Eu<sub>x□0.5x</sub>WO<sub>4</sub> and A<sub>0.64−0.5y</sub>Eu<sub>0.24</sub>Li<sub>y□0.12−0.5y</sub>WO<sub>4</sub> (A = Ca, Sr, □ = vacancy). *Dalton Trans.* 2015, 44, 6175–6183. [CrossRef] [PubMed]
- Li, X.; Yang, Z.; Guan, L.; Guo, J.; Wang, Y.; Guo, Q. Synthesis and luminescent properties of CaMoO<sub>4</sub>:Tb<sup>3+</sup>, R<sup>+</sup> (Li<sup>+</sup>, Na<sup>+</sup>, K<sup>+</sup>). J. Alloys Compd. 2009, 478, 684–686. [CrossRef]
- Zhong, J.; Zhao, W.; Lan, L.; Wang, J.; Chen, J.; Wang, N. Enahnced emission from Li<sub>2</sub>CaSiO<sub>4</sub>:Eu<sup>2+</sup> phosphors by doping Y<sup>3+</sup>. J. Alloys Compd. 2014, 592, 213–219. [CrossRef]
- Xiaoye, H.U.; Zhenhua, L.I.; Xin, X.U.; Yongxiu, L.I. Enhancement of photoluminescence of Ba<sub>2</sub>SiO<sub>4</sub>:Eu<sup>2+</sup> by co-doping of La<sup>3+</sup> or Y<sup>3+</sup>. J. Rare Earths 2009, 27, 47–49.
- Gupta, S.K.; Sudarshan, K.; Yadav, A.K.; Gupta, R.; Bhattacharyya, D.; Jha, S.N.; Kadam, R.M. Deciphering the Role of Charge Compensator in Optical Properties of SrWO<sub>4</sub>:Eu<sup>3+</sup>:A (A = Li<sup>+</sup>, Na<sup>+</sup>, K<sup>+</sup>): Spectroscopic Insight Using Photoluminescence, Positron Annihilation, and X-ray Absorption. *Inorg. Chem.* 2018, *57*, 821–832. [CrossRef] [PubMed]
- 6. Jiayue, S.; Jinli, L.; Jianfeng, S.; Haiyan, D. Luminescence properties of a new red emitting Eu<sup>3+</sup>-doped alkaline-earth fluoborate phosphor: BaCa<sub>(1-2x)</sub>BO<sub>3</sub>F:xEu<sup>3+</sup>, xM<sup>+</sup> (M = Li, Na, K). *J. Rare Earths* **2011**, *29*, 321–325.
- Yang, Z.; Yang, L.; Pu, Y.; Zhu, D. The effect and mechanism of different charge compensation on the luminescent properties of Eu-doped BaSiO<sub>3</sub> phosphor calcined in air with self-reduction. *Opt. Mater.* 2021, 114, 110981. [CrossRef]
- 8. Noto, L.L.; Ntwaeaborwa, O.M.; Yagoub, M.Y.; Swart, H.C. Enhancement of persistent luminescence of ZnTa<sub>2</sub>O<sub>6</sub>:Pr<sup>3+</sup> by addition Li<sup>+</sup>, Na<sup>+</sup>, K<sup>+</sup> and Cs<sup>+</sup> ions. *Mater. Res. Bull.* **2015**, *70*, 545–552. [CrossRef]
- 9. Guo, C.; Xu, Y.; Ren, Z.; Bai, J. Blue-White-Yellow Tunable Emission from Ce<sup>3+</sup> and Eu<sup>2+</sup> Co-Doped BaSiO<sub>3</sub> Phosphors. *J. Electrochem. Soc.* **2011**, *158*, J373–J376. [CrossRef]
- 10. Pan, Y.X.; Liu, G.K. Enhancement of Eu<sup>2+</sup> Luminescence in BaO-SiO<sub>2</sub> Compounds Through Composition Modification, Spectroscopy. *Letters* **2011**, *44*, 1–7.
- Namkhai, P.; Jang, K. Optical Properties of Eu<sup>(2+/3+)</sup> on the Fabrication Method for BaSiO<sub>3</sub>:Eu<sup>(2+/3+)</sup> Phosphors. *New Phys. Sae Mulli* 2021, 71, 1010–1017. [CrossRef]
- Cho, I.S.; Yim, D.K.; Kwak, C.H.; An, J.S.; Roh, H.S.; Hong, K.S. Investigation of crystal/electronic structure effects on the photoluminescence properties in the BaO–SiO<sub>2</sub>:Eu<sup>2+</sup> systems. *J. Lumin.* 2012, 132, 375–380.
- 13. Xu, J.; Zhao, Y.; Chen, I.J.; Mao, Z.; Yang, Y.; Wang, D. Insights into the discrepant luminescence for BaSiO<sub>3</sub>:Eu<sup>2+</sup> phosphors prepared by solid-state reaction and precipitation reaction methods. *Luminescence* **2017**, *32*, 957–963. [CrossRef] [PubMed]
- 14. Yang, L.; Zhu, D.; Liu, S.; Wang, J.; Zhao, C.; Pu, Y. Photoluminescence properties and crystal structure of BaSi0<sub>3</sub>:xEu<sup>3+</sup>, yBi<sup>3+</sup> red phosphor synthesized by co-precipitation method. *Phys. B Condens. Matter* **2019**, *556*, 6–11. [CrossRef]
- 15. Nag, A.; Kutty, T.R.N. The light induced valence change of europium in Sr<sub>2</sub>SiO<sub>4</sub>:Eu involing transient crystal structure. *J. Mater. Chem.* **2004**, *14*, 1598–1604. [CrossRef]
- 16. Chang, C.; Kimura, F.; Kimura, T.; Wada, H. Preparation and characterization of rod-like Eu:Gd<sub>2</sub>O<sub>3</sub> phosphor through a hydrothermal routine. *Mater. Lett.* **2005**, *59*, 1037–1041. [CrossRef]
- 17. Song, W.; Kim, H.; Kim, Y.; Yang, H. Synthesis of Ba<sub>2</sub>SiO<sub>3</sub>O<sub>8</sub>:Eu<sup>2+</sup> Phosphor for Fabrication of White Light-Emitting Diodes Assisted by ZnCdSe/ZnSe Quantum. *J. Electrochem. Soc.* **2010**, *157*, J319–J323. [CrossRef]
- Song, W.; Kim, Y.; Yang, H. Yellow-emitting phosphor of Sr<sub>3</sub>B<sub>2</sub>O<sub>6</sub>:Eu<sup>2+</sup> for application to white light-emitting diodes. *Mater. Chem. Phys.* 2009, 117, 500–503. [CrossRef]
- 19. Mukherjee, S.; Sudarsan, V.; Vatsa, R.K.; Tyagi, A.K. Luminescence studies on lanthanide ions (Eu<sup>3+</sup>, Dy<sup>3+</sup> and Tb<sup>3+</sup>) doped YAG:Ce nano-phosphors. *J. Lumin.* **2009**, *129*, 69–72. [CrossRef]
- 20. Chan, W.L.; Liu, Z.; Lu, S.; Tanner, P.A.; Wong, K.L. The reported anomalous emission intensity of the  ${}^{5}D_{0} \rightarrow {}^{7}F_{4}$  transition of Eu<sup>3+</sup> in a molybdate double perovskite. *J. Mater. Chem. C* 2015, *3*, 960–963. [CrossRef]
- 21. Blasse, G. Luminescence from the Eu<sup>3+</sup> Ion in D<sub>4d</sub> Symmetry. *Inorg. Chim. Acta* 1988, 142, 153–154. [CrossRef]