



# Article Mechanical Properties of GaN Single Crystals upon C Ion Irradiation: Nanoindentation Analysis

Zhaohui Dong<sup>1</sup>, Xiuyu Zhang<sup>2</sup>, Shengyuan Peng<sup>2</sup>, Fan Jin<sup>3</sup>, Qiang Wan<sup>3,\*</sup>, Jianming Xue<sup>2,4,\*</sup> and Xin Yi<sup>1,\*</sup>

- <sup>1</sup> Department of Mechanics and Engineering Science, College of Engineering, Peking University, Beijing 100871, China; zhdong@pku.edu.cn
- <sup>2</sup> State Key Laboratory of Nuclear Physics and Technology, School of Physics, Peking University, Beijing 100871, China; xiuyuzhang@pku.edu.cn (X.Z.); 2101110314@pku.edu.cn (S.P.)
- <sup>3</sup> Institute of Systems Engineering, China Academy of Engineering Physics, Mianyang 621999, China; jinfan2046@163.com
- <sup>4</sup> HEDPS and Center for Applied Physics and Technology, College of Engineering, Peking University, Beijing 100871, China
- \* Correspondence: wanzhenyu@126.com (Q.W.); jmxue@pku.edu.cn (J.X.); xyi@pku.edu.cn (X.Y.)

**Abstract:** Mechanical properties of gallium nitride (GaN) single crystals upon carbon ion irradiation are examined using nanoindentation analysis at room temperature. Pop-in events in the load-depth curves are observed for unirradiated and irradiated GaN samples. A statistical linear relationship between the critical indentation load for the occurrence of the pop-in event and the associated displacement jump is exhibited. Both the slope of linear regression and the measured hardness increase monotonically to the ion fluence, which can be described by logistic equations. Moreover, a linear relationship between the regression slope as a micromechanical characterization and the hardness as a macroscopic mechanical property is constructed. It is also found that the maximum resolved shear stress of the irradiated samples is larger than that of the unirradiated samples, as the dislocation loops are pinned by the irradiation-induced defects. Our results indicate that the nanoindentation pop-in phenomenon combined with a statistical analysis can serve as a characterization method for the mechanical properties of ion-irradiated materials.

**Keywords:** GaN single crystals; mechanical properties; ion irradiation; nanoindentation; pop-in; activation volume; dislocation nucleation

## 1. Introduction

Owing to excellent physical and chemical properties, such as high mobility, high thermal conductivity, thermal stability, good heat dissipation [1], gallium nitride (GaN), as a wide bandgap semiconductor material, has become one of the most promising raw materials for electronic devices. To evaluate the function of GaN-based devices in environments of high radiation dose, studies on the radiation effect on the mechanical and physical properties of GaN samples are called for.

With features of high damage efficiency, low cost, and low residual radioactivity, nowadays, ion irradiation serves as a main method for studying the radiation effect on material properties. Irradiation could induce material defects such as vacancies, interstitial atoms, and dislocation loops. These defects in turn cause a certain extent of lattice disorder and stress-field variation. Low-level stress could significantly affect the photoelectric properties of GaN, such as the bandgap, and damage the performance of the device, while high-level stress could cause local plastic deformation of the material, dislocations to increase, and even cracking, resulting in device failure [2–4]. So far, extensive studied have been performed on the effects of irradiation dose, incident ion species, irradiation temperature, and annealing conditions on the dynamic process of lattice disorder and defect migration of GaN samples [5–7]. In comparison, only a few studies have been carried out



Citation: Dong, Z.; Zhang, X.; Peng, S.; Jin, F.; Wan, Q.; Xue, J.; Yi, X. Mechanical Properties of GaN Single Crystals upon C Ion Irradiation: Nanoindentation Analysis. *Materials* 2022, 15, 1210. https://doi.org/ 10.3390/ma15031210

Academic Editor: Elena Ferretti

Received: 2 January 2022 Accepted: 2 February 2022 Published: 5 February 2022

**Publisher's Note:** MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



**Copyright:** © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/). to investigate the mechanical properties of GaN single crystals [8,9]. However, the studies on radiation damage and mechanical behaviors of GaN samples are uncoupled, and there are rare studies considering the impact of irradiation on the mechanical properties of GaN samples, especially for GaN single crystals minimizing the effect of grain boundaries on hindering the dislocation motion and trapping irradiation defects [10]. Therefore, studies of the effect of irradiation on the mechanical properties of GaN single crystals are called for, so as to aid the fundamental understanding and engineering evaluation of GaN and GaN-based device performances.

The penetration depth of ion beams is generally limited within a range from tens of nanometers to several micrometers, and the distribution of irradiation-induced defects is non-uniform within the irradiated layer [11]. These aspects make conventional measurement techniques hardly appropriate for determining the mechanical properties of ion-irradiated samples, and small-scale testing approaches are called for. In comparison with small-scale testing methods, such as microcolumn stretching, compression and bending experiments of small samples, the sample preparation for nanoindentation is relatively simple and a large amount of effective experimental data could be obtained in a relatively short period of time, making nanoindentation an effective, convenient, and popular experimental technology for investigating mechanical properties of ion-irradiated samples [11–13]. Further studies indicate that the statistical analysis of pop-in events in the load-depth curves of nanoindentation can be used to quantify irradiation damage at a low irradiation dose [13].

In this work, we experimentally investigate the effect of C ion irradiation on the hardness of GaN single crystals using nanoindentation analysis at room temperature. Pop-in events for unirradiated and irradiated GaN samples are analyzed. It is found that the critical indentation load for the occurrence of the pop-in event and the associated displacement jump follows a statistical linear relationship. The hardness increases monotonically to the ion fluence, following logistic equations. A linear relationship between the slope of the critical load–displacement jump regression and the hardness is determined. Our results shed light on the influence of ion irradiation on mechanical properties of GaN single crystals and have implications for developing high-performance wide bandgap semiconductor-based devices.

### 2. Materials and Methods

The samples are freestanding wurtzite-type undoped c-plane (0001) GaN single crystals fabricated using hydride vapor phase epitaxy (HVPE) (Suzhou Nanowin Science and Technology Co., Ltd., Suzhou, China). A detailed overview of the mechanism and features of HVPE for the growth of III–V and nitride semiconductor structures can be found in [14]. The sample size is 10.0 mm × 10.5 mm × 0.35 mm. The density of in-grown dislocations is about  $3 \times 10^6$  cm<sup>-2</sup>, determined by cathodoluminescence imaging. The crystal orientation is identified using X-ray diffraction. The Ga surface is treated using chemical mechanical polishing with colloidal silica nanoparticles, achieving a mirror-like surface with surface roughness of less than 0.2 nm.

The GaN single crystal samples are irradiated with 3 MeV C<sup>+</sup> ions with different fluences of  $0.72 \times 10^{15}$  ions/cm<sup>2</sup>,  $1.4 \times 10^{15}$  ions/cm<sup>2</sup>,  $2.4 \times 10^{15}$  ions/cm<sup>2</sup>,  $4.8 \times 10^{15}$  ions/cm<sup>2</sup>, and  $9.6 \times 10^{15}$  ions/cm<sup>2</sup>. During ion irradiation, the ambient temperature is room temperature (23 °C). The flux of the C<sup>+</sup> ion is set at  $1 \times 10^{12}$  ions/(cm<sup>2</sup>·s) to avoid the increase in sample temperature. The displacements-per-atom (dpa) values of energetic ions are calculated using SRIM-2013 [15] with "Quick" Kinchin-Pease option [16]. The depth profiles of dpa and ion concentration are shown in Figure 1. According to the dpa profile, the damaged layer can be roughly divided into two regions. Region I, a near surface plat region in which the dpa value gradually increases with depth, and region II, a heavily damaged region with a significantly non-uniform damage distribution. In this study, the dpa value refers to the average dpa value over region I. The thickness of region I is around 1.75 µm.



**Figure 1.** Depth profiles of the displacement damage and C<sup>+</sup> ion concentration of GaN single crystals implanted with C<sup>+</sup> at 3 MeV with an ion fluence of  $0.72 \times 10^{15}$  cm<sup>-2</sup>. Inset is a magnified view of the damage-depth region at all five ion fluences from  $0.72 \times 10^{15}$  cm<sup>-2</sup> to  $9.6 \times 10^{15}$  cm<sup>-2</sup>.

To study the effects of C<sup>+</sup> ion irradiation on the mechanical properties of GaN single crystals, a nanoindentation analysis using Hysitron TI 980 Triboindenter (Bruker, Minneapolis, MN, USA) system is conducted. The diamond Berkovich indenter is used and its effective tip radius is calibrated as R = 351 nm using standard techniques [17,18]. The projected contact area of the tip is calibrated and the frame stiffness is corrected by indenting fused quartz. The indentation test procedure is load controlled, adopting a trapezoidal load-time input function with a 5 s linear loading segment, a 2 s holding segment at peak load, and a 5 s linear unloading segment. The holding segment reduces the effect of creep [19]. To obtain the sample hardness, at least 20 indents are performed on each sample with the maximum load of 10 mN. To observe and analyze the pop-in effect more precisely, at least 200 indents are performed on each sample with a maximum load of 2 mN. The indentation load at which the pop-in event occurs and the pop-in depth or called displacement excursion are recorded. Neighboring indentation sites of a given sample have sufficient separation distance to avoid possible interference. All nanoindentation tests are performed at room temperature (23 °C).

#### 3. Results and Discussion

Figure 2 presents the representative load-depth (*P-h*) curves for GaN single crystals subjected to different ion fluences. The maximum load is 2 mN. The maximum indentation depth is less than 10% of the thickness of region I around 1.75  $\mu$ m, indicating that the substrate effect on the indentation could be neglected [17]. Regardless of the irradiation fluence values, pop-in events during loading are observed. Similar pop-in events on unirradiated GaN samples have been observed [8,9,20]. The indentation load at which the first pop-in occurs is referred to as the critical load  $P_c$ , and the corresponding displacement jump  $\Delta h$  (length of the horizontal plateau) is referred to as the displacement excursion. For displacement-controlled nanoindentation experiments, a vertical load drop could be observed on the load-depth curve with a pop-in.



**Figure 2.** Load–depth (*P-h*) curves for GaN single crystals obtained from the nanoindentation experiments with maximum load of 2 mN. The GaN samples are subjected to different values of ion fluence *D* from  $0.72 \times 10^{15}$  cm<sup>-2</sup> to  $9.6 \times 10^{15}$  cm<sup>-2</sup>. The inset shows pop-in events in the loading parts of the *P-h* curves.

According to the Hertzian elastic contact theory [21], the elastic response of a sample to a spherical indentation obeys

$$P = \frac{4}{3}E^*R^{1/2}h^{3/2},\tag{1}$$

where *P* is the applied indenter load, *R* is the radius of the indenter tip, *h* is the indentation depth, and the reduced modulus  $E^*$  combines the moduli of the indenter and sample as

$$\frac{1}{E^*} = \frac{1 - \nu_{\rm i}^2}{E_{\rm i}} + \frac{1 - \nu_{\rm GaN}^2}{E_{\rm GaN}}$$

with  $\nu$  and E denoting the Poisson ratio and Young's modulus, respectively, and subscripts i and GaN are used to identify quantities pertaining to the indenter tip and GaN sample, respectively. As indicated in Figure 2, the Hertzian Equation (1) fits well with the initial portion of the load–depth curve before pop-in, indicating a perfect elastic response at  $P < P_c$  (for clarity only the fitting for the unirradiated case is shown here). As P exceeds  $P_c$ , the P-h curves deviate from the Hertzian equation with not only a horizontal shift but also a different curve slope, indicating that the sample deformation has transformed into an elastic-plastic way. The load  $P_c$  is regarded as a critical load for the onset plasticity. In comparison to unirradiated GaN samples, the pop-in phenomenon for ion-irradiated GaN samples is associated with a larger critical load.

The occurrence of pop-in events is stochastic. As indicated in Table 1, there is no evident law for the distribution of the critical load  $P_c$  with the ion fluence D. However, it has been reported in ref. [22] that the critical load  $P_c$  and the displacement excursion  $\Delta h$  increase after irradiation. In contrast, some studies report that the critical load decrease after irradiation [23]. In addition, existing studies show that the presence of impurity atoms could increase the critical load for pop-in [24–26]. These contradictions may be attributed to the different interaction between dislocation and irradiation.

Fluence D	Hardness H	$ au_{\max}$	Mean Value of $ au_{\max}$	Pc	Mean Value of P <sub>c</sub>	V <sup>1</sup>	$\Delta h$	K
$(10^{15} \text{ cm}^{-2})$	(GPa)	(GPa)	(GPa)	(µN)	(µN)	(Å <sup>3</sup> )	(nm)	(µN/nm)
0	$19.2\pm0.2$	11.0-14.5	13.1	423.3-982.4	712.8	$7.24 (= 0.22b^3)$	0.5-6.2	$81.5\pm2.0$
0.72	$21.1\pm0.4$	11.2-14.2	13.0	447.4-907.9	703.4	$8.52 (=0.26b^3)$	0.6 - 4.5	$108.4\pm4.7$
1.4	$22.1\pm0.2$	11.3-14.6	13.3	461.4-994.4	745.6	$8.16 (=0.25b^3)$	0.7 - 4.5	$121.9\pm3.6$
2.4	$22.6\pm0.3$	11.6-15.8	14.1	501.8-1261.4	899.1	$7.77 (= 0.24b^3)$	0.7 - 4.6	$142.6\pm3.4$
4.8	$22.8\pm0.5$	11.5-15.5	14.0	491.5-1187.1	867.6	$7.40 (=0.23b^3)$	0.4 - 4.7	$143.5\pm3.3$
9.6	$23.2\pm0.3$	11.7–15.9	14.5	518.0-1277.5	967.3	$8.47 (= 0.26b^3)$	0.7-4.2	$149.2\pm5.9$

**Table 1.** Measured mechanical and physical properties of unirradiated and irradiated GaN single crystals by nanoindentation.

<sup>1</sup> For GaN single crystals, the magnitude of the Burgers vector  $\mathbf{b} = 1/3[2-1-10]$  is b = 3.191 Å [27].

To correlate the pop-in behavior to the irradiation-induced defects, the critical load  $P_c$  is converted to the maximum resolved shear stress  $\tau_{max}$  as [21]

$$\tau_{\rm max} = 0.31 \left(\frac{6P_{\rm c}E^{*2}}{\pi^3 R^2}\right)^{1/3}$$

The range and average value of  $\tau_{max}$  for unirradiated and irradiated samples are listed in Table 1. The theoretical shear strength of GaN is 23.76 GPa [27], and  $\tau_{max}$  of unirradiated and irradiated samples does not exceed 67% of the theoretical shear strength of GaN. This implies that the onset of pop-in events might be triggered by the presence of dislocations that contribute to the heterogeneous dislocation nucleation of indentation-induced slip during loading [28]. In addition, the  $\tau_{max}$  of irradiated samples is larger than that of the unirradiated samples, because the pre-existing dislocation loops before indentation are pinned by the irradiation-induced defects, and the extent of the increase in  $\tau_{max}$  is related to the pinning extent of the defects [22,28].

To describe the stochastic feature of pop-in events, a quantity named the cumulative probability, the probability that a pop-in event occurs before the critical load reaches a value  $P_c$ , has been introduced [29,30]. Figure 3 presents the cumulative pop-in probability F as functions of  $P_c$  at different values of ion fluence D.



**Figure 3.** Cumulative pop-in probability as functions of the critical load  $P_c$  at different values of ion fluence *D*.

According to the statistical method proposed by Schuh et al. [29,30], the cumulative probability *F* can be correlated with the critical load  $P_c$  of pop-in  $F = F(P_c)$  as

$$\ln[-\ln(1-F)] = \alpha P_{\rm c}^{1/3} + \beta(P_{\rm c}), \tag{2}$$

where  $\beta(P_c)$  is a function of weak dependency on  $P_c$ . The parameter  $\alpha$  in Equation (2) is correlated with the activation volume *V* through

$$V = \frac{\pi}{0.47} \left(\frac{3R}{4E^*}\right)^{2/3} k_{\rm B} T \cdot \alpha \tag{3}$$

Plotting  $\ln[-\ln(1 - F)]$  versus  $P^{1/3}$  in Figure 4, one can see that experimental data roughly fall onto linear lines, consistent with Equation (2). Slopes of these fitted straight lines determine values of  $\alpha$  for unirradiated and irradiated GaN samples, from which values of the activation volume *V* can be obtained using Equation (3). For GaN single crystals, the magnitude of the Burgers vector  $\mathbf{b} = 1/3[2-1-10]$  is 3.191 Å [27]. The value of *V* varies as the ion fluence varies (see Table 1), implying heterogeneous dislocation nucleation during the pop-in at different ion fluence [31].



**Figure 4.** Extracting activation volume from experimental data using Equation (2). Straight lines are best linear fits of Equation (2) to the symbols.

In indentation experiments, the pop-in event is caused by the transformation of the elastic deformation to plastic deformation [32]. Figure 5 plots the critical load  $P_c$  versus  $\Delta h$ , at different values of ion fluence D. At least 200 indentation experiments of unirradiated and irradiated GaN samples have been performed. It can be seen that the pop-in event does not necessarily occur at the same critical load, and a statistical linear dependency of  $P_c$  on  $\Delta h$  is exhibited. The larger the ion fluence D is, the larger the slope  $K = dP_c/d(\Delta h)$  is. A similar linear relationship between  $P_c$  and  $\Delta h$  for unirradiated GaN sample has been observed for unirradiated GaN samples [33]. Values of K at different values of D are shown in Table 1 and plotted in Figure 6. It is shown that the *K*-D relationship can be described by the governing logistic equation

$$\frac{\mathrm{d}K}{\mathrm{d}D} = r_K K \left( 1 - \frac{K}{K_c} \right) \text{ with } K(0) = K_0 \tag{4}$$

Here,  $r_K$  is the increment rate,  $K_c$  is the capacity of the K value, and  $K_0$  is the value of K at zero ion fluence (D = 0). From Equation (4), one has

$$K(D) = \frac{K_0 K_c}{K_0 + (K_c - K_0)e^{-r_K D}},$$
(5)

where  $r_K = 1.09599 \times 10^{-15} \text{ cm}^2$ ,  $K_c = 146.62116 \,\mu\text{N/nm}$ , and  $K_0 = 81.35841 \,\mu\text{N/nm}$  are obtained with regression to the experimental data in Figure 6 with  $10^{15} \text{ cm}^{-2}$  and  $\mu\text{N/nm}$  taken as the unit of fluence and *K*, respectively.



**Figure 5.** The critical load for pop-in versus the corresponding displacement excursion for unirradiated and irradiated GaN samples. Straight lines are linear fits to experimental pop-in data (symbols).



Figure 6. K values of GaN single crystal samples as a function of ion fluence D.

Following the well-established Oliver and Pharr method [17], one can determine the hardness of the unirradiated and irradiated GaN samples from the nanoindentation experiments. Here, we extract the value of *H* from *P-h* curves measured at a maximum load of 10 mN. In these experiments, the indention depth does not exceed 165 nm, less than 1/10 of the thickness of region I in Figure 1. Therefore, the substrate effect on the measured hardness is negligible. The Poisson ratio  $v_{GaN} = 0.22$  is adopted here [34]. The Young's modulus and Poisson ratio of the diamond indenter are  $E_i = 1141$  GPa and  $v_i = 0.07$ ,

respectively. Each sample is measured with more than 20 indentations to obtain an average value. As indicated in Figure 7 and similar to the analysis of Figure 6, the hardness *H* of the GaN single crystal increases monotonically to the ion fluence *D* and their relation can be described by a logistic equation

$$\frac{\mathrm{d}H}{\mathrm{d}D} = r_H H \left(1 - \frac{H}{H_c}\right) \text{ with } H(0) = H_0 \tag{6}$$

Here,  $r_H$  is the increment rate,  $H_c$  is the hardness capacity, and  $H_0$  is the hardness for unirradiated samples. From equation (6), one has

$$H(D) = \frac{H_0 H_c}{H_0 + (H_c - H_0)e^{-r_H D}},$$
(7)

where  $r_H = 1.09008 \times 10^{-15} \text{ cm}^2$ ,  $H_c = 23.03968$  GPa, and  $H_0 = 19.18533$  GPa are the fitting parameters with  $10^{15} \text{ cm}^{-2}$  as the unit of fluence *D* and GPa as the unit of hardness *H*. The obtained mechanical parameters of unirradiated and irradiated GaN single crystals are summarized in Table 1.



Figure 7. The hardness *H* of GaN single crystal samples as a function of ion fluence *D*.

As indicated in Figure 7, the hardness of GaN single crystals is modified by the ion bombardment. For the unirradiated GaN single crystals, the hardness is  $19.2 \pm 0.2$  GPa, consistent with reported values in the literature [8,9]. As the ion influence *D* increases, the hardness *H* of GaN single crystals increases and saturates following Equation (7). Related to the elastoplastic behavior of single crystal materials, the hardness can be regarded as the sum of the resistance of the atomic bonds per unit area under the indenter to the indentation deformation, which is mainly attributed to the bond density, shear strength, and the move of dislocations [35], and these aspects could be tuned by irradiation. On one hand, the irradiation-induced defects gradually reduce the density and strength of chemical bonds, increase the lattice spacing, and cause a decrease in hardness. On the other hand, the irradiation defects interact with the dislocation, inhibit the dislocation motion, and increase the resistance to volume changes, leading to an increase in hardness [36]. Therefore, the irradiation effect on hardness is a result of the competition between structural defects and stress field caused by irradiation. As indicated in Equations (5) and (7), the *H*-*D* and *K*-*D* relationships can be captured by the logistic equations of the same form, which indicates that there might exist a simple relationship between *H* and *K*. By extracting the values of *H* and *K* and plotting the *H*-*K* relationship in Figure 8, one can observe that the *H*-*K* relationship can be described by

$$H = mK + n$$

where  $m = 0.05606 \ \mu m^{-1}$  and n = 14.86 GPa are the two fitting parameters. Similar linear behaviors have also been observed in the nanoindentation of compound semiconductors [28] and even perovskites such as APbX<sub>3</sub> (A=Cs, CH<sub>3</sub>NH<sub>3</sub>; X=I, Br) single crystals [37]. Based on a simple nanoindentation model proposed by Field and Swain [32], *K* has also been predicted to have a linear dependency on the hardness *H*. The hardness *H* is a macroscopic mechanical property and the parameter *K* as the slope  $dP_c/d(\Delta h)$  characterizing the material micromechanical responses. It is interesting to note that an appropriate choice or introduction of the statistical trend of the material micromechanical responses can be used to characterize the macroscopic mechanical properties. Therefore, the nanoindentation pop-in phenomenon combined with a statistical analysis can be used as a characterization method for the mechanical properties of ion-irradiated materials.



**Figure 8.** Relationship between the hardness *H* and the *K* values for GaN samples. The dotted straight line is a linear fit of the extracted data.

In the present experimental study, we have focused on the nanoindentation of ionirradiated GaN samples at room temperature. Future work will be aimed at evaluating the effects of neutron- and ion-irradiation damage as well as high temperatures on the mechanical properties of III–V and nitride semiconductors using more sophisticated experimental techniques [38] and theoretical modeling [39].

#### 4. Conclusions

Using nanoindentation technique, the effects of C ion irradiation with different ion fluences on the mechanical and physical properties of GaN single crystals are investigated, including the critical load and displacement excursion of pop-in events, maximum resolved shear stress, activation volume, and the hardness. For both unirradiated and irradiated GaN samples upon nanoindentation, the sample deformation is perfectly elastic before the first pop-in event. The mechanism of pop-in events is a heterogeneous dislocation nucleation process. It is found that there is a statistical linear relationship between the critical indentation load, which exhibits a statistical linear dependence on the displacement excursion. As the ion fluence increases, both the slope of that linear regression and the measured hardness increase monotonically to the ion fluence following the logistic feature. Moreover, the maximum shear stress of irradiated GaN samples is larger than that of the unirradiated samples, attributed to pinning dislocation loops by the irradiation-induced defects. Combining nanoindentation pop-in events with statistical analysis could characterize the irradiation effect on the mechanical properties of materials.

**Author Contributions:** Conceptualization, Z.D. and X.Y.; methodology, Z.D., X.Z., S.P., F.J., Q.W., J.X. and X.Y.; investigation, Z.D., X.Z., S.P., F.J., Q.W., J.X. and X.Y.; writing—original draft preparation, Z.D.; writing—review and editing, X.Y.; supervision, X.Y.; funding acquisition, X.Y. All authors have read and agreed to the published version of the manuscript.

**Funding:** This research was funded by the National Natural Science Foundation of China (grant Nos. U1830121 and 11988102).

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: Not applicable.

Conflicts of Interest: The authors declare no conflict of interest.

### References

- 1. Mukai, T.; Nakamura, S. Ultraviolet InGaN and GaN single-quantum-well-structure light-emitting diodes grown on epitaxially laterally overgrown GaN substrates. *Jpn. J. Appl. Phys.* **1999**, *38*, 5735–5739. [CrossRef]
- Wang, R.J.; Wang, C.Y.; Feng, Y.T. Effective geometric size and bond-loss effect in nanoelasticity of GaN nanowires. *Int. J. Mech. Sci.* 2017, 130, 267–273. [CrossRef]
- Liu, Z.; Xiu, X.; Zhang, L.; Zhang, R.; Zhang, Y.; Su, J.; Xie, Z.; Liu, B.; Shan, Y. Strain in GaN epi-layer grown by hydride vapor phase epitaxy. *Spectrosc. Spectr. Anal.* 2013, 33, 2105–2108.
- Kumar, A.; Kanjilal, D.; Kumar, V.; Singh, R. Defect formation in GaN epitaxial layers due to swift heavy ion irradiation. *Radiat.* Eff. Defects Solids 2011, 166, 739–742. [CrossRef]
- Ai, W.S.; Zhang, L.M.; Jiang, W.; Peng, J.X.; Chen, L.; Wang, T.S. Raman study of In<sub>x</sub>Ga<sub>1-x</sub>N(x=0.32–0.9) films irradiated with Xe ions at room temperature and 773 K. *Nucl. Instrum. Methods Phys. Res. Sect. B* 2018, 415, 48–53. [CrossRef]
- Zhang, L.Q.; Zhang, C.H.; Li, J.J.; Meng, Y.C.; Yang, Y.T.; Song, Y.; Ding, Z.N.; Yan, T.X. Damage to epitaxial GaN layer on Al<sub>2</sub>O<sub>3</sub> by 290-MeV <sup>238</sup>U<sup>32+</sup> ions irradiation. *Sci. Rep.* 2018, *8*, 4121. [CrossRef]
- Zhang, L.Q.; Zhang, C.H.; Xian, Y.Q.; Liu, J.; Ding, Z.N.; Yan, T.X.; Chen, Y.G.; Su, C.H.; Li, J.Y.; Liu, H.P. Degradation mechanisms of optoelectric properties of GaN via highly-charged <sup>209</sup>Bi<sup>33+</sup> ions irradiation. *Appl. Surf. Sci.* 2018, 440, 814–820. [CrossRef]
- 8. Fujikane, M.; Leszczyński, M.; Nagao, S.; Nakayama, T.; Yamanaka, S.; Niihara, K.; Nowak, R. Elastic-plastic transition during nanoindentation in bulk GaN crystal. *J. Alloy. Compd.* **2008**, 450, 405–411. [CrossRef]
- 9. Huang, J.; Xu, K.; Fan, Y.M.; Niu, M.T.; Zeng, X.H.; Wang, J.F.; Yang, H. Nanoscale anisotropic plastic deformation in single crystal GaN. *Nanoscale Res. Lett.* 2012, 7, 150. [CrossRef]
- 10. Schiøtz, J.; Di Tolla, F.D.; Jacobsen, K.W. Softening of nanocrystalline metals at very small grain sizes. *Nature* **1998**, *391*, 561–563. [CrossRef]
- Lupinacci, A.; Chen, K.; Li, Y.; Kunz, M.; Jiao, Z.; Was, G.S.; Abad, M.D.; Minor, A.M.; Hosemann, P. Characterization of ion beam irradiated 304 stainless steel utilizing nanoindentation and Laue microdiffraction. J. Nucl. Mater. 2015, 458, 70–76. [CrossRef]
- 12. Hosemann, P.; Shin, C.; Kiener, D. Small scale mechanical testing of irradiated materials. J. Mater. Res. 2015, 30, 1231–1245. [CrossRef]
- Jin, K.; Xia, Y.; Crespillo, M.; Xue, H.; Zhang, Y.; Gao, Y.F.; Bei, H. Quantifying early stage irradiation damage from nanoindentation pop-in tests. Scr. Mater. 2018, 157, 49–53. [CrossRef]
- Gil, E.; André, Y.; Cadoret, R.; Trassoudaine, A. Hydride vapor phase epitaxy for current III–V and nitride semiconductor compound issues. In *Handbook of Crystal Growth*, 2nd ed.; Kuech, T.F., Ed.; North-Holland: Boston, MA, USA, 2015; pp. 51–93.
- 15. Ziegler, J.F.; Ziegler, M.D.; Biersack, J.P. SRIM–The stopping and range of ions in matter (2010). *Nucl. Instrum. Methods Phys. Res. Sect. B* 2010, *268*, 1818–1823. [CrossRef]
- Stoller, R.E.; Toloczko, M.B.; Was, G.S.; Certain, A.G.; Dwaraknath, S.; Garner, F.A. On the use of SRIM for computing radiation damage exposure. *Nucl. Instrum. Methods Phys. Res. Sect. B* 2013, 310, 75–80. [CrossRef]
- 17. Oliver, W.C.; Pharr, G.M. An improved technique for determinning hardness and elastic modulus using load and displacement sensing indentation experiments. *J. Mater. Res.* **1992**, *7*, 1564–1583. [CrossRef]
- Bei, H.; Xia, Y.Z.; Barabash, R.I.; Gao, Y.F. A tale of two mechanisms: Strain-softening versus strain-hardening in single crystals under small stressed volumes. *Scr. Mater.* 2016, *110*, 48–52. [CrossRef]
- 19. Geetha, D.; Sophia, P.J.; Radhika, R.; Arivuoli, D. Evaluation of nanoindentation and nanoscratch characteristics of GaN/InGaN epilayers. *Mater. Sci. Eng. A* 2017, 683, 64–69. [CrossRef]

- 20. Fujikane, M.; Yokogawa, T.; Nagao, S.; Nowak, R. Strain rate controlled nanoindentation examination and incipient plasticity in bulk GaN crystal. *Jpn. J. Appl. Phys.* 2013, 52, 08JJ01. [CrossRef]
- 21. Johnson, K.L. Contact Mechanics; Cambridge University Press: Cambridge, UK, 1985.
- 22. Kucheyev, S.O.; Bradby, J.E.; Williams, J.S.; Jagadish, C.; Swain, M.V.; Li, G. Deformation behavior of ion-beam-modified GaN. *Appl. Phys. Lett.* **2001**, *78*, 156–158. [CrossRef]
- 23. Xiao, X.; Xiao, C.; Xia, X. Force-depth relationships with irradiation effect during spherical nano-indentation: A theoretical analysis. *J. Nucl. Mater.* **2020**, *531*, 152012. [CrossRef]
- 24. Sekido, K.; Ohmura, T.; Zhang, L.; Hara, T.; Tsuzaki, K. The effect of interstitial carbon on the initiation of plastic deformation of steels. *Mater. Sci. Eng. A* 2011, 530, 396–401. [CrossRef]
- 25. Jian, S.-R.; Ke, W.-C.; Juang, J.-Y. Mechanical characteristics of Mg-doped GaN thin films by nanoindentation. *Nanosci. Nanotechnol. Lett.* **2012**, *4*, 598–603. [CrossRef]
- 26. Pöhl, F. Pop-in behavior and elastic-to-plastic transition of polycrystalline pure iron during sharp nanoindentation. *Sci. Rep.* **2019**, *9*, 15350. [CrossRef] [PubMed]
- Qian, Y.; Shang, F.; Wan, Q.; Yan, Y. A molecular dynamics study on indentation response of single crystalline wurtzite GaN. J. Appl. Phys. 2018, 124, 115102. [CrossRef]
- Bradby, J.E.; Williams, J.S.; Swain, M.V. Pop-in events induced by spherical indentation in compound semiconductors. *J. Mater. Res.* 2004, 19, 380–386. [CrossRef]
- Mason, J.K.; Lund, A.C.; Schuh, C.A. Determining the activation energy and volume for the onset of plasticity during nanoindentation. *Phys. Rev. B* 2006, 73, 054102. [CrossRef]
- Schuh, C.A.; Mason, J.K.; Lund, A.C. Quantitative insight into dislocation nucleation from high-temperature nanoindentation experiments. *Nat. Mater.* 2005, 4, 617–621. [CrossRef]
- 31. Wen, M.; Zhang, L.; An, B.; Fukuyama, S.; Yokogawa, K. Hydrogen-enhanced dislocation activity and vacancy formation during nanoindentation of nickel. *Phys. Rev. B* 2009, *80*, 094113. [CrossRef]
- 32. Field, J.S.; Swain, M.V. A simple predictive model for spherical indentation. J. Mater. Res. 1993, 8, 297–306. [CrossRef]
- Lu, J.; Ren, H.; Deng, D.; Wang, Y.; Chen, K.J.; Lau, K.; Zhang, T. Thermally activated pop-in and indentation size effects in GaN films. J. Phys. D: Appl. Phys. 2012, 45, 085301. [CrossRef]
- Nowak, R.; Pessa, M.; Suganuma, M.; Leszczynski, M.; Grzegory, I.; Porowski, S.; Yoshida, F. Elastic and plastic properties of GaN determined by nano-indentation of bulk crystal. *Appl. Phys. Lett.* 1999, 75, 2070–2072. [CrossRef]
- Gao, F.; He, J.; Wu, E.; Liu, S.; Yu, D.; Li, D.; Zhang, S.; Tian, Y. Hardness of covalent crystals. *Phys. Rev. Lett.* 2003, 91, 015502. [CrossRef] [PubMed]
- Burnett, P.J.; Page, T.F. Criteria for mechanical property modifications of ceramic surfaces by ion implantation. *Radiat. Eff.* 1986, 97, 283–296. [CrossRef]
- Reyes-Martinez, M.A.; Abdelhady, A.L.; Saidaminov, M.I.; Chung, D.Y.; Bakr, O.M.; Kanatzidis, M.G.; Soboyejo, W.O.; Loo, Y.-L. Time-dependent mechanical response of APbX<sub>3</sub> (A = Cs, CH<sub>3</sub>NH<sub>3</sub>; X = I, Br) single crystals. *Adv. Mater.* 2017, 29, 1606556. [CrossRef] [PubMed]
- 38. Tsui, T.; Volinsky, A.A. (Eds.) Small Scale Deformation Using Advanced Nanoindentation Techniques; MDPI AG: Basel, Switzerland, 2019.
- Xiao, X.; Terentyev, D.; Chu, H.; Duan, H. Theoretical models for irradiation hardening and embrittlement in nuclear structural materials: A review and perspective. *Acta Mech. Sin.* 2020, *36*, 397–411. [CrossRef]