Article

NH₃-Selective Catalytic Reduction of NO_x to N₂ over Ceria Supported WO_x Based Catalysts: Influence of Tungsten Content

Imane El Arrouji ^{1,2}, Cuirong Chen ², Jamil Toyir ³ , Cherif Larabi ², Kai C. Szeto ², Aimery de Mallmann ² , Mostafa Taoufik ^{2,*} and Abdallah Oulmekki ^{1,*}

¹ Laboratoire des Procédés, Matériaux et Environnement (LPME), Faculté des Sciences et Techniques de Fès, Université Sidi Mohammed Ben Abdellah, Fès BP. 2202, Morocco; imane.elarrouji@usmba.ac.ma

² Institut de Chimie Lyon, Université Lyon 1, CPE Lyon CNRS, UMR 5265 C2P2, LCOMS, 43 Bd du 11 Novembre 1918, CEDEX, 69616 Villeurbanne, France; cuirong.chen@etu.univ-lyon1.fr (C.C.); cherif.larabi@univ-lyon1.fr (C.L.); kai-chung.szeto@univ-lyon1.fr (K.C.S.); aimery.de-mallmann@univ-lyon1.fr (A.d.M.)

³ Laboratoire des Procédés, Matériaux et Environnement (LPME), Faculté Polydisciplinaire (FP-Taza), Université Sidi Mohammed Ben Abdellah, Taza BP. 1223, Morocco; jamil.toyir@usmba.ac.ma

* Correspondence: mostafa.taoufik@univ-lyon1.fr (M.T.); abdallah.oulmekki@usmba.ac.ma (A.O.); Tel.: +33-472431798 (M.T.)

Abstract: A series of HPW/CeO₂ catalysts generated from 12-tungstophosphoric acid, H₃PW₁₂O₄₀ (HPW), supported on ceria and presenting different tungsten loadings (2, 4.5, 9, 16, and 40 wt% W) were prepared and characterized by N₂ physisorption, XRD, IR, Raman, and UV-Vis. The different characterization techniques suggested that low loading of tungsten resulted in mainly isolated sites, while high tungsten loading produced polymeric or tungsten clusters. Those materials exhibited high activity in NH₃-SCR of NO_x into N₂. Moreover, the series of experiments indicated that low loading in tungsten (2% HPW/CeO₂) displayed the highest activity with a remarkable N₂ selectivity (99%) at medium-high temperature (300–515 °C), owing to the high amount of monomeric tungstate coverage on the catalyst surface.

Keywords: DeNO_x; 12-tungstophosphoric acid; ceria; tungsten monomeric

Citation: El Arrouji, I.; Chen, C.; Toyir, J.; Larabi, C.; Szeto, K.C.; de Mallmann, A.; Taoufik, M.; Oulmekki, A. NH₃-Selective Catalytic Reduction of NO_x to N₂ over Ceria Supported WO_x Based Catalysts: Influence of Tungsten Content. *Catalysts* **2021**, *11*, 950. <https://doi.org/10.3390/catal11080950>

Academic Editor:
Antonella Gervasini

Received: 16 July 2021
Accepted: 6 August 2021
Published: 9 August 2021

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Copyright: © 2021 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

1. Introduction

In the last decades, growing interest has been given to developing novel technologies for reducing the harmful gases in environment. Among these technologies are denitration processes for the removal of nitrogen oxides (NO and NO₂ or NO_x). Emitted NO_x is mainly originated from combustion reactions at fairly high temperatures, typically in hydrocarbon fuel combustion engines, industrial plants, and ammonia combustion power plants [1,2]. Nonetheless, the modifications made to the combustor type or in the combustion processes effectively reduce NO_x emissions [3,4]. For example, in currently operated power plants it is possible to improve combustion efficiency up to 99% and reduce pollutant emissions to concentrations lower than 100 ppm just by optimization of injection angles and temperatures at the inlet of combustors [5]. The corresponding optimization of mobile combustion engines has also been conducted. However, due to pursued restriction in NO_x emission for mobile transport application, such engineering optimization remains insufficient to satisfy upcoming regulations. Hence, the urgency to develop more efficient NO_x abatement technologies is still essential. NO_x removal includes three approaches [6]: (i) direct decomposition of NO_x into O₂ and N₂; (ii) NO_x storage reduction (NSR); and (iii) NO_x selective catalytic reduction (SCR). NO_x selective catalytic reduction (SCR) technology is classified according to the reducing agents used, such as hydrocarbons [7], oxygenated hydrocarbons [8,9], hydrogen [10], or ammonia (or urea) [11,12]. The latter is regarded as an efficient approach to reduce NO_x emissions due to its high selectivity and relatively simple implementation (without compromising the engine efficiency).

Commercial NH_3 -SCR applications typically use $\text{V}_2\text{O}_5\text{-WO}_3/\text{TiO}_2$ as a catalytic converter due to its high performance in a broad temperature window, low cost, and an excellent resistance to SO_2 [13]. Nevertheless, the N_2 selectivity decreases at high temperatures. Furthermore, the release of toxic V_2O_5 at high temperatures creates another environmental issue [14]. Therefore, developing high performance and eco-friendly catalysts to perform effective SCR denitration turns out to be a key step for the success of this process.

Tungsten based catalysts have attracted more interest owing to their superior acidity, high capacity to suppress undesirable reactions (such as SO_2 oxidation) and ability to lead to a better dispersion of the deNO_x active sites [15,16]. In recent investigations, the incorporation of the tungsten to metal oxides such as MnO_x , CuO_x , TiO_x , ZrO_x , and FeO_x greatly increased the NH_3 -SCR activity [17]. Shibo et al. reported that the addition of a small amount of tungsten to $\text{Cu}_{0.02}\text{Fe}_{0.2}\text{TiO}_x$ improves the active surface acidity and increases both the specific surface area and the number of total active sites, which all promote catalytic activity [18]. Additionally, Wang et al. found that the presence of W with $\text{MnO}_x\text{-TiO}_2$ forms the active intermediates species responsible for SCR performance [19]. NH_3 -SCR on supported catalysts showed high performance with ceria support in association with tungsten, and the redox behavior of ceria and its high capacity to store oxygen were remarkably improved during the SCR process [20]. Several research investigations indicate that the synergic effect is created between the tungsten and $\text{Ce}^{4+}/\text{Ce}^{3+}$ on the ceria support surface, resulting in a better catalytic conversion [21–23]. In order to further improve and optimize this system, it is crucial to investigate the relationship between the structure of tungsten and the reactivity in NH_3 -SCR reactions.

12-tungstophosphoric acid $\text{H}_3\text{PW}_{12}\text{O}_{40}$ (HPW) with a Keggin structure is a cheap and readily available tungsten source and is widely used for both acid and redox-catalyzed reactions [24]. For the NH_3 -SCR, HPW has been used as precursor on ceria (CeO_2) to improve the NH_3 adsorption ability after calcination [25]. However, this catalyst shows a poor performance that may be due to low surface area, low dispersion of the tungsten species, and uncontrolled synthesis method. In other studies, Song et al. [26] and Geng et al. [22] described the higher performance of ceria grafted HPW which the authors claimed to be related to better NH_3 adsorption. Nevertheless, for these systems, the active species controlling the activity are not precisely determined.

In the present study, a series of HPW/ CeO_2 (2, 4.5, 9, 16 and 40 wt% W) catalysts were synthesized and characterized. The intention is to evaluate the nature of tungsten supported on ceria in NH_3 -SCR efficiency. A series of different tungsten loadings allows determining the effect of the dispersion. Simultaneously, this study will also reveal the amount of tungsten required to obtain the optimal catalyst. Special attention is addressed to the structure analysis of the materials using X-ray diffraction, FTIR, and Raman spectroscopy, to the surface characterization by means of N_2 adsorption, in relationship with NH_3 -SCR performance.

2. Results and Discussion

2.1. Characterization of the Catalysts

The catalysts textural properties and tungsten surface density (Equation (1)) are presented in Table 1. HPW is a non-porous solid and possesses only a low specific surface area. On the other hand, when deposited on a high surface area ceria ($S_{\text{BET}} = 247 \text{ m}^2 \text{ g}^{-1}$, surface area determined by the BET approach), a tungsten functionalized material with high specific surface area can be obtained. The surface area and the average pore volume decrease with increasing W loading (Figure S1). This can be explained by a pore blocking mechanism when larger tungsten content is introduced. Thus, the surface is partially inhibited [27]. Changes in surface area and pore volume may affect the catalytic activity of the materials.

Table 1. Textural properties of CeO₂, H₃PW₁₂O₄₀, and HPW/CeO₂ (2, 4.5, 9, 16, and 40 wt% W).

Catalysts	S _{BET} (m ² g ^{−1})	Pore Volume (cm ³ g ^{−1})	Surface Density (W at/nm ²)	Average Crystallite Sizes (Å)
H ₃ PW ₁₂ O ₄₀	9	0.019	-	
CeO ₂	247	0.18	-	56
2 % HPW/CeO ₂	221	0.17	0.3	57
4.5 % HPW/CeO ₂	156	0.16	0.95	67
9 % HPW/CeO ₂	141	0.15	2.08	60
16 % HPW/CeO ₂	92	0.13	5.69	64
40 % HPW/CeO ₂	85	0.08	15.4	58

The HPW shows diffraction peaks of the Keggin structure, assigned to the triclinic space group P-1 (PDF#00-050-0656). The cubic CeO₂ phase (PDF#04-013-4361) is successfully identified for all of the HPW/CeO₂ catalysts (Figure 1). The peaks at $2\theta = 28.1^\circ$, 33.2° , 47.4° , 52.2° , 56.3° , and 69.5° are ascribed to the diffraction lines (111), (200), (220), (311), (222), and (400), respectively [28] (PDF#04-013-4361). In addition, no characteristic peaks related to the Keggin structure are detected even at higher tungsten contents, which indicates that the Keggin structure is either decomposed during calcination into tungsten oxides with an amorphous form or is highly dispersed on CeO₂. Based on the Scherrer equation, the average crystallite sizes (Table 1) remain more or less in the same order.

Figure 1. XRD patterns of CeO₂, H₃PW₁₂O₄₀, and HPW/CeO₂ (2, 4.5, 9, 16, and 40 wt% W).

FT-IR spectra of the catalysts are illustrated in Figure 2 and Figure S2. The prepared samples display a peak at 493 cm^{-1} , attributed to stretching vibrations of Ce-O [29]. The rather weak IR signals observed around 947 cm^{-1} and 682 cm^{-1} are assigned to $\nu_s(\text{W}=\text{O})$ fragment and W-O-W moiety, respectively. For the catalysts containing 16 and 40 wt% W, a novel band appeared at 820 cm^{-1} assigned to asymmetric stretching vibrations of $\text{W}=\text{O}$ [30]. Compared with the tungstophosphoric acid precursor [31], the HPW in the catalysts did not preserve its Keggin framework, also suggesting that the HPW is decomposed into tungsten oxides after calcination [32].

Figure 2. FT-IR spectra of CeO_2 , $\text{H}_3\text{PW}_{12}\text{O}_{40}$, and HPW/CeO_2 (2, 4.5, 9, 16, and 40 wt% W).

$\text{H}_3\text{PW}_{12}\text{O}_{40}$ Raman spectrum (Figure 3a, lower spectrum) displays the Keggin skeleton characteristic peaks ascribed to symmetric-asymmetric stretching modes of $\text{W}^{\text{I}} = \text{O}_d$ (1011 cm^{-1}), $\text{W}^{\text{II}} = \text{O}_d$ (994 cm^{-1}), $\text{P}-\text{O}_a$ (906 cm^{-1}), $\text{W}-\text{O}_b-\text{W}$ (522 cm^{-1}), and $\text{W}-\text{O}_c-\text{W}$ (237 cm^{-1}) bonds [33]. For the ceria, an intense symmetrical band at 459 cm^{-1} is ascribed to the F_{2g} vibration mode in the cubic fluorite phase [34]. Additionally, another band observed at 590 cm^{-1} can probably be instigated by Ce-O symmetry perturbation due to the oxygen vacancies presence in the CeO_2 structure (Figure S3) [35]. All the supported catalysts show the ceria bands with a slight shift. The $I_{\text{O}_v}/I_{\text{F}_{2g}}$ values (where $I_{\text{F}_{2g}}$ and I_{O_v} were the intensity of F_{2g} (459 cm^{-1}) and O_v (590 cm^{-1}), respectively) reveal the oxygen vacancies contents in the catalysts, which are determined by Raman deconvolution of O_v and F_{2g} peaks. These fairly low values are similar for all catalysts even at higher immobilized W amount (Figure S4, Table S1), indicating that the ceria preserves its surface morphology [36]. In order to further explore the W effect on the ceria support, Raman analysis of tungsten species are shown in $650\text{--}1000\text{ cm}^{-1}$ range. It has been reported that the WO_3 bulk, monomeric and polymeric tungstate configurations appeared respectively at 810 cm^{-1} , 930 cm^{-1} and 960 cm^{-1} [23]. In this series of HPW/CeO_2 catalyst, peaks centered around $805\text{--}815$, $915\text{--}930$, and $945\text{--}960\text{ cm}^{-1}$ are observed. Moreover, for high W content, the mono ($915\text{--}930\text{ cm}^{-1}$) and poly-tungstate ($945\text{--}960\text{ cm}^{-1}$) appear as one broad peak, which is submitted to a deconvolution operation in order to calculate the contributions of both forms (Figure S4, Table 2). The 2 and 4.5 wt% W/ CeO_2 catalysts (0.3 and 0.95 W at/nm^2) show only monomeric tungsten species. When increasing the tungsten loading, the monomeric form would decrease and the ceria surface should gradually be covered by the poly-tungstate oligomeric structure and WO_3 nanoparticles.

Figure 3. Raman spectra of CeO_2 , $\text{H}_3\text{PW}_{12}\text{O}_{40}$, HPW/ CeO_2 (2, 4.5, 9, 16, and 40 wt% W) (a) and enlarged image of tungsten species at 650–1000 cm^{-1} (b).

Table 2. Structure parameters of HPW/ CeO_2 (2, 4.5, 9, 16, and 40 wt% W) catalysts.

Catalysts	W Monomeric/W Mono + Oligo ¹	WO_3 Nanoparticles ² ($I_{\text{A1g}}/I_{\text{F2g}}$)	Estimation of W Monomeric Proportion
2% HPW/ CeO_2	1	0	100%
4.5% HPW/ CeO_2	1	0.04	96%
9% HPW/ CeO_2	0.67	0.05	64%
16% HPW/ CeO_2	0.47	0.06	44%
40% HPW/ CeO_2	0.42	0.17	36%

¹ The area ratios are calculated from the deconvolution of monomeric and oligomeric peaks. ² The normalized intensity of ν_{A1g} W-O-W (805–813 cm^{-1})/ ν_{F2g} Ce-O (459 cm^{-1}).

The evolution of the bandgap as a function of tungsten loading is determined by UV-visible diffuse reflectance spectroscopy, using the O^{2-} to metal charge transfer band (Figure 4). The HPW polytungstate cluster gave an edge energy value ($E_g = 3.03$ eV) between the isolated tungsten (Na_2WO_4 : $E_g = 4.89$ eV) and WO_x crystals ($E_g = 2.3$ eV) [37]. The W-O-W bonds number and the electronic delocalization through the WO_x polyhedral neighbors can alter the bandgaps. Nevertheless, the nature of the support oxides also affects the E_g values. CeO_2 itself has a bandgap at 2.7 eV and will inevitably prevent a reliable determination of the bandgap of the catalysts. Hence, it is difficult to probe the tungsten forms on the surface based on UV-Vis. Nevertheless, this investigation clearly shows that higher loading of tungsten gradually decreases the edge energy (Figure 4b), indicating the presence of more oligomeric/polymeric tungsten species.

Figure 4. Tauc plots (a); the energy gaps (E_g) as function of W loadings for HPW/ CeO_2 (2, 4.5, 9, 16, and 40 wt% W) (b).

The characterization studies carried out for the different catalysts have shown that for low W loadings (2.5 and 4 wt% W), tungsten is mainly present on the ceria surface as monomeric species (Figure 5) while increasing the W loading also leads to oligomeric supported species and some WO_3 bulk. The estimated proportion of monomeric W species decreasing from 100% (2 wt% W) to 96 (4.5 wt% W), 64 (9 wt% W), 44 (16 wt% W), and 36% (40 wt% W).

Figure 5. Proposed structure of isolated tungsten bis-oxo on CeO_2 .

2.2. Catalytic Activity

The NO conversion and N_2 selectivity of HPW/ CeO_2 with various W contents and 2% HPW/ SiO_2 (used for comparison) are displayed in Figure 6 and Figure S6. The NO_x reduction performance of the catalysts decreased in the order 2% HPW/ CeO_2 = 4.5% HPW/ CeO_2 > 9% HPW/ CeO_2 > 16% HPW/ CeO_2 > 40% HPW/ CeO_2 > 2% HPW/ SiO_2 > CeO_2 > HPW. Pure HPW showed almost no activity under the experimental conditions of the reaction due to its high non selective NH_3 oxidation. Modest NH_3 -SCR catalytic activity is observed on the pure ceria support, with a NO conversion less than 30% at 400 °C. It is observed that when the HPW is loaded on the ceria, the activity is significantly improved (NO conversion up to 98%). This is due probably to the synergistic effect created between tungsten species and CeO_2 . The Ce^{4+} ions on CeO_2 had a good NO_x oxidation ability but a poor NH_3 adsorption [22]. The 2–4.5% HPW/ CeO_2 show an outstanding de- NO_x activity, reaching a maximum NO conversion of 98% across the temperature range 300–515 °C. Meanwhile, the catalysts maintained a higher N_2 selectivity, particularly above 515 °C. Such performance is comparable with existing conventional catalysts [38]. When the tungsten loading was increased to 9%, the catalyst became less efficient with a NO_x removal of 98% at the 296–420 °C interval. The operation temperature interval is

also reduced with the insertion of higher amounts of tungsten into the ceria. The 16% HPW/CeO₂ and 40% HPW/CeO₂ catalysts showed NO_x conversion of 98% at 286–416 °C and 274–405 °C, respectively. based on the obtained results, it is worthwhile to note that the NO efficiency is gradually reduced with increasing tungsten loadings to 9, 16, and 40 wt%. Interestingly, the SCR activity is closely dependent on the tungsten loading. It is known for these catalysts types that the modification of ceria with a high amount of tungsten (from HPW acid) enhances the acidity and promotes the NH₃ adsorption at low temperature [22]. This can explain the higher activity observed for highly loaded tungsten catalysts at low temperature, as shown in Figure 6. However, the opposite trend is observed in the high temperature region. It was found that at higher degree of tungsten loadings, an intense agglomeration of particles was produced, which would cover the active sites. Furthermore, the presence of WO₃ nanoparticles on the ceria surface may affect the nature of these sites. The catalytic performance decreased then from 9% tungsten loading.

Figure 6. Activity (a) and N₂ selectivity (b) of CeO₂, HPW/CeO₂ (2, 4.5, 9, 16, and 40 wt% W) and 2% HPW/SiO₂. Condition: [NH₃] = 350 ppm, [NO] = 300 ppm and GHSV = 30,000 h^{−1}.

The performance of 2% HPW/CeO₂ catalyst is greatly superior to that of 2% HPW/SiO₂ (80% NO conversion is achieved at 420 °C), indicating the favorable synergistic effect created between tungsten and the ceria. In the 2% HPW/CeO₂, the interaction between Ce atom and isolated tungsten (monomeric) (revealed by Raman) produces W(=O)₂(O-Ce)₂ and W(=O)(O-Ce)₄ species [23,39]. This may explain the best activity and the highest stability at high temperature obtained for this 2% HPW/CeO₂ catalyst, where the highest proportion of isolated species is observed. Isolated tungsten species on ceria surface, prepared by an organometallic approach, has recently been demonstrated to be extremely active for NH₃-SCR [40].

The turnover frequencies TOF (calculated based on the converted NO over the total amount of tungsten) were determined to compare the catalytic activity as a function of the tungsten loadings at low (219–253 °C) and high temperatures (525–560 °C). As suggested above, materials with high tungsten loading contain mainly polymeric tungsten species, while samples with low tungsten content comprise mostly isolated species. Hence, a detailed TOF analysis (Figure 7) may provide insights to associate the nature of the active sites with the activity. The TOF is higher at the low temperature region for highly loaded tungsten on ceria, demonstrating that 40% HPW/CeO₂ is more active catalyst. Conversely, in the high temperature region, an increase in the TOF values is observed with lower tungsten contents. These findings indicate that the polymeric tungsten species can readily perform SCR of NO in the low temperature region, while the isolated tungsten species are more active in the high temperature region. Indeed, the isolate tungstate sites in 2% HPW/CeO₂ would be more accessible to reactants. Moreover, this material shows an acidic behavior, as determined by NH₃-TPD (33.4 μmol/g), a parameter known to improve the

catalytic performances even with low W concentration (Figure S6). For this reason, the use of only a small amount of tungsten is enough to achieve the best activity for NO reduction.

Figure 7. TOF of HPW/CeO₂ (2, 4.5, 9, 16, and 40 wt% W) at low (a) and high temperatures (b).

Additional catalysis experiment has been investigated for 2% HPW/CeO₂ catalyst in the presence of 5% water (Figure S8), reflecting more realistic conditions in combustion engines. The conversion slightly decreased in the presence of water, which is typical. This could be attributed to agglomeration of the tungsten species accelerated by the presence of water. However, the activity and selectivity remained high.

3. Materials and Methods

3.1. Catalysts Preparation

A series of HPW/CeO₂ catalysts with increasing tungsten amounts (2, 4.5, 9, 16, and 40 wt%) were synthesized by wet impregnation method. The solution of tungstophosphoric acid (HPW) in ethanol was added to the ceria (CeO₂) at room temperature. The solvent was removed by a rotary evaporator at 30 °C. Afterwards, the samples were calcined in air at 500 °C for 3 h, yielding the catalysts for further characterization and catalytic evaluation.

3.2. Catalysts Characterization

The surface areas were determined with an ASAP 2020 Micromeritics instrument (Norcross, GA, USA) and calculated from the Brunauer, Emmett, and Teller (BET) equation. The catalysts were outgassed at 200 °C for 4 h before the physisorption measurements. The tungsten surface density was calculated based on the following Equation (1):

$$\text{Surface density (W/nm}^2\text{)} = \frac{X_W N_A}{S_{\text{BET}} M_W} \quad (1)$$

where X_W is the loading of the W in the catalyst, N_A is the Avogadro number; M_W is the atomic weight of W and S_{BET} is the surface area of each catalyst.

X-ray Diffraction (XRD) patterns were registered by Bruker D8 Advance diffractometer (Billerica, MA, USA) using Cu-K α_1 radiation at 40 KV and 40 mA. The refractory lights were collected by a Bruker Lynxeye XE detector for one hour. The diffractograms were analyzed by the X'pert high score software.

IR spectra were recorded in transmission mode in a JASCO FT/IR-4100 spectrometer (Tokyo, Japan) with 2 cm⁻¹ resolution.

Raman spectroscopy was executed on Labram HR Evo spectrophotometer (from Horiba Jobin-Yvon, Kyoto, Japan) with a green laser diode ($\lambda = 533$ nm) using a CDD detector. The spectra were analyzed by LabSpec software with a spectral resolution < 0.5 cm⁻¹.

UV–visible spectroscopy was carried out on a PerkinElmer Lambda 900 (Waltham, MA, USA). The samples were measured in 190–850 nm range at room temperature using BaSO₄ as a reference. Tauc plot was used to determine the band gaps (E_g) by the Kubelka–Munk function in indirect transition, which allows the analysis of crystalline and amorphous compounds. The band gaps (E_g) are estimated from the plot of the tangent line of the $(\alpha h\nu)^{1/2} = f(E)$ curve extrapolated to the abscissa.

Determination of the acidity of the 2%HPW/CeO₂ catalyst by NH₃ desorption: A typical mass of 50 mg of material was used during the experiments. The experiment included four steps: (1) degasification of the sample in Ar at 500 °C for 2 h; (2) adsorption of NH₃ at 120 °C for 1 h; (3) isothermal desorption with Ar at 120 °C until almost no NH₃ was detected; and (4) temperature programmed desorption in Ar at 10 °C/min up to 650 °C. The amount of NH₃ in the gas phase was obtained by using an Antaris IGS FTIR (Thermo-Fischer).

3.3. Catalysts Measurement

The NH₃-SCR tests were carried out in a quartz continuous-flow reactor using 30 mg catalyst diluted in silicon carbide (SiC). The reactant mixture is composed by 350 ppm NH₃, 10 vol. % O₂, 300 ppm NO in helium with a 300 mL/min total gas flow rate at a velocity of 30,000 h^{−1} (GHSV). The reactor was heated from room temperature to 600 °C (heating rate of 10 °C min^{−1}). The outlet gas concentrations (NH₃, NO, N₂O and NO₂) were analyzed by an Antaris IGS (Thermo-Fischer, Waltham, MA, USA) FT-IR equipped with a 200 mL gas cell and a DTGS detector. The NO conversion and N₂ selectivity were calculated as follows (Equations (2) and (3)):

$$\text{NO}_{\text{conversion}}(\%) = \frac{[\text{NO}]_{\text{in}} - [\text{NO}_x]_{\text{out}}}{[\text{NO}]_{\text{in}}} \times 100 \quad (2)$$

$$\text{N}_{2\text{selectivity}}\% = \frac{[\text{NO}]_{\text{in}} + [\text{NH}_3]_{\text{in}} - [\text{NO}_x]_{\text{out}} - [\text{NH}_3]_{\text{out}} - 2[\text{N}_2\text{O}]_{\text{out}}}{[\text{NO}]_{\text{in}} + [\text{NH}_3]_{\text{in}} - [\text{NO}_x]_{\text{out}} - [\text{NH}_3]_{\text{out}}} \times 100 \quad (3)$$

where $[\text{NO}_x] = [\text{NO}] + [\text{NO}_2]$.

4. Conclusions

HPW/CeO₂ catalysts are prepared with different tungsten loadings by wet impregnation method and characterized by N₂ physisorption, XRD, FT-IR, Raman and UV-Vis spectroscopies. The different characterization techniques suggested that low loading of tungsten resulted in mainly isolated sites, while high tungsten loading produced polymeric or tungsten clusters. Those materials exhibited high activity in NH₃-SCR of NO_x into N₂. The materials were further studied for selective reduction reaction of NO_x by ammonia. The series of catalysts with different loading allowed further structure-reactivity assignments. Polymeric tungsten species can readily perform SCR of NO in the low temperature region, while the isolated tungsten species are more active in the high temperature region. In terms of catalytic activity, at temperatures higher than 500 °C, the best NO conversion is obtained for the 2 wt% W HPW/CeO₂ catalyst and decreased when increasing the tungsten amount. The enhanced catalytic performance can be attributed to a synergetic interaction between the isolated W and CeO₂, described by monomeric surface moiety expressed as W(=O)(O-Ce)₄ and W(=O)₂(O-Ce)₂ on the interface of the 2 wt% W HPW/CeO₂. Such species are believed to improve its stability at high temperature and facilitate the adsorption of reactants. Particularly with this catalyst, a high activity (NO conversion above 98%) is reached at temperature between 300–515 °C, which can be compared with the best catalysts described in the literature with high tungsten loadings [41]. Current findings reveal that the tungsten dispersion will highly affect the NH₃-SCR of NO, in which high dispersion is favorable. The latter has recently been confirmed by a catalytic material based on isolated tungsten species supported on ceria prepared through a delicate organometallic approach. Nevertheless, current work presents a simple synthesis method

to access highly dispersed and active catalyst with low loading of tungsten. These result shows that isolated atom materials are highly effective heterogeneous catalysts for future automotive applications [42].

Supplementary Materials: The following are available online at <https://www.mdpi.com/article/10.3390/catal11080950/s1>, Figure S1: N₂ physisorption isotherms for each catalyst; Figure S2: IR spectra of ceria and HPW; Figure S3: Enlarged picture of the bands attributed to the LO vibration mode of CeO₂ at 500–700 cm^{−1} (Raman spectra); Figure S4: deconvolutions of Raman spectra for each catalyst in the range 300–650 cm^{−1}; Figure S5: Deconvolutions of Raman spectra for each catalyst in the range 800–1050 cm^{−1}; Figure S6: NO_x conversion, over HPW as a function of temperature. Feed composition: 300 ppm NO, 350 ppm NH₃, 5 vol. % H₂O and 10 vol. % O₂ in He; Figure S7: Determination of the acidity of the catalysts 2%HPW/CeO₂ by NH₃ desorption; Figure S8: NO_x conversion and N₂ selectivity obtained with 2%HPW/CeO₂ as a function of temperature with and without water. Feed composition: 300 ppm NO, 350 ppm NH₃, 5 vol. % H₂O and 10 vol. % O₂ in He; Table S1: Oxygen vacancies values of HPW/CeO₂ (2, 4.5, 9, 16 and 40 wt% W) catalysts.

Author Contributions: I.E.A. writing—original draft preparation, data interpretation and experiments. C.C. contributed to the experiments. K.C.S., A.d.M. and C.L. writing and revising. J.T., A.O. and M.T. supervision, project administration and funding acquisition. All authors have read and agreed to the published version of the manuscript.

Funding: This investigation has been supported by the R&D Initiative—Appel à projets autour des phosphates APPHOS—sponsored by OCP (OCP Foundation, R&D OCP, Mohammed VI Polytechnic University, National Center of Scientific and technical Research CNRST, Ministry of Higher Education, Scientific Research and Professional Training of Morocco MESRSFC) under the project ID * CHF-OUL-01/2017. Imane El Arrouji acknowledges a Ph.D. grant from the OCP Foundation for R&D (grant number CHF-OUL-01/2017). CC thanks CSC (China Scholarship Council, grant number 201906740011) for financial support.

Acknowledgments: The authors wish to thank Marc Jeannin and Aabdelali Oudriss (LaSIE/La Rochelle University) for RAMAN experiments.

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Franco, M.C.; Rocha, R.C.; Costa, M. Characteristics of NH₃/H₂/air flames in a combustor fired by a swirl and bluff-body stabilized burner. *Proc. Combust. Inst.* **2021**, *38*, 5129–5138. [CrossRef]
2. Ariemma, G.B.; Sabia, P.; Sorrentino, G.; Bozza, P.; De Joannon, M.; Ragucci, R. Influence of water addition on MILD ammonia combustion performances and emissions. *Proc. Combust. Inst.* **2021**, *38*, 5147–5154. [CrossRef]
3. Funke, H.H.; Beckmann, N.; Abanteriba, S. An overview on dry low NO_x micromix combustor development for hydrogen-rich gas turbine applications. *Int. J. Hydrogen Energy* **2019**, *44*, 6978–6990. [CrossRef]
4. Sorrentino, G.; Sabia, P.; Bozza, P.; Joannon, M. De Low-NO_x conversion of pure ammonia in a cyclonic burner under locally diluted and preheated conditions. *Appl. Energy* **2019**, *254*, 113676. [CrossRef]
5. Okafor, E.C.; Somarathne, K.D.K.A.; Hayakawa, A.; Kudo, T.; Kurata, O.; Iki, N. Towards the development of an efficient low-NO_x ammonia combustor for a micro gas turbine. *Proc. Combust. Inst.* **2018**, *37*, 4597–4606. [CrossRef]
6. Liu, S.; Wang, H.; Wei, Y.; Zhang, R.; Royer, S. Morphology-Oriented ZrO₂-Supported vanadium oxide for the NH₃-SCR process importance of structural and textural properties. *ACS Appl. Mater. Interfaces* **2019**, *11*, 22240–22254. [CrossRef]
7. Shimizu, K.; Satsuma, A.; Hattori, T. Catalytic performance of Ag-Al₂O₃ catalyst for the selective catalytic reduction of NO by higher hydrocarbons. *Appl. Catal. B Environ.* **2000**, *25*, 239–247. [CrossRef]
8. Valanidou, L.; Theologides, C.; Zorpas, A.A.; Savva, P.G.; Costa, C.N. A novel highly selective and stable Ag MgO-CeO₂-Al₂O₃ catalyst for the low-temperature ethanol-SCR of NO. *Appl. Catal. B Environ.* **2011**, *107*, 164–176. [CrossRef]
9. Popovych, N.; Kirienko, P.; Soloviev, S.; Orlyk, S. Selective catalytic reduction of NO_x by C₂H₅OH over Ag/Al₂O₃/cordierite: Effect of the surface concentration of silver. *Catal. Today* **2012**, *191*, 38–41. [CrossRef]
10. Hamada, H.; Haneda, M. A review of selective catalytic reduction of nitrogen oxides with hydrogen and carbon monoxide. *Appl. Catal. A Gen.* **2012**, *421*, 1–13. [CrossRef]
11. Koebel, M.; Elsener, M.; Kleemann, M. Urea-SCR: A promising technique to reduce NO_x emissions from automotive diesel engines. *Catal. Today* **2000**, *59*, 335–345. [CrossRef]
12. Ciardelli, C.; Nova, I.; Tronconi, E.; Chatterjee, D.; Bandl-konrad, B.; Weibel, M.; Krutzsch, B. Reactivity of NO/NO₂-NH₃ SCR system for diesel exhaust aftertreatment: Identification of the reaction network as a function of temperature and NO₂ feed content. *Appl. Catal. B Environ.* **2007**, *70*, 80–90. [CrossRef]

13. Huang, X.; Li, S.; Qiu, W.; Chen, Y.; Cheng, J.; Sun, Y.; Bai, G. Effect of organic assistant on the performance of ceria-based catalysts for the selective catalytic. *Catalyst* **2019**, *9*, 357. [\[CrossRef\]](#)
14. Chen, M.; Jin, Q.; Tao, X.; Pan, Y.; Gu, S. Novel W-Zr-Ox/TiO₂ catalyst for selective catalytic reduction of NO by NH₃ at high temperature. *Catal. Today* **2019**, *358*, 254–262. [\[CrossRef\]](#)
15. Kwon, D.W.; Nam, K.B.; Hong, S.C. Influence of tungsten on the activity of a Mn/Ce/W/Ti catalyst for the selective catalytic reduction of NO with NH₃ at low temperatures. *Appl. Catal. A Gen.* **2015**, *497*, 160–166. [\[CrossRef\]](#)
16. Li, C.; Shen, M.; Wang, J.; Wang, J.; Yanping, Z. New Insights into the Role of WO₃ in Improved Activity and Ammonium Bisulfate Resistance for NO Reduction with NH₃ over V–W–Ce–Ti Catalyst. *Ind. Eng. Chem. Res.* **2018**, *57*, 8424–8435. [\[CrossRef\]](#)
17. Rui, Y.; Zhenchao, Z.; Shi, C.; Zhang, W. Insight into the synergic effect of Fe-SSZ-13 zeolite and FeMnTiZrOx catalyst with enhanced reactivity in NH-SCR of NOx. *J. Phys. Chem. C* **2019**, *123*, 2216–2227. [\[CrossRef\]](#)
18. Ma, S.; Zhao, X.; Li, Y.; Zhang, T.; Yuan, F.; Niu, X.; Zhu, Y. Effect of W on the acidity and redox performance of the Cu_{0.02}Fe_{0.2}W_{0.2}TiO_x (a = 0.01, 0.02, 0.03) catalysts for NH₃-SCR of NO. *Appl. Catal. B Environ.* **2019**, *248*, 226–238.
19. Wang, X.; Li, X.; Zhao, Q.; Sun, W.; Tade, M.; Liu, S. Improved activity of W-modified MnOx-TiO₂ catalysts for the selective catalytic reduction of NO with NH₃. *Chem. Eng. J.* **2016**, *288*, 216–222. [\[CrossRef\]](#)
20. Trovarelli, A. Structural and oxygen storage/release properties of CeO₂-based solid solutions. *J. Crit. Discuss. Curr. Lit.* **1999**, *20*, 263–284. [\[CrossRef\]](#)
21. Liang, C.; Junhua, L.; Maofa, G. DRIFT Study on Cerium-Tungsten/Titanium catalyst for selective catalytic reduction of NOx with NH₃. *Environ. Sci. Technol.* **2010**, *44*, 9590–9596.
22. Geng, Y.; Xiong, S.; Li, B.; Liao, Y.; Xiao, X.; Yang, S. H3PW12O₄₀ grafted on CeO₂: A High-performance catalyst for the selective catalytic reduction of NOx with NH₃. *Ind. Eng. Chem. Res.* **2018**, *57*, 856–866. [\[CrossRef\]](#)
23. Kim, G.J.; Lee, S.H.; Nam, K.B.; Hong, S.C. A study on the structure of tungsten by the addition of ceria: Effect of monomeric structure over W/Ce/TiO₂ catalyst on the SCR reaction. *Appl. Surface Sci.* **2020**, *507*, 145064. [\[CrossRef\]](#)
24. Narasimharao, K.; Brown, D.R.; Lee, A.F.; Newman, A.D.; Siril, P.F.; Tavener, S.J.; Wilson, K. Structure-activity relations in Cs-doped heteropolyacid catalysts for biodiesel production. *J. Catal.* **2007**, *248*, 226–234. [\[CrossRef\]](#)
25. Weng, X.; Dai, X.; Zeng, Q.; Liu, Y.; Wu, Z. DRIFT studies on promotion mechanism of H3PW12O₄₀ in selective catalytic reduction of NO with NH₃. *J. Colloid Interface Sci.* **2016**, *461*, 9–14. [\[CrossRef\]](#) [\[PubMed\]](#)
26. Song, Z.; Zhang, Q.; Ma, Y.; Liu, Q.; Ning, P.; Liu, X. Mechanism-dependent on the different CeO₂ supports of phosphotungstic acid modification CeO₂ catalysts for the selective catalytic reduction of NO with NH₃. *J. Taiwan Inst. Chem. Eng.* **2017**, *71*, 277–284. [\[CrossRef\]](#)
27. García-fernández, S.; Gandarias, I.; Requies, J.; Güemez, M.B.; Bennici, S.; Auroux, A.; Arias, P.L. New approaches to the Pt/WOx/Al₂O₃ catalytic system behavior for the selective glycerol hydrogenolysis to 1, 3-propanediol. *J. Catal.* **2015**, *323*, 65–75. [\[CrossRef\]](#)
28. Ramasamy, V.; Mohana, V.; Rajendran, V. Characterization of Ca doped CeO₂ quantum dots and their applications in photocatalytic degradation. *OpenNano* **2018**, *3*, 38–47. [\[CrossRef\]](#)
29. Kannan, S.K.; Sundarajan, M.; Green, A. A green approach for the synthesis of a cerium oxide nanoparticle: Characterization and antibacterial activity. *Int. J. Nanosci.* **2014**, *13*, 1450018. [\[CrossRef\]](#)
30. Kim, D.S.; Ostromecki, M.; Wachs, I.E.; Kohler, S.D.; Ekerdt, J.G. Preparation and characterization of WO₃/SiO₂ catalysts. *Catal. Lett.* **1995**, *33*, 209–215. [\[CrossRef\]](#)
31. Javidi, J.; Esmaeilpour, M.; Rahiminezhad, Z.; Dodeji, F.N. Synthesis and characterization of H3PW12O₄₀ and H3PMo12O₄₀ nanoparticles by a simple method. *J. Clust. Sci.* **2014**, *25*, 1511–1524. [\[CrossRef\]](#) [\[PubMed\]](#)
32. Dong, L.; Hu, Y.; Xu, F.; Lu, D.; Xu, B.; Hu, Z.; Chen, Y. A study on the surface properties of ceria-supported tungsten and copper oxides. *J. Phys. Chem. B* **2000**, *104*, 78–85. [\[CrossRef\]](#)
33. Marci, G.; García-lópez, E.I.; Rita, F.; Liotta, L.F.; Palmisano, L. General Enhanced (photo) catalytic activity of Wells-Dawson (H6P2W18O62) in comparison to Keggin (H3PW12O40) heteropolyacids for 2-propanol dehydration in gas-solid regime. *Appl. Catal. A Gen.* **2016**, *528*, 113–122. [\[CrossRef\]](#)
34. Castro, D.; Sigoli, F.A.; Mazali, I.O. Reversible Oxygen Vacancy Generation on Pure CeO₂ Nanorods Evaluated by in Situ Raman Spectroscopy. *J. Phys. Chem. C* **2017**, *121*, 12928–12935.
35. Farias, M.D.D.; Nguyen-thanh, D.; Fraga, M.A. Environmental Discussing the use of modified ceria as support for Pt catalysts on water-gas shift reaction. *Appl. Catal. B Environ.* **2010**, *93*, 250–258. [\[CrossRef\]](#)
36. Li, X.; Wang, Z.; Sun, J.; Oh, R.; Feng, J.; Shi, D.; Zhao, W.; Liu, S. Influence of CeO₂ morphology on WO₃/CeO₂ catalyzed NO selective catalytic reduction by NH₃. *J. Energy Inst. J.* **2020**, *93*, 1–8. [\[CrossRef\]](#)
37. Howell, J.; Li, Y.; Bell, A.T. Propene metathesis over supported tungsten oxide catalysts: A study of active site formation. *ACS Catal.* **2016**, *6*, 1–32. [\[CrossRef\]](#)
38. Li, Z.; Li, J.; Liu, S.; Ren, X.; Ma, J.; Su, W. Ultra hydrothermal stability of CeO₂-WO₃/TiO₂ for NH₃-SCR of NO compared to traditional V₂O₅-WO₃/TiO₂ catalyst. *Catal. Today* **2015**, *258*, 11–16. [\[CrossRef\]](#)
39. Gu, Y.; Cai, T.; Gao, X.; Xia, H.; Sun, W.; Zhao, J.; Dai, Q.; Wang, X. Catalytic combustion of chlorinated aromatics over WOx/CeO₂ catalysts at low temperature. *Appl. Catal. B Environ.* **2019**, *248*, 264–276. [\[CrossRef\]](#)

-
40. Larabi, C.; Chen, C.; Merle, N.; Charlin, M.; Szeto, K.C.; De Mallmann, A.; Benayad, A.; Ben Tayeb, K.; Kaddouri, A.; Nguyen, H.P.; et al. Well-defined surface tungstenocarbene complex through the reaction of $[W(\equiv CtBu)(CH_2tBu)_3]$ with CeO_2 : A highly and stable precatalyst for NO_x reduction with NH_3 . *New J. Chem.* **2021**, *45*, 12024–12032. [[CrossRef](#)]
 41. Ma, Z.; Weng, D.; Wu, X.; Si, Z. Effects of WO_x modification on the activity, adsorption and redox properties of CeO_2 catalyst for NO_x reduction with ammonia. *J. Environ. Sci.* **2012**, *24*, 1305–1316. [[CrossRef](#)]
 42. Higashi, A.; Shougo, B. Towards dense single-atom catalysts for future automotive applications. *Nat. Catal.* **2019**, *2*, 590–602.