



Article Efficient Synthesis of Dihydropyrimidines Using a Highly Ordered Mesoporous Functionalized Pyridinium Organosilica

Fatemeh Rajabi ^{1,}*¹, Mika Sillanpää ^{2,3}¹, Christophe Len ⁴¹ and Rafael Luque ^{5,}*¹

- ² Department of Biological and Chemical Engineering, Aarhus University, 8000 Aarhus, Denmark; mikaesillanpaa@gmail.com
- ³ International Research Centre of Nanotechnology for Himalayan Sustainability (IRCNHS), Shoolini University, Solan 173212, India
- ⁴ CNRS, Institute of Chemistry for Life and Health Sciences, Chimie Paris Tech, PSL Research University, 11 rue Pierre et Marie Curie, F-75005 Paris, France; christophe.len@chimieparistech.psl.eu
- ⁵ Departamento de Química Orgánica, Campus de Rabanales, Edificio Marie Curie (C-3), Universidad de Córdoba, Ctra Nnal IV-A, Km 396, E14014 Cordoba, Spain
- * Correspondence: f_rajabi@pnu.ac.ir (F.R.); q62alsor@uco.es (R.L.)

Abstract: A Brönsted acidic ionic solid pyridinium-functionalized organosilica network (PMO-Py-IL) was demonstrated to efficiently catalyse one-pot Biginelli condensation reaction. The green synthesis of 3,4-dihydro-2(H)-pyrimidinones (DHPMs) with high yield was carried out via one-pot three component condensation of β - dicarbonyls, aldehydes, and urea in the presence of a catalytic amount of PMO-Py-IL nanomaterial as an efficient nanocatalyst under solvent free conditions. Furthermore, the catalyst showed outstanding stability and could be easily separated and reused for at least ten reaction runs without significant loss of activity and product selectivity. The green protocol features simple set-up, cost-effectiveness, easy work-up, eco-friendly and mild reaction conditions.

Keywords: biginelli reaction; dihydropyrimidines; pyridinium-functionalized organosilica; reusable nanocatalyst

1. Introduction

3,4-Dihydro-2(*H*)-pyrimidinones (DHPMs) are one of the most biologically important families of nitrogen-containing heterocycles in natural and synthetic chemistry [1]. The pyrimidine ring system could be naturally found in vitamins such as thiamin, folic acid and riboflavin; nucleic acids such as uracil, thymine, and cytosine, and alkaloids such as heteromine and manzacidin [2]. DHPMs have been found to exhibit distinct pharmacological and biological activities such as being anti-tumor [3], anti-cancer [4,5], anti-inflammatory [6], anti-viral [7], anti-fungal [8], and as calcium channel blockers [9,10]. Furthermore, the industrial applications include their use as additive to agrochemicals, dyes, and organic compounds [11]. Some examples of biologically and pharmacologically active dihydropyrimidine derivatives such as [bis(2-chloroethyl)amino] pyrimidine-2,4(1*H*,3*H*)-dione (Uramustine), 5-fluoro-1-(tetrahydro-2-furyl)pyrimidine-2,4(1*H*,3*H*)-dione (Tegafur), 4-amino-1- β -darabinofuranosyl pyrimidine-2(1*H*)-one (Cytarabine), 5-Fluoropyrimidine-2,4(1*H*,3*H*)-dione (Fluorouracil), 1,2,3,6-Tetrahydro-2,6-dioxo pyrimidine-4-carboxylic acid (Orotic Acid), and 5-Bromo-2'-deoxyuridine-5-bromo-1-(2-deoxy- β -D-ribofuranosyl) pyrimidine-2,4-(1*H*,3*H*)-dione (Broxuridine) are shown in Figure 1.

One-pot Biginelli condensation reaction is the original procedure for the synthesis of DHPMs reported by Biginelli in 1891. This procedure involved reaction of β -dicarbonyl compounds, aromatic aldehydes, and urea under strongly acidic conditions [12–15]. Biginelli reaction was carried out by refluxing a mixture of the three components such as ethyl acetoacetate, benzaldehyde, and urea in the presence of ethanol catalyzed by hydrochloric acid which often resulted in poor to moderate yields of desired products. Due



Citation: Rajabi, F.; Sillanpää, M.; Len, C.; Luque, R. Efficient Synthesis of Dihydropyrimidines Using a Highly Ordered Mesoporous Functionalized Pyridinium Organosilica. *Catalysts* **2022**, *12*, 350. https://doi.org/10.3390/ catal12030350

Academic Editor: Elisabete C.B.A. Alegria

Received: 1 February 2022 Accepted: 11 March 2022 Published: 21 March 2022

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/).

¹ Department of Science, Payame Noor University, P.O. Box 19395-4697, Tehran 19569, Iran

to remarkable biological and pharmacological activities and versatile use of DHPMs, the synthesis of DHPMs has been revalued. Several improved synthetic methodologies for the Biginelli condensation have recently been developed by employing various catalysts such as p-toluenesulfonic acid [16], Ni(II) coordination complex [17], chloroacetic acid [18], TiCl₄ [19], RuCl₃ [20], Sc(OTf)₃ [21], Co(OAc)₂ [22], sulfated zirconia [23], FeCl₃.6H₂O [24], MgBr₂ [25], NbCl₅ [26], Yb(OTf)₃ [27], InCl₃ [28], CuCl₂ [29], SnCl₂ [30], BF₃.OEt₂ [31], ZrCl₄ [32], ZnCl₂ [33], TMSOTf [34], CdCl₂ [35], CH₃SO₃H [36], Iron(III) [37], SmI₂ [38], Pb(NO₃)₃ [39], Ba(OH)₃ [40], solvent-free synthesis [41], microwave irradiation [42], ultrasound radiation [43], visible light irradiation [44], Brønsted acidic ionic liquid [45], solid supported reagent [46–50], and enzymatic catalysts [51]. In spite of progress in the synthesis of these compounds, however, some of the previously reported procedures have significant drawbacks such as harsh reaction conditions, low product yield, use of expensive or toxic reagents, laborious workup, and large amount of toxic wastes generation. Therefore, the development of green, efficient, simple, clean, high yielding, mild, environmentally benign and cost-effective approaches using reusable catalysts is highly desirable and is of utmost importance for the synthesis of DHPMs.



Figure 1. Chemical structures of some biologically and pharmacologically active DHPMs.

The activity of the heterogeneous catalysts with various supports is dependent on the size, morphology, surface area, and nature of the support. Among them, periodic mesoporous organosilicas (PMOs) with high loading of organic functional groups, high surface area, periodically ordered and tunable pores is most favorable and have various applications such as in adsorption, catalysis, separation, medicine, and advanced materials [52–57]. –Numerous organosilane precursors can be used to successfully form PMOs via surfactant-based sol-gel technique allowing a better control of the size, structure, and composition of the PMO materials for the specific application requirements.

In continuation of our efforts towards sustainable development of highly efficient and recyclable catalysts for green chemicals synthesis [58–60] we have very recently developed a highly ordered porous PMO nanomaterial based on pyridinium ionic liquid as ionic solid catalyst (PMO-Py-IL), which showed excellent activity towards biodiesel production via Fischer esterification [60]. Herein, we demonstrate the application of this efficient and reusable nanocatalyst for one-pot three component Biginelli condensation reaction under mild and eco-friendly conditions.

2. Results and Discussion

The synthesis and characterization of ionic solid-acid hybrid nanomaterial with pyridinium ionic liquid framework (PMO-Py-IL) was reported according to our recently published work [60]. The growing interest towards the development of green reaction conditions has motivated us to develop 3,4-dihydro-2(*H*)-pyrimidinones (DHPMs) via one-pot three component condensation of β -dicarbonyls, aldehydes, and urea for further application of PMO-Py-IL nanomaterials.

The catalytic activity of PMO-Py-IL nanocatalyst has been investigated in the reaction of three-component condensation of ethyl acetoacetate, benzaldehyde and urea as a model reaction. In order to optimize the reaction conditions, the effect of different reaction parameters such as reaction time, reaction temperature, catalyst amount, and solvent were evaluated, and results are summarized in Table 1. According to the results, blank runs (in the absence of catalyst or solvent) provide a low yield of the product even after 2 h at 100 $^{\circ}$ C (Table 1, Entries 1,2). We screened the effect of solvents such as acetonitrile (CH₃CN), ethanol (C_2H_5OH), dichloromethane (CH_2Cl_2), tetrahydrofuran (THF), and water (H_2O) using 10 mg of the PMO-Py-IL nanocatalyst in the model reaction under reflux conditions. The excellent yield of the product was observed with C_2H_5OH (Entry 3), and the lowest yield was observed in CH_2Cl_2 (Entry 4). It was found that the reaction was carried out in excellent yield under solvent-free condition (Entry 9). Next, the effect of catalyst loading on the reaction efficacy was studied. The reaction yield was found to be significantly decreased at lower loading (Entry 10). In order to study the influence of the reaction temperature, the model reaction was carried out at different reaction temperatures (Entries 11–14). Interestingly, excellent yield of product was obtained at 50 $^{\circ}$ C. Further studies were done to optimize the reaction time. As displayed in Table 1 (Entries 15–18), it was observed that the PMO-Py-IL nanocatalyst showed the highest product yield within the short time span (of 15 min), utilizing 10 mg of the PMO-Py-IL nanocatalyst under solvent free conditions.

Entry	PMO-Py-IL (mg)	Solvent	Temp. (°C)	Time (min)	Yield (%) ^a
1	-	-	100	120	20
2	-	C ₂ H ₅ OH	Reflux	120	28
3	10	C ₂ H ₅ OH	Reflux	120	95
4	10	CH_2Cl_2	Reflux	120	42
5	10	THF	Reflux	120	54
6	10	H ₂ O	Reflux	120	82
8	10	CH ₃ CN	Reflux	120	58
9	10	-	80	120	99
10	8	-	80	120	88
11	10	-	70	120	84
12	10	-	60	120	87
13	10	-	50	120	99
14	10	-	40	120	70
15	10	-	50	60	98
16	10	-	50	30	98
17	10	-	50	15	98
18	10	-	50	10	91

Table 1. Effect of different parameters on the Biginelli reaction of ethyl acetoacetate (10 mmol), benzaldehyde (10 mmol), and urea (12 mmol).

^a Isolated yields.

To evaluate the scope and limitation of the process, a series of DHPMs were synthesized via one-pot Biginelli condensation reaction under optimized conditions (Scheme 1). As shown in Table 2, various aromatic aldehydes were reacted with -dicarbonyls and urea to give desired DHPM products in high yields under optimal reaction conditions.



Scheme 1. PMO-Py-IL catalyzed the one-pot Biginelli condensation reaction.

 Table 2. Synthesis of dihydropyrimidones catalyzed by PMO-Py-IL nanocatalyst under solvent free conditions.

Entry	R ¹	R ²	Product	Yield (%) ^a	M.P(°C) [Ref.]
1	C_6H_5	OEt	4a	98	201–203 [16]
2	$4-NO_2-C_6H_4$	OEt	4b	94	211–213 [16]
3	4-Cl-C ₆ H ₄	OEt	4c	92	210–212 [16]
4	2-OH-C ₆ H ₄	OEt	4d	80	217–219 [16]
5	2-Cl-C ₆ H ₄	OEt	4e	82	220–223 [16]
6	4-OCH ₃ - C ₆ H ₄	OEt	4f	84	201–203 [16]
7	C_6H_5	OMe	4g	96	221–223 [16]
8	$4-NO_2-C_6H_4$	OMe	4h	92	233–235 [16]
9	4-Cl-C ₆ H ₄	OMe	4i	85	154–156 [16]
10	2-OH-C ₆ H ₄	OMe	4j	78	243–244 [45]
11	2-Cl-C ₆ H ₄	OMe	4k	82	249–252 [16]
12	4-OCH ₃ - C ₆ H ₄	OMe	41	80	232–233 [16]
13	C_6H_5	Me	4m	98	231–233 [45]
14	$4-NO_2-C_6H_4$	Me	4n	93	229–230 [45]
15	$4-Cl-C_6H_4$	Me	40	90	204–206 [45]
16	$2-OH-C_6H_4$	Me	4p	82	215–217 [45]
17	2-Cl-C ₆ H ₄	Me	4q	85	201–203 [45]
18	4-OCH ₃ - C ₆ H ₄	Me	4r	84	172–174 [45]

^a Isolated yield.

From the data presented in Table 2, it is clearly observed that the method was effective for both electron-withdrawing groups and electron-donating in the aromatic ring of the aldehydes. When reaction was carried out using aliphatic aldehydes such as acetaldehyde and propanal, a trace of corresponding dihydropyrimidone product was obtained even after 3 h.

To evaluate the heterogeneity of PMO-Py-IL and leaching of active species from the support, a hot filtration test was performed during the Biginelli reaction of three-component ethyl acetoacetate, benzaldehyde, and urea under optimized conditions. PMO-Py-IL nanocatalyst was removed by hot filtration after 6 min, and the filtrate solution was further left to react after catalyst filtration for 30 min. No Biginelli condensation reaction progress was observed (monitored by GC) after catalyst filtration. The results confirmed that no catalytically active species remained in the reaction solution and strong incorporation of the active sites in the organosilica framework suppressed leaching of the active phase.

In order to check the reusability and robustness of the PMO-Py-IL nanocatalyst, some studies were performed to find the lifetime and recovery factors of the nanocatalyst in the Biginelli reaction of three-component ethyl acetoacetate, benzaldehyde, and urea under optimized conditions. After ten consecutive cycles, illustrated in Scheme 1, it was found that reusable PMO-Py-IL nanocatalyst can be fully recyclable and showed outstanding structural stability maintaining the catalytic activity to around 90% of its initial activity under studied conditions. The SEM image presented in Figure 2 confirmed that the uniform cylindrical/spheroidal shape structure of porous pyridinium trifluoroacetate organosilica (PMO-Py-IL) after ten runs was similar to reported pristine PMO-Py-IL materials. Moreover, XRD analyses of PMO-Py-IL nanocatalyst before and after recycling were shown in Figure 3. The patterns are identical, and no obvious change was observed, which could be further evidence of the strong stability of the PMO-Py-IL nanocatalyst.



Figure 2. SEM image of the fresh PMO-Py (left) and recycled PMO-Py-IL after ten runs (right).



Figure 3. XRD patterns corresponding to the fresh PMO-Py-IL (**left**) and recycled PMO-Py-IL after ten runs (**right**).

We further compared the catalytic performance of PMO-Py-IL nanocatalyst with reported catalysts for the synthesis of DHPMs. As can be seen in Table 3, our recoverable catalytic system possesses good activity, as compared to those of previously reported heterogeneous catalytic systems; the results obtained using the method described herein provides a more environmentally benign and economically attractive system.

Entry	Catalyst	T (°C)	Time	Conversion (%)	Ref.
1	PMO-Py-IL (0.002 g)	50	15 min	98	This work
2	Cu@SBA-15 (0.01 g)	100	5 min	94	[50]
3	TSA/bent (0.09 g)	80	5 h	86	[61]
4	TSILS (ionic liquids)	90	10 min	94	[62]
5	PTA@MIL-101 (0.6 mol%)	100	60 min	90	[63]
6	PMo ₇ W ₅ /kaolin (20%)	100	8 min	95	[64]
7	β-Cyclodexterin (0.5 mol%)	100	180 min	85	[65]
8	NH ₄ H ₂ PO ₄ /MCM-41 (0.04 g)	100	6 h	72	[66]
9	40% w/w WSi/A-15 (0.05 g)	92	4.5	88	[67]
10	Nano-y-Al ₂ O ₃ /BF ₃ /Fe ₃ O ₄ (0.008 g)	80	30 min	95	[68]

Table 3. Comparison of catalytic activities in the Biginelli condensation reaction of benzaldehyde, ethyl acetoacetate, and urea using heterogeneous catalysts under solvent-free conditions.

3. Experimental Section

3.1. General Remarks

All solvents and chemicals were used as received without further purification. The melting points were measured with an Electrothermal model 9100 apparatus. FTIR spectra were obtained using a Shimadzu 4300 spectrophotometer. The ¹H NMR and ¹³C NMR spectra were recorded in DMSO-d₆ on Bruker DRX-300 Avance spectrometers. Proton chemical shifts (δ) were reported in ppm and were referenced to the NMR solvent (a septet centered at 39.52 ppm in ¹³CNMR related to DMSO-d₆). The scanning electron microscope (SEM) images were produced utilizing a Jeol JSM 6490 LA field emission device with an acceleration voltage of 15 kV.

3.2. Synthesis of PMO Materials Bearing Protic Pyridinium Ionic Liquid (PMO-Py-IL)

PMO-Py-IL was synthesized following our previously reported work [60].

3.3. General Procedure for the Preparation of 3,4-dihydropyrimidin-2(1H)-Ones Using PMO-Py-IL Nanocatalyst

In a typical experiment, a mixture of aldehyde (10 mmol), 1,3-dicarbonyl compound (10 mmol), urea (12 mmol), and PMO-Py-IL nanocatalyst (10 mg) were heated at 50 °C for 15 min under stirring and solvent-free conditions. Upon reaction completion, and monitored by thin-layer chromatography (TLC), the resulting mixture was cooled to room temperature and then hot ethanol (50 °C) was added to the mixture, and the heterogeneous PMO-Py-IL nanocatalyst was separated by filtration. In order to study the reusability of the PMO-Py-IL nanocatalyst, after the first reaction run, the PMO-Py-IL nanocatalyst was separated from the reaction mixture by simple filtration. Then, the heterogeneous PMO-Py-IL nanocatalyst was washed with water and ethanol, dried in vacuum, and reused for the subsequent run. The final products were recrystallized from ethanol. All products were analyzed by ¹H NMR, ¹³C NMR, FTIR, and melting points. The melting points of the product were matched well with literature reported data for the corresponding compounds. The spectral data of some products (4a-r) are presented below:

5-(*Ethoxycarbonyl*)-6-*methyl*-4-*phenyl*-3,4-*dihydropyrimidin*-2(1*H*)-*one* (4a): White crystal; Mp 201–203 °C; FT-IR (KBr, cm⁻¹) ν max 3244, 3115, 2977, 1724, 1647, 1464, 1290, 1220, 1090, 781, 698. ¹H NMR (DMSO-*d*₆) δ: 1.2 (3H, t, J = 7.2 Hz, OCH₂CH₃), 2.24 (3H, s, CH₃), 3.967 (2H, q, J = 7.2 Hz, OCH₂CH₃), 5.136 (d,1H, J = 3 Hz, -CH), 7.314 (m, 5H, Ar-H), 7.68 (1H, s, NH), 9.136 (1H, s, NH).¹³C NMR (DMSO-*d*₆) δ: 14.5, 18.3, 54.4, 59.7, 99.7, 118.5, 126.7, 127.7, 128.9, 144.3, 149.2, 152.6, 165.8.

5-(*Ethoxycarbonyl*)-6-*methyl*-4-(4-*nitrophenyl*)-3,4-*dihydropyrimidin*-2(1*H*)-*one* (4b): Colorless solid; Mp 210–212 °C; FT-IR (KBr, cm⁻¹) ν max: 3235, 3118, 2976, 1727, 1648, 1610, 1462, 1391, 1214, 1091, 783, 697. ¹H NMR (DMSO-*d*₆) δ: 2.06 (3H, t, J = 7.2 Hz, OCH₂CH₃), 2.18 (3H, s, CH₃), 2.41 (2H, q, J = 7.2 Hz, OCH₂CH₃), 5.23 (d,1H, J = 3.3 Hz, -CH), 7.49 (2H, d, J = 8.4 Hz, Ar-H), 7.94 (1H, s, NH), 8.08 (2H, d, J = 8.4 Hz, Ar-H), 9.29 (1H, s, NH). ¹³C NMR (DMSO-*d*₆) δ: 19.6, 31.1, 53.6, 109.9, 124.3, 128.1, 147.1, 149.6, 152.1, 152.5, 194.46.

5-(*Ethoxycarbonyl*)-4-(4-*Chlorophenyl*)-6-*methyl*-3,4-*dihydropyrimidin*-2(1*H*)-*one* (4c): Yellow powder; Mp 213–215 °C; FT-IR (KBr, cm⁻¹) ν max: 3242, 3116, 2979, 1723, 1647, 1489,

1291, 1220, 1088, 781, 492. ¹H NMR (DMSO- d_6) δ :1.08 (3H, t, J = 7.0 Hz, OCH₂CH₃), 2.46 (3H, s, CH₃), 3.96 (2H, q, J = 7.0 Hz, OCH₂CH₃), 5.12 (1H, d, J = 2.7 Hz, -CH), 7.12–7.39 (4H, m, Ar-H), 7.72 (1H, s, NH), 9.19 (1H, s, NH). ¹³C NMR (DMSO- d_6) δ : 14.5, 18.3, 53.9, 59.7, 99.3, 128.7, 128.9, 132.3, 144.3, 149.2, 152.4, 165.7.

5-(*Ethoxycarbonyl*)-6-*methyl*-4-(2-*Chlorophenyl*)-3,4-*dihydropyrimidin*-2(1*H*)-*one* (4e): Pale yellow powder; Mp 214–215 °C; FT-IR (KBr, cm⁻¹) ν max: 3342, 3241, 2986, 1667, 1460, 1233, 1091,757. ¹H NMR (DMSO- d_6) δ:1.03 (3H, t, J = 7.0 Hz, OCH₂CH₃), 2.31 (3H, s, CH₃), 3.91 (2H, q, J = 7.0 Hz, OCH₂CH₃), 5.60 (1H, s, -CH), 7.25–7.28 (1H, m, Ar-H), 7.28–7.30 (2H, m, Ar-H), 7.39–7.70 (1H, m, Ar-H), 7.71 (1H, s, NH), 9.28 (1H, s, NH).

5-(*Ethoxycarbonyl*)-4-(4-*methoxyphenyl*)-6-*methyl*-3,4-*dihydropyrimidin*-2(1*H*)-*one* (4f): Pale yellow powder; Mp 201–203 °C; FT-IR (KBr, cm⁻¹) ν max: 3322, 3126, 2937, 1720, 1670, 1434, 1276, 1215, 1075, 801, 503. ¹H NMR (DMSO-*d*₆) δ: 1.07 (3H, t, J = 7.1 Hz, OCH₂CH₃), 2.20 (3H, s, CH₃), 3.72 (3H, s, OCH₃), 3.95 (2H, q, J = 7.1 Hz, OCH₂CH₃), 5.23 (s, 1H, CH), 7.10 (2H, d, J = 8.1 Hz, Ar-H), 7.36 (2H, d, J = 8.1 Hz, Ar-H), 7.88 (1H, s, NH), 9.07 (1H, s, NH). ¹³C NMR (DMSO-*d*₆) δ: 14.1, 18.0, 54.2, 60.4, 99.7, 121.8, 126.4, 130.3, 143.4, 146.0, 155.7, 166.3.

5-Acetyl-6-methyl-4-phenyl-3,4-dihydropyrimidin-2(1H)-one (4m): White powder; Mp 221–223 °C; FT-IR (KBr, cm⁻¹) ν max: 3332, 3223, 1697, 1667, 1414, 1340, 1239, 1094, 698. ¹H NMR (DMSO- d_6) δ: 2.062 (3H, s, CH₃), 3.322 (3H, s, OCH₃), 5.242 (1H, s, -CH), 7.12–7.34 (m, 5H, Ar-H), 7.771 (1H, s, NH), 9.127 (1H, s, NH). ¹³CNMR (DMSO- d_6) δ: 19.412, 30.801, 30.837, 54.312, 110.096, 126.919, 127.842, 129.011, 144.732, 152.749, 194.774.

5-Methoxycarbonyl-6-methyl-4-(4-Nitrophenyl)-3,4-dihydropyrimidin-2(1H)one (4h): White powder; Mp 233–235 °C; FT-IR (KBr, cm⁻¹) ν max: 3368, 3235, 3109, 2946, 1689, 1617, 1348, 1228, 1095, 855, 700. ¹H NMR (DMSO-*d*₆) δ : 2.31 (3H, s, CH₃), 3.55 (3H, s, OCH₃), 5.26 (1H, s, CH), 7.46 (2H, d, J = 8.6 Hz, Ar-H), 7.89(1H, s, NH), 8.19 (2H, d, J = 8.6 Hz, Ar-H), 9.36 (1H, s, NH).

5-Methoxycarbonyl-6-methyl-4-(4-Chlorophenyl)-3,4-dihydropyrimidin-2(1H)-one (4i): Yellow powder; Mp 154–156 °C; FT-IR (KBr, cm⁻¹) ν max: 3324, 3219, 3105, 1698, 1675, 1491, 1420, 1342, 1295, 1239, 1093, 938, 700. ¹H NMR (DMSO- d_6) δ: 2.13 (3H, s, CH₃), 3.66 (3H, s, OCH₃), 5.24 (1H, s, CH), 7.03 (2H, d, J = 7.9 Hz, Ar-H), 7.35 (2H, d, J = 7.9 Hz, Ar-H), 7.88 (1H, s, NH), 9.23 (1H, s, NH). ¹³CNMR(DMSO- d_6) δ: 14.1, 17.8, 54.9, 100.6, 122.5, 126.5, 130.3, 142.9, 146.0, 155.5, 166.7.

5-Methoxycarbonyl-6-methyl-4-(2-Chlorophenyl)-3,4-dihydropyrimidin-2(1H)one (4k): Pale yellow powder; Mp 265–268 °C; FT-IR (KBr, cm⁻¹) ν max: 3441, 3351, 3250, 1690, 1660, 1458, 1086, 960, 800, 462. ¹H NMR (DMSO- d_6) δ: 2.32 (3H, s, CH₃), 3.51 (3H, s, OCH₃), 5.57 (1H, d, J = 3.4 Hz, CH), 7.30–7.44 (4H, m, Ar-H), 7.53 (1H, s, NH), 9.32 (1H, s, NH).

5-Acetyl-6-methyl-4-phenyl-3,4-dihydropyrimidin-2(1H)-one (4m): White powder; Mp 231–233 °C; FT-IR (KBr, cm⁻¹) ν max: 3268, 1702, 1675, 1599, 1493, 1236, 1106, 767, 704, 571. ¹H NMR (DMSO- d_6) δ: 2.09 (3H, s, CH₃), 2.24 (3H, s, CH₃), 5.22 (1H, d, J = 3.5 Hz, 1H), 7.17 (3H, d, J = 6.5 Hz, Ar-H), 7.22–7.34 (2H, m, Ar-H), 7.81 (1H, s, NH), 9.16 (1H, s, NH).¹³CNMR(DMSO- d_6) δ: 18.4, 30.2, 39.6, 54.0, 109.6, 126.5, 127.4, 128.6, 144.265, 148.1, 152.2, 194.3.

5-Acetyl-6-methyl-4-(4-Nitrophenyl)-3,4-dihydropyrimidin-2(1H)-one (4n): White powder; Mp 229–230 °C; FT-IR (KBr, cm⁻¹) ν max: 3342, 3252, 3143, 1709, 1674, 1608, 1515, 1446, 1384, 1239, 1279, 1237, 1187, 1102, 862, 763, 698. ¹H NMR (DMSO- d_6) δ: 2.10 (3H, s, CH₃), 2.25 (3H, s, CH₃), 5.24 (1H, d, J = 3.4 Hz, 1H), 7.24 (2H, d, J = 8.4 Hz, Ar-H), 7.40 (2H, d, J = 8.4 Hz, Ar-H), 7.84 (1H, s, NH), 9.21 (1H, s, NH).¹³CNMR(DMSO- d_6) δ: 18.9, 30.5, 53.17, 109.6, 128.4, 128.6, 131.9, 143.3, 148.5, 152.1, 193.9.

5-Acetyl-6-methyl-4-(4-Chlorophenyl)-3,4-dihydropyrimidin-2(1H)-one (4o): Yellow powder; Mp 204–206 °C; FT-IR (KBr, cm $^{-1}$) ν max: 3288, 3121, 2915, 1699, 1618, 1424, 1322, 1262, 1236, 1091, 837, 789, 581. 1 H NMR (DMSO-d₆) δ: 2.13 (s, 3H), 2.29 (s, 3H), 5.257 (d, J = 3.2 Hz, 1H), 7.26 (d, J = 8.4 Hz, 2H), 7.41 (d, J = 8.4 Hz, 2H), 7.88 (s, 1H), 9.25 (s, 1H).

5-Acetyl-6-methyl-4-(2-*Hydroxyphenyl*)-*3,4-dihydropyrimidin-2*(1*H*)-*one* (4p): Pale yellow powder; Mp 204–208 °C; FT-IR (KBr, cm⁻¹) v max: 3240, 3096, 2982, 1682, 1603, 1584, 1503, 1173, 1113, 925, 867, 762.

5-*Acetyl*-6-*methyl*-4-(4-*methoxyphenyl*)-3,4-*dihydropyrimidin*-2(1H)-one (4r): Yellow powder; Mp 172–174 °C. ¹HNMR (DMSO-d₆) δ: 2.073 (s, 3H), 2.275 (s, 3H), 3.72 (s, 3H), 5.19 (d, J = 3.2 Hz, 1H), 6.87 (d, J = 8.4 Hz, 2H), 7.16 (d, J = 8.4 Hz, 2H), 7.71 (s 1H), 9.13 (s, 1H).

4. Conclusions

In summary, one-pot Biginelli condensation reaction for a series of aryl aldehydes, β -dicarbonyls and urea using protic pyridinium functionalized hybrid mesoporous materials (PMO-Py-IL) as catalyst in high yield and under solvent-free conditions was described. Moreover, the catalyst showed superior stability and could be easily separated and reused at least for ten Biginelli reaction cycles. The uniform cylindrical/spheroidal structure of porous PMO-Py-IL nanomaterial was confirmed by the SEM image of the PMO-Py-IL nanomaterial after ten reaction runs. The ultimate goal of present work was the development of a cost-effective, green, sustainable, reusable, and simple and mild process for synthesis of 3,4-dihydro-2(*H*)-pyrimidinones (DHPMs).

Author Contributions: F.R. and R.L. conceived the study, contributed with characterization and writing of the manuscript; F.R. performed the experiments; M.S. and C.L. contributed with the useful advice and editing the manuscript. All authors have read and agreed to the published version of the manuscript.

Funding: This research received no external funding.

Data Availability Statement: Data is contained within the article.

Acknowledgments: F.R. is grateful to Payame Noor University for partial support of this work.

Conflicts of Interest: The authors declare no conflict of interest.

References

- Busse, W.-D.; Garthoff, B.; Seuter, F. Dihydropyridines Progress in Pharmacology and Therapy; Springer: Berlin/Heidelberg, Germany, 1993.
- Lagoja, I.M. Pyrimidine as constituent of natural biologically active compounds. *Chem. Biodivers.* 2005, 2, 1–50. [CrossRef] [PubMed]
- 3. Kimura, H.; Katoh, T.; Kajimoto, T.; Node, M.; Hisaki, M.; Sugimoto, Y.; Majima, T.; Uehara, Y.; Yamori, T. Modification of pyrimidine derivatives from antiviral agents to antitumor agents. *Anticancer Res.* **2006**, *26*, 91–97. [PubMed]
- Santana, M.L.H.; Masson, F.T.; Simeoni, L.A.; Homem-de-Mello, M. Biological activity of dihydropyrimidinone (DHPM) derivatives: A systematic review. *Eur. J. Med. Chem.* 2018, 143, 1779–1789.
- Fargualy, A.M.; Habib, N.S.; Ismail, K.A.; Hassan, A.M.M.; Sarg, M.T.M. Synthesis, biological evaluation and molecular docking studies of some pyrimidine derivatives. *Eur. J. Med. Chem.* 2013, *66*, 276–295. [CrossRef]
- 6. Amir, M.; Javed, S.A.; Kumar, H. Pyrimidine as antiinflammatory agent: A Review. Indian J. Pharm. Sci. 2007, 69, 337. [CrossRef]
- Mayer, T.U.; Kapoor, T.M.; Haggarty, S.J.; King, R.W.; Schreiber, S.L.; Mitchison, T.J. Small molecule inhibitor of mitotic spindle bipolarity identified in a phenotype-based screen. *Science* 1999, 286, 971–974. [CrossRef]
- 8. Nagarajaiah, H.; Khazi, I.M.; Begum, N.S. Synthesis, characterization and biological evaluation of thiazolopyrimidine derivatives. *J. Chem. Sci.* **2012**, *124*, 847–855. [CrossRef]
- Rovnyak, G.C.; Kimball, S.D.; Beyer, B.; Cucinotta, G.; DiMarco, J.D.; Gougoutas, J.; Hedberg, A.; Malley, M.; McCarthy, J.P. Calcium entry blockers and activators: Conformational and structural determinants of dihydropyrimidine calcium channel modulators. *J. Med. Chem.* 1995, 38, 119–129. [CrossRef]
- 10. Kappe, C.O. Biologically active dihydropyrimidones of the Biginelli-type—a literature survey. *Eur. J. Med. Chem.* **2000**, *35*, 1043–1052. [CrossRef]
- 11. Chorlton, A.P. Pyrimidine and pyrimidine derivatives. In *Ullmann, F. Ullmann's Encyclopedia of Industrial Chemistry*, 1st ed.; Wiley-VCH: Weinheim, Germany, 1999.
- 12. Biginelli, P. Ueber aldehyduramide des acetessigäthers. Ber. Dtsch. Chem. Ges. 1891, 24, 1317–1319. [CrossRef]
- 13. Biginelli, P. Synthesis of 3,4-Dihydropyrimidin-2(1*H*)-Ones. *Gazz. Chim. Ital.* **1893**, 23, 360–416.
- Kampe, O.C. The Biginelli Reaction. In *Multicomponent Reactions*; Zhu, J., Bienaymé, H., Eds.; Wiley-VCH: Weinheim, Germany, 2005.
- 15. Kappe, C.O.; Stadler, A. The Biginelli Dihydropyrimidine Synthesis. Org. React. 2004, 63, 1–116.
- 16. Jin, T.; Zhang, S.; Li, T. p-Toluenesulfonic acid-catalyzed efficient synthesis of dihydropyrimidines: Improved high yielding protocol for the biginelli reaction. *Synth. Commun.* **2002**, *32*, 1847–1851. [CrossRef]
- 17. Gangu, K.K.; Maddila, S.; Mukkamala, S.B.; Jonnalagadda, S.B. Catalytic activity of supra molecular self-assembled Nickel (II) coordination complex in synthesis of indeno-pyrimidine derivatives. *Polyhedron* **2019**, *158*, 464–470. [CrossRef]

- 18. Yu, Y.; Liu, D.; Liu, C.; Luo, G. One-pot synthesis of 3,4-dihydropyrimidin-2(1*H*)-ones using chloroacetic acid as catalyst. *Bioorganic. Med. Chem. Lett.* 2007, 17, 3508–3510. [CrossRef]
- Nagawade, R.R.; Kotharkar, S.A.; Shinde, D.B. Titanium (IV) chloride catalyzed one-pot synthesis of 3,4-dihydropyrimidin-2(1H)ones and thiones. *Mendeleev Commun.* 2005, 15, 150–151. [CrossRef]
- De, S.K.; Gibbs, R.A. Ruthenium (III) chloride-catalyzed one-pot synthesis of 3,4-dihydropyrimidin-2-(1*H*)-ones under solvent-free conditions. *Synthesis* 2005, 2005, 1748–1750. [CrossRef]
- De, S.K.; Gibbs, R.A. Scandium (III) Triflate as an Efficient and Reusable Catalyst for Synthesis of 3,4-Dihydropyrimidin-2(1*H*)-ones. Synth. Commun. 2005, 35, 2645–2651. [CrossRef]
- Pasha, A.; Puttaramegowda, J.V. Co(OAc)₂-catalyzed tandem reaction: Synthesis of 3,4-dihydropyrimidin-2(1H)-ones/thiones from β-keto ester. *Heterocycl. Commun.* 2006, 12, 61–66.
- 23. Reddy, B.M.; Sreekanth, P.M.; Lakshmanan, P. Sulfated zirconia as an efficient catalyst for organic synthesis and transformation reactions. *J. Mol. Catal. A Chem.* **2005**, 237, 93–100. [CrossRef]
- Mirza-Aghayan, M.; Bolourtchian, M.; Hosseini, M. Microwave-assisted efficient synthesis of dihydropyrimidines in solvent-free condition. *Synth. Commun.* 2004, *34*, 3335–3341. [CrossRef]
- Salehi, H.; Guo, Q.-X. A facile and efficient one-pot synthesis of dihydropyrimidinones catalyzed by magnesium bromide under solvent-free conditions. *Synth. Commun.* 2004, 34, 171–179. [CrossRef]
- 26. Yadav, J.S.; Reddy, B.V.S.; Srinivas, R.; Venugopal, C.; Ramalingam, T. LiClO₄-catalyzed one-pot synthesis of dihydropyrimidinones: An improved protocol for Biginelli reaction. *Synthesis* **2001**, 2001, 1341–1345. [CrossRef]
- 27. Ma, Y.; Qian, C.; Wang, L.; Yang, M. Lanthanide triflate catalyzed Biginelli reaction. One-pot synthesis of dihydropyrimidinones under solvent-free conditions. *J. Org. Chem.* **2000**, *65*, 3864–3868. [CrossRef]
- Ranu, B.C.; Hajra, A.; Jana, U. Indium (III) chloride-catalyzed one-pot synthesis of dihydropyrimidinones by a three-component coupling of 1,3-dicarbonyl compounds, aldehydes, and urea: An improved procedure for the Biginelli reaction. *J. Org. Chem.* 2000, 65, 6270–6272. [CrossRef]
- 29. Gohain, M.; Prajapati, D.; Sandhu, J.S. A novel Cu-catalysed three-component one-pot synthesis of dihydropyrimidin-2(1*H*)-ones using microwaves under solvent-free conditions. *Synlett* **2004**, 2004, 235–238.
- Russowsky, D.; Lopes, F.A.; da Silva, V.S.S.; Canto, K.F.S.; D'Oca, M.G.M.; Godoi, M.N. Multicomponent Biginelli's synthesis of 3, 4-dihydropyrimidin-2(1H)-ones promoted by SnCl₂. 2H₂O. J. Braz. Chem. Soc. 2004, 15, 165–169. [CrossRef]
- Hu, E.H.; Sidler, D.R.; Dolling, U.-H. Unprecedented catalytic three component one-pot condensation reaction: An efficient synthesis of 5-alkoxycarbonyl-4-aryl-3,4-dihydropyrimidin-2(1H)-ones. J. Org. Chem. 1998, 63, 3454–3457. [CrossRef]
- 32. Rodriguez-Domínguez, J.C.; Bernardi, D.; Kirsch, G. ZrCl₄ or ZrOCl₂ under neat conditions: Optimized green alternatives for the Biginelli reaction. *Tetrahedron Lett.* **2007**, *48*, 5777–5780. [CrossRef]
- Pasha, M.A.; Swamy, N.R.; Jayashankara, V.P. One pot synthesis of 3,4-dihydropyrimidin-2(1*H*)-ones-thiones catalysed by zinc chloride: An improved procedure for the Biginelli reaction using microwaves under solvent free condition. *Indian. J. Chem.* 2005, 44B, 823–826.
- 34. Bose, D.S.; Kumar, R.K.; Fatima, L. A remarkable rate acceleration of the one-pot three-component cyclocondensation reaction at room temperature: An expedient synthesis of mitotic kinesin Eg5 inhibitor monastrol. *Synlett* **2004**, 2004, 279–282. [CrossRef]
- Narsaiah, A.V.; Basak, A.K.; Nagaiah, K. Cadmium chloride: An efficient catalyst for one-pot synthesis of 3,4-dihydropyrimidin-2(1H)-ones. Synthesis 2004, 2004, 1253–1256. [CrossRef]
- Jin, T.-S.; Wang, H.-X.; Xing, C.-Y.; Li, X.-L.; Li, T.-S. An efficient one-pot synthesis of 3,4-dihydropyrimidin-2-ones catalyzed by methanesulfonic acid. *Synth. Commun.* 2004, 34, 3009–3016. [CrossRef]
- Wang, Z.-T.; Xu, L.-W.; Xia, C.-G.; Wang, H.-Q. Novel Biginelli-like three-component cyclocondensation reaction: Efficient synthesis of 5-unsubstituted 3, 4-dihydropyrimidin-2(1*H*)-ones. *Tetrahedron Lett.* 2004, 45, 7951–7953. [CrossRef]
- Han, X.; Xu, F.; Luo, Y.; Shen, Q. An Efficient One-Pot Synthesis of Dihydropyrimidinones by a Samarium Diiodide Catalyzed Biginelli Reaction Under Solvent-Free Conditions. *Eur. J. Org. Chem.* 2005, 2005, 1500–1503. [CrossRef]
- Kolosov, M.A.; Orlov, V.D.; Beloborodov, D.A.; Dotsenko, V.V. A chemical placebo: NaCl as an effective, cheapest, non-acidic and greener catalyst for Biginelli-type 3, 4-dihydropyrimidin-2(1*H*)-ones (-thiones) synthesis. *Mol. Divers.* 2009, 13, 5–25. [CrossRef] [PubMed]
- Khakyzadeh, V.; Moosavi-Zare, A.R.; Sheikhaleslami, S.; Ehsani, A.; Sediqi, S.; Rezaei-Gohar, M.; Jalilian, Z. Boric acid in magnetized water: Clean and powerful media for synthesis of 3,4-dihydropyrimidin-2(1*H*)-ones. *RSC Adv.* 2021, 11, 22751–22755. [CrossRef]
- Dondoni, A.; Massi, A. Parallel synthesis of dihydropyrimidinones using Yb (III)-resin and polymer-supported scavengers under solvent-free conditions. A green chemistry approach to the Biginelli reaction. *Tetrahedron Lett.* 2001, 42, 7975–7978. [CrossRef]
- 42. Ahn, B.J.; Gang, M.S.; Chae, K.; Oh, Y.; Shin, J.; Chang, W. A microwave-assisted synthesis of 3,4-dihydro-pyrimidin-2-(1*H*)-ones catalyzed by FeCl₃-supported Nanopore Silica under solvent-free conditions. *J. Ind. Eng. Chem.* **2008**, *14*, 401–405. [CrossRef]
- 43. Zhang, X.; Li, Y.; Liu, C.; Wang, J. An efficient synthesis of 4-substituted pyrazolyl-3, 4-dihydropyrimidin-2(1*H*)-(thio) ones catalyzed by Mg (ClO₄)₂ under ultrasound irradiation. *J. Mol. Catal. A Chem.* **2006**, 253, 207–211. [CrossRef]
- 44. Foroughifar, N.; Mobinikhaledi, A.; Fathinejad Jirandehi, H. Synthesis of Some Biginelli Compounds in Solvent Medium Using a Photochemistry Method, Phosphorus. *Sulfur Silicon Relat. Elem.* **2003**, *178*, 495–500. [CrossRef]

- Zheng, R.; Wang, X.; Xu, H.; Du, J. Brønsted Acidic Ionic Liquid: An Efficient and Reusable Catalyst for the Synthesis of 3,4-Dihydropyrimidin-2(1*H*)-ones. *Synth. Commun.* 2006, 36, 1503–1513. [CrossRef]
- 46. Khodamorady, M.; Sohrabnezhad, S.; Bahrami, K. Efficient one-pot synthetic methods for the preparation of 3,4-dihydropyrimidinones and 1,4-dihydropyridine derivatives using BNPs@ SiO₂(CH₂)₃NHSO₃H as a ligand and metal free acidic heterogeneous nano-catalyst. *Polyhedron* 2020, 178, 114340. [CrossRef]
- Patil, R.V.; Chavan, J.U.; Dalal, D.S.; Shinde, V.S.; Beldar, A.G. Biginelli reaction: Polymer supported catalytic approaches. ACS Comb. Sci. 2019, 21, 105–148. [CrossRef]
- 48. Shi, X.-L.; Xing, X.; Lin, H.; Zhang, W. Synthesis of Polyacrylonitrile Fiber-Supported Poly (ammonium methanesulfonate) s as Active and Recyclable Heterogeneous Brønsted Acid Catalysts. *Adv. Synth. Catal.* **2014**, *356*, 2349–2354. [CrossRef]
- Wang, J.-H.; Tang, G.-M.; Yan, S.-C.; Wang, Y.-T.; Zhan, S.-J.; Zhang, E.; Sun, Y.; Jiang, Y.; Cui, Y.-Z. Cobalt-based metal coordination polymers with 4, 4'-bipyridinyl groups: Highly efficient catalysis for one-pot synthesis of 3,4-dihydropyrimidin-2(1H)-ones under solvent-free conditions. *Appl. Organomet. Chem.* 2016, *30*, 1009–1021. [CrossRef]
- Diarjani, E.S.; Rajabi, F.; Yahyazadeh, A.; Puente-Santiago, A.R.; Luque, R. Copper tridentate Schiff base complex supported on SBA-15 as efficient nanocatalyst for three-component reactions under solvent less conditions. *Materials* 2018, 11, 2458. [CrossRef]
- Xie, O.-B.; Wang, N.; Wu, W.-X.; Le, Z.-G.; Yu, X.-Q. Trypsin-catalyzed tandem reaction: One-pot synthesis of 3,4dihydropyrimidin-2(1*H*)-ones by in situ formed acetaldehyde. *J. Biotechnol.* 2014, 170, 1–5. [CrossRef]
- 52. Van der Voort, P.; Esquivel, D.; De Canck, E.; Goethals, F.; Van Driessche, I.; Romero-Salguero, F.J. Periodic mesoporous organosilicas: From simple to complex bridges; a comprehensive overview of functions, morphologies and applications. *Chem. Soc. Rev.* **2013**, *42*, 3913–3955. [CrossRef]
- 53. Hoffmann, F.; Cornelius, M.; Morell, J.; Fröba, M. Silica-based mesoporous organic–inorganic hybrid materials. *Angew. Chem. Int. Ed.* **2006**, *45*, 3216–3251. [CrossRef] [PubMed]
- Asefa, T.; MacLachlan, M.J.; Coombs, N.; Ozin, G.A. Periodic mesoporous organosilicas with organic groups inside the channel walls. *Nature* 1999, 402, 867–871. [CrossRef]
- Melde, B.J.; Holland, B.T.; Blanford, C.F.; Stein, A.A. Mesoporous sieves with unified hybrid inorganic/organic frameworks. *Chem. Mater.* 1999, 11, 3302–3308. [CrossRef]
- 56. Inagaki, S.; Guan, S.; Fukushima, Y.; Ohsuna, T.; Terasaki, O. Novel mesoporous materials with a uniform distribution of organic groups and inorganic oxide in their frameworks. *J. Am. Chem. Soc.* **1999**, *121*, 9611–9614. [CrossRef]
- Waki, M.; Inagaki, S. Periodic mesoporous organosilicas possessing molecularly mixed pyridine and benzene moieties in the frameworks. *Microporous Mesoporous Mater.* 2019, 284, 10–15. [CrossRef]
- 58. Rajabi, F.; Pinilla-de Dios, M.; Abdollahi, M.; Luque, R. Aqueous synthesis of 1,8-dioxo-octahydroxanthenes using supported cobalt nanoparticles as a highly efficient and recyclable nanocatalyst. *Catal. Commun.* **2019**, *120*, 95–100. [CrossRef]
- 59. Rajabi, F.; Ebrahimi, A.Z.; Rabiee, A.; Pineda, A.; Luque, R. Synthesis and characterization of novel pyridine periodic mesoporous organosilicas and its catalytic activity in the Knoevenagel condensation reaction. *Materials* **2020**, *13*, 1097. [CrossRef]
- 60. Rajabi, F.; Luque, R. Highly ordered mesoporous functionalized pyridinium protic ionic liquids framework as efficient system in esterification reactions for biofuels production. *Mol. Catal.* **2020**, *498*, 111238. [CrossRef]
- 61. Chopda, L.V.; Dave, P.N. 12-Tungstosilicic Acid H₄[W₁₂SiO₄₀] Over Natural Bentonite as a Heterogeneous Catalyst for the Synthesis of 3,4-dihydropyrimidin-2(1*H*)-Ones. *ChemistrySelect* **2020**, *5*, 2395–2400. [CrossRef]
- Dong, F.; Jun, L.; Xinli, Z.; Zhiwen, Y.; Zuliang, L. One-pot green procedure for Biginelli reaction catalyzed by novel task-specific room temperature ionic liquids. J. Mol. Catal. A Chem. 2007, 274, 208–211. [CrossRef]
- 63. Saikia, M.; Bhuyan, D.; Saikia, L. Keggin type phosphotungstic acid encapsulated chromium (III) terephthalate metal organic framework as active catalyst for Biginelli condensation. *Appl. Catal. Gen.* **2015**, *505*, 501–506. [CrossRef]
- Aher, D.S.; Khillare, K.R.; Chavan, L.D.; Shankarwa, S.G. Tungsten-substituted molybdophosphoric acid impregnated with kaolin: Effective catalysts for the synthesis of 3,4-dihydropyrimidin-2(1*H*)-ones via biginelli reaction. *RSC Adv.* 2021, 11, 2783–2792. [CrossRef]
- Liberto, N.A.; Silva, S.D.P.; Fatima, A.D.; Fernandes, S.A. β-Cyclodextrin-assisted synthesis of Biginelli adducts under solvent-free conditions. *Tetrahedron* 2013, 69, 8245–8249. [CrossRef]
- Tayebee, R.; Ghadamgahi, M. Solvent free one-pot multi-component synthesis of 3,4-dihydropyrimidin-2(1*H*)-ones catalyzed by mesoporous NH₄H₂PO₄/MCM-41 as an environmentally friendly, cheap, and effective catalyst. *Arab. J. Chem.* 2017, 10, S757–S764. [CrossRef]
- 67. Bosica, G.; Cachia, F.; De Nittis, R.; Mariotti, N. Efficient One-Pot Synthesis of 3,4-Dihydropyrimidin-2(1*H*)-ones via a Three-Component Biginelli Reaction. *Molecules* **2021**, *26*, 3753. [CrossRef]
- Bamoniri, A.; Mirjalili, B.B.F.; Mahmoodi Fard Chegeni, M. Synthesis of 3,4-Dihydropyrimidinones using Nano γ-Al₂O₃/BF₃/Fe₃O₄ as an Efficient Magnetic Nanocatalyst under Solvent-free Conditions. J. Nanostruct. 2020, 10, 751–759.