

Supporting information of:

Engineering and Characterization of Antibacterial Coaxial Nanofibers

Membranes for Oil/Water Separation

Hamouda M. Mousa^{1, *}, Husain Alfadhel², Emad Abouel Nasr^{3,4}

¹Department of Mechanical Engineering, Faculty of Engineering, South Valley University, Qena 83523, Egypt.

²Department of Mechanical Engineering, University of Portsmouth, UK.

³Department of Industrial Engineering, College of Engineering, King Saud University, Riyadh 11421, Saudi Arabia.

⁴Department of Mechanical Engineering, Faculty of Engineering, Helwan University, Cairo 11732, Egypt.

* Author to whom correspondence should be addressed.

E-Mail: H. M. Mousa (hmousa@eng.svu.edu.eg)




Fig.S1 high resolution image of coaxial nanofiber membrane.




Fig.S2 EDS point analysis of the electrospun co-axial nanofibers membranes before and after surface treatment.

(M1)					(M2)					(M3)				
Element	Weight %	Atomic %	Net Int.	Error %	Element	Weight %	Atomic %	Net Int.	Net Int. Error	Element	Weight %	Atomic %	Net Int.	Net Int. Error
C K	71.66	78.83	282.63	7.86	C K	65.05	74.89	19.9	0.03	C K	68.64	78.45	49.6	0.02
O K	22.93	18.94	64.05	12.52	O K	25.48	22.03	6.7	0.05	O K	21.19	18.18	12.9	0.03
S K	5.41	2.23	148.31	3.03	S K	4.91	2.12	11.3	0.05	S K	5.68	2.43	32.2	0.03
					Zn K	4.56	0.96	1.5	0.18	Zn K	4.49	0.94	3.7	0.17

(M4)					(M5)					(M6)				
Element	Weight %	Atomic %	Net Int.	Error %	Element	Weight %	Atomic %	Net Int.	Net Int. Error	Element	Weight %	Atomic %	Net Int.	Net Int. Error
C K	28.74	38.52	117.07	10.1	C K	20.32	28.61	68.59	11.06	C K	64.7	72.7	583.45	7.43
O K	38.83	39.07	358.04	9.21	O K	40.65	42.97	419.91	8.52	O K	28.27	23.85	198.95	11
Na K	30.9	21.64	595.94	7.35	Na K	37.65	27.69	681.66	7.2	Na K	2.94	1.73	77.53	9.51
S K	1.53	0.77	56.33	9.13	S K	1.37	0.72	44.98	9.69	S K	4.09	1.72	248.88	2.77

Fig.S3 EDS point analysis of the electrospun co-axial nanofibers membranes before and after surface treatment in terms of weight and atomic percent.