

Supplementary

Natural Rigid and Hard Plastic Fabricated from Elastomeric Degradation of Natural Rubber Composite with Ultra-High Magnesium Carbonate Content

Abedeem Dasaesamoh, Kittikhun Khotmungkhun and Kittitat Subannajui *

Material Science and Engineering Program, School of Materials Science and Innovation,
Faculty of Science, Mahidol University, Bangkok 10400, Thailand;
kittikhun.kho@alumni.mahidol.ac.th (K.K.)

* Correspondence: kittitat.sub@mahidol.ac.th

Figure S1. a) Abrasion test of $\text{Al}_2\text{O}_3/\text{NR}$ composites b) Abrasion test of SiO_2/NR composites c) Hardness of $\text{Al}_2\text{O}_3/\text{NR}$ composites d) Hardness of SiO_2/NR composites




Table S1. The molecular weight of 0 Phr natural rubber measured by GPC-SEC

Molecular weight g/mol	Mp	Mn	Mw	Mz
0 Phr	17387	9043	15198	21690