polymers

MDPI

*Article*

# Functional Poly(Ionic Liquid)s: Catalytic Conversion of $CO_2$

**Maria Atlaskina [1], Kirill Smorodin [1], Sergey Kryuchkov [1], Artem Atlaskin [1,*], Alexander Sysoev [1], Olga Kazarina [2], Anton Petukhov [2], Andrey Vorotyntsev [2] and Ilya Vorotyntsev [1]**

[1] Laboratory of SMART Polymeric Materials and Technologies, Mendeleev University of Chemical Technology of Russia, 125047 Moscow, Russia; atlaskina.m.ev@muctr.ru (M.A.); smorodin.k.a@muctr.ru (K.S.); kriuchkov.s.s@muctr.ru (S.K.); sysoev.a.a@muctr.ru (A.S.); vorotyntsev.i.v@muctr.ru (I.V.)

[2] Chemical Engineering Laboratory, Lobachevsky State University of Nizhny Novgorod, 603022 Nizhny Novgorod, Russia; olga_kazarina@list.ru (O.K.); fox-off@mail.ru (A.P.); an.vorotyntsev@gmail.com (A.V.)

* Correspondence: atlaskin.a.a@muctr.ru or atlaskin@gmail.com

## Abstract

This study reports the synthesis and catalytic evaluation of a series of imidazolium-based polymeric ionic liquids (PILs) for the cycloaddition of $CO_2$ to epichlorohydrin (ECH). The synthesized catalysts include homopolymers, poly(3-hydroxyethyl-1-vinylimidazole chloride) (p[HVIm][Cl]) and poly(3-carboxymethyl-1-vinylimidazole chloride) (p[CMVIm][Cl]), and their block copolymers with polystyrene, synthesized for the first time, pS-b-p[HVIm][Cl] and pS-b-p[CMVIm][Cl]. Structural characterization by NMR, IR spectroscopy, and gel permeation chromatography confirmed the successful synthesis. The block copolymers exhibited a low polydispersity index (PDI 1.1–1.2), which is indicative of homogeneous chain lengths and the propensity to form ordered nanostructures, whereas the homopolymers showed higher PDI (2.4–2.9). Catalytic testing at 90 °C and 1 MPa $CO_2$ for 4 h revealed a clear activity trend: p[CMVIm][Cl] < p[HVIm][Cl] < pS-b-p[CMVIm][Cl] < pS-b-p[HVIm][Cl], with conversions exceeding 75% for all catalysts and a maximum of 82.69% for pS-b-p[HVIm][Cl]. These results demonstrate that the catalytic performance of PILs is governed by a synergistic interplay between the local chemical functionality of the ionic moiety and the overall polymer architecture. Based on these results, the synthesized polymeric ionic liquids, particularly pS-b-p[HVIm][Cl], demonstrate strong potential for creating multifunctional materials. Their ability to self-assemble into ordered nanostructures with distinct hydrophobic and hydrophilic domains provides a foundational architecture for combined gas separation and catalysis. The observed "micellar catalytic effect", which enhances local reagent concentration near active sites, could be leveraged in a membrane reactor to simultaneously capture and convert $CO_2$ directly within the membrane. This integrated "separation–reaction" approach represents a promising strategy for advancing circular carbon economy technologies.

**Keywords:** carbon dioxide; cyclic carbonates; cycloaddition; polymeric ionic liquids

Check for updates

Academic Editors: Deshetti Jampaiah and Paramita Koley

Received: 7 February 2026
Revised: 23 February 2026
Accepted: 24 February 2026
Published: 25 February 2026

**Copyright:** © 2026 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license.

## 1. Introduction

The escalating concentration of atmospheric carbon dioxide ($CO_2$) is the most pressing issue of our time, as it is the primary driver of climate change. Renewable energy sources, highly efficient thermal power plants converting coal into syngas, with residual heat used in the steam cycle, and biofuels are among the best examples of efficient energy systems with low greenhouse gas emissions [1]. However, developing $CO_2$ capture and

storage technologies that would immediately reduce $CO_2$ emissions remains a pressing challenge. Common $CO_2$ separation technologies include sorption, a membrane and combined methods. The chemical absorption method is based on the selective chemical reaction of $CO_2$ with a liquid absorbent, typically an aqueous solution of alkanolamines, to form chemical compounds [2–6]. In recent years, combined solutions of alkanolamines, including highly effective additives such as piperazine or ionic components, have been used as absorbents. The process involves absorption at 40–60 °C, followed by thermal regeneration of the absorbent (desorption) at 100–120 °C, which is accompanied by the release of $CO_2$. This technology is the most mature among existing technologies, achieving high capture rates (>90%) and selectivity even at low $CO_2$ partial pressures (12–15 vol%) typical of thermal power plant flue gases. However, this process is characterized by the corrosiveness of the regenerated solutions, thermal and oxidative degradation of amines, and the significant size of the equipment [7,8].

Adsorption methods rely on the physical sorption of $CO_2$ molecules on the surface of microporous solid materials (zeolites, activated carbons, and metal–organic frameworks) followed by desorption by reducing the overall pressure, increasing the temperature, or a combination of these factors [9]. The absence of liquid corrosive media and potentially lower specific energy consumption compared to absorption allow adsorption methods to be used for capturing $CO_2$ from streams with medium and high concentrations (steel mill process gases, converter gases, biogas) [10]. The key technological constraints are a decrease in adsorption effectiveness at low $CO_2$ concentration, a reduction in adsorption capacity in the presence of water vapor, which requires feed gas dehydration, and adsorbent mechanical degradation due to cyclic load, which results in selectivity loss.

The gas hydrate-based $CO_2$ capture method relies on the ability of gas molecules to integrate into clathrates formed by water molecules under specific thermobaric conditions (high pressure, low temperature) [11,12]. Then the resulting solid hydrates are separated and subjected to controlled destabilization, releasing $CO_2$. Promising applications for gas hydrate-based methods include long-term geological storage, particularly in offshore environments, and in methane substitution projects. Hydrate-based capture technologies remain an area of active laboratory research, with potential applications including $CO_2$ capture from associated gases on offshore platforms. Despite the potential of this technology, its technology readiness level is currently low—4. Furthermore, this process is characterized by slow hydrate formation kinetics and high operating pressures, which require the use of chemical promoters and high-power compression.

Membrane gas separation represents another effective and non-reactive approach for $CO_2$ removal from gas mixtures, operating on differences in the partial pressures of the mixture components [13–15]. Membrane processes represent an energy-efficient alternative technology, characterized by low energy consumption, a relatively small footprint, modular configuration, and reagent- and heat-free operation.

Furthermore, an excellent solution is to combine processes to overcome their individual limitations and minimize overall energy costs. Examples of such technologies include hybrid gas hydrate and membrane technologies, hybrid batch distillation/membrane processing, and membrane-assisted gas absorption [16–22].

Although most of these $CO_2$ capture methods are actively used in real chemical facilities, the current emphasis is shifting to the development of technologies for their subsequent conversion into valuable products. Converting carbon dioxide into feedstock for the production of fuels, polymers, or building materials closes the carbon cycle, transforming an environmental problem into an economic opportunity [23–26]. This allows not only to sequester carbon but to recycle it, which is consistent with the principles of the circular carbon economy and sustainable chemistry. The atom-economical cycloaddition of $CO_2$

to epoxides to form cyclic carbonates forms is a highly attractive and industrially relevant process [27,28]. These products find extensive applications as polar aprotic solvents, electrolytes in lithium-ion batteries, and precursors for polymeric materials [29–33].

This reaction typically requires an efficient catalyst to overcome the kinetic and thermodynamic stability of $CO_2$. As catalysts, zeolite imidazolate frameworks (ZIF), aluminum complexes, metal–organic frameworks (MOFs), and organocatalysts are used. However, many of these frameworks face fundamental limitations. The primary challenge for porous coordination polymers such as ZIFs and MOFs is their limited stability under extreme conditions. Many of these materials exhibit structural degradation in the presence of water vapor or at elevated temperatures, critically reducing their catalytic activity and lifetime. Many of traditional ZIFs do not have sufficient Lewis acid sites to activate the epoxide, resulting in low conversions, and often require high temperatures, high pressures, or co-catalysts to improve process efficiency [34–38]. The synthesis of these frameworks often involves expensive ligands and multistep processes, complicating their scale-up for industrial applications. Organocatalysts, such as tertiary amines like triethanolamine, typically exhibit high activity, but their homogeneous nature poses challenges in separation and recycling from the reaction mixture, increasing process costs and waste generation [39,40].

In this context, ionic liquids (ILs) represent an alternative class of catalytic media, whose properties can be tailored to overcome these drawbacks. A key advantage of ILs is their exceptional thermal and chemical stability, including resistance to hydrolysis and high temperatures, which enables long-term operation under harsh conditions [41–48]. A crucial property is their high ionic conductivity, making them ideal electrolytes and catalysts for the electrochemical reduction of $CO_2$, paving the way for the use of renewable energy for the synthesis of valuable products [49–51].

Polymeric ionic liquids, while retaining the key advantages of traditional ionic liquids, additionally address the problem of high viscosity by improving the mass transfer of reagents and can be used both as individual catalysts for $CO_2$ conversion reactions and as components of catalytic systems [52–58]. They can also be formed into rigid yet flexible membranes or porous structures, simplifying their integration into reactors and the regeneration process [59–61]. Moreover, the high density of Lewis acidic and basic sites that makes PILs excellent catalysts also makes them promising materials for gas separation membranes. This is particularly true for $CO_2$ capture, as these sites exhibit a strong affinity for molecules with a significant quadrupole moment. While the catalytic performance of PILs in cyclic carbonate synthesis and their gas transport properties have been investigated independently, these two research streams remain largely disconnected. The design of a single bifunctional PIL material capable of simultaneously facilitating $CO_2$ transport (separation function) and catalyzing its subsequent conversion (catalytic function) represents a groundbreaking integrative approach. This synergy could lead to the development of efficient catalytic membrane reactors, intensifying the process of $CO_2$ utilization.

Ionic liquids based on imidazole cations are highly effective catalysts for the conversion of $CO_2$, for example, into cyclic carbonates, due to the combination of high catalytic activity and low volatility. The key role is played by the cation, which, due to the acidic proton of the imidazole ring, carries out electrophilic activation of the substrate (epoxide), polarizing it and facilitating ring opening [62,63]. The catalytic properties can be significantly enhanced by introducing functional groups into the cation structure, such as OH or COOH, which act as internal co-catalysts, forming hydrogen bonds with the substrate and creating a bifunctional catalytic center [64,65]. The choice of anion is no less important: nucleophilic halide ions ($Cl^-$, $Br^-$, $I^-$), which are directly involved in the reaction mechanism by attacking the activated epoxide, are effective for catalysis [66]. Thus, the high activity of catalytic systems will be due to the synergistic action of the imidazolium cation (often

modified with functional groups) and the nucleophilic halide anion. Therefore, in this study, functionalized polymeric ionic liquids based on the N-vinylimidazolium cation with halide anions and various substituents were synthesized and characterized. Additionally, new copolymers based on these PILs and styrene were synthesized and characterized for the first time. Their ability to catalyze the conversion of $CO_2$ to cyclic carbonates using epichlorohydrin as a substrate was assessed.

## 2. Materials and Methods

### 2.1. Materials

Table 1 presents the chemicals used in this study. The pre-treatment procedure for removing the stabilizer from the styrene included washing it five times with a 20% NaOH solution. Azobisisobutyronitrile was recrystallized in ethanol. All other chemicals were used without extra purification.

**Table 1.** Materials.

| Name | CAS | Abbr. | Purity | Supplier |
|---|---|---|---|---|
| 1-Vinylimidazole | 1072-63-5 | VIm | 99% | Macklin Inc., China, Shanghai |
| Styrene | 100-42-5 | Sty | ≥99% | Rushim, Russia, Moscow |
| Azobisisobutyronitrile | 78-67-1 | AIBN | >98% | Clearsynth, India, Mumbai |
| 2-Chloroethan-1-ol | 107-07-3 | | 99% | Acros Organics, Belgium, Geel |
| Chloroacetic acid | 79-11-8 | MCA | ≥99% | Sigma-Aldrich, Germany, Schnelldorf |
| Dimethylformamide | 68-12-2 | DMF | 99% | LLC "Component-Reactive", Russia, Moscow |
| Acetonitrile | 75-05-8 | ACN | 99% | Chimmed, Russia, Moscow |
| Toluene | 108-88-3 | PhMe | 99% | |
| Hexane | 110-54-3 | - | 99% | LLC "Component-Reactive", Russia, Moscow |
| Epichlorohydrin | 106-89-8 | ECH | >99% | Chemical Line Co. Ltd., Russia, Saint Petersburg |
| Carbon dioxide | 124-38-9 | $CO_2$ | ≥99.99% | Monitoring LLC, Russia, Saint Petersburg |

### 2.2. Synthesis and Characterization

The chemical structures of the synthesized polymeric ionic liquids were analyzed by $^1$H nuclear magnetic resonance ($^1$H NMR) using an Ascend400 NMR spectrometer (Bruker, Switzerland, Zurich) with deuterated solvents including deuterium oxide, chloroform-d, and DMSO-d6.

IR spectra were recorded on a Bruker Equinox 55/s FTIR spectrometer (Ettlingen, Germany) in the range of 4000–550 $cm^{-1}$ to characterize the synthesized polymeric ionic liquids (reveal their structures and functional groups).

Gel permeation chromatography (GPC) measurements were performed on a Stayer setup with Phenogel columns (1–500) $\times 10^3$ using DMF as eluent at 60 °C and a flow rate of 1 mL/min. Polystyrene standards with M = (30, 70, 150, 300) $\times 10^3$ were used as a standard. Data processing was performed using the MultiChrom Version 1.5X software.

Analysis of the morphology of homo- and block copolymer samples was performed using a JSM-IT500 scanning electron microscope (SEM) from JEOL (Japan, Akishima, Tokyo).

#### 2.2.1. Synthesis of Imidazolium-Based PILs

Reaction of 1-vinylimidazole polymerization was carried out at 70 °C under $N_2$ atmosphere using toluene as the solvent and 2 mas. % AIBN as the initiator. After 12 h of stirring on a magnetic stirrer, the obtained light-yellow solid product was filtered and vacuum-dried for 12 h at 70 °C (the product was a white powder; the reaction yield was 71%). Then, 2-Chloroethan-1-ol or chloroacetic acid was dissolved with p[VIm] in acetonitrile (2:1 mol) for obtaining Poly (3-hydroxyethyl-1-vinylimidazole chloride) (p[HVIm][Cl]) or Poly(3-carboxymethyl-1-vinylimidazole chloride) (p[CMVIm][Cl]). Reactions were carried

out at 70 °C under $N_2$ atmosphere for 12 h. Obtained PILs were filtered and vacuum-dried for 24 h at 60 °C (light-yellow powders; the reaction yields were 76% for p[HVIm][Cl] and 74% for p[CMVIm][Cl]). The synthesis scheme is shown in Figure 1 (left). The photos of the synthesized p [HVIm][Cl] and p[CMVIm][Cl] are shown at the top of Figure 2.





**Figure 1.** Synthesis scheme of PILs.




**Figure 2.** Photos of the PILs.

[HVIm][Cl]: $^1$H NMR (300 MHz, deuterium oxide) δ 7.30–7.24 (m, 2H), 6.82–6.49 (m, 1H), 4.20 (s, 2H), 3.99–3.54 (m, 2H), 2.13 (d, 6H). [CMVIm][Cl]: $^1$H NMR (300 MHz, deuterium oxide) δ 2.02 (d, 6H), 7.36 (d, 1H), 7.44 (d, 1H), 8.70 (s, 1H), 4.74 (s, 2H), 4.28–4.06 (m, 1H).

### 2.2.2. Synthesis of Imidazolium Copolymer-Based PILs

Styrene and 1-vinylimidazole (1:1 mol) were combined in a flask with the addition of 2 mas. % (Sty+VIm) AIBN. Reaction was carried out at 60 °C for 12 h under $N_2$, using a magnetic stirrer. The reaction solution was then added dropwise into a cold mixture of diethyl ether/hexane (20/80 vol.%). Precipitated pS-b-p[VIm] was filtered, washed several times with cold hexane, and vacuum-dried for 24 h at 80 °C (the product was a white

powder; the reaction yield was 53%). For obtaining imidazolium copolymer-based PILs 2-Chloroethan-1-ol or chloroacetic acid was dissolved with pS-b-p[VIm] in DMF (2:1 mol) for obtaining pS-b-p[HVIm][Cl] or pS-b-p[CMVIm][Cl]. Reactions were carried out at 70 °C under $N_2$ atmosphere for 12 h. Obtained PILs were filtered and vacuum-dried for 24 h at 60 °C (light-yellow powders; the reaction yields were 71% for pS-b-p[HVIm][Cl], 70% for pS-b-p[CMVIm][Cl]). The synthesis scheme is shown in Figure 1 (right). Photos of the synthesized pS-b-p[HVIm][Cl] and pS-b-p[CMVIm][Cl] are shown at the bottom of Figure 2.

pS-b-p[HVIm][Cl]: $^1$H NMR (300 MHz, chloroform-*d*) δ 7.29 ppm (s, 1H), 7.27–6.86 ppm (br.s, 2H), 6.80–6.51 ppm (br.s, 4H), 6.49 ppm (s, 1H), 3.88 ppm (t, 2H), 3.79 ppm (m, 1H), 3.68 ppm (t, 2H), 3.08 ppm (m, 1H), 2.10–1.16 ppm (m, 7H), 0.91 ppm (m, 3H). pS-b-p[CMVIm][Cl]: $^1$H NMR (300 MHz, DMSO-*d*6) δ 6.80 (dd, *J* = 155.0 Hz, 2H), 4.52–4.48 (m, 2H), 4.46–4.37 (m, 3H), 4.27 (s, 1H), 4.07–3.80 (m, 1H), 3.63–3.54 (m, 1H), 2.54–2.48 (m, 4H), 2.00–1.07 (m, 6H).

### 2.3. Study of Catalytic Activity

The catalytic activity of the prepared polymeric ionic liquids was studied using the experimental setup shown in Figure 3. A stainless steel reactor was loaded with a fixed amount of substrate (epichlorohydrin) and 2 mol% catalyst (polymeric ionic liquid). At the beginning of the experiment, the reactor was evacuated using a Vacuubrand MZ 2C NT vacuum pump (Vacuubrand GmbH & Co. KG, Wertheim am Main, Germany), and then a fixed amount of $CO_2$ was added (the set pressure was maintained constant using a back pressure regulator Bronkhorst P702CM (Ruurlo, The Netherlands)). The constant temperature (90 °C) of the gas lines and reactor was maintained using a thermostat. After reaction time (4 h) the pressure in the reactor was slowly released by back pressure regulator and then it was cooled. The liquid phase was sampled for GC analysis using a sampler through a special septum, preventing air from entering the reactor from the atmosphere. The reaction scheme of cycloaddition of $CO_2$ to epichlorohydrin (Oxirane, (chloromethyl)-) with the formation of chloropropylene carbonate (4-Chloromethyl-1,3-dioxolan-2-one) is shown in Figure 4.

Qualitative analysis of the reaction mixture was performed using a Thermo Scientific Chromatec-Crystal 5000 chromatograph (Russia, Yoshkar-Ola) with an ISQ mass spectrometric detector to identify the resulting product. Quantitative analysis of the product was performed using a Chromatec Crystal 5000 chromatograph with a flame ionization detector (FID). Chromatec Analytic software (version 4.0.2601.30) was used to set the chromatography parameters. For quantitative analysis of samples, absolute calibration was performed using pure reagents. The GC system included an automatic liquid sample injector, a hydrogen generator, a compressed air compressor, and a catalytic gas filter. High-purity helium was used as the carrier and makeup gas, while hydrogen and air were used for flame combustion in the FID. The operating conditions and components characteristics of the GC system are given in Table 2.





**Figure 3.** Experimental setup for obtaining and analyzing cyclic carbonates. 1—$CO_2$ gas cylinder; 2—vacuum pump; 3—valve; 4—stainless steel reactor; 5—magnetic stirrer; 6—pressure sensor; 7—back pressure regulator; 8—thermostat; 9—sampler.





**Figure 4.** The reaction scheme of cycloaddition of $CO_2$ to epichlorohydrin.

**Table 2.** GC analysis conditions.

| Component | Characteristics | |
|---|---|---|
| | **GC-FID** | **GC–MS** |
| Carrier gas | Helium > 99.99999 vol.%; 1 mL/min | |
| Splitting | 1:10 | 1:20 |
| Chromatography column | TR-5MS | |
| Description | 30 m × 0.32 mm × 0.5 µm | 30 m × 0.25 mm × 0.25 µm |
| Column stationary phase | mixture of 5% diphenyl polysiloxane and 95% dimethylpolysiloxane | |
| Column thermostat mode | 50 °C—6 min, 250 °C (10 °C/min), 250—2 min | 80 °C—6 min, 310 °C (10 °C/min), 310—7 min |
| Injector | 250 °C | |
| Electron ionization (EI) | - | 70 eV |

## 3. Results and Discussion

The IR spectra of the synthesized polymeric ionic liquids are shown in Figure 5. All catalysts exhibit characteristic vibrational peaks at 1163 $cm^{-1}$, which correspond to the in-plane C-H bond deformation vibration of the imidazole ring [67]. PILs with chloroacetic acid, attached to the imidazole ring, exhibit a stretching vibration peak of the C–O bond at 1741 $cm^{-1}$, which indicates the successful attachment of halogen acetic acids to the imidazole ring [68]. PILs p[HVIm][Cl] and pS-b-p[HVIm][Cl] demonstrate an in-plane

bending vibration peak of C-OH at 1352 $cm^{-1}$, which indicates the successful attachment of 2-chloroethanol to the imidazole ring [68]. In addition, the C–H out-of-plane bending vibrations of ring of styrene fragment were found at 754 and 698 $cm^{-1}$ [69]. The bands at 2925 and 2850 $cm^{-1}$ were the C–H stretching vibrations of $CH_2$ and CH groups on the main polystyrene chain [69]. In the range from 3005 to 3104 $cm^{-1}$, bands corresponding to the C–H stretching vibrations of aromatic bonds in polystyrene were observed [69,70]. The absorption band at 3082 $cm^{-1}$ corresponds to the C–H stretching vibrations of bonds in the imidazole ring [71]. The absorption bands in the region of 2946 $cm^{-1}$ for p[HVIm][Cl] and 2916 $cm^{-1}$ for p[CMVIm][Cl] correspond to asymmetric stretching vibrations of C–H bonds in methylene fragments (-$CH_2$-) both in the polymer chain and in the N-$CH_2$-$CH_2$-OH and N-$CH_2$-COOH bridges, respectively [72,73]. The absorption bands in the region of 758 $cm^{-1}$ correspond to out-of-plane deformation vibrations of C–H bonds in the imidazole ring [74].





**Figure 5.** IR spectra of p[HVIm][Cl], p[CMVIm][Cl], pS-b-p[HVIm][Cl], and pS-b-p[CMVIm][Cl].

Table 3 shows a diagram of the distribution of the weight-average molecular weight (Mw) and number-average molecular weight (Mn) of PILs. Block copolymers pS-b-p[HVIm][Cl] and pS-b-p[CMVIm][Cl] are characterized by low polydispersity index (PDI) (1.2 and 1.1, respectively), indicating chain homogeneity and likely forming ordered nanostructures (micelles, spheres, cylinders) with a distinct boundary between the hydrophobic and hydrophilic blocks. This may lead to a "micellar catalytic effect", which is likely to provide increased catalytic activity. The block copolymer pS-b-p[HVIm][Cl] has a Mw approximately 2-fold higher (15.3 kDa) than pS-b-p[CMVIm][Cl] (7.4 kDa). This may indicate different reactivity of the monomers. The carboxymethyl substituent in p[CMVIm][Cl] may exert a steric or electronic influence, slightly slowing polymerization or resulting in shorter blocks under the same synthesis conditions. Homopolymers (p[HVIm][Cl] and p[CMVIm][Cl]) are characterized by higher PDI (2.4 and 2.9, respectively), suggesting that they form coils in solution.

**Table 3.** Molecular weight characterization of PILs.

| PIL | Mw | Mn | PDI |
|---|---|---|---|
| p[HVIm][Cl] | 11,690.4 | 4822.8 | 2.4 |
| p[CMVIm][Cl] | 9923.1 | 3433.6 | 2.9 |
| pS-b-p[HVIm][Cl] | 15,342.3 | 12,405.0 | 1.2 |
| pS-b-p[CMVIm][Cl] | 7390.5 | 6978.0 | 1.1 |

As seen from SEM microphotographs given in Figure 6a, the p[HVIm][Cl] polymer is characterized by irregular particles with a broad size distribution. The particles form loose agglomerates, with a rough, folded surface but no signs of ordered nanostructures (pores, channels, or regular domains). The morphology of the p[CMVIm][Cl] (Figure 6b) is similar: irregularly shaped particles with a pronounced tendency to agglomerate, a broad size distribution, and a developed rough surface. The formation of large conglomerates from adhered small particles is observed. Ordered structures are also absent.





**Figure 6.** SEM micrographs of polymeric ionic liquids: (**a**) p[HVIm][Cl]; (**b**) p[CMVIm][Cl]; (**c**) p-S-b-p[HVIm][Cl]; (**d**) p-S-b-p[CMVIm][Cl].

SEM of the p-S-b-p[HVIm][Cl] (Figure 6c) block copolymer at ×50 magnification reveals large agglomerates with a distinct surface microrelief, including folds and layers. At ×350 magnification (in the green square at the top of Figure 6c), a complex hierarchical structure is clearly visible: the surface is covered with folds, grooves, and "flaky" formations reminiscent of lamellar morphology. The observed relief indicates microphase separation of the blocks, characteristic of block copolymers, and differs fundamentally from the smooth or irregular surface of homopolymers.

The block copolymer p-S-b-p[CMVIm][Cl] (Figure 6d) exhibits a complex hierarchical organization: large agglomerates (50–500 μm) with a developed surface. Signs of internal porosity (indentations, cavities) are observed, which may be a consequence of microphase

separation. The morphology is fundamentally different from the dense, unstructured agglomerates of the p[CMVIm][Cl] homopolymer.

The results obtained by GC-MS are shown in Figure 7. The main reaction product is chloropropylene carbonate (4). Possible byproducts of the reaction are 2,3-dichloropropan-1-ol (2) and vinyl chloroacetate (3), the content of which in the reaction mixture was insignificant.





**Figure 7.** GC-MS spectrum of the reaction: 1—ECH; 2—2,3-dichloropropan-1-ol (byproduct); 3—vinyl chloroacetate (byproduct); 4—chloropropylene carbonate (main product).

Table 4 presents the average results of determining the catalytic activity of the synthesized polymer catalysts (three experiments for p[HVIm][Cl] and p[CMVIm][Cl] and four experiments for pS-b-p[HVIm][Cl] and pS-b-p[CMVIm][Cl]). As a result of carrying out the reaction at 90 °C and 1 MPa of $CO_2$ for 4 h, a conversion of epichlorohydrin above 75% was achieved for all studied samples. The conversion ECH values increased in the series p[CMVIm][Cl] < p[HVIm][Cl] < pS-b-p[CMVIm][Cl] < pS-b-p[HVIm][Cl]. This trend indicates that the catalytic activity is governed not only by the presence of the imidazolium–chloride ion pair, but also by secondary functional groups and polymer morphology effects. Selectivity was determined as the ratio of the amount of the main product formed to the total amount of all products, including byproducts. Therefore, the slight decrease in selectivity with increasing ECH conversion is caused by the appearance of small amounts of byproducts in the case of block copolymers.

**Table 4.** Catalytic performance of the polymeric ionic liquids.

| PIL | Conversion ECH, % | Selectivity, % |
|---|---|---|
| p[HVIm][Cl] | 76.88 ± 2.03 | 98.49 |
| p[CMVIm][Cl] | 68.30 ± 2.49 | 98.65 |
| pS-b-p[HVIm][Cl] | 82.69 ± 1.69 | 95.27 |
| pS-b-p[CMVIm][Cl] | 80.53 ± 1.72 | 93.95 |

Reaction conditions: 90 °C; 1 MPa; 4 h.

A comparison between the homopolymeric catalysts shows a clear enhancement in epichlorohydrin conversion when the carboxymethyl-functionalized polymer (p[CMVIm][Cl]) is replaced by the hydroxyethyl analog (p[HVIm][Cl]). The lower activity of p[CMVIm][Cl] can be attributed to the presence of carboxylic acid groups, which are capable of forming strong hydrogen-bonding and ionic interactions with chloride anions. Such interactions reduce the effective nucleophilicity and mobility of $Cl^-$, which is the key species responsible for the nucleophilic ring opening of the epoxide. In contrast, hydroxyl groups in

p[HVIm][Cl] provide moderate hydrogen bonding interactions that preferentially stabilize and activate the epoxide ring without significantly suppressing the nucleophilicity of the chloride anion. As a result, the cooperative activation of epichlorohydrin via hydrogen bonding and nucleophilic attack by $Cl^-$ is more efficient, leading to higher substrate conversion. A substantial increase in catalytic performance is observed upon introducing a polystyrene block into the polymeric ionic liquid structure. Both block copolymers, pS-b-p[CMVIm][Cl] and pS-b-p[HVIm][Cl], exhibit higher epichlorohydrin conversions compared to their corresponding homopolymers. Apparently, the hydrophobic polystyrene segments enhance the local concentration of epichlorohydrin near the catalytic sites. Among all catalysts studied, pS-b-p[HVIm][Cl] demonstrates the highest epichlorohydrin conversion, highlighting a pronounced synergistic effect between the hydroxy-functionalized imidazolium units and the block copolymer architecture. In this system, hydroxyl groups effectively activate the epoxide ring through hydrogen bonding, and the amphiphilic nature of the block copolymer may facilitate local $CO_2$ accumulation in the vicinity of the imidazolium domains, thereby accelerating the cyclization step leading to cyclic carbonate formation. The simultaneous optimization of anion nucleophilicity, epoxide activation, and polymer morphology results in the most favorable catalytic environment, explaining the superior performance of pS-b-p[HVIm][Cl].

Overall, the observed activity trend underscores the importance of balancing chemical functionality and macromolecular design in polymeric ionic liquid catalysts. While strongly acidic groups can hinder catalytic activity by immobilizing nucleophilic anions, moderately hydrogen-bonding functionalities, combined with block copolymer-induced microphase separation, provide an optimal platform for efficient $CO_2$–epoxide cycloaddition. These results demonstrate that rational tuning of both the local chemical environment and polymer architecture is a powerful strategy for enhancing the catalytic conversion of epoxides into cyclic carbonates.

The efficiency of catalyst recycling was assessed over three cycles (Figure 8). Reusing the catalyst under the same conditions (90 °C; 1 MPa; 4 h) resulted in only a slight efficiency decrease. Thus, over three extra cycles, epichlorohydrin conversion decreased by 9.2% when using p[HVIm][Cl], by 8% for p[CMVIm][Cl], by 8.5% for pS-b-p[HVIm][Cl], and by less than 9% for pS-b-p[CMVIm][Cl].





**Figure 8.** Studies on the possibility of reuse of the PIL catalysts.

## 4. Conclusions

In this study, a series of imidazolium-based polymeric ionic liquids (PILs) was designed and synthesized, in which variation of the functional group (hydroxyethyl vs. carboxymethyl) and polymer architecture (homopolymer vs. polystyrene block copolymer) directly controlled catalytic efficiency for the model reaction of $CO_2$ with epichlorohydrin. The excellent performance of the block copolymer pS-b-p[HVIm][Cl], which provides

82.69% epichlorohydrin conversion at 90 °C and 1 MPa $CO_2$ in 4 h, can probably be attributed to the synergistic triple effect:

(1) The moderate hydrogen-bonding ability of the hydroxyl group, which activates the epoxide ring without deactivating the nucleophilic chloride anion;
(2) The amphiphilic block structure (PS and PIL blocks), which drives microphase separation into ordered nanostructures with low polydispersity (PDI 1.2);
(3) The resulting "micellar catalytic effect," which enhances the local concentration of both the hydrophobic substrate and $CO_2$ at the hydrophilic imidazolium-chloride catalytic sites.

In such a membrane, continuous hydrophobic domains of polystyrene will likely act as a selective matrix for the permeation and concentration of $CO_2$ or light hydrocarbons, while dispersed, nanoscale hydrophilic domains of PIL will function as immobilized catalytic reactors for the continuous conversion of the permeant gas—for example, into cyclic carbonates.

The results of molecular weight determination, catalytic activity, and SEM micrographs are consistent with the hypothesis that the high catalytic activity of block copolymers in the $CO_2$ conversion reaction may be due to the formation of a nanostructured environment leading to a synergistic triple effect. However, more complex studies are needed to more accurately determine the type of ordering or the characteristic domain sizes, which are beyond the framework of the present study.

Thus, this work demonstrates the potential for further comprehensive study of synthesized polymeric ionic liquids and creating membranes based on them for the production of bifunctional materials.

**Author Contributions:** M.A.: Conceptualization, Project administration, Writing—review and editing; K.S.: Investigation, Methodology; S.K.: Formal analysis, Writing—original draft; A.A.: Supervision, Data curation; A.S.: Formal analysis, Software; O.K.: Validation, Data curation; A.P.: Supervision; A.V.: Methodology; I.V.: Supervision. All authors have read and agreed to the published version of the manuscript.

**Funding:** The main part of this work was supported by the Russian Science Foundation, grant number 22-79-10302-P, https://rscf.ru/project/22-79-10302/ (accessed on 23 February 2026). The part related to the study of the molecular mass characteristics of the polymers was financially supported by Ministry of Science and Higher Education of the Russian Federation, Laboratory of ionic materials (LIM), project number FSSM-2024-0006.

**Institutional Review Board Statement:** Not applicable.

**Data Availability Statement:** The raw data supporting the conclusions of this article will be made available by the authors on request.

**Conflicts of Interest:** The authors declare no conflicts of interest.

## References

1. Leung, D.Y.C.; Caramanna, G.; Maroto-Valer, M.M. An Overview of Current Status of Carbon Dioxide Capture and Storage Technologies. *Renew. Sustain. Energy Rev.* **2014**, *39*, 426–443. [CrossRef]
2. Atlaskina, M.E.; Kazarina, O.V.; Petukhov, A.N.; Atlaskin, A.A.; Tsivkovsky, N.S.; Tiuleanu, P.; Malysheva, Y.B.; Lin, H.; Zhong, G.J.; Lukoyanov, A.N.; et al. Amino Acid-Based Ionic Liquid as a Promising $CO_2$ Sorption Increasing Agent by Aqueous MDEA Solution. *J. Mol. Liq.* **2024**, *395*, 123635. [CrossRef]
3. Kim, Y.E.; Lim, J.A.; Jeong, S.K.; Yoon, Y.I.; Bae, S.T.; Nam, S.C. Comparison of Carbon Dioxide Absorption in Aqueous MEA, DEA, TEA, and AMP Solutions. *Bull. Korean Chem. Soc.* **2013**, *34*, 783–787. [CrossRef]
4. Akinola, T.E.; Oko, E.; Wang, M. Study of $CO_2$ Removal in Natural Gas Process Using Mixture of Ionic Liquid and MEA through Process Simulation. *Fuel* **2019**, *236*, 135–146. [CrossRef]

5. Dave, N.; Do, T.; Puxty, G.; Rowland, R.; Feron, P.H.M.; Attalla, M.I. $CO_2$ Capture by Aqueous Amines and Aqueous Ammonia-A Comparison. *Energy Procedia* **2009**, *1*, 949–954. [CrossRef]
6. Cullinane, J.T.; Rochelle, G.T. Kinetics of Carbon Dioxide Absorption into Aqueous Potassium Carbonate and Piperazine. *Ind. Eng. Chem. Res.* **2006**, *45*, 2531–2545. [CrossRef]
7. Islam, M.S.; Yusoff, R.; Ali, B.S.; Islam, M.N.; Chakrabarti, M.H. Degradation Studies of Amines and Alkanolamines during Sour Gas Treatment Process. *Int. J. Phys. Sci.* **2011**, *6*, 5877–5890.
8. Hatchell, D.; Namjoshi, O.; Fischer, K.; Rochelle, G.T. Thermal Degradation of Linear Amines for $CO_2$ Capture. *Energy Procedia* **2014**, *63*, 1558–1568. [CrossRef]
9. Yang, J.; Cao, N.; Liu, Y.; Lu, Y. $CO_2$ Capture with Adsorption Strategies: Achievements, Challenges, and Prospects. *J. Clean. Prod.* **2025**, *515*, 145798. [CrossRef]
10. Zentou, H.; Hoque, B.; Abdalla, M.A.; Saber, A.F.; Abdelaziz, O.Y.; Aliyu, M.; Alkhedhair, A.M.; Alabduly, A.J.; Abdelnaby, M.M. Recent Advances and Challenges in Solid Sorbents for $CO_2$ Capture. *Carbon Capture Sci. Technol.* **2025**, *15*, 100386. [CrossRef]
11. Kudryavtseva, M.S.; Petukhov, A.N.; Shablykin, D.N.; Atlaskin, A.A.; Stepanova, E.A.; Vorotyntsev, V.M.; Vorotyntsev, A.V. Separation of CH4-$CO_2$ Gas Mixture by Gas Hydrate Crystallisation: A Parametric Study. *Gas Sci. Eng.* **2023**, *116*, 205026. [CrossRef]
12. Mok, J.; Sum, A.K. An Efficient and Sustainable Method for Improved $CO_2$ Capture Based on Gas Hydrate Condensation. *Chem. Eng. J.* **2025**, *513*, 162971. [CrossRef]
13. K.S, A.; Penkova, A.; Aravind, U.K.; C.T, A. Innovations in $CO_2$ Separation Technologies Using Polyetherimide-Based Membranes. *Sep. Purif. Rev. 2025*, 2595707. [CrossRef]
14. Baker, R.W. *Membrane Technology and Applications*; John Wiley & Sons Ltd.: Hoboken, NJ, USA, 2023; pp. 1–539. [CrossRef]
15. Merkel, T.; Amo, K.; Baker, R.; Daniels, R.; Friat, B.; He, Z.; Lin, H.; Serbanescu, A. *Membrane Process to Sequester $CO_2$ from Power Plant Flue Gas*; Membrane Technology & Research Incorporated: Newark, CA, USA, 2009. [CrossRef]
16. Petukhov, A.N.; Shablykin, D.N.; Trubyanov, M.M.; Atlaskin, A.A.; Zarubin, D.M.; Vorotyntsev, A.V.; Stepanova, E.A.; Smorodin, K.A.; Kazarina, O.V.; Petukhova, A.N.; et al. A Hybrid Batch Distillation/Membrane Process for High Purification Part 2: Removing of Heavy Impurities from Xenon Extracted from Natural Gas. *Sep. Purif. Technol.* **2022**, *294*, 121230. [CrossRef]
17. Otvagina, K.V.; Maslov, A.A.; Fukina, D.G.; Petukhov, A.N.; Malysheva, Y.B.; Vorotyntsev, A.V.; Sazanova, T.S.; Atlaskin, A.A.; Kapinos, A.A.; Barysheva, A.V.; et al. The Influence of Polycation and Counter-Anion Nature on the Properties of Poly(Ionic Liquid)-Based Membranes for $CO_2$ Separation. *Membranes* **2023**, *13*, 539. [CrossRef] [PubMed]
18. Stepanova, E.A.; Atlaskin, A.A.; Kudryavtseva, M.S.; Shablykin, D.N.; Markin, Z.A.; Dokin, E.S.; Zarubin, D.M.; Prokhorov, I.O.; Vshivtsev, M.A.; Kazarina, O.V.; et al. Combining Gas Hydrate Crystallization and Membrane Technology: A Synergistic Approach to Natural Gas Separation. *Chem. Eng. Process. Process Intensif.* **2025**, *208*, 110130. [CrossRef]
19. Petukhov, A.N.; Atlaskin, A.A.; Kudryavtseva, M.S.; Kryuchkov, S.S.; Shablykin, D.N.; Stepanova, E.A.; Smorodin, K.A.; Kazarina, O.V.; Trubyanov, M.M.; Atlaskina, M.E.; et al. $CO_2$ Capture Process through Hybrid Gas Hydrate-Membrane Technology: Complex Approach for the Transition from Theory to Practice. *J. Environ. Chem. Eng.* **2022**, *10*, 108104. [CrossRef]
20. Atlaskin, A.A.; Kryuchkov, S.S.; Yanbikov, N.R.; Smorodin, K.A.; Petukhov, A.N.; Trubyanov, M.M.; Vorotyntsev, V.M.; Vorotyntsev, I.V. Comprehensive Experimental Study of Acid Gases Removal Process by Membrane-Assisted Gas Absorption Using Imidazolium Ionic Liquids Solutions Absorbent. *Sep. Purif. Technol.* **2020**, *239*, 116578. [CrossRef]
21. Petukhov, A.N.; Atlaskin, A.A.; Smorodin, K.A.; Atlaskina, M.E.; Zarubin, D.M.; Kryuchkov, S.S.; Stepakova, A.N.; Vorotyntsev, A.V.; Kazarina, O.V.; Suvorov, S.S.; et al. An Efficient Technique to Remove Acid Gases from Natural Gas with a Hollow Fiber-Based Membrane-Assisted Gas Absorption Unit. *Int. J. Technol.* **2025**, *16*, 1630–1650. [CrossRef]
22. Atlaskina, M.E.; Petukhov, A.N.; Atlaskin, A.A.; Smorodin, K.A.; Zarubin, D.M.; Tsivkovsky, N.S.; Kryuchkov, S.S.; Stepakova, A.N.; Vorotyntsev, A.V.; Kazarina, O.V.; et al. Natural Gas Sweetening via Membrane-Assisted Gas Absorption Part 2: A Hollow-Fiber Unit with Dimethyl Diethanolammonium Glycinate-Based Absorbent. *Int. J. Technol.* **2025**, *16*, 2025–2042. [CrossRef]
23. Ghorai, S.; Nanda, D.; Ghosh, A.; Dash, P.S. Review on the Recent Advances in Catalytic Conversion of Carbon Dioxide for Synthesis of Cyclic Propylene Carbonate. *Mol. Catal.* **2024**, *553*, 113720. [CrossRef]
24. Olah, G.A.; Prakash, G.K.S.; Goeppert, A. Anthropogenic Chemical Carbon Cycle for a Sustainable Future. *J. Am. Chem. Soc.* **2011**, *133*, 12881–12898. [CrossRef] [PubMed]
25. Cheon, J.; Yang, J.Y.; Koper, M.; Ishitani, O. From Pollutant to Chemical Feedstock: Valorizing Carbon Dioxide through Photo- and Electrochemical Processes. *Acc. Chem. Res.* **2022**, *55*, 931–932. [CrossRef] [PubMed]
26. Song, B.; Qin, A.; Tang, B.Z. Syntheses, Properties, and Applications of $CO_2$-Based Functional Polymers. *Cell Rep. Phys. Sci.* **2022**, *3*, 100719. [CrossRef]
27. Zhang, Z.; Fan, F.; Xing, H.; Yang, Q.; Bao, Z.; Ren, Q. Efficient Synthesis of Cyclic Carbonates from Atmospheric $CO_2$ Using a Positive Charge Delocalized Ionic Liquid Catalyst. *ACS Sustain. Chem. Eng.* **2017**, *5*, 2841–2846. [CrossRef]

28. Artz, J.; Müller, T.E.; Thenert, K.; Kleinekorte, J.; Meys, R.; Sternberg, A.; Bardow, A.; Leitner, W. Sustainable Conversion of Carbon Dioxide: An Integrated Review of Catalysis and Life Cycle Assessment. *Chem. Rev.* **2017**, *118*, 434–504. [CrossRef] [PubMed]
29. Pescarmona, P.P. Cyclic Carbonates Synthesised from $CO_2$: Applications, Challenges and Recent Research Trends. *Curr. Opin. Green Sustain. Chem.* **2021**, *29*, 100457. [CrossRef]
30. Gao, F.; Bai, R.; Ferlin, F.; Vaccaro, L.; Li, M.; Gu, Y. Replacement Strategies for Non-Green Dipolar Aprotic Solvents. *Green Chem.* **2020**, *22*, 6240–6257. [CrossRef]
31. Schäffner, B.; Schäffner, F.; Verevkin, S.P.; Börner, A. Organic Carbonates as Solvents in Synthesis and Catalysis. *Chem. Rev.* **2010**, *110*, 4554–4581. [CrossRef]
32. Jessop, P.G. Searching for Green Solvents. *Green Chem.* **2011**, *13*, 1391–1398. [CrossRef]
33. Scrosati, B.; Hassoun, J.; Sun, Y.K. Lithium-Ion Batteries. A Look into the Future. *Energy Environ. Sci.* **2011**, *4*, 3287–3295. [CrossRef]
34. Xiang, W.; Shen, C.; Lu, Z.; Chen, S.; Li, X.; Zou, R.; Zhang, Y.; Liu, C.J. $CO_2$ Cycloaddition over Ionic Liquid Immobilized Hybrid Zeolitic Imidazolate Frameworks: Effect of Lewis Acid/Base Sites. *Chem. Eng. Sci.* **2021**, *233*, 116429. [CrossRef]
35. Babu, R.; Kathalikkattil, A.C.; Roshan, R.; Tharun, J.; Kim, D.W.; Park, D.W. Dual-Porous Metal Organic Framework for Room Temperature $CO_2$ Fixation via Cyclic Carbonate Synthesis. *Green Chem.* **2015**, *18*, 232–242. [CrossRef]
36. Yang, Z.; Xu, Z.; Ni, J.; Feng, Y.; Yao, J. ZIF-8 Nanowires Enable Superior $CO_2$ Cycloaddition Catalysis through Synergistic Morphological and Lewis Acidity Effects. *J. Environ. Chem. Eng.* **2025**, *13*, 119955. [CrossRef]
37. Hu, L.; Xu, W.; Jiang, Q.; Ji, R.; Yan, Z.; Wu, G. Recent Progress on $CO_2$ Cycloaddition with Epoxide Catalyzed by ZIFs and ZIFs-Based Materials. *J. $CO_2$ Util.* **2024**, *81*, 102726. [CrossRef]
38. Qu, Z.; Zhou, M.; Zhang, J.; Jiang, H.; Tang, Z.; Xing, W.; Chen, R. $CO_2$ Fixation via Epoxide Cycloaddition with a Highly Active and Stable MOF-808/GO Composite Catalyst. *Sep. Purif. Technol.* **2025**, *358*, 130448. [CrossRef]
39. Zhang, F.; Wang, Y.; Zhang, X.; Zhang, X.; Liu, H.; Han, B. Recent Advances in the Coupling of $CO_2$ and Epoxides into Cyclic Carbonates under Halogen-Free Condition. *Green Chem. Eng.* **2020**, *1*, 82–93. [CrossRef]
40. Weidlich, T.; Kamenická, B. Utilization of $CO_2$-Available Organocatalysts for Reactions with Industrially Important Epoxides. *Catalysts* **2022**, *12*, 298. [CrossRef]
41. Singh, S.K.; Savoy, A.W. Ionic Liquids Synthesis and Applications: An Overview. *J. Mol. Liq.* **2020**, *297*, 112038. [CrossRef]
42. Zhang, S.; Sun, J.; Zhang, X.; Xin, J.; Miao, Q.; Wang, J. Ionic Liquid-Based Green Processes for Energy Production. *Chem. Soc. Rev.* **2014**, *43*, 7838–7869. [CrossRef]
43. Welton, T. Room-Temperature Ionic Liquids. Solvents for Synthesis and Catalysis. *Chem. Rev.* **1999**, *99*, 2071–2083. [CrossRef] [PubMed]
44. Lei, Z.; Dai, C.; Chen, B. Gas Solubility in Ionic Liquids. *Chem. Rev.* **2014**, *114*, 1289–1326. [CrossRef] [PubMed]
45. Bernardino, K.; Zhang, Y.; Ribeiro, M.C.C.; Maginn, E.J. Effect of Alkyl-Group Flexibility on the Melting Point of Imidazolium-Based Ionic Liquids. *J. Chem. Phys.* **2020**, *153*, 044504. [CrossRef]
46. Smiglak, M.; Pringle, J.M.; Lu, X.; Han, L.; Zhang, S.; Gao, H.; Mac Farlane, D.R.; Rogers, R.D. Ionic Liquids for Energy, Materials, and Medicine. *Chem. Commun.* **2014**, *50*, 9228–9250. [CrossRef]
47. Al-Bodour, A.; Alomari, N.; Perez-Duran, G.; Rozas, S.; Iglesias-Silva, G.; Aparicio, S.; Gutierrez-Vega, A.; Atilhan, M. Ionic Liquids as Multidimensional Materials: A Review from Fundamentals to Applications. *Energy Fuels* **2025**, *39*, 12791–12829. [CrossRef]
48. Lei, Z.; Chen, B.; Koo, Y.M.; Macfarlane, D.R. Introduction: Ionic Liquids. *Chem. Rev.* **2017**, *117*, 6633–6635. [CrossRef] [PubMed]
49. Ghazali-Esfahani, S.; Song, H.; Păunescu, E.; Bobbink, F.D.; Liu, H.; Fei, Z.; Laurenczy, G.; Bagherzadeh, M.; Yan, N.; Dyson, P.J. Cycloaddition of $CO_2$ to Epoxides Catalyzed by Imidazolium-Based Polymeric Ionic Liquids. *Green Chem.* **2013**, *15*, 1584–1589. [CrossRef]
50. Atlaskina, M.; Markin, Z.; Smorodin, K.; Kryuchkov, S.; Tsivkovsky, N.; Petukhov, A.; Atlaskin, A.; Kazarina, O.; Vorotyntsev, A.; Vorotyntsev, I. Optimized $CO_2$ Cycloaddition to Epichlorohydrin Catalyzed by Ionic Liquid with Microwave and Ultrasonic Irradiation. *Int. J. Technol.* **2025**, *16*, 378–394. [CrossRef]
51. Xing, H.; Yu, F.; Li, X.; Bao, Y.; Ye, W.; Li, C.; Zheng, S.; Huang, M. Application of Ionic Liquids in $CO_2$ Capture and Conversion: A Review. *Sep. Purif. Technol.* **2025**, *360*, 130981. [CrossRef]
52. Li, R.; Lei, Y.; Yin, M.; Wang, L.; Tang, S. Poly(Ionic Liquid)s-Loaded Metal-Organic Framework Gel for $CO_2$ Capture and Cycloaddition Catalytic Conversion. *J. Environ. Chem. Eng.* **2025**, *13*, 120398. [CrossRef]
53. Zhang, W.; Ye, T.; Li, S.; Liu, Y.; Li, X.; Li, J.; Zhi, Y.; Hu, T.; Liu, D.; Shan, S.; et al. Simple Preparation of Poly(Ionic Liquids) Containing Hydrogen Bond Donors for Efficient Catalysis of $CO_2$ Cycloaddition. *Colloids Surf. A Physicochem. Eng. Asp.* **2026**, *735*, 139577. [CrossRef]
54. Tan, Z.; Zhang, J.; Yang, Y.; Zhong, J.; Zhao, Y.; Teng, Y.; Han, B.; Chen, Z. Polymeric Ionic Liquid Promotes Acidic Electrocatalytic $CO_2$ Conversion to Multicarbon Products with Ampere Level Current on Cu. *Nat. Commun.* **2025**, *16*, 1843. [CrossRef] [PubMed]

55. Kharade, J.; Lozano, K. Ionic Liquids and Poly (Ionic Liquids) for $CO_2$ Capture: A Comprehensive Review. *Energies* **2025**, *18*, 4257. [CrossRef]
56. Du, Y.R.; Yang, X.; Wang, Y.F.; Guan, P.X.; Wang, R.; Xu, B.H. Immobilization Poly(Ionic Liquid)s into Hierarchical Porous Covalent Organic Frameworks as Heterogeneous Catalyst for Cycloaddition of $CO_2$ with Epoxides. *Mol. Catal.* **2022**, *520*, 112164. [CrossRef]
57. Zhu, M.; Yang, Y. Poly(Ionic Liquid)s: An Emerging Platform for Green Chemistry. *Green Chem.* **2024**, *26*, 5022–5102. [CrossRef]
58. Li, R.; Wang, L.; Yin, M.; Lei, Y.; Tang, S. Functionalized Poly(Ionic Liquid)s-Covalent Organic Framework Materials for Catalyzing $CO_2$ Cycloaddition Reaction. *Mol. Catal.* **2025**, *574*, 114849. [CrossRef]
59. Molina-Fernández, C.; Chaplier, G.; Deveen, V.; Hartanto, Y.; Luis, P. Poly(Ionic Liquid) Composite Membranes Bearing Different Anions as Biocatalytic Membranes for $CO_2$ Capture. *Carbon Capture Sci. Technol.* **2024**, *13*, 100269. [CrossRef]
60. Natongchai, W.; Crespy, D.; D'Elia, V. $CO_2$ Fixation: Cycloaddition of $CO_2$ to Epoxides Using Practical Metal-Free Recyclable Catalysts. *Chem. Commun.* **2024**, *61*, 419–440. [CrossRef] [PubMed]
61. Liu, Y.; Dong, L.; Wang, Y.; Su, Q.; Meng, X.; Cheng, W. Polymeric Ionic Liquid Membranes for the Absorption-Conversion of $CO_2$ and Epoxides into Cyclic Carbonates. *Mol. Catal.* **2022**, *530*, 112597. [CrossRef]
62. Bragato, N.; Perosa, A.; Selva, M.; Fiorani, G. Dihydroxybenzene-Derived ILs as Halide-Free, Single-Component Organocatalysts for $CO_2$ Insertion Reactions. *ChemCatChem* **2023**, *15*, e202201373. [CrossRef]
63. Atlaskina, M.; Markin, Z.; Smorodin, K.; Kryuchkov, S.; Tiuleanu, P.; Sysoev, A.; Petukhov, A.; Atlaskin, A.; Kazarina, O.; Vorotyntsev, A.; et al. Carboxylation Reaction of Epichlorohydrin: Spectra-Based Experimental and Analytical System for Online Reaction Study. *Int. J. Technol.* **2025**, *16*, 1375–1388. [CrossRef]
64. Xuan, X.P.; Chang, L.L.; Zhang, H.; Wang, N.; Zhao, Y. Hydrogen Bonds in the Crystal Structure of Hydrophobic and Hydrophilic COOH-Functionalized Imidazolium Ionic Liquids. *CrystEngComm* **2014**, *16*, 3040–3046. [CrossRef]
65. Sun, J.; Zhang, S.; Cheng, W.; Ren, J. Hydroxyl-Functionalized Ionic Liquid: A Novel Efficient Catalyst for Chemical Fixation of $CO_2$ to Cyclic Carbonate. *Tetrahedron Lett.* **2008**, *49*, 3588–3591. [CrossRef]
66. Yu, J.-I.; Ju, H.-Y.; Kim, K.-H.; Park, D.-W. Cycloaddition of Carbon Dioxide to Butyl Glycidyl Ether Using Imidazolium Salt Ionic Liquid as a Catalyst. *Korean J. Chem. Eng.* **2010**, *27*, 446–451. [CrossRef]
67. Zhang, J.; Ma, C.; Zhu, X.; Lu, Y.; Meng, H.; Li, C.; Chen, B.; Lei, Z. Effect of Quaternization on Structure and Adsorptivity of Hyper Cross-Linked Poly(Vinyl Imidazole) for Thiohenic Sulfurs in Model Oil. *Ind. Eng. Chem. Res.* **2016**, *55*, 8079–8086. [CrossRef]
68. Yang, H.; Wang, L.; Xu, J.; Lin, L.; Liu, Y.; Cui, W.; Zhi, Y.; Shan, S.; Miao, Y. Preparation of Imidazole-Based Polymeric Ionic Liquid Catalysts and Their Catalysis in the Copolymerization with Sulfur Dioxide. *Colloids Surf. A Physicochem. Eng. Asp.* **2024**, *692*, 133986. [CrossRef]
69. Panawong, C.; Martwiset, S. Synthesis and Characterization of Poly(Styrene Sulfonic Acid-Co-1-Vinylimidazole-Co-Styrene) and Its Blends with Poly(Vinyl Chloride) as Proton Conducting Membranes. *Polym. Bull.* **2017**, *75*, 3843–3858. [CrossRef]
70. Bhutto, A.A.; Vesely, D.; Gabrys, B.J. Miscibility and Interactions in Polystyrene and Sodium Sulfonated Polystyrene with Poly(Vinyl Methyl Ether) PVME Blends. Part II. FTIR. *Polymer* **2003**, *44*, 6627–6631. [CrossRef]
71. Dutta, S. Synthesis and Anthelmintic Activity of Some Novel 2-Substituted-4,5-Diphenyl Imidazoles. *Acta Pharm.* **2010**, *60*, 229–235. [CrossRef]
72. Marcilla, R.; Blazquez, J.A.; Fernandez, R.; Grande, H.; Pomposo, J.A.; Mecerreyes, D. Synthesis of Novel Polycations Using the Chemistry of Ionic Liquids. *Macromol. Chem. Phys.* **2005**, *206*, 299–304. [CrossRef]
73. Jin, X.; Tao, J.; Yang, Y. Synthesis and Characterization of Poly(1-Viny1-3-Propylimidazolium) Iodide for Quasi-Solid Polymer Electrolyte in Dye-Sensitized Solar Cells. *J. Appl. Polym. Sci.* **2010**, *118*, 1455–1461. [CrossRef]
74. Wójcik, M.J.; Kwiendacz, J.; Boczar, M.; Boda, Ł.; Ozaki, Y. Theoretical and Spectroscopic Study of Hydrogen Bond Vibrations in Imidazole and Its Deuterated Derivative. *Chem. Phys.* **2010**, *372*, 72–81. [CrossRef]


**Disclaimer/Publisher's Note:** The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.