

Table S4. Chemical composition of BaBi_{1.90}Eu_{0.10}B₄O₁₀ and BaBi_{1.60}Eu_{0.40}B₄O₁₀ (wt.%).

Constituent	Mean	Range	S.D.
$x = 0.40$			
BaO	21.06	20.33–21.53	0.49
Bi ₂ O ₃	50.31	49.91–51.50	0.84
Eu ₂ O ₃	9.46	8.81 – 10.73	0.71
B ₂ O ₃	19.39	18.15–20.95	0.96
$x = 0.10$			
BaO	20.07	19.94–20.47	0.22
Bi ₂ O ₃	58.96	58.49–59.37	0.31
Eu ₂ O ₃	2.37	2.12–2.54	0.36
B ₂ O ₃	18.60	18.05–19.31	0.66