

Viscosity data obtained during the experiment:

Gothic model glass			Renaissance model glass			Baroque model glass		
t [°C]	time [s]	log η [dPa.s]	t [°C]	time [s]	log η [dPa.s]	t [°C]	time [s]	log η [dPa.s]
1381	1.33	2.181	1381	0.8	1.913	1382	6.16	2.990
1334	2.1	2.385	1335	1.29	2.129	1335	9.73	3.194
1288	3.48	2.615	1288	2.1	2.349	1288	16.14	3.424
1240	6.98	2.945	1239	3.62	2.598	1241	28.94	3.695
1193	10.36	3.116	1191	6.58	2.875	1194	51.65	3.964
1145	20.52	3.439	1143	12.75	3.187	1146	102.35	4.287
1098	42.56	3.787	1095	27.14	3.548	1098	219.92	4.653
1050	90.84	4.150	1047	63.1	3.955	-	-	-
1001	238.14	4.619	1000	173.56	4.452	-	-	-