



Article On the Absorption and Photoluminescence Properties of Pure ZnSe and Co-Doped ZnSe:Eu³⁺/Yb³⁺ Crystals

Behnaz Abbasgholi-NA¹, Osamah A. Aldaghri², Khalid Hassan Ibnouf², Nawal Madkhali^{2,*} and Humberto Cabrera^{1,*}

- ¹ Optics Lab, STI Unit, The Abdus Salam International Centre for Theoretical Physics, Strada Costiera 11, 34151 Trieste, Italy; be.asbaghi@yahoo.com
- ² Physics Department, College of Sciences, Imam Mohammad Ibn Saud Islamic University (IMSIU),
- Riyadh 13318, Saudi Arabia; odaghri@imamu.edu.sa (O.A.A.); khiahmed@imamu.edu.sa (K.H.I.)
- * Correspondence: namadkhali@imamu.edu.sa (N.M.); hcabrera@ictp.it (H.C.)

Abstract: Co-doped Zinc selenide (ZnSe) is a promising material because of a high photoluminescence efficiency and wide spectral range emission in the visible region. In this work, ZnSe and Eu^{3+}/Yb^{3+} co-doped ZnSe crystals were grown by the chemical vapour transport method. Photoluminescence and optical measurements revealed the effect of trivalent rare earth Eu^{3+}/Yb^{3+} ions on the emission of new lines with enhancement intensity. In the photoluminescence spectrum, some sharp and intense lines were observed that allow for the possibility of covering a broad emission range. Moreover, the optical measurement showed a lower bandgap compared to that of pure ZnSe bulk crystal. This material is suitable for developing optoelectronic devices, which can emit light in the visible and near infrared range with an improved emission efficiency and wide tunability.

Keywords: ZnSe; co-doped ZnSe; rare earths; Eu³⁺/Yb³⁺

1. Introduction

New materials, hetero-structures, hetero-junctions, and doped single crystal have been the subject of numerous studies to produce optoelectronics devices emitting from blue to near-IR region [1]. Recent applications such as high-density optical memories, display devices, and biological applications require solid-state semiconductor laser and light emitting diodes (LED) emitting in the blue and green wavelengths. Others, for example, the LED of high efficiency for illumination, require high as well as low wavelengths to illuminate inner spaces. The possible semiconductors that emit light in these wavelengths are the ones of the II–VI semiconductor family. These materials have direct gap edge of energy capable of emitting photons with a wavelength less than 500 nm.

Investigations for laser devices with materials such as GaN and ZnSe have had a tremendous progress in the last thirty years. In 1991, a ZnCdSe/ZnSe quantum well laser diode successfully demonstrated a pulsed operation at room temperature [2]. The first solid-state semiconductor blue-green laser and light emitting diode (LED) were built in 1991–1992 using wide band gap II–VI semiconductors with a ZnSe-based single quantum well structure [3,4]. A GaN/AlGaN double-heterostructure has shown optically a pumped lasing in the UV region at room temperature [5]. High efficiency InGaN/GaN double-heterostructure LEDs have also been obtained [6]. Other materials and technologies to produce compact diode-pumped Nd: LuVO₄ solid state lasers have been studied [7] as well as the high-efficiency nitride semiconductor blue lasers and light emitting diodes [8].

ZnSe is chemically stable metal chalcogenide, which possesses many advantages, making it an important optoelectronic material. It has useful electronic properties such as a wide and direct bandgap, low electrical resistivity, and n-type conductivity. Regarding optical properties, it has a broad transparency from visible to mid infrared wavelengths, high refractive index, low dispersion, and high photosensitivity. From the other side,



Citation: Abbasgholi-NA, B.; Aldaghri, O.A.; Ibnouf, K.H.; Madkhali, N.; Cabrera, H. On the Absorption and Photoluminescence Properties of Pure ZnSe and Co-Doped ZnSe:Eu³⁺/Yb³⁺ Crystals. *Appl. Sci.* 2022, *12*, 4248. https:// doi.org/10.3390/app12094248

Academic Editors: Cid Bartolomeu de Araújo, Luciana R. P. Kassab and Davinson Mariano da Silva

Received: 27 February 2022 Accepted: 20 April 2022 Published: 22 April 2022

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/). the trivalent rare earth ions are particularly useful because they produce additional lines and enhance the intensity of the emission spectra because f-electron absorption transitions are much weaker than those of the d electrons. This allows for the use of much higher active ion concentrations without complications from extensive self-absorption or excitation depletion.

Recently several papers have reported on the luminescence of II–VI semiconductors doped with Tb³⁺, Sm²⁺, Eu³⁺/Eu²⁺, or Er [8,9] particularly on the luminescence of ZnSe:Eu³⁺ and ZnSe:Yb [10,11]. Moreover, the co-doping with two rare earths gives the possibility of optical pumping between the f electron quantum levels of one rare earth to the other. Additionally, Yb³⁺ has a relatively simple energy diagram presented by one excited state ${}^{2}F_{5/2}$ and a ground ${}^{2}F_{7/2}$ state lying \approx 1.2 eV below, absence of the line widening, and absorption on the excited state [12]. Therefore, the energy level configuration of ZnSe: Eu³⁺/Yb³⁺ may generate transitions, which allow for a wider range of wavelengths in the photoluminescence spectrum. However, there have not been any reports on the photoluminescence properties of ZnSe co-doped with Eu³⁺ and Yb³⁺.

In this work, high quality single crystals were doped and co-doped with Eu^{3+}/Yb^{3+} rare earths in order to obtain semiconductors with very high photoluminescence in the visible and near infrared region. The luminescence spectra of these materials give multiple intense and sharp emission lines. The material was characterized using photoluminescence and UV–Vis techniques in order to obtain their photoluminescence and absorption properties. This material exhibited new and more intense emission lines in the visible and near infrared spectral region, thus giving the possibility of developing high efficacy and tunable light emitting devices.

2. Materials and Methods

The samples were prepared by chemical vapour transport method using iodine as a transporting agent following the procedure reported elsewhere [13]. Pure ZnSe (purity was 99.99%) single crystal and the other samples doped with a single rare earth and co-doped with two rare earths Eu^{3+}/Yb^{3+} were grown by this method. The binary compounds were synthesized first from the high purity elements by direct flame heating in quartz ampoules under vacuum. Then, the very high quality samples were produced after mixing in appropriate proportions with the concentration of the doping impurity. ZnSe crystals were doped with 1 mol % Eu^{3+} or co-doped with 1 mol % Eu^{3+} and 1 mol % Yb^{3+} .

X-ray diffraction (XRD, Rigaku, Tokyo, Japan) with a monochromatic Cu k α target in 2 theta geometry was used to determine the crystal structure of the samples.

The crystallinity of the pure ZnSe single crystal was confirmed using grazing incidence X-ray diffraction with a grazing angle of 1° and 2θ in the range of 10° – 80° , as shown in Figure 1. The results show a polycrystalline structure and a cubic zinc blende crystal structure with orientation mainly toward the (111) axis perpendicular to the surface.



Figure 1. XRD pattern of pure ZnSe.

The absorption spectra were taken for each sample as a function of temperature between 20 K to room temperature from 350 nm to 1100 nm. The experimental setup consisted of a closed cycle helium cooling system, with controlled temperature using a Cary 17D spectrophotometer.

Photoluminescence (PL) measurement is crucial for the registration of the emission spectra of new materials in order to calculate their efficiency and tunability [14,15]. In this direction, the spectra were recorded using a one-meter Spex monochromator equipped with a GaAs photomultiplier and the excitation source from an argon ion laser (Innova 300C series, Coherent USA) at 488 nm or 457.9 nm wavelengths operated at 10 mW power. The photoluminescence spectra were recorded using Labview data acquisition software as a function of temperature from 20 K to room temperature.

The basic algorithm procedure for the fitted experimental data is as follows. First, the data were normalized to minimize the computational processing time. Second, an error function based on a square mean error between the experimental data and the physical model was defined. Third, the parameters of the error function were optimized by genetic algorithms adapted to each particular situation. Finally, the parameters of the fitting function were obtained. The experimental data were fitted to theoretical models using the genetic algorithm routines briefly described above.

3. Results and Discussion

3.1. Absorption Measurement Energy Band Gap Determination

Theoretical analysis of the absorption coefficients α for the ZnSe pure materials and the doped ones show that they obey the following relations [16]:

$$\alpha = \frac{A}{h\nu}\sqrt{h\nu - E_g} \tag{1}$$

where *A* is a parameter; E_g is the band gap of allowed transitions (eV); *h* is Planck's constant (6.63 × 10⁻³⁴ Js); and *v* is the frequency of the light (s⁻¹). The values of band gaps were obtained from the absorption spectra at room temperature using a UV–Vis spectrophotometer (Figure 2). In all samples, the absorption edge was very sharp and was located at about 465 nm, 496 nm, and 563 nm for ZnSe, ZnSe:Eu³⁺Yb³⁺, and ZnSe:Eu³⁺, respectively. The obtained values were in quite good agreement with the literature reports [17,18]. In order to determine the values of the band gaps for the examined samples, we plotted the graph of $[\alpha hv]^2$ as a function of photon energy E = hv. Extrapolation of the linear part of the graph gives the values of the band gaps for all examined samples are presented in Table 1 and the procedure is shown for the ZnSe:Eu³⁺ sample in Figure 3.



Figure 2. Absorbance spectra of ZnSe (green line), ZnSe:Eu³⁺/Yb³⁺ (blue line), and ZnSe:Eu³⁺ (red line) at 300 K.

Temperature, K	Zn:Se:Eu ³⁺ , eV	Zn:Se:Eu ³⁺ /Yb ³⁺ , eV
15	2.225	2.562
25	2.216	2.554
50	2.228	2.562
75	2.250	2.551
100	2.249	2.549
150	2.234	2.548
200	2.211	2.515
300	2.201	2.492

Table 1. Values of the direct band gaps of samples at different temperatures by UV–Vis spectrophotometry and Kubelka–Munk theory.



Figure 3. Energy gap calculation plot for ZnSe:Eu³⁺ at 300 K. The circles represents the experimental values and the line is the extrapolation of the linear part.

From the results presented in Table 1, it is clear that the bandgap energy of the doped and co-doped semiconductors decreased compared with the host matrix ZnSe (2.67 eV). It is well known that impurities generate additional donor and acceptor levels in the host material, which can produce drastic changes in the optical behaviour and reduce the band-gap energy.

The Varshni semi empirical relation [19] describes the energy band gap variation as a function of temperature for a doped semiconductor with different rare earths:

$$E(T) = E_0(0) - \frac{\gamma T^2}{\beta + T}$$
 (2)

where $E_0(0)$ is the energy band gap value at T = 0 K; γ is a parameter related to the electronphonon interaction; T is the absolute temperature; and β is a parameter related to the Debye temperature. A routine to fit the experimental data to the Varshni semi empirical relation was developed using a genetic algorithm. All Varshni semi empirical relation parameters were obtained using the developed routine, and are listed in Table 2. The energy band gap dependence with the temperature for ZnSe:Eu³⁺ and ZnSe:Eu³⁺ /Yb³⁺ is shown in Figure 4.



Table 2. Values of the Varshni parameters obtained from the fitting of Equation (2).

Figure 4. Energy band gap variation as a function of temperature for $ZnSe:Eu^{3+}$ (green squares) and $ZnSe:Eu^{3+}/Yb^{3+}$ (red dots). The line represents a theoretical fitting with Equation (2).

3.2. Photoluminescence Measurements

The photoluminescence emission spectrum for pure ZnSe is shown in Figure 5. Two bands A and B are seen in the figure. The B band was centred around 610 nm at low temperatures and showed a slight shift to the lower wavelengths decreasing with temperature, as shown in Table 3. The band A was centred at 637 nm at low temperature. The theoretical fitting of these curves as a function of temperature for the two bands gives the following equations, respectively:

$$\lambda_A = 610.6 - 0.0247T \text{ (nm)}$$
(3)
$$\lambda_B = 636 + 0.09T - 0.001T^2 \text{ (nm)}$$

Table 3. Temperature dependence of the bands for ZnSe.

	Temperature								
18 K	25 K	50 K	75 K	100 K	150 K	200 K	Dered		
						Band			
610	В	609	609	609	613	608	В		
637	А	638	636	627	626	625	А		



Figure 5. Photoluminescence spectrum of pure ZnSe. A, B are the emission bands, the blue line represents the sum of bands A plus B. The excitation was performed at 457.9 nm.

Figure 6 shows the photoluminescence emission when the ZnSe semiconductor was doped with a single rare earth Eu³⁺. The emission spectrum was the same as pure ZnSe (Figure 5), but band B was more intense. Moreover, the temperature at which the photoluminescence was detectable was higher (250 K), as shown in Table 4. This is an expected result because of the additional photon energy supplied by donor–acceptor levels created with the inclusion of Eu³⁺ ions in the crystal, which enables more efficient pumping.



Figure 6. Photoluminescence bands of ZnSe doped with Eu³⁺. A, B are the emission bands, the blue line represents the sum of bands A and B.

	Temperature								
	18 K	25 K	50 K	75 K	100 K	150 K	200 K	250 K	Band
	λ (nm)								Dana
	613.5	612.7	612.5	612.4	612.3	612.3	612.3		В
	625.2	624.5	624.0	623.7	623.4	623.1	623.0	622.1	А
_									

Table 4. Temperature dependence of the bands for ZnSe:Eu³⁺.

Eu shows two valence states, trivalent (Eu³⁺) and divalent (Eu²⁺), in certain compounds. However, the co-existence of (Eu³⁺) and (Eu²⁺) is hard to deduce from the absorption measurements directly. In fact, the conduction band absorption edge was much more intense than the Eu absorption peaks, which makes the identification of Eu bands a very difficult task. Nevertheless, the variation in the valence states of the Eu ions tends to influence the emission properties. In this regard, the photoluminescence spectrum carries useful information on the valence state of Eu ions. In general, the emission spectrum should include a broad emission band and several sharp emission lines throughout the visible light region if the sample is excited at 310 nm. We observed only the sharp emission lines that peaked around 622 nm, which were attributed to the ⁵D₀ \rightarrow ⁷F₂ transition emissions of Eu³ ions incorporated in the ZnSe lattice. The samples were excited at 488 nm, and because of that, we did not observe the broad emission band positioned at 445 nm, which can be assigned to the 5d–4f transition emission of Eu²⁺ ions. Therefore, we cannot completely discard the eventual presence of Eu²⁺ in addition to Eu³⁺.

Interestingly, when this semiconductor was co-doped with the two rare earths (Eu^{3+} and Yb³⁺), the spectrum presented new narrow emissions (b, c, d) and more intense lines, as shown in Figures 7–9.

The emission spectrum of ZnSe co-doped Eu^{3+}/Yb^3 at 20 K is shown in Figure 7, which had characteristic bands belonging to the ZnSe and superimposed the narrow emission bands of the rare earths. Eliminating the ZnSe bands from the emission spectrum, the pure emission spectra of co-doped rare earths at the temperature of 20 K is shown in Figure 8 and at 200 K in Figure 9, respectively. The temperature dependence of the photoluminescence peak emission is shown in Table 5.



Figure 7. Photoluminescence spectrum of ZnSe co-doped with Eu^{3+}/Yb^{3+} at 20 K. a is the emission line of pure ZnSe and b, c, d are the new emission lines due to dopants.



Figure 8. Photoluminescence spectrum of ZnSe co-doped with Eu^{3+}/Yb^{3+} at 20 K without the ZnSe contribution. a is the emission line of pure ZnSe and b, c, d are the new emission lines due to dopants.



Figure 9. Photoluminescence spectrum of ZnSe co-doped with Eu^{3+}/Yb^{3+} at 200 K after eliminating the ZnSe bands. a is the emission line of pure ZnSe and b, C are the new emission lines due to dopants.

It is clear from the figures and Table 5 that the position of the bands remained fixed with temperature; however, their intensity was a function of temperature. The spectra exhibited narrow emission bands assigned according to Table 5. It can be seen from the results presented in this table that co-doping of the ZnSe semiconductor led to an enrichment of the photoluminescence spectrum. Moreover, the spectrum at low temperature clearly showed more emission peaks and at 20 K, was shifted to longer wavelengths (peak d in Figure 8). The peak b intensity increased with temperature, while in contrast, the peak c intensity decreased with temperature, as can be noted from Figures 8 and 9.

	Transition						
20 K	50 K	75 K	100 K	150 K	300 K		
		λ (nm)				ν (cm $^{-1}$)	
743.9						13.443	$^5D_0 \rightarrow {}^7F_5$ *
739.6						13.521	*
733.9						13.626	*
720.6	720.7	720.9	720.9	720.9		13.872	*
711.7	710.4	711.4	711.5	711.2	711.1	14.061	
707.3	708.8	709.3	709.2	708.9	708.9	14.106	${}^{5}\text{D}_{1} \rightarrow {}^{7}\text{F}_{6}$
	705.1	705.7	705.7	705.7	705.8	14.170	${}^{5}\text{D}_{1} \rightarrow {}^{7}\text{F}_{6}$
700.0	699.9	699.9	700.5	700.0	700.2	14.286	1 0
695.7		696.4	696.2	695.9	696	14.370	**
689.7	689.6	690.0	689.9	689.8	690	14.496	${}^{5}\text{D}_{0} \rightarrow {}^{7}\text{F}_{4}$ **
672.3		678.1	680.2	680.0	680.2	14.706	**
666.9		668.5	668.5	668.7	668.8	14.957	
660.4	661.9	661.8	661.8	661.7	661.5	15.113	${}^{5}\text{D}_{0} \rightarrow {}^{7}\text{F}_{3}$
657.6	657.5	657.6	657.6	657.7	657.8	15.205	${}^{5}\text{D}_{1} \rightarrow {}^{7}\text{F}_{5}$
610.3	610.3	610.4	610.0	610.2	610.2	16.388	${}^{5}\text{D}_{0} \rightarrow {}^{7}\text{F}_{2}$
604.8	604.7	604.3	604.8	604.7	604.7	16.537	${}^{5}\text{D}_{0} \rightarrow {}^{7}\text{F}_{1}$
	595.9	599.2				16.781	${}^{5}D_{2} \rightarrow {}^{7}F_{6}$
	544.4	544.0				18.368	2 0
	534.5	534.6				18.705	$^5D_1 \rightarrow {^7F_1}$

Table 5. Photoluminescence spectra and transition assignment for the ZnSe:Eu^{3+/}Yb³⁺ semiconductor. *, ** cubic crystal field splitting.

The energy value for the theoretical transitions shown in the photoluminescence spectrum can be described by the Hamiltonian equation for electrons with the $4f^N$ configuration. Two important assumptions were made: first, the electronic states were well separated from the other electronic states of the matrix; and second, the non-spherical crystal field contribution due to the matrix that surrounds the rare earth ion can be treated as a perturbation of the $4f^N$ ion configuration. Then, we can use the following Hamiltonian [20]:

$$H = H_F + H_{CF} = \sum_{i=2,4,6} F^i f_i + \xi_i A_{so} + \eta L(L+1) + \beta G(G_2) + \gamma G(G_7) + \sum_{i=2,3,4,6,8} T^i t^i + \sum_{i=0,2,4} M^i m^i + \sum_{i=2,4,6} P^i p^i + H_{CF}$$
(4)

The first part of the Hamiltonian H_F contains the contribution of the electrostatic repulsion between the 4f^N electrons in the trivalent ion configuration and the spin orbit couplings. This term represents the atomic (or free ion) contribution and H_{CF} the crystal field interactions. F^i and ξ_i are the electrostatic and spin–orbit integrals; f_i and A_{SO} are the angular parts of the electrostatic and spin–orbit interactions. η , β , and γ are parameters associated with the two body correction terms. $G(G_2)$ and $G(G_7)$ are Casimir's operators for the G_2 and G_7 groups, and L is the total orbital angular momentum [20].

Judd proposed the three particle configuration interaction terms [21], which arose from the perturbation effects of those configurations that differed from f^N in the quantum numbers of a simple electron. These terms can be represented as t_iT^i , where T^i are the parameters and t_i are three particle operators, and M^i represents the spin–spin and spin– other–orbit relativistic corrections. The parameters P^i represent electrostatically correlated spin–orbit perturbation, which involves the excitation of an f electron into a higher-lying f shell. The operators m^i and p^i are associated with the magnetically correlated corrections.

The corrections of the free ion including the crystal field were conducted using the crystal field theory [22]. The theoretical results and transition assignment, along with the experimental values, are given in Table 5. A good correlation between the experimental and theoretical values was found.

The rare earth ion Eu⁺³ has a regular ⁷F (⁷F₀–⁷F₆) multiplet as the ground level, followed by a ⁵D multiplet ⁵D₀–⁵D₂. The ground level was split in seven levels ⁷F₀–⁷F₆ by the crystal field, as shown in Figure 10. The 5D was also split into four levels by the crystal field and only three levels were observed due to the wavelength of the excitation laser. These splitting levels have new splitting levels, as reported in Figure 10. Dieke [23] provides a complete list of levels for known Stark levels for the anhydrous chloride and ethylsulfate crystals. The values reported in this work were in good agreement with the values reported by Dieke using a different matrix, but the same rare earth ions.



Figure 10. Energy level diagram for Eu³⁺/Yb³⁺ co-doped ZnSe semiconductors showing activity transitions and ground state field splitting.

The values assigned with asterisks (Table 5) correspond to the excited ion level to crystal field splitting levels of the ground state. Figure 10 shows that the experimental values corresponded to the exited ion levels to the eight-splitted 3H ground state.

Our results demonstrated that because of the Yb³⁺ co-doping, the semiconductor was able to generate emission lines with higher intensity. The mechanism involved in the energy transfer between Yb³⁺ and Eu³⁺ ions is still unclear and needs further theoretical analysis and calculations. However, one possible emission mechanism in the Eu³⁺/Yb³⁺ doped ZnSe semiconductor is presented in Figure 10. Yb³⁺ is often used as a co-doping ion since it has a single excited state ${}^{2}F_{5/2}$ with an energy difference to the ground state ${}^{2}F_{7/2}$ of 10,000 cm⁻¹ (1000 nm), which matched the phonon energy of the Eu³⁺ ion (>10,000 cm⁻¹) (Figure 10). In the so-called cross-relaxation process (I), Eu³⁺ ion, after being excited by 488 nm radiation, in the ${}^{5}D_{0}$ excited state, can transfer its energy to two Yb³⁺ ions mediated by phonons, as indicated in the Figure 10 [24]. However, the population of Eu³⁺ excited levels can be recovered again because of the cooperative energy transfer process (II) mediated by the pair of previously excited Yb³⁺ ions [25] according to the following relation:

$$2 \times Yb^{3+}({}^{2}F_{5/2}) + Eu^{3+}({}^{7}F_{0}) = 2 \times Yb^{3+}({}^{2}F_{5/2}) + Eu^{3+}({}^{5}D_{1})$$
(5)

The probability of this mechanism is very low; therefore, a second most probable enhancement emission mechanism could be related to the charge transferring between the Yb³⁺ and Eu³⁺ ions. In addition, the excitation wavelength (488 nm-2.54 eV) may also give rise to interband transitions (Eg~2.5 eV). Thus, energy transfer from the matrix itself should not be discarded. Collectively our results suggest that co-doping with Yb³⁺ enables one to enhance the emission efficiency, thus representing an important advantage if we compare it with other similar compounds that only contain Eu³⁺ [26–28].

4. Conclusions

In this study, we prepared and characterized a co-doped II–VI semiconductor ZnSe with one and two rare earths simultaneously. The values of optical band gaps and photoluminescence spectra were measured at different temperatures. The correlation between the theory and the experimental results was in good agreement. One important experimental fact is that the power of the laser used in the photoluminescence measurements was 10 mw, which indicated the quality of the single crystals, good quantum efficiency and show potential applications in the future. According to the presented results, the emission spectra of these materials give new narrow and very intense lines in the visible and near infrared region, and this fact could be used for the future development of efficient diode lasers and LEDs. The energy transfer mechanism from the Yb³⁺ to the Eu³⁺ ion in the ZnSe matrix is unclear and needs further analysis.

Author Contributions: Conceptualization and review, O.A.A. and K.H.I.; Methodology, H.C. and N.M.; Writing—original draft preparation, H.C.; Writing—review and editing, H.C., B.A.-N. and N.M.; Funding acquisition, N.M. and O.A.A.; Data curation, B.A.-N. and K.H.I.; Supervision, H.C. All authors have read and agreed to the published version of the manuscript.

Funding: The authors extend their appreciation to the Deanship of Scientific Research at Imam Mohammad Ibn Saud Islamic University for funding this work through Research Group no. RG-21-09-53.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: The data presented in this study are available on request from the corresponding author.

Acknowledgments: We acknowledge the funding received from the Deanship of Scientific Research at Imam Mohammad Ibn Saud Islamic University. The authors gratefully acknowledge Ahmed Alsadig (University of Trieste) for his kind assistance throughout this work.

Conflicts of Interest: The authors declare no conflict of interest.

References

- Georgobiani, A.N. The construction of light emitting diodes on the base of wide gap II–VI semiconductor compounds. *J. Lumin.* 1991, 48, 839–844. [CrossRef]
- Tetsuichiro, O.; Kawaguchi, Y.; Ohki, A.; Matsuoka, T. ZnCdSe/ZnSe Quantum-Well Laser Diode on a (711)A GaAs Substrate. Jpn. J. Appl. Phys. 1994, 33, 5766.
- 3. Haase, M.A.; Qiu, J.; DePuydt, J.M.; Cheng, H. Blue-green laser diodes. Appl. Phys. Lett. 1991, 59, 1272–1274. [CrossRef]
- Xie, W.; Grillo, D.C.; Gunshor, R.L.; Kobayashi, M.; Jaon, H.; Ding, J.; Nurmikko, A.V.; Hua, G.C.; Otauka, N. Room temperature blue light emitting *p-n* diodes from Zn(S,Se)-based multiple quantum well structures. *Appl. Phys. Lett.* 1992, 60, 1999–2001. [CrossRef]
- Aggarwal, R.L.; Maki, P.A.; Molnar, R.J.; Liau, Z.L.; Melngailis, I. Optically pumped GaN/Al0.1Ga0.9N double-heterostructure ultraviolet laser. J. Appl. Phys. 1995, 79, 2148–2150. [CrossRef]
- Nakamura, S.; Senoh, M.; Mukai, T. High-power lnGaN/GaN double-heterostructure violet light emitting diodes. *Appl. Phys. Lett.* 1993, 62, 2390–2392. [CrossRef]
- Zhang, L.; Zhang, C.Y.; Wei, Z.Y.; Zhang, C.; Long, Y.B.; Zhang, Z.G.; Zhang, H.J.; Wang, J.Y. Compact Diode-Pumped Continuous-Wave Nd:LuVO₄ Lasers Operated at 916 nm and 458 nm. *Chin. Phys. Lett.* 2006, 23, 1192.
- Ponce, F.A.; Bour, D.P. Nitride-based semiconductors for blue and green light-emitting devices. *Nature* 1997, 386, 351–359.
 [CrossRef]
- Schmidt, T.; Muller, G.; Spanhel, L. Activation of 1.54 μm Er³⁺ Fluorescence in Concentrated II-VI Semiconductor Cluster Environments. *Chem. Mater.* 1998, 10, 65–71. [CrossRef]
- 10. Ivashchenko, M.M.; Opanasyuk, A.S.; Buryk, I.P.; Lutsenko, V.A.; Shevchenko, A.V. Optical Properties of Pure and Eu Doped ZnSe Films Deposited by CSVS Technique. *J. Nano-Electron. Phys.* **2017**, *9*, 01011-1–01011-5. [CrossRef]
- 11. Radevici, I.; Sushkevich, K.; Sirkeli, V.; Huhtinen, H.; Nedeogl, D.; Paturi, P. Luminescent properties of the ZnSe:Yb crystals in the visible spectral range. *J. Lumin.* **2013**, *143*, 275–279. [CrossRef]
- 12. Brown, M.R.; Cox, A.F.J.; Shand, W.A.; Williams, J.M. Defect configuration for rare earth ions in zinc selenide. *J. Phys. C Solid State Phys.* **1971**, *4*, 2550. [CrossRef]

- 13. Triboulet, R.; Rabago, F.; Legros, R.; Lozykowski, H.; Didier, D. Low-temperature growth of ZnSe crystals. *J. Cryst. Growth.* **1982**, 59, 172–177. [CrossRef]
- 14. Nasiri, S.; Hosseinnezhad, M.; Rabiei, M.; Palevicius, A.; Janusas, G. The effect of calcination temperature on the photophysical and mechanical properties of copper iodide (5 mol%)–doped hydroxyapatite. *Opt. Mater.* **2021**, 121, 111559. [CrossRef]
- Nasiri, S.; Dashti, A.; Hosseinnezhad, M.; Rabiei, M.; Palevicius, A.; Doustmohammadi, A.; Janusas, G. Mechanochromic and thermally activated delayed fluorescence dyes obtained from D–A–D' type, consisted of xanthen and carbazole derivatives as an emitter layer in organic light emitting diodes. *Chem. Eng.* 2022, 430, 131877. [CrossRef]
- 16. Murphy, A.B. Band-gap determination from diffuse reflectance measurements of semiconductor films, and application to photoelectrochemical water-splitting. *Sol. Energy Mater. Sol. Cells* **2007**, *91*, 1326–1337. [CrossRef]
- 17. Allegretti, F.; Carrara, A.; Pizzini, S. Growth and characterization of ZnSe for low temperature calorimetry applications. *J. Crystal Growth* **1993**, *128*, 646–649. [CrossRef]
- Hile, D.D.; Swart, H.C.; Motloung, S.V.; Motaung, T.E.; Kroon, R.E.; Egbo, K.O.; Pawade, V.B.; Koao, L.F. Synthesis and characterization of europium doped zinc selenide thin films prepared by photo-assisted chemical bath technique for luminescence application. *Mater. Chem. Phys.* 2021, 262, 124303. [CrossRef]
- 19. Varshni, Y.P. Temperature dependence of the energy gap in semiconductors. *Physica* 1967, 34, 149–154. [CrossRef]
- Carnall, W.T.; Goodman, G.L.; Rajnak, K.; Rana, R.S. A systematic analysis of the spectra of the lanthanides doped into single crystal LaF₃. J. Chem. Phys. 1989, 90, 3443–3457. [CrossRef]
- 21. Judd, B.R. Three-particle operators for equivalent electrons. Phys. Chem. Rev. 1966, 141, 4–14. [CrossRef]
- 22. Hufner, S. Optical Spectra of Transparent Rare Earths Compounds; Academic Press: New York, NY, USA, 1978.
- 23. Dieke, G.H. Spectra and Energy Levels of Rare Earth Ions in Crystals; Crosswhite, H.M., Ed.; Wiley: New York, NY, USA, 1968.
- 24. Nato, Y.; Shigeo, S.; Takashi, K. Phonon-assisted energy transfer between trivalent Rare Earth ions. J. Phys. Soc. Jap. 1972, 32, 1577.
- 25. Loiko, P.A.; Rachkovskaya, G.E.; Zakharevich, G.B.; Kornienko, A.A.; Dunina, E.B.; Yasukevich, A.S.; Yumashev, K.V. Cooperative up–conversion in Eu³⁺, Yb³⁺ doped SiO₂–PbO–PbF₂–CdF₂ oxyfluoride glass. *J. Non-Cryst. Solids* **2014**, 392, 39–44. [CrossRef]
- Ekambarama, S.; Maaza, M. Combustion synthesis and luminescent properties of Eu³⁺-activated cheap red phosphors. J. Alloys Compd. 2005, 395, 132–134. [CrossRef]
- Mohamed, H.E.A.; Hkiri, K.; Khenfouch, M.; Dhlamini, S.; Henini, M.; Maaza, M. Optical properties of biosynthesized nanoscaled Eu₂O₃ for red luminescence applications. *JOSA B* 2020, *37*, C73–C79. [CrossRef] [PubMed]
- Ekambaram, S.; Patil, K.C.; Maaza, M. Synthesis of lamp phosphors: Facile combustion approach. J. Alloys Compd. 2005, 393, 81--92. [CrossRef]