Article

Charging Effect by Fluorine-Treatment and Recess Gate for Enhancement-Mode on AlGa_N/Ga_N High Electron Mobility Transistors

Soo Cheol Kang ^{1,*} , Hyun-Wook Jung ¹, Sung-Jae Chang ¹, Seung Mo Kim ², Sang Kyung Lee ², Byoung Hun Lee ², Haechon Kim ¹, Youn-Sub Noh ¹, Sang-Heung Lee ¹, Seong-Il Kim ¹, Ho-Kyun Ahn ¹ and Jong-Won Lim ¹

¹ DMC Convergence Research Department, Electronics and Telecommunications Research Institute (ETRI), Daejeon 34129, Korea; hujung@etri.re.kr (H.-W.J.); sjchang@etri.re.kr (S.-J.C.); khc@etri.re.kr (H.K.); nohys@etri.re.kr (Y.-S.N.); shl@etri.re.kr (S.-H.L.); sikim@etri.re.kr (S.-I.K.); hkahn@etri.re.kr (H.-K.A.); jwlim@etri.re.kr (J.-W.L.)

² Center for Emerging Electronic Devices and Systems (CEEDS), Gwangju Institute of Science and Technology (GIST), Gwangju 61005, Korea; kims2110@gist.ac.kr (S.M.K.); leeskgist@gist.ac.kr (S.K.L.); bhl@gist.ac.kr (B.H.L.)

* Correspondence: kangsc817@etri.re.kr; Tel.: +82-(0)42-860-5932

Received: 7 October 2020; Accepted: 22 October 2020; Published: 24 October 2020

Abstract: An enhancement-mode AlGa_N/Ga_N metal-insulator-semiconductor high-electron-mobility-transistor was fabricated using a recess gate and CF₄ plasma treatment to investigate its reliable applicability to high-power devices and circuits. The fluorinated-gate device showed hysteresis during the DC current-voltage measurement, and the polarity and magnitude of hysteresis depend on the drain voltage. The hysteresis phenomenon is due to the electron trapping at the Al₂O₃/AlGa_N interface and charging times longer than milliseconds were obtained by pulse I-V measurement. In addition, the subthreshold slope of the fluorinated-gate device was increased after the positive gate bias stress because of the two-dimensional electron gas reduction by ionized fluorine. Our systematic observation revealed that the effect of fluorine ions should be considered for the design of AlGa_N/Ga_N power circuits.

Keywords: AlGa_N/Ga_N HEMTs; enhancement-mode; fluorinated-gate; recessed gate

1. Introduction

AlGa_N/Ga_N high electron mobility transistors (HEMTs) have recently demonstrated to be excellent devices for high-frequency and high-power electronics, thanks to the high breakdown voltage [1] and the low on-state resistance [2] and gate leakage [3]. The AlGa_N/Ga_N HEMTs show normally on operation, since the two-dimensional electron gas (2DEG) channel is generated by the spontaneous and piezoelectric polarization at the AlGa_N/Ga_N hetero-interface [4]. Various methods for enhancement mode (E-mode) device manufacturing through modulating the threshold voltage (V_T) have been studied for the reduction in power consumption and circuit producing, such as an inverter using a depletion mode (D-mode) and an E-mode device [5–9]. The AlGa_N barrier recess and fluorine ion implantation methods had been widely studied to shift the V_T in the positive direction.

Although these methods modulate the V_T , the gate modifications introduce side effects resulting from the surface damage during the device fabrication process [10–12], and the electrical and frequency characteristics are degraded due to the poor interface conditions [13]. Various methods have been studied to improve the recessed interface condition [14,15]. However, hysteresis and V_T instability remain critical issues so far. In this perspective, it is necessary to better understand the

degradation mechanisms and the trends of changing electrical properties related to charge trapping for reliable application.

In this study, the V_T was modulated by the gate recess and fluorine treatment employing CF_4 plasma. The fluorinated-gate device (7-nm thick gate recess + fluorine plasma treatment) exhibited more positive-shifted V_T compared to the recess only gate device (7-nm thick gate recess). However, hysteresis of the fluorinated-gate device occurred during the DC current-voltage (I-V) measurement and the hysteresis depended on drain voltage (V_D). We demonstrated that the cause of hysteresis was the charge trapping/detrapping effect introduced at the dielectric (Al_2O_3) and fluorinated AlGaIn interface and gate leakage characteristics corresponding to V_D . The increase in the subthreshold slope (SS) of the fluorinated-gate device after positive gate bias stress indicated the degradation in the AlGaIn/GaN interface and the decrease in 2DEG density. As a result, we have revealed the effect of fluorine treatment on the dielectric/AlGaIn and AlGaIn/GaN interfaces through experimental evidence.

2. Device Fabrication and Electrical Characterization

The AlGaIn/GaN heterostructure was grown by metal-organic chemical vapor deposition (MOCVD) on a sapphire substrate, which consists of a 21-nm AlGaIn (26% Al) barrier with a 2-nm GaN cap layer. The Ti/Al/Ni/Au ohmic contact was formed by an E-beam evaporator and annealed at 900 °C for 150 s. After device isolation via phosphorus implantation, a 50-nm SiN passivation layer was deposited by plasma-enhanced chemical vapor deposition (PECVD).

Subsequently, the gate recess area was defined by electron-beam (E-beam) lithography and then the SiN was removed via an inductively-coupled plasma (ICP) etch. In order to obtain the etch rate of the gate region using a digital etch process, O_2 plasma ashing (3 min) and 1:10 hydrochloric acid (HCl) dipping (1 min) were repeated 15 times in the test sample. An etch rate of 6.6 Å/cycle was obtained (in Figure 1a). The digital etches of 10 and 21 cycles were conducted with the same etch condition and each device had an etch depth of about 7 and 14 nm. For the fabrication of fluorinated-gate devices, CF_4 plasma using reactive ion etching (RIE) was carried out for 30 s on the 7-nm recessed device. After that, Al_2O_3 with the thickness of 10 nm was deposited at 300 °C by atomic layer deposition (ALD). A T-shaped Ni/Au gate electrode was deposited by an E-beam evaporator. D-mode metal-insulator-semiconductor HEMTs (MIS-HEMTs) without gate recess and fluorine treatment were also prepared as a reference device. Figure 1b illustrates the cross-sectional view of the fabricated E-mode Al_2O_3 /AlGaIn/GaN MIS-HEMTs with a recessed gate. The fabricated device geometries are $L_G = 0.25 \mu m$, $W_G = 50 \mu m$, $L_{GD} = 3.5 \mu m$ and $L_{GS} = 1 \mu m$. The DC I-V, pulse I-V measurement and stress application (for repetition of stress and measurement) were performed using a Keithley 4200-SCS parameter analyzer. The delay between the stress and measurement was less than tens of milliseconds. Capacitance of the device was measured using an Agilent 4294A impedance analyzer. The voltage was applied to the gate while the source and drain were grounded.

Figure 1. The fabricated AlGaIn/GaN MIS-HEMTs on sapphire substrate. Recessed gate was formed under gate region for V_T modulation. (a) The TEM image of the recessed gate. The AlGaIn layer was etched by the digital etch process in 15 cycles. (b) Schematic cross-section of the processed device. (c) Band diagram of MIS-HEMTs under equilibrium condition. (d) Band diagram of MIS-HEMTs after CF_4 treatment under equilibrium condition.

3. Results and Discussion

Figure 2 shows the I-V transfer curves and transconductance (g_m) of AlGaIn/GaN MIS-HEMTs with various gate condition. The V_T moves in the positive direction from the V_T of D-MIS-HEMT after the 7-nm gate recess and fluorine treatment, and the V_T further shifted after the 14-nm gate recess. The V_T depends on the barrier thickness, since the 2DEG concentration and electron mobility reduce with the decrease in AlGaIn barrier thickness [16]. The fluorine treatment modulates the V_T by incorporating negatively charged fluorine ions into the AlGaIn barrier. As a result, the V_T of D-MIS-HEMT, 7-nm recess, 7-nm recess + CF_4 and 14-nm recess were -6.5 , -5.2 , -2.5 and $+0.5$ V, respectively. The V_T can be expressed as an Equation (1) [17]. The t_b denotes the barrier thickness, ϕ_b is the barrier height, q is the electron charge, σ_p is the 2DEG sheet charge density, N_F is the density of ionized fluorine atoms, X_F is the triangular fluorine ion distribution peaked at the surface and extending to a given depth and ϵ and ΔE_c are the dielectric constant and conduction band offset, respectively.

$$V_T = \phi_b - \left[\frac{q \left(\sigma_p t_b - \frac{N_F X_F^2}{6} \right)}{\epsilon} \right] - \Delta E_c \quad (1)$$

However, the g_m of the 7-nm recess + CF_4 device decreased sharply after maximum value in comparison with other devices. It is attributed to the electron trap in the AlGaIn barrier under the gate region by the fluorine treatment [18]. The 7-nm recess + CF_4 device shows hysteresis and it depends on the V_D , as shown in Figure 3a. The characteristics of recessed gate (7-nm recess) and fluorinated-gate devices (7 nm-recess + CF_4) were discussed to compare the fluorine treatment effect. For the hysteresis and V_D effect observation, the V_G increased in the forward direction (from the off-state to the on-state) and then decreased again in the reverse direction (from the on-state to the off-state) during the DC

I-V measurement for various V_D . When the V_D is increased from 1 V to 10 V and returned to 1 V, the hysteresis magnitudes ($V_{\text{Hysteresis}}$) are almost symmetric. The $V_{\text{Hysteresis}}$ is the V_G difference at a specific I_D ($= 1 \times 10^{-7}$ A/mm). It shows that the DC I-V measurement does not cause permanent charging. However, when the V_D is higher than 5 V, the direction of hysteresis becomes negative and the $V_{\text{Hysteresis}}$ enlarges with increasing V_D , as shown in Figure 3c. On the contrary, when the V_D is lower than 5 V, the direction of hysteresis is positive and the $V_{\text{Hysteresis}}$ is relatively small. The negligible hysteresis of recessed gate device without fluorine treatment was achieved (Figure 3b,d).

Figure 2. The I-V transfer curves (solid line) and transconductance (open circle line) of AlGaIn/GaN MIS-HEMTs with various gate conditions at $V_D = 10$ V. Black, blue, red and pink colors indicate the D-mode device, 7-nm gate recessed, 7-nm gate recessed and CF_4 treatment and 14-nm gate recessed device, respectively.

Figure 3. (a,b) The I-V hysteresis curves of 7-nm recess + CF_4 and 7-nm recess devices measured at $V_D = 2$ V and 8 V, respectively. The solid line and circle line indicate the forward and reverse sweep, respectively. (c,d) The voltage difference of 7-nm recess + CF_4 and 7-nm recess devices by hysteresis at various V_D . Red and blue regions show the positive and negative direction of hysteresis, respectively.

The V_D dependence of hysteresis in the fluorinated-gate device was investigated in more detail by comparing the gate leakage current (I_G) as a function of V_D in Figure 4a, and the band diagram and I_G flow direction are represented in Figure 4b. The I_G also depends on the V_D , and when the V_D is larger than 6 V, the polarity of the I_G is negative. This means that the electrons are trapped in the Al_2O_3 /fluorinated-AlGaIn barrier as they move from the gate metal to the channel along the I_G ,

and the V_T is negatively shifted. However, when the V_D is in between -2 V and 6 V, the polarity of I_G is positive, showing that some of electrons are detrapped from the Al_2O_3 /fluorinated-AlGa N barrier to the gate metal and the V_T is slightly shifted to the positive direction.

Figure 4. (a) The gate leakage current of the 7-nm recess + CF_4 device for various V_D . The solid lines and open circles reflect the increase in V_D and decrease of V_D , respectively. (b) The band diagram of the 7-nm recess + CF_4 device. The blue and red arrows indicate the flow of gate current. The trapped charges at the dielectric/AlGa N interface reduce by positive gate current ($V_D < 5$ V) and the trapped charges increase by negative gate current ($V_D > 5$ V).

The charging time in the Al_2O_3 /fluorinated-AlGa N barrier was studied through a triangular pulse I-V measurement with rising (t_R) and falling time (t_F) of 1 millisecond (ms). As shown in Figure 5a, the hysteresis and the V_D dependence of V_T were obtained only in the fluorinated-gate device, whereas insignificant hysteresis was achieved for pulse I-V measurements, and the V_T is hardly changed with V_D (Figure 5c). However, the transfer curve of recessed gate devices is almost identical regardless of the pulse I-V measurement (Figure 5b,d). Therefore, it implies that the electron trapping/detrapping in the Al_2O_3 /fluorinated-AlGa N barrier is a very slow charging mechanism and the trapping/detrapping time is longer than ms.

To investigate the effect of fluorine in AlGa N under the gate bias stress, negative (-2 V) and positive ($+2$ V) gate bias stresses were applied to devices. Although the V_T of devices is different, the same stress voltage was introduced to compare the effect of the stress polarity (Figure 6). The V_D of 5 V was used as a condition to monitor the electrical characteristics of the devices and to minimize the charging effects that occurred during DC I-V measurements. The direction of V_T shift under the negative gate bias stress is negative; by contrast, the positive direction of V_T shift under the positive gate bias stress is positive, and this phenomenon is the same for both devices. It indicates the trapping (or detrapping) of electrons under the negative (or positive) gate bias stress at the AlGa N /Ga N barrier. The different directions of V_T shift under negative and positive gate bias stress have been analyzed with the same mechanism in many other studies [19–21]. However, in the fluorinated-gate device, the V_T moved more, even under other stress conditions ($V_{\text{stress}} = V_T + 1.0$ V and $V_{\text{stress}} = +0.5, +1.0$ V), as shown in Figure 7a,b, due to the plasma-induced surface damage of the AlGa N barrier during fluorine treatment. In addition, the SS of the fluorinated-gate device is higher than that of the recessed gate device before stress. This indicates a higher interface state and is further evidence of the AlGa N surface damage caused by the CF_4 plasma process. Furthermore, the SS of the fluorinated-gate device increased with stress time under the positive gate bias stress, whereas the SS of the recessed gate device without fluorine hardly changed with stress time, even under negative and positive gate bias stress. To observe in more detail, the change in SS is represented in Figure 7c,d. There are two possible origins of the SS increase after gate bias stress. One is the 2DEG reduction. The accelerated electrons from the channel under the positive gate bias stress induce the ionization of fluorine in the AlGa N barrier [22], and the ionized fluorine atoms are capable of forming bonds with gallium atoms with dangling bonds at the interface. The formation of Ga–F bonds is able to weaken the 2DEG channel and AlGa N /Ga N interface [23].

Another is the degradation of the AlGaIn/GaN interfacial layer by accelerated electrons under positive gate bias stress. For metal-oxide-semiconductor field-effect transistors (MOSFETs), the increase in SS primarily reflects the degradation of the interfacial layer [24,25]. However, the recessed gate device without fluorine did not show an SS change, even under the positive gate bias stress. Therefore, the Ga–F bonding mechanism makes more sense than the interface degradation.

Figure 5. (a,b) The dual swept DC I-V transfer curve of 7-nm recess + CF_4 and 7-nm recess devices measured at various V_D . (c,d) Pulsed I-V curve of 7-nm recess + CF_4 and 7-nm recess devices measured for various V_D . The rising and falling time of 1 ms was used for pulse measurement.

Figure 6. (a,b) The change in I-V transfer curves of the 7-nm recess + CF_4 device under negative and positive gate bias stress conditions according to stress time, respectively. (c,d) The change in I-V transfer curves of the 7-nm recess device under negative and positive gate bias stress conditions, respectively.

Figure 7. The V_T shift by gate bias stress according to stress time. A (a) negative ($V_T + 1.0$ V) and (b) positive gate bias stress were applied to the devices. The red and black circle line indicate the 7-nm recess + CF_4 and 7-nm recess devices, respectively. (c,d) The change in the subthreshold slope for various gate bias stress corresponding to the stress time. The negative biases near the V_T and positive bias at 1.0 V and 2.0 V were used to estimate the degradation phenomenon.

The capacitance–voltage (C–V) curve was measured before and after positive gate bias stress at 1 MHz, as shown in Figure 8a, and the C–V curve moved to a positive direction and the slope of the C–V curve lowered. AlGaIn/GaN interface degradation and reduction in 2DEG after positive gate bias stress is also shown. We represent the schematic degradation model of fluorinated-gate device in Figure 8b. At the $\text{Al}_2\text{O}_3/\text{AlGaIn}$ interface, the trapped charges in the border trap site and/or interface state induce hysteresis during DC I–V measurement. The fluorine ions ionized by accelerated electrons by positive gate bias, and formation of the Ga–F bonds induces the reduction in 2DEG at the AlGaIn/GaN barrier.

Figure 8. (a) The change in capacitance of the 7-nm recess + CF_4 device before and after positive gate bias stress for 1000 s. The closed circle and opened circle indicate the capacitance before and after stress, respectively. (b) Schematic representation of the model used to explain the V_T shift of the 7-nm recess + CF_4 device. The black circle and red X represent the border traps and interface states, respectively.

4. Conclusions

An E-mode AlGaIn/GaN HEMT was fabricated employing a gate recess and CF₄ plasma treatment, and the effect of fluorine in the device was investigated using an analysis of electrical characteristics. The fluorinated-gate device showed hysteresis during DC I-V measurement, which depends on the V_D. The pulse I-V measurement was used to observe the charge trapping/detrapping effect of fluorine, and the charging time is longer than a few ms. It was also figured out that the SS of the fluorinated-gate device increased due to the 2DEG reduction by fluorine ions and the formation of Ga-F bonds after positive gate bias stress. We highlight that the impact of fluorine ions should be taken into account for circuit design when the E-mode device is employed.

Author Contributions: Conceptualization and formal analysis and writing, S.C.K.; device fabrication, H.-W.J.; validation, writing—review, investigation and editing, H.-W.J., S.-J.C., H.-K.A. and J.-W.L.; characterization support, S.M.K., S.K.L. and B.H.L.; data analysis, S.K.L., H.K., Y.-S.N., S.-H.L. and S.-I.K.; funding acquisition, H.-K.A. and J.-W.L. All authors have read and agreed to the published version of the manuscript.

Funding: This work was supported by the National Research Council of Science and Technology (NST) grant by the Korean government (MSIT) (No. CRC-19-02-ETRI).

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Dora, Y.; Chakraborty, A.; McCarthy, L.; Keller, S.; Denbaars, S.P.; Mishra, U.K. High Breakdown Voltage Achieved on AlGaIn/GaN HEMTs With Integrated Slant Field Plates. *IEEE Electron Device Lett.* **2006**, *27*, 713–715. [\[CrossRef\]](#)
2. Moens, P.; Banerjee, A.; Uren, M.J.; Meneghini, M.; Karboyan, S.; Chatterjee, I.; Vanmeerbeek, P.; Căsar, M.; Liu, C.; Salih, A.; et al. Impact of buffer leakage on intrinsic reliability of 650V AlGaIn/GaN HEMTs. In Proceedings of the 2015 IEEE International Electron Devices Meeting (IEDM), Washington, DC, USA, 7–9 December 2015; pp. 35.2.1–35.2.4.
3. Ando, Y.; Kaneki, S.; Hashizume, T. Improved operation stability of Al₂O₃/AlGaIn/GaN MOS high-electron-mobility transistors grown on GaN substrates. *Appl. Phys. Express* **2019**, *12*, 024002. [\[CrossRef\]](#)
4. Sippel, J.C.; Islam, S.S.; Mukhejee, S.S. A physics-based analytical model of a GaN/AlGaIn HEMT incorporating spontaneous and piezoelectric polarization. In Proceedings of the Canadian Conference on Electrical and Computer Engineering 2004 (IEEE Cat. No.04CH37513), Niagara Falls, ON, Canada, 2–5 May 2004; Volume 3, pp. 1401–1404.
5. Chiu, H.-C.; Yang, C.-W.; Chen, C.-H.; Fu, J.S.; Chien, F.-T. Characterization of enhancement-mode AlGaIn/GaN high electron mobility transistor using N₂O plasma oxidation technology. *Appl. Phys. Lett.* **2011**, *99*, 153508. [\[CrossRef\]](#)
6. Palacios, T.; Suh, C.-S.; Chakraborty, A.; Keller, S.; DenBaars, S.P.; Mishra, U.K. High-performance E-mode AlGaIn/GaN HEMTs. *IEEE Electron Device Lett.* **2006**, *27*, 428–430. [\[CrossRef\]](#)
7. Majumdar, S.; Sahu, C.; Biswas, D. Fabrication of E-mode InGaIn/AlGaIn/GaN HEMT using FIB based lithography. In Proceedings of the 2017 IEEE Electron Devices Technology and Manufacturing Conference (EDTM), Toyama, Japan, 28 February–2 March 2017; pp. 175–177.
8. Lee, F.; Su, L.-Y.; Wang, C.-H.; Wu, Y.-R.; Huang, J. Impact of Gate Metal on the Performance of p-GaN/AlGaIn/GaN High Electron Mobility Transistors. *IEEE Electron Device Lett.* **2015**, *36*, 232–234. [\[CrossRef\]](#)
9. Dutta Gupta, S.; Soni, A.; Joshi, V.; Kumar, J.; Sengupta, R.; Khand, H.; Shankar, B.; Mohan, N.; Raghavan, S.; Bhat, N.; et al. Positive Threshold Voltage Shift in AlGaIn/GaN HEMTs and E-Mode Operation By Al_xTi_{1-x}O Based Gate Stack Engineering. *IEEE Trans. Electron Devices* **2019**, *66*, 2544–2550. [\[CrossRef\]](#)
10. Wu, T.-L.; Franco, J.; Marcon, D.; De Jaeger, B.; Bakeroot, B.; Stoffels, S.; Van Hove, M.; Groeseneken, G.; Decoutere, S. Toward Understanding Positive Bias Temperature Instability in Fully Recessed-Gate GaN MISFETs. *IEEE Trans. Electron Devices* **2016**, *63*, 1853–1860. [\[CrossRef\]](#)
11. Lagger, P.; Ostermaier, C.; Pobegen, G.; Pogany, D. Towards understanding the origin of threshold voltage instability of AlGaIn/GaN MIS-HEMTs. In Proceedings of the 2012 International Electron Devices Meeting, San Francisco, CA, USA, 10–13 December 2012; pp. 13.1.1–13.1.4.

12. Kim, K.-W.; Jung, S.-D.; Kim, D.-S.; Kang, H.-S.; Im, K.-S.; Oh, J.-J.; Ha, J.-B.; Shin, J.-K.; Lee, J.-H. Effects of TMAH Treatment on Device Performance of Normally Off Al₂O₃/GaN MOSFET. *IEEE Electron Device Lett.* **2011**, *32*, 1376–1378. [\[CrossRef\]](#)
13. Jung, H.-W.; Chang, S.-J.; Do, J.-W.; Ahn, H.-K.; Cho, K.-J.; Kim, J.-J.; Kim, S.-I.; Min, B.-G.; Kim, H.; Yoon, H.S.; et al. DC and RF Characteristics of Enhancement-Mode Al₂O₃/AlGaIn/GaN MIS-HEMTs Fabricated by Shallow Recess Combined with Fluorine-Treatment and Deep Recess. *ECS J. Solid State Sci. Technol.* **2018**, *7*, 197–200. [\[CrossRef\]](#)
14. Wang, Y.; Wang, M.; Xie, B.; Wen, C.P.; Wang, J.; Hao, Y.; Wu, W.; Chen, K.J.; Shen, B. High-Performance Normally-Off Al₂O₃/GaIn MOSFET Using a Wet Etching-Based Gate Recess Technique. *IEEE Electron Device Lett.* **2013**, *34*, 1370–1372. [\[CrossRef\]](#)
15. Li, S.; Hu, Q.; Wang, X.; Li, T.; Li, X.; Wu, Y. Improved Interface Properties and Dielectric Breakdown in Recessed AlGaIn/GaN MOS-HEMTs Using HfSiO_x as Gate Dielectric. *IEEE Electron Device Lett.* **2019**, *40*, 295–298. [\[CrossRef\]](#)
16. Zhao, Y.; Wang, C.; Zheng, X.; Ma, X.; He, Y.; Liu, K.; Li, A.; Peng, Y.; Zhang, C.; Hao, Y. Effects of recess depths on performance of AlGaIn/GaN power MIS-HEMTs on the Si substrates and threshold voltage model of different recess depths for the using HfO₂ gate insulator. *Solid State Electron.* **2020**, *163*, 107649. [\[CrossRef\]](#)
17. Klein, B.A.; Douglas, E.A.; Armstrong, A.M.; Allerman, A.A.; Abate, V.M.; Fortune, T.R.; Baca, A.G. Enhancement-mode Al_{0.85}Ga_{0.15}N/Al_{0.7}Ga_{0.3}N high electron mobility transistor with fluorine treatment. *Appl. Phys. Lett.* **2019**, *114*, 112104. [\[CrossRef\]](#)
18. Du, J.; Chen, N.; Jiang, Z.; Bai, Z.; Liu, Y.; Liu, Y.; Yu, Q. Study on transconductance non-linearity of AlGaIn/GaN HEMTs considering acceptor-like traps in barrier layer under the gate. *Solid State Electron.* **2016**, *115*, 60–64. [\[CrossRef\]](#)
19. Meneghini, M.; Rossetto, I.; Bisi, D.; Ruzzarin, M.; Van Hove, M.; Stoffels, S.; Wu, T.-L.; Marcon, D.; Decoutere, S.; Meneghesso, G.; et al. Negative Bias-Induced Threshold Voltage Instability in GaN-on-Si Power HEMTs. *IEEE Electron Device Lett.* **2016**, *37*, 474–477. [\[CrossRef\]](#)
20. Guo, A.; del Alamo, J.A. Unified Mechanism for Positive- and Negative-Bias Temperature Instability in GaN MOSFETs. *IEEE Trans. Electron Devices* **2017**, *64*, 2142–2147. [\[CrossRef\]](#)
21. Cheng, L.; Xu, W.; Pan, D.; Liang, H.; Wang, R.; Zhu, Y.; Ren, F.; Zhou, D.; Ye, J.; Chen, D.; et al. Gate-first AlGaIn/GaN HEMT technology for enhanced threshold voltage stability based on MOCVD-grown in situ SiNx. *J. Phys. Appl. Phys.* **2020**. [\[CrossRef\]](#)
22. Ma, C.; Chen, H.; Zhou, C.; Huang, S.; Yuan, L.; Roberts, J.; Chen, K.J. ON-state critical gate overdrive voltage for fluorine-implanted enhancement-mode AlGaIn/GaN high electron mobility transistors. *J. Appl. Phys.* **2011**, *110*, 114514. [\[CrossRef\]](#)
23. Huang, S.; Chen, H.; Chen, K.J. Effects of the fluorine plasma treatment on the surface potential and Schottky barrier height of Al_xGa_{1-x}N/GaN heterostructures. *Appl. Phys. Lett.* **2010**, *96*, 233510. [\[CrossRef\]](#)
24. Kang, S.C.; Kim, S.M.; Jung, U.; Kim, Y.; Park, W.; Lee, B.H. Interface state degradation during AC positive bias temperature instability stress. *Solid State Electron* **2019**, *158*, 46–50. [\[CrossRef\]](#)
25. Cho, M.; Roussel, P.; Kaczer, B.; Degraeve, R.; Franco, J.; Aoulaiche, M.; Chiarella, T.; Kauerauf, T.; Horiguchi, N.; Groeseneken, G. Channel Hot Carrier Degradation Mechanism in Long/Short Channel Si/Si-Ge FinFETs. *IEEE Trans. Electron Devices* **2013**, *60*, 4002–4007. [\[CrossRef\]](#)

Publisher’s Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.

© 2020 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).