

Characteristics of Cellulose Nanofibrils from Transgenic Trees with Reduced Expression of Cellulose Synthase Interacting 1

Simon Jonasson ¹, Anne Bündler ², Linn Berglund ¹, Totte Niittylä ² and Kristiina Oksman ^{1,3,4,*}

¹ Division of Materials Science, Luleå University of Technology, 97187 Luleå, Sweden

² Umeå Plant Science Centre, Department of Forest Genetics and Plant Physiology, Swedish University of Agricultural Sciences, 90183 Umeå, Sweden

³ Mechanical & Industrial Engineering, University of Toronto, Toronto, ON M5S 3G8, Canada

⁴ Wallenberg Wood Science Centre (WWSC), Luleå University of Technology, 97187 Luleå, Sweden

* Correspondence: kristiina.oksman@ltu.se

Table S1. Chemical composition of wood cell wall [1].

Tree ID	Total lignin [%]	Hemicelluloses [%]	Cellulose [%]
WT	21.5 (±0.5)	21.4 (±1.0)	40.1 (±0.7)
T1	20.2 (±0.5)	19.2 (±1.1)	37.1 (±0.3)
T2	20.5 (±1.1)	20.3 (±1.5)	40.4 (±1.0)

Reference

- Bündler, A.; Sundman, O.; Mahboubi, A.; Persson, S.; Mansfield, S.D.; Rüggeberg, M.; Niittylä, T. Cellulose synthase interacting 1 is required for wood mechanics and leaf morphology in aspen. *Plant J.* **2020**, *103*, 1858–1868. <https://doi.org/10.1111/tpj.14873>.