



Article A Simple Doping Process Achieved by Modifying the Passivation Layer for Self-Aligned Top-Gate In-Ga-Zn-O Thin-Film Transistors at 200 °C

Cong Peng 🗅, Huixue Huang, Meng Xu, Longlong Chen, Xifeng Li * and Jianhua Zhang

Key Laboratory of Advanced Display and System Applications of Ministry of Education, Shanghai University, Shanghai 200072, China

* Correspondence: lixifeng@shu.edu.cn

Abstract: In this paper, a facile modifying technique of source/drain regions conductivity was proposed for self-aligned top-gate In-Ga-Zn-O (IGZO) thin-film transistors (TFTs) by controlling the process parameter of the passivation layer at relatively low temperatures. The sheet resistance of the source and drain regions of IGZO was approximately 365 Ω/\Box , and there was no significant change within a month. The device parameters of mobility, threshold voltage, subthreshold swing, and current switching ratio of the fabricated device were $15.15 \text{ cm}^2 \text{V}^{-1} \text{s}^{-1}$, 0.09 V, 0.15 V/dec, and higher than 10⁹, respectively. The threshold voltage drift under negative bias illumination stress was -0.34 V. In addition, a lower channel width-normalized contact resistance of 9.86 Ω ·cm was obtained.

Keywords: InGaZnO; self-aligned top-gate; thin-film transistors



Citation: Peng, C.; Huang, H.; Xu, M.; Chen, L.; Li, X.; Zhang, J. A Simple Doping Process Achieved by Modifying the Passivation Layer for Self-Aligned Top-Gate In-Ga-Zn-O Thin-Film Transistors at 200 °C. *Nanomaterials* **2022**, *12*, 4021. https:// doi.org/10.3390/nano12224021

Academic Editor: Detlef W. Bahnemann

Received: 17 July 2022 Accepted: 25 August 2022 Published: 16 Novemer 2022

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/).

1. Introduction

Nowadays, amorphous indium gallium zinc oxide (a-IGZO) receives significant attention as an active layer of thin film transistors (TFTs) in the display industry because of its high mobility, very low off-state current, low process temperature, and intermittent refreshing [1–7]. The typical bottom gate structure of AOS TFTs, including back-channeletch and etch-stopper-layer, inevitably suffer from resistor-capacitor delay and image lagging, which is mainly due to the parasitic capacitance formed by the overlap between the gate (G)-source/drain (S/D) electrodes [8]. However, the source/drain and gate of the self-aligned top gate (SATG) structure are located on the same side of the active layer and have relatively small parasitic capacitance, so they have drawn the attention of more and more researchers [5,9–14]. The key technical challenge of SATG TFT is how to form source– drain regions with low resistance. Up to now, several solutions have been put forward to rise to this challenge, such as ion implantations [9], metal reaction-induced [5,10], plasma treatment [11], and hydrogen (H) doping in time of interlayer dielectric or passivation deposition [12,13]. Nevertheless, some problems with these methods cannot be ignored. Regarding the high activation temperature of ion implantations, guaranteed precise film thickness with metal reaction-induced, plasma-induced damages effect the plasma as a result of the uncontrollable rapid hydrogen diffusion of the high-temperature activation process with hydrogen incorporation. Furthermore, low-resistance IGZO films can also be prepared by coating with organic interlayer dielectric [15] or ultraviolet irradiation [16], which may result in an undercut and worse step coverage due to the gate stack directly formed by one-step dry etching. Based on the key technical challenges of SATG TFTs, there are currently few reports on the indirect processing of IGZO source-drain regions to form highly conductive regions in active oxide channels. Thus, in this study, we propose the vertical diffusion of hydrogen by modifying the hydrogen content of the passivation layer process to form low-resistance IGZO source-drain regions for indirectly realizing self-aligns. This simple doping process not only optimizes the process steps for reducing

the resistance of the source/drain regions but also improves the water and oxygen barrier capabilities of the device. SATG TFTs with good electrical properties and excellent negative bias illumination stress (NBIS) stability were successfully fabricated under a low-temperature process.

2. Materials and Methods

First of all, a 200 nm thick buffer layer with SiO₂ was deposited on 200 × 200 mm glass by plasma-enhanced chemical vapor deposition (PECVD). Then, the IGZO with a thickness of 40 nm was sputtered as an active layer and was patterned using a wet etchant. Furthermore, SiO₂ (SiH₄/N₂O = 6/94) with the thickness of 300 nm was deposited as a gate insulating layer (GI) by PECVD at 200 °C. Secondly, Mo (30 nm)/ITO (5 nm) was sputtered as a gate electrode using magnetron sputtering. Next, the gate electrode was formed by a two-step wet etch of the Mo/ITO stack. After SiO₂ (SiH₄/N₂O = 6/94) or Si₃N₄ (SiH₄/NH₃/N₂ = 6/22/72) with a thickness of 200 nm was deposited as a passivation layer (PA) at 200 °C., the n⁺ IGZO extension regions (the size of one side is $25 \times 50 \ \mu\text{m}^2$) were automatically formed through the gate. Moreover, the contact holes were exposed by dry etching. In the end, the ITO with a thickness of 35 nm was sputtered again by sputtering as a source–drain electrode. It is worth noting that the process temperature during device fabrication was not higher than 200 °C. The channel width of the device was fixed at 50 µm, and the channel length (*L*) was 4 µm, 6 µm, and 8 µm, respectively. Figure 1a,b represents the schematic cross-section and top optical image of the SATG IGZO TFT, respectively.



Figure 1. (a) The schematic diagram of SATG IGZO TFTs. (b) Top view of SATG IGZO TFT.

The electrical characteristics for the fabricated a-IGZO TFTs were measured using Keithley 4200. We define the corresponding gate voltage (V_{GS}) when the leakage current (I_{DS}) is 1 nA as the threshold voltage (V_{TH}) of the TFT device. The mobility (μ) was calculated according to the following equation: $\mu = 2L \cdot I_{DS} / W \cdot C_i \cdot (V_{GS} - V_{TH})^2$, where C_i is the gate of the capacitance per unit area. The sheet resistance was measured by the 3 m mini type four-probe tester in the dark at 300 K. The light source used in the NBIS tests was white light with a brightness of 10,000 lux by applying $V_{G-Stress} = -10$ V of 1000 s with source and drain electrodes grounded. The light source was emitted from the bottom of the device.

3. Results and Discussion

To verify the effect of the passivation layer process with different hydrogen contents on device characteristics, SATG IGZO TFTs with three passivation layers were fabricated without a passivation layer (w/o). SiO₂ and Si₃N₄, respectively, represent the low, medium, and high hydrogen content in the passivation layer film.

The transfer performance with SATG IGZO TFTs with different passivation is shown in Figure 2a. When the hydrogen concentration of the passivation layer increases, the μ increases from 0.31 to 15.15 cm²V⁻¹s⁻¹, threshold voltage (V_{TH}) from 3.91 V to 0.09 V, subthreshold swing (SS) from 0.10 V/dec to 0.15 V/dec, and I_{on}/I_{off} increases from 1.17 × 10⁸ to 2.86×10^9 . Figure 2b show the output characteristic of TFT with Si₃N₄ as passivation. The output characteristics show good ohmic contact at low drain voltages and low source/drain resistance [17]. This can be attributed to not only higher electron mobility but also lower contact resistance [10,18].



Figure 2. (a) Variation of I_{DS} - V_{GS} transfer curves of SATG IGZO TFTs prepared with different passivation layers, (b) output curve of SATG IGZO TFT with Si₃N₄ as a passivation layer.

It can be intuitively seen from Figure 2a that the *I*_{on} of the device gradually increases from $\sim 10^6$ A to $\sim 10^4$ A as the hydrogen content increases. Although the IGZO/GI interface will have a serious impact on *I*_{on}, the fabrication processes of the three devices are basically the same, that is, the IGZO/GI interface defects should be the same, which can be reflected from the SS value with no obvious change. Therefore, the increase of I_{on} is mainly due to the decrease of the contact resistance. After the passivation layer is deposited, since the passivation layer contains a high concentration of hydrogen, a large amount of hydrogen will first pass through the insulating layer from the passivation layer and then vertically diffuse to the IGZO layer [19]. In addition, because the densified gate can block the diffusion of hydrogen, hydrogen will vertically diffuse down to the IGZO layer along the edge of the gate, reducing the resistance and self-aligning to form the IGZO source and drain regions. Although a small amount of hydrogen will diffuse laterally, it will only remain in the insulating layer above the channel. As the hydrogen content in the passivation layer increases, the hydrogen diffused into the IGZO layer must increase, so the formed IGZO source and drain regions have better conductivity, and the TFT device has smaller parasitic resistance. At the same time, the channel carrier concentration increases, and the V_{TH} shifts to the left.

To demonstrate that the contact resistance is reduced, the sheet resistance of S/D regions in the IGZO was measured. Figure 3a show the variation of sheet resistance of the IGZO source and drain regions with deposition temperature. The sheet resistance decreases gradually with the increase of deposition temperature. At 150 °C, the sheet resistance corresponding to the Si₃N₄ passivation layer is much lower than that of SiO₂, but when the temperature increases to 200 °C, the effects of the two passivation layers are similar and remain basically unchanged. The sheet resistance varies around 365 Ω/\Box . Therefore, its resistivity is $1.5 \times 10^{-3} \Omega \cdot cm$ because its thickness is 40 nm. Table 1 summarize the resistance and device mobility obtained by different treatments for the source and drain regions of IGZO. In this work, the PA/GI processing approach exhibits low resistivity and high device mobility and achieves a level comparable to other methods.



Figure 3. (a) Variation of sheet resistance with deposition temperature, (b) variation of sheet resistance with placement time, (c) R_{tot} -L plot measured from the TFTs with different L at various gate voltage biases, (d) width-normalized contact resistance as a function of gate voltage.

Table 1. This is a table. Tables should be placed in the main text	near to the f	first time they	y are cited.
---------------------------------------------------------------------------	---------------	-----------------	--------------

Treatment Methods	μ (cm ² V ⁻¹ s ⁻¹)	Resistivity (Ω·cm)	Temperature (°C)	References
PA/GI	15.15	$1.5 imes10^{-3}$	200	This Work
Ion implantations	7	-	350	2021 [9]
Metal reaction-induced	13	$2.4 imes10^{-3}$	200	2021 [10]
Plasma	5.13	$2 imes 10^{-3}$	350	2021 [11]
Zeocoat	18.84	$3.8 imes10^{-4}$	150	2020 [15]
Interlayer dielectric layer	14	$3 imes 10^{-3}$	250	2019 [13]
ultraviolet irradiation	6.7	$3 imes 10^{-5}$	300	2015 [16]

As shown in Figure 3b, with the passage of time, the two passivation layers have different changes to the IGZO source and drain regions. The Si₃N₄ passivation layer maintained good stability for one month, while the SiO₂ passivation layer showed poor stability. After 3 days, the sheet resistance increased to more than 156 k Ω/\Box , increased to about 526 k Ω/\Box after a week, and exceeded the test limit of the device after a month. This can be attributed to the low hydrogen content in the SiO₂ film, which has an insufficient degree of influence on the IGZO film. With the increase of the standing time, the hydrogen in the SiO₂ film diffused outward, reducing the hydrogen content in the IGZO film, and thus the sheet resistance increased.

The contact resistance (R_C) was calculated according to the transmission line method. It includes the contact resistance between the metal and semiconductor and the resistance of the S/D extension part inside the semiconductor. The following equation may be used to calculate the R_{tot} [15]:

$$R_{tot} = \frac{V_{DS}}{I_{DS}} = \frac{R_S}{W}L + 2R_C \tag{1}$$

 R_S is the channel resistance. Figure 3c show the total resistance (R_{tot}) corresponding to different *L* at various V_{GS} . The transmission line method was used to extract the width-normalized R_C ($R_C \cdot W$) and the diffusion distance, as shown in Figure 3d [5]. For SATG

IGZO TFT with Si₃N₄ passivation layer, the $R_C \cdot W$ values were approximately 9.86 $\Omega \cdot cm$, and the lateral diffusion distance was only 0.07 μm .

To verify the prospect of passivation in practical applications of SATG IGZO TFT, the NBIS is shown in Figure 4. As the time of illumination and gate voltage are increased, the V_{TH} drifts in the negative direction. However, the threshold voltage drift (ΔV_{TH}) of TFTs with w/o or SiO₂ is reduced from -1.19 V or -1.04 V to -0.34 V compared to TFTs with Si_3N_4 . This shows that the Si_3N_4 can improve device stability. The V_{TH} drift under NBIS is mainly due to the formation of positively ionized oxygen vacancies under the combined effect of illumination and negative gate voltage $(V_O \rightarrow V_O^+/V_O^{++})$ [20]. The ΔV_{TH} for SATG IGZO TFTs with Si₃N₄ as passivation is as low as -0.32 V, which may be due to the reduction of positive charge (V_O^+/V_O^{++}) by the formation of substitutional hydrogen ($H^{O} + e^{-} \rightarrow H^{-} + V_{O} \rightarrow H_{O}$), where H^{O} and H_{O} represent a hydrogen atom and substitutional hydrogen, respectively [21]. In addition, as the hydrogen in the passivation layer increases, the lateral diffusion of hydrogen remaining in the insulating layer also increases. In subsequent processes, hydrogen will diffuse from the GI to the IGZO/GI interface, passivate the V_O-related point defects, and reduce the deep donor electron traps $(H^{O} + O^{2-} \rightarrow OH^{-} + e^{-})$ [4,20]. At the same time, hydrogen implantation from GI to the IGZO/GI interface also increases the carrier concentration and reduces the interfacial trap states, thereby reducing ΔV_{TH} [22,23].



Figure 4. Evolutions of transfer characteristics of the IGZO TFTs with increasing NBIS: (a) w/o, (b) SiO₂, (c) Si₃N₄, (d) ΔV_{TH} as a function of stress time.

4. Conclusions

In this paper, SATG TFTs were successfully fabricated by modifying the hydrogen content of the passivation layer process under a low-temperature process. The influence of the passivation layer on the electrical properties was compared, and it was proven that the modification of the passivation layer process can effectively reduce the resistance of the source and drain regions of IGZO. The prepared TFT had a low $R_C \cdot W$ of 9.86 $\Omega \cdot cm$ and a low lateral diffusion distance of 0.07 µm. The fabricated SATG TFT exhibited excellent electrical properties with μ of 15.15 cm²V⁻¹s⁻¹ and I_{on}/I_{off} higher than 10⁹, respectively. Meanwhile, NBIS stability was remarkably improved from -1.19 to -0.34 V.

Author Contributions: Conceptualization, X.L. and J.Z.; methodology, C.P. and X.L.; funding acquisition, X.L. and J.Z.; investigation, C.P., H.H. and M.X.; writing—original draft preparation, C.P. and H.H.; writing—review and editing, C.P., L.C. and X.L.; supervision, X.L. All authors have read and agreed to the published version of the manuscript.

Funding: This work is supported by the National Natural Science Foundation of China under Grant 62174105, Shanghai Education Development Foundation and Shanghai Municipal Education Commission under Grant 18SG38, and the Program of Shanghai Academic/Technology Research Leader under Grant 18XD1424400.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: The data and contributions presented in the study are included in the article. Further inquiries can be directed to the corresponding author.

Conflicts of Interest: The authors declare no conflict of interest.

References

- Kim, D.G.; Ryu, S.H.; Jeong, H.J.; Park, J.S. Facile and Stable n⁺ Doping Process Via Simultaneous Ultraviolet and Thermal Energy for Coplanar ALD-IGZO Thin-Film Transistors. ACS Appl. Electron. Mater. 2021, 3, 3530–3537. [CrossRef]
- 2. Wang, X.; Liang, L.; Zhang, H.; Wu, H.; Li, W.; Ning, C.; Yuan, G.; Cao, H. Huge mobility enhancement of InSnZnO thin-film transistors via Al-induced microstructure regularization. *Appl. Phys. Lett.* **2021**, *119*, 212102. [CrossRef]
- 3. Peng, C.; Jiang, W.; Li, Y.; Li, X.; Zhang, J. Photoelectric IGZO Electric-double-layer transparent artificial synapses for emotional state simulation. *ACS Appl. Electron. Mater.* **2019**, *1*, 2406–2414. [CrossRef]
- 4. Peng, C.; Yang, S.; Pan, C.; Li, X.; Zhang, J. Effect of Two-Step Annealing on High Stability of a-IGZO Thin-Film Transistor. *IEEE Trans. Electron Devices* 2020, 67, 4262–4268. [CrossRef]
- Peng, H.; Chang, B.; Fu, H.; Yang, H.; Zhang, Y.; Zhou, X.; Lu, L.; Zhang, S. Top-Gate Amorphous Indium-Gallium-Zinc-OxideThin-Film Transistors With Magnesium Metallized Source/Drain Regions. *IEEE Trans. Electron Devices* 2020, 67, 1619–1624. [CrossRef]
- 6. Sun, J.; Xu, S.; Ren, H.; Wu, S.-T.P. 1:Distinguished Student Poster Paper: Submillisecond-response Polymer Network Liquid Crystal Cylindrical Microlens Array for 3D Displays. *SID Symp. Dig. Tech. Pap.* **2013**, *44*, 989–992. [CrossRef]
- Zhang, W.; Fan, Z.; Shen, A.; Dong, C. Atmosphere Effect in Post-Annealing Treatments for Amorphous InGaZnO Thin-Film Transistors with SiOx Passivation Layers. *Micromachines* 2021, 12, 1551. [CrossRef]
- Choi, S.; Park, J.; Hwang, S.H.; Kim, C.; Kim, Y.S.; Oh, S.; Baeck, J.H.; Bae, J.U.; Noh, J.; Lee, S.W.; et al. Excessive Oxygen Peroxide Model-Based Analysis of Positive-Bias-Stress and Negative-Bias-Illumination-Stress Instabilities in Self-Aligned Top-Gate Coplanar In-Ga-Zn-O Thin-Film Transistors. *Adv. Electron. Mater.* 2022, *8*, 2101062. [CrossRef]
- 9. Takechi, K.; Lin, F.; He, S.; Yuan, Y.; Tanaka, J.; Sera, K. Short-Channel Top-Gate InGaZnO Thin-Film Transistors Fabricated with Boron Implantation into Source/Drain Regions. *IEEE Trans. Electron Devices* **2021**, *68*, 4161–4163. [CrossRef]
- Yang, H.; Zhou, X.; Fu, H.; Chang, B.; Min, Y.; Peng, H.; Lu, L.; Zhang, S. Metal Reaction-Induced Bulk-Doping Effect in Forming Conductive Source-Drain Regions of Self-Aligned Top-Gate Amorphous InGaZnO Thin-Film Transistors. ACS Appl Mater Interfaces 2021, 13, 11442–11448. [CrossRef]
- Kim, Y.G.; Bukke, R.N.; Lee, J.; Saha, J.K.; Jang, J. Formation of F-Doped Offset Region for Spray Pyrolyzed Self-Aligned Coplanar Amorphous Zinc-Tin-Oxide Thin-Film Transistor by NF₃ Plasma Treatment. *IEEE Trans. Electron Devices* 2021, 68, 1057–1062. [CrossRef]
- 12. Chen, H.; Chen, J.; Zhou, K.; Chen, G.; Kuo, C.; Shih, Y.; Su, W.; Yang, C.; Huang, H.; Shih, C.; et al. Hydrogen Diffusion and Threshold Voltage Shifts in Top-Gate Amorphous InGaZnO Thin-Film Transistors. *IEEE Trans. Electron Devices* **2020**, *67*, 3123–3128. [CrossRef]
- 13. Katsouras, I.; Frijters, C.; Poodt, P.; Gelinck, G.; Kronemeijer, A.J. Large-area spatial atomic layer deposition of amorphous oxide semiconductors at atmospheric pressure. *J. Soc. Inf. Disp.* **2019**, *27*, 304–312. [CrossRef]
- 14. Zhang, Y.-Y.; Shin, S.-H.; Kang, H.-J.; Jeon, S.; Hwang, S.H.; Zhou, W.; Jeong, J.-H.; Li, X.; Kim, M. Anti-reflective porous Ge by open-circuit and lithography-free metal-assisted chemical etching. *Appl. Surf. Sci.* **2021**, *546*, 149083. [CrossRef]
- 15. Kim, H.E.; Furuta, M.; Yoon, S.M. A Facile Doping Process of the Organic Inter-Layer Dielectric for Self-Aligned Coplanar In-Ga-Zn-O Thin-Film Transistors. *IEEE Electron Device Lett.* **2020**, *41*, 393–396. [CrossRef]
- 16. Kim, M.M.; Kim, M.H.; Ryu, S.m.; Lim, J.H.; Choi, D.K. Coplanar homojunction a-InGaZnO thin film transistor fabricated using ultraviolet irradiation. *RSC Adv.* **2015**, *5*, 82947–82951. [CrossRef]
- 17. Bukke, R.N.; Mude, N.N.; Saha, J.K.; Jang, J. High Performance of a-IZTO TFT by Purification of the Semiconductor Oxide Precursor. *Adv. Mater. Interfaces* **2019**, *6*, 1900277. [CrossRef]
- Taniguchi, S.; Yokozeki, M.; Ikeda, M.; Suzuki, T.-K. Transparent Oxide Thin-Film Transistors Using n-(In₂O₃)_{0.9}(SnO₂)_{0.1}/InGaZnO₄ Modulation-Doped Heterostructures. *Jpn. J. Appl. Phys.* 2011, 50, DF11. [CrossRef]

- 19. Chen, C.; Yang, B.; Li, G.; Zhou, H.; Huang, B.; Wu, Q.; Zhan, R.; Noh, Y.; Minari, T.; Zhang, S.; et al. Analysis of Ultrahigh Apparent Mobility in Oxide Field-Effect Transistors. *Adv Sci* **2019**, *6*, 1801189. [CrossRef]
- Rabbi, M.H.; Billah, M.M.; Siddik, A.B.; Lee, S.; Lee, J.; Jang, J. Extremely Stable Dual Gate Coplanar Amorphous InGaZnO Thin Film Transistor With Split Active Layer by N₂O Annealing. *IEEE Electron Device Lett.* 2020, 41, 1782–1785. [CrossRef]
- 21. Bang, J.; Matsuishi, S.; Hosono, H. Hydrogen anion and subgap states in amorphous In–Ga–Zn–O thin films for TFT applications. *Appl. Phys. Lett.* **2017**, *110*, 232105. [CrossRef]
- Peng, C.; Dong, P.; Li, X. Improvement of solution-processed Zn-Sn-O active-layer thin film transistors by novel high valence Mo Doping. *Nanotechnology* 2020, 32, 025207. [CrossRef] [PubMed]
- 23. Chowdhury, M.D.H.; Mativenga, M.; Um, J.G.; Mruthyunjaya, R.K.; Heiler, G.N.; Tredwell, T.J.; Jang, J. Effect of SiO₂ and SiO₂/SiN_x Passivation on the Stability of Amorphous Indium-Gallium Zinc-Oxide Thin-Film Transistors Under High Humidity. *IEEE Trans. Electron Devices* **2015**, *62*, 869–874. [CrossRef]