

Electronic Supplementary Information (ESI) for: **Ln³⁺-Induced Diblock Copolymeric Aggregates for Full Flexible Tunable White-Light Materials**

Xinzhi Wang,^a Jianguo Tang,^{*a} Guanghui Wang,^a Wei Wang,^a Junjie Ren,^a Yao Wang,^a Wenfei Shen,^a Linjun Huang,^a and Laurence A. Belfiore^{*a,b}

Table of Contents

Figure S1. ¹H NMR spectra of (a) 4-cyano-4-ethyl trithiopentanoic acid and (b) RAFT agent.

Figure S2. EDS spectrum of BCPs-Ln³⁺-Phen (Eu:Tb=1:1).

Table S1. Molar ratios of Eu³⁺, Tb³⁺, "phen", PS-b-PAA and their concentrations in DMF solutions before reaction.




Figure 1. ¹H NMR spectra of (a) 4-cyano-4-ethyl trithiopentanoic acid and (b) RAFT agent.




Figure S2. EDS spectrum of BCPs-Ln³⁺-Phen (Eu:Tb=1:1)

Table S1. Molar ratios of Eu³⁺, Tb³⁺, “phen”, PS-b-PAA and their concentrations in DMF solutions before reaction.

Sample	C_{PS-b-PAA} (mol/L)	C_{Eu} (mol/L)	C_{Tb} (mol/L)	C_{Phen} (mol/L)	Eu/Tb
a	0.008	0.003	0.001	0.004	3:1
b	0.006	0.002	0.001	0.003	2:1
c	0.004	0.001	0.001	0.002	1:1
d	0.006	0.001	0.002	0.003	1:2
e	0.008	0.001	0.003	0.004	1:3