

Article



Eroding the Surface of Rare Earth Microcrystals through Vanadate Ions for Considerable Improvement of Luminescence

Jiao Qu¹, Juanjuan Liu² and Qi Zhu^{2,*}

- ¹ School of Mechanical Engineering and Automation, Shenyang Institute of Technology, Fushun 113122, China; qujiao0611@163.com
- ² Key Laboratory for Anisotropy and Texture of Materials (Ministry of Education), School of Materials Science and Engineering, Northeastern University, Shenyang 110819, China; Ijjuan5409953@163.com
- * Correspondence: zhuq@smm.neu.edu.cn; Tel.: +86-24-8369-1570

Abstract: Developing an efficient approach to improve the luminescence of the phosphors without heating processing is a challenge, but attracts much attention. In the present paper, prismatic microcrystals of RE₄O(OH)₉NO₃ (RE = Y, Eu) were synthesized by a hydrothermal reaction at 180 °C for 24 h. The reaction with VO₃⁻ did not change the crystal structure of the microcrystals and VO₃⁻ substituting for NO₃⁻ anions did not take place. However, it contributed to the formation of amorphous particles containing VO₃⁻ on the surface of a prism, which is similar to the surface corrosion of a metal, called "surface eroding". Therefore, surface modification was successfully achieved by eroding the surface of the microcrystals through the reaction with vanadate ions. As a result of VO₃⁻ \rightarrow Eu³⁺ energy transfer and the light-harvesting ability of VO₃⁻, the red emission intensity at 617 nm of the modified microcrystals greatly increased. Eroding the surface of rare earth microcrystals recommends a new paradigm for luminescence improvement of rare earth compounds.

Keywords: Y4O(OH)9NO3; Eu3+; eroding; rare earth compounds; microcrystals

1. Introduction

Directly exciting RE³⁺ ions upon irradiation for luminescence is not an efficient method, because the f-f electronic transitions of the rare earth ions (RE³⁺) are usually forbidden by the spin selection rules [1]. Therefore, doping RE³⁺ ions with a low concentration into an appropriate host lattice is widely used to produce solid-solution phosphor and obtain desirable luminescence [2]. In recent years, much attention has been paid to RE³⁺-doped inorganic materials with a uniform size and specific morphology, because they allow for the attainment of functionalities, not only from the constituent substance but also from the special structure [3-6]. For rare earth oxide phosphors, calcining the precursors is widely used to obtain the phosphors with a variety of novel structures, since the precursors and their calcined products tend to exhibit generic relationships [3,7–11]. RE2(OH)5NO3·nH2O layered rare earth hydroxide (LRH), RE4O(OH)9NO3 oxy-hydroxyl nitrate, RE(OH)294(NO3)0.06·nH2O hydroxyl nitrate, and RE(OH)₃ hydroxide are the reported products synthesized from the hydrothermal reaction system [7–10], and their morphology and size could be easily regulated by varying the synthesis conditions, including the pH value, reaction temperature, and reaction time. Therefore, they are the desirable precursors for rare earth oxide phosphors. Therefore, there are a lot of investigations on these precursors. However, abundant water molecules or hydroxyls directly coordinate to the rare earth ions, which result in a serious luminescence quenching [8,9]. Thus, there is the question of how to enhance the emission intensity of the rare earth phosphors. Of course, the thermal decomposition of the precursors is an efficient method to synthesize rare earth oxides, and it could remove

Citation: Qu, J.; Liu, J.; Zhu, Q. Eroding the Surface of Rare Earth Microcrystals through Vanadate Ions for Considerable Improvement of Luminescence. *Coatings* **2022**, *12*, 230. https://doi.org/10.3390/ coatings12020230

Academic Editor: Alina Pruna

Received: 29 December 2021 Accepted: 8 February 2022 Published: 10 February 2022

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https://creativecommons.org/license s/by/4.0/). the water molecules/dehydroxyl and thus enhance the luminescence intensity [3]. However, morphological damage and crystal-structure collapse would take place during the annealing process, which may significantly affect the final performance [12]. Therefore, developing an efficient approach to improve the luminescence of the phosphors without heating processing is a challenge, but attracts much attention.

Recently, it has been reported that an antenna effect could give rise to an enhanced photoluminescence upon light irradiation, because an effective intramolecular energy transfer from coordinated ligands to the activated RE³⁺ ions can enhance the absorption of the optical excitation. This antenna effect effectively promotes the energy transfer from coordinated ligands to the activated RE³⁺ ions, and thus enhances the emission intensity [13]. This light-harvesting ability was successfully applied onto the layered rare earth hydroxide nanosheets [14,15], hydroxyl nitrate square nanoplates [16], and rare earth nanoparticles [17,18], through the grafting of organic ligands, including picolinic acid and a rare earth complex, on the surface of the nanocrystals. Indeed, a considerable improvement of luminescence was observed for these rare earth crystals. However, the organic ligands were indirectly linked to the surface of the nanocrystals by hydrogen bonding, indicating that the hybrid phosphors grafted organic ligands were unstable. In addition, the hydrogen bonding connection made the energy transfer from the ligands to the activated RE³⁺ ions difficult [7,15], so it is not the most effective way for energy transfer, compared to the directly connecting coordination.

In the present work, prismatic microcrystals of RE₄O(OH)₉NO₃ (RE = Y, Eu) were synthesized by the hydrothermal reaction. The surface modification of the microcrystals was successfully achieved by eroding the surface of the microcrystals through vanadate ions. The main means of sample characterization are X-ray diffraction (XRD), transmission electron microscopy (TEM), selected area electron diffraction (SAED), scanning transmission electron microscopy (STEM), photoluminescence (PL)/photoluminescence excitation (PLE) spectroscopy, and fluorescence decay curve analysis. The reaction with VO₃⁻ contributed to the formation of amorphous particles containing VO₃⁻ on the surface of the prism, which lead to a great enhancement of luminescence. The usage of the energy transfer to the activated RE³⁺ ions through surface eroding processing, paves a new paradigm for luminescence improvement of the rare earth compounds.

2. Experimental Section

2.1. Synthesis

Preparation of oxy-hydroxyl nitrate microcrystals. The starting rare earth sources are rare earth oxides, which are Y₂O₃ and Eu₂O₃, all 99.99% pure products from Huizhou Ruier Rare-Chem, Hi-Tech, Co., Ltd. (Huizhou, China). Dissolving the rare earth oxide in hot nitric acid yielded a rare earth nitrate solution, which was then treated by evaporation at 90 °C to remove the excess acid. The synthesis of Y/Eu binary microcrystals (Y:Eu molar ratio of 0.95:0.05) was conducted via a hydrothermal reaction at 180 °C for 24 h with a pH value of 10–11, which was described in our previous work [3].

Erosion of the microcrystal surface. In typical processing, 2 mmol of RE₄O(OH)₉NO₃ microcrystals was dispersed in 60 mL of water containing a proper amount of NH₄VO₃ and NH₄OH with the pH value of 10–11. After being stirred for 30 min, the resultant suspension was transferred into a Teflon-lined stainless-steel autoclave of 100 mL capacity. The autoclave was tightly sealed and was put in an electric oven preheated to 200 °C. After a 12 h reaction, the autoclave was left to cool naturally to room temperature, and then the product was collected via centrifugation. The wet precipitate was washed with distilled water 3 times, rinsed with absolute ethanol, and was finally dried in air at 60 °C for a day. The oxy-hydroxyl nitrate microcrystals and the microcrystals eroded by VO₃⁻ are denoted as MC and MC-*R*V hereafter, with the *R*-fold VO₃⁻ in the reaction system.

2.2. Characterization Techniques

Phase identification was performed by X-ray diffraction (XRD, Model SmartLab, Rigaku, Tokyo, Japan), operating at 40 kV/40 mA using nickel-filtered Cu K α radiation and a scanning speed of $6.0^{\circ} 2\theta$ /min. The product morphology was analyzed by field emission scanning electron microscopy (FE-SEM, Model JSM-7001F, JEOL, Tokyo, Japan) and transmission electron microscopy (TEM, Model JEM-2000FX, JEOL, Tokyo, Japan). Elemental mapping was performed using scanning transmission electron microscopy (STEM, Model JEM-2000FX, JEOL, Tokyo, Japan). Fourier transform infrared spectroscopy experiments (FT-IR, Nicolet iS5, Thermal Fisher Scientific, NY, USA) were under taken using the standard KBr method. Photoluminescence (PL), photoluminescence excitation (PLE), and fluorescence decay were analyzed at room temperature using an FP-8600 fluorospectrophotometer (JASCO, Tokyo, Japan) equipped with a $\Phi 60$ mm integrating sphere and a 150-W Xe-lamp. The slit widths were 5 nm for both the excitation and emission sides. The spectral responses were corrected in the range 220-850 nm with a Rhodamine-B solution (5.5 g/L in ethylene glycol, for 220-600 nm range) and with a standard light source unit (ECS-333, JASCO, for 350-850 nm) as references. The external quantum efficiency (ε_{ex} , the total number of emitted photons divided by the total number of excitation photons) and the internal quantum efficiency (ε_{in} , the total number of emitted photons divided by the number of photons absorbed by the sample) of the phosphors are derived from the following equations [19], using the built-in analysis software:

$$\varepsilon_{\rm ex} = \frac{\int \lambda P(\lambda) d\lambda}{\int \lambda E(\lambda) d\lambda} \tag{1}$$

$$\varepsilon_{\rm in} = \frac{\int \lambda P(\lambda) d\lambda}{\int \lambda [E(\lambda) - R(\lambda)] d\lambda}$$
(2)

where $E(\lambda)/hv$, $R(\lambda)/hv$, and $P(\lambda)/hv$ are the number of photons in the excitation, reflectance, and emission spectra of the samples, respectively. The reflection spectrum of the spectral on diffusive white standards was used for calibration.

3. Results and Discussion

In the present study, the RE $_4O(OH)$ 9NO $_3$ (RE = Y, Eu) microcrystals (termed as MC) was chosen as an example for surface modification. As reported in the literature [3], Y4O(OH)9NO3 is a monoclinic crystal structure, which is a three-dimensional framework with one-dimensional channels containing NO₃⁻. The NO₃⁻ is indirectly linked to Y_{3+} rather than forming a direct connection. There are 4 trivalent yttrium ions in the asymmetric unit, with 3 in a 7-coordinated environment with a capped trigonal prismatic geometry and 1 in a 9-coordinated environment with a tricapped trigonal prismatic geometry. The trivalent yttrium ions are linked through hydroxide anions forming the framework around the channels. In the channel, the nitrate ion is indirectly linked to Y³⁺ through the hydrogen bonding. As a result of the one-dimensional channels, Y4O(OH)9NO3 always crystallizes into prismatic and wire-like crystallites [3]. Here, the incorporation of Eu³⁺ in Y₄O(OH)₉NO₃ does not significantly affect its crystal structure, because the diffractions of MC are indexed to the monoclinic Y4O(OH)9NO3 (JCPDS File no. 79-1352), except for slight spectral shifts to the lower angle side (Figure 1c). The replacement of Y³⁺ with larger Eu³⁺ ions (for 8-fold coordination, $r_{y^{3+}} = 0.1019$ nm, $r_{Eu^{3+}} = 0.1066$ nm) contributed to the lattice expansion, thus resulting in the diffraction shifts [20]. Figure 1d shows the FE-SEM image of MC, and pure hexagonal prisms with a diameter of $\sim 0.3-0.5 \,\mu m$ and a length of ~1.5–2.5 µm are found in the observation.



Figure 1. (a,b) Crystal structure of Y4O(OH)9NO3, (c) XRD patterns, and (d) FE-SEM image of MC.

Figure 2 shows the XRD patterns of MC after the reaction with VO₃-. Evidently, the reaction products are the same as MC, because all the diffractions are indexed to the monoclinic Y4O(OH)9NO3 (JCPDS File no. 79-1352), indicating that the reaction with VO3did not result in a phase transformation. Increasing the R value from 0 to 1.5 (R, the molar ratio of VO₃- to MC) induced a small shift of the diffraction positions. Since VO₃- is smaller than NO3- [21], VO3- substituting for NO3- anions may induce the diffraction shift to the higher angle side arising from the lattice contraction. Indeed, NO₃- is indirectly coordinated in Y4O(OH)₉NO₃ rather than the free anion, so it cannot be easily replaced by other anions through ion exchange. After the reaction with VO₃-, the products mainly remain in the original morphology of MC (Figure 3). However, the surface of MC-RV (microcrystals reacted with VO₃-, with R-fold VO₃- in the reaction system) is not smooth, with nano-sized crystals on the prism surface. Increasing the R value from 0.25 to 1.5 contributed to a rougher particle surface for MC-RV. Since the above phenomenon is similar to that for the surface corrosion of metal, in the present paper, it is called "surface eroding" for the reaction with VO₃-. However, there are not any other impurity phases in the XRD patterns, indicating that the nano-sized crystals are amorphous.



Figure 2. XRD patterns of MC-*R*M, with (**a**) *R* = 0.25, (**b**) *R* = 0.5, (**c**) *R* = 1.0, and (**d**) *R* =1.5.



Figure 3. FE-SEM micrographs of MC (**a**) and MC-RM (**b**–**d**), with (**b**) R = 0.25, (**c**) R = 1.0, and (**d**) R = 1.5.

Figure 4 shows the FT-IR spectra for the samples after the reaction with different VO₃⁻ contents. The MC exhibits splitting absorption peaks in the range of 3350–3750 cm⁻¹, with intense absorptions at 3401, 3487, and 3615 cm⁻¹, which arise from hydroxyl (OH⁻) groups [22,23]. This is in compliance with the derived chemical formula of RE₄O(OH)₉NO₃. The absorption peaks around 1364 and 1407 cm⁻¹ are assignable to the v_3 vibration mode of NO₃⁻ and the v_4 asymmetric stretch of O-NO₂, respectively [22,23]. It is clearly seen that the absorptions of NO₃⁻ in MC are different from those of the interlaye-free NO₃⁻ in layered rare earth hydroxide. After the reaction with VO₃⁻, NO₃⁻ still exists in the FT-IR spectra and is not significantly affected by the reaction. However, the absorption for VO₃⁻ at 792 cm⁻¹ appeared after the reaction with VO₃⁻ [22–24], and more intense absorption is found at a higher *R* value.



Figure 4. FT-IR spectra for MC (R = 0) and MC-RM after the reaction with VO₃⁻.

Figure 5 shows the elemental mapping distribution of MC, and the results indicate that MC is a homogeneous solid solution, because all the elements of Y, Eu, and N are distributed among the particles. In addition, the close observation of MC through the TEM image found that MC is well crystallized, with sharp edges and corners, and the surface is smooth. Selected area electron diffraction (SAED) found that the MC is a single crystalline. The calculated planar spacings of ~0.352 nm and ~0.268 nm correspond well with the (230) and (-141) planes of Y4O(OH)9NO3. After the reaction with VO3⁻, V is distributed among the particles, except for the original component elements of Y, Eu, and N (Figures 6 and 7). The TEM images of MC-RV confirmed that there are nano-sized crystals on the surface of the prisms, and they grow up and tend to dendritic growth. Evidently, the materials needed for growth are obtained from the dissolution of the MC surface, similar to the surface corrosion of metal. The diameter of the prisms became slimmer at a higher R value, further presenting direct evidence. Selected area electron diffraction (SAED) yields circular patterns, suggesting the MC-RV consists of polycrystalline (Figure 6). The calculated planar spacings of ~0.374 nm, ~0.301 nm, ~0.287 nm, and ~0.184 nm correspond well with the (140), (310), (320), and (500) planes of Y4O(OH)9NO3, i.e., d(140) = 0.374026 nm, d(310) = 0.301376 nm, d(320) = 0.287141 nm, and d(500) = 0.183968 nm (JCPDS File no. 79-1352). Evidently, amorphous diffraction circular patterns were found in the SAED patterns, confirming the existence of amorphous particles on the surface of the prism. Collectively, the results from these analyses confirmed that the reaction with VO3⁻ contributed to the formation of amorphous particles containing VO3⁻ on the surface of the prism, which is similar to the surface corrosion of metal, called "surface



eroding". Therefore, it can be said that the surface modification of MC was successfully achieved by eroding the surface of MC through vanadate ions.

Figure 5. (a–c) Elemental mapping, (d) TEM image, and (e) SAED for MC.



Figure 6. (a–d) Elemental mapping, (e) TEM image, and (f) SAED for MC-0.25V.







Figure 8 shows the PLE and PL spectra for MC. By monitoring the ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$ emission at 617 nm, a series of sharp lines in the PLE spectrum ranging from 300 nm to 500 nm can

be ascribed to the transitions within the Eu³⁺ 4f⁶ electronic configuration. Different from other rare earth hydroxide precursors, MC exhibited O²⁻-Eu³⁺ charge transfer (CT) transitions at ~255 nm, as were commonly found for Eu³⁺-activated Y₂O₃ [7–10]. Upon excitation at 395 nm (intra-4f° transition of Eu³⁺), the PL spectrum displayed the typical ${}^{5}D_{0} \rightarrow {}^{7}F_{J}$ (J = 0-4) transitions of Eu³⁺. The relative intensities of the transitions to different J levels depended on the symmetry of the Eu³⁺ environment and can be described in terms of the Judd-Ofelt theory [7]. The Judd-Ofelt parity law predicts that the magnetic dipole ${}^{5}D_{0} \rightarrow {}^{7}F_{1}$ transition is permitted while the electric dipole ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$ transition is forbidden, and the latter is allowed only on the condition that the Eu³⁺ ions occupy the asymmetric site [7–9]. The MC, having the composition of (Y0.95Eu0.05)4O(OH)9NO3, has a monoclinic structure and 2 kinds of Eu³⁺ ions, which are 7-coordinated Eu³⁺ ions in $C_{2\nu}$ non-centrosymmetric sites and 9-coordinated Eu³⁺ ions in D_{3h} centrosymmetric sites [3]. Since the molar ratio of C_{2v} occupancy to that of D_{3h} is 3, most Eu³⁺ ions occupy the asymmetric site, and thus the ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$ transition at 617 nm is stronger than the ${}^{5}D_{0} \rightarrow {}^{7}F_{1}$ transition at 595 nm [3]. However, the MC did not output a strong red light, mainly due to the fact that the hydroxyls directly coordinated to the rare earth ions Eu³⁺, which resulted in serious luminescence quenching [24].



Figure 8. (a) PLE and (b) PL spectra for MC at room temperature.

Figure 9 shows the PLE and PL spectra for MC-RV, which was eroded by vanadate ions. The excitation spectrum consisted of a strong and broad absorption band ranging from 200 to 350 nm, which was assigned to the energy transfer from VO₃⁻ to Eu³⁺. The overlapped excitation was from 2 individual bands located at ~275 nm and ~323 nm, which corresponded to the transitions of ${}^{1}A_{2}({}^{1}T_{1}) \rightarrow {}^{1}E$ (${}^{1}T_{2}$) and ${}^{1}A_{2}({}^{1}T_{2}) \rightarrow {}^{1}A_{1}$ (${}^{1}E$) of V⁵⁺, respectively [25,26]. The band at ~255 nm was the contribution of the $O^{2-}Eu^{3+}$ charge transfer [7–9], while the very weak transitions of ${}^{7}F_{0,1} \rightarrow {}^{5}L_{6}$ and ${}^{7}F_{0,1} \rightarrow {}^{5}D_{2}$ at 395 nm and 463 nm for Eu³⁺ were observed in the excitation spectra [7–9]. Since the strongest excitation was located at ~323 nm, the excitation wavelength was chosen as 323 nm $({}^{1}A_{2}({}^{1}T_{2}) \rightarrow {}^{1}A_{1}$ (${}^{1}E$) transition of V⁵⁺). Upon UV excitation at 323 nm, the PL spectra displayed strong emissions at 540 nm, 590 nm, 617 nm, 650 nm, and 702 nm, which were assigned to ${}^{5}D_{1} \rightarrow {}^{7}F_{0,1}$, ${}^{5}D_{0} \rightarrow {}^{7}F_{1}$, ${}^{5}D_{0} \rightarrow {}^{7}F_{2}$, ${}^{5}D_{0} \rightarrow {}^{7}F_{3}$, and ${}^{5}D_{0} \rightarrow {}^{7}F_{4}$ transitions of Eu³⁺, respectively. tively. The emission at 617 nm attained the dominate role. This further confirmed the existence of VO₃⁻ \rightarrow Eu³⁺ energy transfer. Interestingly, the emission intensity at 617 nm was greatly enhanced by increasing the R value from 0 to 0.25, indicating that the VO₃-→Eu³⁺ energy transfer contributed to the improved luminescence. The external/internal quantum efficiencies for R = 0 were $6 \pm 1\%/11 \pm 1\%$, and the external/internal quantum efficiencies for R = 0.25 were $36 \pm 1\%/65 \pm 1\%$, directly confirm the great enhancement of luminescence. However, a higher R value induced a rougher particle surface, which contributed to the light scattering and quenching of the luminescence. Therefore, increasing the R value further resulted in the luminescent decay. The external/internal quantum efficiencies for R = 0.5, R = 1.0, and R = 1.5 were $25 \pm 1\%/49 \pm 2\%$, 18 $\pm 2\%/43 \pm 1\%$, and $10 \pm 1\%/37 \pm 2\%$, respectively. However, the emission intensity for MC-RV is evidently stronger than that for MC on the whole, indicating that the erosion of the surface of rare earth microcrystals through vanadate ions can contribute to the considerable improvement to luminescence (Figure 10).



Figure 9. (a) PLE and (b) PL spectra for MC and MC-RV at room temperature.



Figure 10. Schematic illustration of VO₃⁻→Eu³⁺ energy transfer.

The decay kinetics of the ${}^{5}\text{D}_{0} \rightarrow {}^{7}\text{F}_{2}$ transition at 617 nm for MC and MC-*R*Vre a investigated in Figure 11. All the fluorescence decay curves can be fitted to single exponentials. The average lifetimes of the MC, MC-0.25V, MC-0.50V, MC-1.0V, and MC-1.5V samples determined in this work are ~0.67 ms, ~1.38 ms, ~1.21 ms, ~1.14 ms, and ~1.12 ms, respectively. Evidently, the lifetime for MC-*RV* is longer than that for MC, since the energy transfer of VO₃⁻ to Eu³⁺ is more time consuming.



Figure 11. Fluorescence decay curves for the 617 nm emission of MC and MC-RV.

4. Conclusions

In the present study, prismatic microcrystals of RE4O(OH)₉NO₃ (RE = Y, Eu) were synthesized by a hydrothermal reaction (180 °C for 24 h, pH = 10–11). The surface modification of the microcrystals was successfully achieved by eroding the surface of the microcrystals through vanadate ions. The main means of sample characterization were XRD, TEM, SAED, STEM, PLE/PL spectroscopy, and fluorescence decay curve analysis. The reaction with VO₃⁻ contributed to the formation of amorphous particles containing VO₃⁻ on the surface of the prism, which was similar to the surface corrosion of metal, called "surface eroding". Upon UV excitation at 323 nm ($^{1}A_{2}(^{1}T_{2})\rightarrow ^{1}A_{1}$ (^{1}E) transition of V⁵⁺), the modified microcrystals displayed a strong red emission at 617 nm ($^{5}D_{0}\rightarrow ^{7}F_{2}$ transition of Eu³⁺). As a result of the VO₃⁻ \rightarrow Eu³⁺ energy transfer, the emission intensity at 617 nm for the modified microcrystals increased greatly after modification by vanadate ions. Additionally, due to the VO₃⁻ \rightarrow Eu³⁺ energy transfer, the modified microcrystals exhibited longer lifetimes. The usage of the energy transfer to the activated RE³⁺ ions through surface eroding processing for rare earth compounds recommends a new paradigm for luminescence improvement.

Author Contributions: Writing-original draft preparation, data curation, J.Q.; Formal analysis, investigation, J.L.; Conceptualization, writing-review and editing, visualization, Q.Z. All authors have read and agreed to the published version of the manuscript.

Funding: This research was founded by the Natural Science Foundation of Liaoning Province (Grant 2020-MS-081) and the National Natural Science Foundation of China (Grant 51302032).

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable

Data Availability Statement: Data sharing is not applicable to this article.

Acknowledgments: This work was supported in part by the Natural Science Foundation of Liaoning Province (Grant 2020-MS-081) and the National Natural Science Foundation of China (Grant 51302032).

Conflicts of Interest: The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

References

- 1. Blasse, G.; Grabmaier, B.C. Luminescent Materials; Springer: Berlin/Heidelberg, Germany, 1994.
- Gai, S.L.; Li, C.X.; Yang, P.P.; Lin, J. Recent progress in rare earth micro/nanocrystals: Soft chemical synthesis, luminescent properties, and biomedical applications. *Chem. Rev.* 2014, *114*, 2343–2389.
- Zhu, Q.; Li, J.-G.; Ma, R.; Sasaki, T.; Yang, X.; Li, X.D.; Sun, X.D.; Sakka, Y. Well-defined crystallites autoclaved from the nitrate/NH₄OH reaction system as the precursor for (Y,Eu)₂O₃ red phosphor: Crystallization mechanism, phase and morphology control, and luminescent property. J. Solid State Chem. 2012, 192, 229–237.
- Zhang, F.; Zhao, D.Y. Synthesis of uniform rare earth fluoride (NaMF4) nanotubes by *in situ* ion-exchange from their hydroxide [M(OH)3] parents. ACS Nano 2009, 3, 159–164.
- Xie, J.-H.; Wang, J.; Qiu, G.-H.; Li, X.-B.; Huang, W.-T.; Zhang, R.-R.; Lin, T.; Wang, L.-X.; Zhang, Q.-T. A strategy to achieve efficient green-emission dual-mode luminescence of Yb³⁺, Er³⁺ doped NaBiF₄. *Rare Met.* **2021**, *40*, 2040–2048.
- Fu, R.; Hu, Y.-Y.; Qiao, H.-N.; Yang, C.-L.; Yin, H.; Qu, M.-G. Luminescence property and magnetic resonance imaging of Gd₂O₃:Tb³⁺ nanocrystals doped with Zn²⁺, Li⁺. *Rare Met.* 2021, 40, 2049–2058.
- 7. Geng, F.X.; Ma, R.Z.; Sasaki, T. Anion-exchangeable layered materials based on rare-earth phosphors: Unique combination of rare-earth host and exchangeable anions. *Acc. Chem. Res.* **2010**, *43*, 1177–1185.
- Xu, Z.H.; Kang, X.J.; Li, C.X.; Hou, Z.Y.; Zhang, C.M.; Yang, D.M.; Li, G.G.; Lin, J. Ln³⁺ (Ln=Eu, Dy, Sm, and Er) ion-doped YVO₄ nano/microcrystals with multiform morphologies: Hydrothermal synthesis, growing mechanism, and luminescent properties. *Inorg. Chem.* 2010, 49, 6706–6715.
- Li, G.C.; Chao, K.; Peng, H.R.; Chen, K.Z. Hydrothermal synthesis and characterization of YVO₄ and YVO₄:Eu³⁺ nanobelts and polyhedral micron crystals. J. Phys. Chem. C2008, 112, 6228-6231.
- Li, C.X.; Quan, Z.W.; Yang, J.; Yang, P.P.; Lin, J. Highly uniform and monodisperse -NaYF₄:Ln³⁺ (Ln = Eu, Tb, Yb/Er, and Yb/Tm) hexagonal microprism crystals: Hydrothermal synthesisand luminescent properties. *Inorg. Chem.* 2007, 46, 6329–6337.

- 11. Selvi, G.T.; Grace, A.N.; Jeong, S.K. Synthesis of rare earth hydroxycarbonate (LaOHCO₃) nanocrystals with tuneable morphology and luminescence properties. *Adv. Powder Technol.* **2020**, *31*, 2366–2378.
- Zhang, Y.; Wu, Z.; Geng, D.; Kang, X.; Shang, M.; Li, X.; Lian, H.; Cheng, Z.; Lin, J.; Full color emission in ZnGa₂O₄: Simultaneous control of the spherical morphology, luminescent, and electric properties via hydrothermal approach. *Adv. Funct. Mater.* 2014, 24, 6581–6593.
- 13. Allendorf, M.D.; Bauer, C.A.; Bhakta, R.K.; Houk, R.J.T. Luminescent metal-organic frameworks. *Chem. Soc. Rev.* 2009, 38, 1330–1352.
- 14. Zhu, Q.; Li, S.Y.; Wang, Q.; Qi, Y.; Li, X.D.; Sun, X.D.; Li, J.-G. Grafting of terbium (III) complexes onto layered rare-earth hydroxide nanosheets to fabricate novel optical fiber temperature sensors. *Nanoscale* **2019**, *11*, 2795–2804.
- 15. Zhu, Q.; Ding, S.N.; Xiahou, J.Q.; Li, S.Y.; Xu, X.D.; Li, J.-G. A groundbreaking strategy for fabricating YAG:Ce³⁺ transparent ceramic film via sintering of LRH nanosheets on sapphire. *Chem. Commun.* **2020**, *56*, 12761–12764.
- Zhu, Q.; Liu, J.J.; Li, X.D.; Li, J.-G. Grafting organic antenna onto rare earth hydroxynitrate nanosheets for excitation-dependent and greatly enhanced photoluminescence by multi-modal energy transfer. *Appl. Surf. Sci.* 2019, 489, 142–148.
- 17. Zhu, Q.; Song, C.Y.; Tong, W.P.; Li, J.-G. Controllable phase/morphology tailoring of REF₃ and NaREF₄ (RE=La-Lu, Y), and insights into the up-conversion luminescence of GdF₃:Yb³⁺/Tm³⁺ spheres. *Adv. Powder Technol.* **2020**, *31*, 2235–2243.
- 18. Fan, X.F.; Gu, L.Q.; Hu, Y.L.; Zhu, Q. Wearing an organic "coat" on nanocrystals of LaF₃:Eu³⁺ to generate dynamic luminescence for optical anti-counterfeit. *Adv. Powder Technol.* **2021**, *32*, 2645–2653.
- 19. Okubo, K.; Shigeta, T. Absolute fluorescent quantum efficiency of NBS phosphor standard sample. J. Illum. Eng. Inst. Jpn. 1999, 83, 87–93.
- 20. Shannon, R.D. Revised effective ionic radii and systematic studies of interatomic distances in halides and chalcogenides. *Acta Cryst.* **1976**, *A32*, 751–767.
- 21. Jeong, H.; Lee, B.-I.; Byeon, S.-H. Antenna effect on the organic spacer-modified Eu-doped layered gadolinium hydroxide for the detection of vanadate ions over a wide pH range. *ACS Appl. Mater. Interfaces* **2016**, *8*, 10946–10953.
- 22. Nakamoto, K. Infrared Spectra of Inorganic and Coordination Compounds; John Wiley & Sons: New York, NY, USA, 1963.
- 23. Gadsden, J.A. Infrared Spectra of Minerals and Related Inorganic Compounds; Butterworths: London, UK, 1975.
- 24. Zhang, L.Z.; Wang, Z.H.; Huang, J.; Tang, F. Fabrication and photoluminescence properties of Eu³⁺ doped Y₂O₃ ceramic fiber with high aspect ratio. *Chin. J. Lumin.* **2021**, *4*, 1891–1899.
- Huang, S.; Wang, Z.H.; Zhu, Q.; Shi, X.F.; Wang, X.J.; Li, X.D.; Sun, X.D.; Li, J.-G. A new protocol for templated synthesis of YVO4: Ln luminescent crystallites (Ln=Eu, Dy, Sm). J. Alloys Compd. 2019, 776, 773–781.
- 26. Hsu, C.; Powell, R.C. Energy transfer in europium doped yttrium vanadate crystals. J. Lumin. 1975, 10, 273–293.