

Supplementary Materials: Anchoring Monodispersed NiSe@Ni Particles on Graphene for Energy Storage in Supercapacitors

Xianbin Xiao ^{1,†}, Fangzhou Jin ^{1,†}, Zhongsheng Pu ^{1,*}, Peng Zhu ¹, Zhiqiang Wei ¹, Hua Yang ¹ and Jinlong Jiang ^{1,2,*}

¹ Department of Physics, School of Science, Lanzhou University of Technology, Lanzhou 730050, China; xxianbin29@163.com (X.X.); hyang@lut.edu.cn (H.Y.)

² Shandong Laboratory of Yantai Advanced Materials and Green Manufacturing, Yantai 264006, China

* Correspondence: zhongshengpu@126.com (Z.P.); jinlong@amgm.ac.cn (J.J.)

† These authors contributed equally to this work.




Figure S1. (a) CV curves. (b) GCD curves. (c) Specific capacities.

Table S1. Comparison between transition metal selenides and graphene composite of electrode materials.

Material	Electrolyte	Current density (A g ⁻¹)	Specific capacity (mAh g ⁻¹)	Ref.
NiSe NNs	3 M KOH	1.0	147	43
NiSe/Ni ₃ S ₂	3 M KOH	1.0	125	44
NiSe/ZnSe	3 M KOH	1.0	267	45
NiSe ₂	4 M KOH	1.0	104	46
CNT@NiSe/SS	3 M LiOH	1.0	126	47
NiSe@Ni/graphene	2 M KOH	1.0	302	This work