

Article

MDPI

A Suppression Method for Elution of F^- , $[B(OH)_4]^-$, AsO₄³⁻, and CrO₄²⁻ from Industrial Wastes Using Some Inhibitors and Crushed Stone Powder

Xiaoxu Kuang ^{1,*}, Atsuki Sentoku ¹, Atsushi Sasaki ² and Masatoshi Endo ¹

- ¹ Department of Chemistry and Chemical Engineering, Graduate School of Science and Engineering, Yamagata University, Jonan, Yonezawa 4-3-16, Yamagata 992-8510, Japan; trm67478@st.yamagata-u.ac.jp (A.S.); endomasa@yz.yamagata-u.ac.jp (M.E.)
- ² Department of Chemistry and Chemical Engineering, Faculty of Engineering, Yamagata University, Jonan, Yonezawa 4-3-16, Yamagata 992-8510, Japan; atsushi@yz.yamagata-u.ac.jp
- * Correspondence: kuangmeinv@hotmail.com; Tel.: +81-070-4201-8226

Received: 20 July 2018; Accepted: 14 August 2018; Published: 19 August 2018



Abstract: The disposal and the reuse of industrial wastes have become increasingly difficult due to the elution of hazardous anions, such as F^- , $[B(OH)_4]^-$, AsO_4^{3-} , and CrO_4^{2-} . Effective methods for removing hazardous ions and reusing solid wastes are urgently required. In this study, $Ca(OH)_2$, $MgCl_2$, and $BaCl_2$ were added to reduce the elution concentrations of F, B, As, and Cr by coprecipitating insoluble inorganic salts. After this, ordinary Portland cement (OPC) was added to the ion exchange and solidified with these hazardous ion-containing substances. The addition of crushed stone powder (CSP), which was a by-product of the process of crushing aggregates or sawing stone, inhibited the elution of hazardous ions and improved the inhibition effect of OPC. The elution concentrations of F, B, As, and Cr were successfully reduced from their maximum elution concentration of 10 mg/L to below the environmental standards values of Japan. A simultaneous inhibition method for the elution of F, B, As, and Cr from industrial wastes has been developed successfully and would be able to promote the reuse and recycling of CSP and other industrial wastes.

Keywords: hazardous anions; solidification; crushed stone powder

1. Introduction

Fluoride (F, F⁻), boron (B, $[B(OH)_4]^-$), arsenate (As(V), AsO₄³⁻), and chromium (Cr(VI), CrO₄²⁻), which are eluted from industrial wastes, such as slag, incineration ash, and so on, are usually present as anions and oxyanions. The environmental standards of the Soil Contamination Countermeasures Law of Japan [1] stipulate that the maximum concentration values of F, B, As(V), and Cr(VI) are 0.8, 1.0, 0.01, and 0.05 mg/L, respectively. It is difficult to remove these harmful ions due to their high solubility. The disposal and the reuse of hazardous ion-containing industrial wastes have become increasingly important. In Japan, intermediate waste treatment, such as burning, crushing, and so on, has been carried out to reduce the quantity of the industrial wastes. However, there are still about 17.2 million cubic meters of wastes in 2014, which are left in landfills due to the presence of hazardous materials [2]. A stabilization/solidification (S/S) process using cement and other cementitious materials has become increasingly popular in the immobilization of hazardous ions and oxyanions [3–8]. The immobilization of wastes or contaminates has been reported that may involve the three following mechanisms: (a) chemical fixation of the contaminate, which occurs by chemical reaction between hydration products of the cement and the contaminate; (b) physical adsorption of the contaminate on the surface of the hydration products of the cements; and (c) encapsulation of the contaminate in the pores of the cement [8]. In addition, ettringite $[Ca_6Al_2(SO_4)_3(OH)_{12} \cdot 26H_2O]$, which is formed during the hydration

of ordinary Portland cement (OPC), showed a high removal preference for F [9–11], B [11–15], As [16,17], and Cr [12,18–21] due to its ion exchange capacity by replacing SO_4^{2-} of ettringite. In our precious study, F concentration eluted from CaF₂ pure reagent could be reduced from 288.5 mg/L to 0.47 mg/L in alkaline regions with the addition of Ca(OH)₂, MgCl₂, and OPC [22]. The coprecipitation effect of Ca^{2+} , ion exchange effect of ettringite, and solidification effect of Ca-bearing hydrates contribute to the decrease in the elution concentration of F. This has been successfully applied for the inhibition of F eluted from paper sludge and coal ash. This method allows treated fluorine-containing wastes to be applied as earth cover or road bed materials. We also studied the solidification/stabilization of arsenic in red mud and gypsum [23,24]. The As concentrations eluted from these wastes were successfully reduced to below the required environmental standards (As ≤ 0.01 mg/L) using Fe(III) and/or Fe(II). The elution of As was reduced by forming insoluble Fe–As compounds, such as FeAsO₄, using Fe(III), and/or Fe(II). Gypsum waste was successfully reused as a soil conditioner without arsenic contamination. However, this method was only carried out under weak acidic conditions and Fe-As compounds subsequently have a strong dependence on pH [25–28]. Moreover, there are usually many hazardous ions, such as F^- , $[B(OH)_4]^-$, AsO_4^{3-} , and CrO_4^{2-} , that coexist in these industrial wastes. These hazardous ions usually need to be treated separately under certain conditions with different reagents, which further complicates the disposal and the reuse of industrial wastes. An effective method for the simultaneous suppression of these hazardous ions and the reuse of industrial wastes is urgently required.

Crushed stone powder (CSP) occurs as a waste by-product from the process of crushing aggregates or sawing stone. The generation rate of CSP during manufacturing processes was 1–25% [29–34]. This suggests that a considerable quantity of CSP would be generated in countries that are rich in the rock deposits, such as Portugal, Spain, and so on. It is difficult to utilize or dispose of this CSP because of its small grain size, the mixing of metals, and so on [31]. Therefore, it is generally disposed of in landfills. However, because of the continuous depletion of natural resources, the limited landfill land available, and increased transportation costs, there is a demand for the effective utilization of CSP. In recent years, there have been an increasing number of studies that focus on the recycling of CSP in concrete instead of in silica powder or sand [35–39]. However, further utilization of CSP in inhibiting the elution of hazardous ions is rarely found.

The aim of this study is to develop an effective method to suppress the elution of F^- , $[B(OH)_4]^-$, AsO_4^{3-} , and CrO_4^{2-} from industrial wastes and to improve the reuse and recycling of CSP and other industrial wastes.

2. Materials and Methods

2.1. Materials

For the hazardous ions, the standard solutions of $[B(OH)_4]^-$ (B 1000 mg/L), AsO₄³⁻ (As 1000 mg/L), and CrO₄²⁻ (Cr 1000 mg/L) were supplied by Kanto Chemical Co., Inc., Tokyo, Japan. F⁻ standard solution (1000 mg/L) was made from NaF (99.0%, Kanto Chemical Co., Inc., Japan). The additives, which were namely Ca(OH)₂ (96.0%), MgCl₂·6H₂O (99.0%), FeSO₄ (99.0%), and BaCl₂ (99.0%), were supplied by Kanto Chemical Co., Inc., Japan. OPC was supplied by Sumitomo Osaka Cement Co., Ltd., Tokyo, Japan. CSP, which was derived from the Fukushima areas of Japan, was supplied by Kanno saiseki Co., Ltd., Japan. The phase composition of CSP was characterized by X-ray diffraction. Chemical compositions and elution concentrations of the hazardous ions were determined according to the testing methods for industrial wastewater of Japan (JIS K 0102) [40] using ion chromatography and inductively coupled plasma mass spectrometer with lithium metaborate fusion method [41]. The equipment used in this study were a Perkin Elmer coupled plasma mass spectrometer (ICP-MS, ELAN DRC II, Kanagawa, Japan), Dionex ion chromatography (IC, DX-100, Tokyo, Japan), Shimadzu atomic absorption spectrophotometers (AAS,

AA7000HVG, Japan), Rigaku multipurpose X-ray diffraction spectrometer (XRD, Ultima IV, Tokyo, Japan), and Hitachi field emission scanning electron microscope (SEM, SU8000, Tokyo, Japan).

2.2. Methods

For the hazardous ions, a solution containing 200 mg/L of F, B, As, and Cr was made from 1000 mg/L of the abovementioned standard solutions of hazardous ions. A total of 5 mL of hazardous ions solution was mixed with 7 g of CSP, 3.0 g of OPC, 0.5 g of Ca(OH)₂, 0.4 g of MgCl₂, and 0.00, 0.10, 0.20, 0.30, and 0.40 g of BaCl₂. The mixed samples were stirred for 30 min with a stirring glass rod in a polypropylene bottle before being dried at room temperature for 48 h in a phenol culture dish ($\Phi = 85$ mm). The dried samples were crushed into a powder and subsequently placed in polypropylene bottles with water so that the water-to-sample ratio was 10:1. After this, they were shaken with a laboratory shaker (SA300, Yamato, Japan) at 200 rpm for 6 h before being filtered through 5C filter paper after centrifuging at 3000 rpm for 20 min with a low-speed centrifuge (LC-120, TOMY, Tokyo, Japan). The elution examination of dried samples was conducted according to the testing methods for industrial wastewater of Japan (JIS K 0102).

The pH measurements of the filtrates were obtained with a pH Meter (F-22, Horiba, Japan). The elution concentration of F was measured using IC. B and Cr were measured using ICP-MS. As was measured using AAS with a hydride generator. In addition, the crystal structure and phase composition of dried samples were characterized by XRD. The microstructures of the dried mixtures were examined using SEM.

3. Results and Discussion

The solutions of hazardous ions (200 mg/L) were added and mixed with CSP and OPC so that the maximum elution concentrations of these hazardous ions during elution examination were 10 mg/L in the case where all hazardous ions had been eluted.

A decrease in the elution concentrations of F, B, As, and Cr was observed with an addition of CSP (Table 1). The elution concentrations of these hazardous ions were 7.15, 8.60, 2.75, and 4.46 mg/L (pH = 8.6), respectively, after the elution experiment. CSP is mainly comprised of components of quartz (SiO₂, File No. 01-046-1045) and albite (NaAlSi₃O₈, File No. 01-001-0739) (Figure 1). Furthermore, it has a high content of SiO₂ (52.9%) and Al₂O₃ (14.4%) (Table 2). In recent years, geopolymer as a type of alkali-activated aluminosilicates, such as calcium aluminosilicate hydrate and alkali aluminosilicate, was reported to immobilize hazardous ions [5,8,42,43]. Albite belongs to a type of sodium aluminosilicate. Geopolymer created from albite would form during the mixing of CSP and water. The forming of the geopolymer would greatly contribute to the immobilization of hazardous ions. The pH values of the filtrates of all the samples were above 12.2 with an addition of OPC. The inhibitory effects of OPC and CSP on the elution of F, B, As, and Cr are illustrated in Table 1.

Table 1. Experimental conditions and the elution concentrations of F, B, As, and Cr with additions of crushed stone powder (CSP) and/or ordinary Portland cement (OPC).

Sample No.	200 mg/L of Hazardous Ions Solution (mL)	CSP (g)	OPC (g)	Weight Ratio of OPC (wt.%)	Elution Conc. (mg/L)				лH
					F	В	As	Cr	pII
1	4.00	8.00	0.00	0	7.15	8.60	2.75	4.46	8.6
2	1.00	-	2.00	-	0.45	0.01	0.01	4.76	12.4
3	1.72	-	3.43	-	0.65	0.01	0.00	6.29	12.5
4	4.00	-	8.00	-	0.70	0.02	0.00	5.80	12.6
5	5.00	8.00	2.00	20	0.64	0.01	0.00	3.78	12.2
6	5.72	8.00	3.43	30	0.47	0.00	0.00	2.41	12.4
7	8.00	8.00	8.00	50	0.35	0.00	0.00	4.20	12.4



Table 2. Chemical compositions of CSP and elution concentrations of the hazardous ions by the testing methods for industrial wastewater of Japan (JIS K 0102).

Figure 1. XRD pattern analysis of CSP.

3.1. Suppression of F Elution

A significant decrease in the elution concentration of F was observed when only OPC was added. The elution concentration of F was reduced to 0.45 mg/L with an addition of 2.0 g of OPC, which was a value below its environmental standards (F \leq 0.8 mg/L). Portlandite (Ca(OH)₂), calcium silicate hydrates (Ca₃SiO₅ and Ca₂SiO₄), and ettringite (Ca₆Al₂(SO₄)₃OH₁₂·26H₂O) are formed during the hydration of OPC. F could be reduced by coprecipitating CaF_2 [9] due to the high content of Ca^{2+} , which originates from cement hydrates. Our previous studies have shown that the solubility of CaF_2 increases with an increase in pH in the alkaline range due to the competition between F⁻ and OH⁻ [22]. However, ettringite with a high ion exchange capacity was formed during the hydration of OPC, and therefore, the elution of F was inhibited due to the replacement of the exchangeable anion, such as SO_4^{2-} in ettringite by F. The coprecipitation effect of Ca^{2+} , ion exchange effect of ettringite, and solidification effect of Ca-bearing hydrates contribute to the inhibition of the elution of F. Additionally, under the conditions of the same added amount of OPC, the elution concentrations of F were lower than those without additions of CSP. SiO₂ and Al₂O₃ in CSP could improve the solidification effect of Ca-bearing hydrates by becoming involved in the pozzolanic reaction. Furthermore, it is possible for CSP to react with OPC to generate calcium aluminosilicate hydrate and alkali aluminosilicate to immobilize F and other hazardous ions. Moreover, due to its small particle size, CSP could also fill in the gaps of cement paste, enhancing the density of the cement paste and improving the inhibitory effects of OPC.

The reflections assigned to quartz, albite, tricalcium silicate (Ca₃SiO₅, ICSD file No. 00-055-0738), dicalcium silicate (Ca₂SiO₄, ICSD file No. 00-039-0298), calcite (CaCO₃, ICSD file No. 01-072-1937), and portlandite (Ca(OH)₂, ICSD file No. 01-076-0571) were observed in the mixture with OPC and CSP OPC (Figure 2b). The generation of calcium aluminosilicate could not be confirmed by XRD, which is possibly due to the reflections assigned to calcium aluminosilicate being too weak to be seen. Ettringite with a high ion exchange capacity is a rod-like particle with 1–2 μ m length. These particles were confirmed in the SEM images of the mixtures of OPC and the hazardous ions with/without an addition of CSP (Figure 3). Consequently, ettringite would form in the mixtures of OPC and the hazardous

ions with/without an addition of CSP. Hence, the coprecipitation effect of Ca²⁺, ion exchange effect of ettringite, and solidification effect of Ca-bearing hydrates would contribute to the decrease in elution concentrations of these hazardous ions.



Figure 2. XRD patterns of hazardous ions mixed with 8.0 g of OPC (a) with CSP and (b) without CSP.



Figure 3. SEM images of (**a**) CSP and (**b**) OPC before reaction; and hazardous ions mixed with (**c**) 8.0 g of OPC and (**d**) 3.43 g of OPC and 8.0 g of CSP after reaction.

3.2. Suppression of B Elution

B was reported to be precipitated with Ca(OH)₂ and OPC as calcium borate (CaO·B₂O₃·6H₂O) [44–46]. The solution would become alkaline with an addition of OPC. B would be reduced by the formation of calcium borate. In this study, the elution concentration of B was reduced to 0.01 mg/L, which is far less than its environmental standards (B \leq 1.0 mg/L), with an addition of 2.0 g of OPC. The coprecipitation effect of Ca²⁺, ion exchange capacity of ettringite, and solidification effect of Ca-bearing hydrates contribute to the inhibition of the elution of B. However, the coexistence of F and B possibly leads to the generation of BF₄⁻⁻, which further complicates the treatment of F and B [47]. In this study, the elution concentration

of BF_4^- was not detected by IC as the generation of BF_4^- requires certain conditions. The elution concentrations of F and B were all successfully reduced with an addition of OPC.

3.3. Suppression of As Elution

As could be reduced by forming insoluble Ca–As precipitates with Ca²⁺ [48–51], such as Ca₃(AsO₄)₂·*x*H₂O, Ca₅(AsO₄)₃OH, and Ca₄(OH)₂(AsO₄)₂·4H₂O. In alkaline regions, the dominant species of As(V) in solution are HAsO₄²⁻ and AsO₄³⁻ at pH > 7 (Figure 4). Zhu et al. studied the solubility and stability of calcium arsenates under different pH values [48]. The results showed that Ca₃(AsO₄)₂·*x*H₂O, Ca₅(AsO₄)₃OH, and Ca₄(OH)₂(AsO₄)₂·4H₂O were identified in the experiment over a wide range of pH (3.0 < pH < 13.4) and for Ca/As molar ratios between 1.0 and 4.0. In this study, the elution concentration of As was reduced to 0.01 mg/L with an addition of 2.0 g of OPC. This elution concentration meets the environmental standards of As (As ≤ 0.01 mg/L). Due to the high content of Ca²⁺ originating from OPC, the elution of As was inhibited by the coprecipitation effect of Ca²⁺, ion exchange capacity of ettringite, and solidification effect of Ca-bearing hydrates. Additionally, the presence of carbonate (≥0.3 mol/L) would capture Ca²⁺ to generate CaCO₃, suppressing the generation of Ca–As compounds and resulting in the release of As into the aqueous solution [51]. Therefore, the prevention of the carbonation of Ca²⁺ could be a way of promoting the inhibitory effect on As.



Figure 4. Eh–pH diagram for aqueous As species in the system As–O₂–H₂O at 25 °C and 1 bar total pressure. Referred from [52].

3.4. Suppression of Cr Elution

The immobilization of Cr(VI) by OPC was achieved due to the formation of the low solubility complex compounds, such as CaCrO₄ [53,54] and CrO₄-ettringite. CaCrO₄ was formed by the reaction between Cr and Ca²⁺ at a high pH value. CrO₄-ettringite was formed by the ion exchange between CrO₄²⁻ and SO₄²⁻ in ettringite. Some researchers studied the inhibitory effect of calcium silicate hydrate on Cr [55–57]. In the study of Zhang et al., in terms of calcium silicate hydrate (C–S–H), one of the most important hydration products of OPC, it seemed that the chemical incorporation degree of Cr(VI) was relatively low and just a sorption mechanism was more possible [21]. In this study, although the elution concentration of Cr decreased with an addition of OPC, it was still higher than its environmental standards (Cr \leq 0.05 mg/L).

 $Ca(OH)_2$, $MgCl_2$, and $BaCl_2$ were added to decrease the quantity of eluted Cr by forming insoluble salts. The addition of $Ca(OH)_2$ results in a reduction in the elution of F, B, As, and Cr. $MgCl_2$ was able to prevent the carbonation of Ca^{2+} [58,59] and coprecipitate with F and B to create MgF_2 and $Mg[B(OH)_4]_2$. $BaCl_2$ could suppress the elution of Cr by coprecipitating into the form of $BaCrO_4$ [60].

Additionally, As could also react with Ba^{2+} to form the insoluble salt $Ba_3(AsO_4)_2$ ($K_{sp} = 2.59 \times 10^{-9}$, 20 °C), which is stable within the pH range of 12–14 [61]. FeSO₄ was added to compare the inhibitory effect on Cr with $BaCl_2$.

The pH values of the filtrates of all the samples were above 12.1 with the additions of CSP, OPC, Ca(OH)₂, MgCl₂, and BaCl₂. The elution concentration of Cr decreased significantly with these additives and further decreased with an increase in the added amount of BaCl₂ (Figure 5). When 0.2 g of BaCl₂ was added, the Cr elution concentration was reduced to 0.01 mg/L, which is below its environmental standard value. In contrast, the lowest elution concentration of total Cr, which was in the forms of Cr(VI) and Cr(III), was 0.14 mg/L with an addition of FeSO₄. BaCl₂ is obviously superior to FeSO₄ in reducing the elution of Cr in this study. On the one hand, FeSO₄ inhibited Cr(VI) by reducing it to Cr(III). This process was generally carried out under acidic conditions. Otherwise, Fe(II) would react with OH^- to form $Fe(OH)_2$ before oxidizing in the air to form $Fe(OH)_3$ and weakening its reduction ability. Moreover, Cr(VI) could be separated from Fe(II) by the generation of floccules, which are namely $Fe(OH)_2$ and/or $Fe(OH)_3$, resulting in a decrease in the inhibiting effect on Cr [62]. On the other hand, additional operations are required to suppress Cr(III) after reduction reaction. Therefore, the treatment of Cr by BaCl₂ was simpler and more effective than FeSO₄. In addition, it was easy to react BaCl₂ with SO₄²⁻ to generate the insoluble salt BaSO₄ (K_{sp} , BaSO₄ = 2.45 × 10⁻⁴, 20 °C) due to its low solubility. This would lead to a reduction in the amount of SO_4^{2-} of gypsum, which plays an important role in the composition of ettringite, resulting in the suppression of the hydration of OPC [63,64]. Therefore, the added amount of BaCl₂ should be controlled. In this study, the elution concentrations of F, B, and As were 0.20, 0.18, and 0.00 mg/L, respectively, with additions of CSP, OPC, Ca(OH)₂, MgCl₂, and 0.2 g of BaCl₂, while there were no obvious changes with an increase in the added amount of BaCl₂. The elution concentrations of F, B, As, and Cr were successfully inhibited to be lower than the environmental standards values with additions of CSP, OPC, Ca(OH)₂, MgCl₂, and 0.2 g of $BaCl_2$.



Figure 5. The elution concentrations of Cr with additions of 7.0 g of CSP, 3.0 g of OPC, 0.5 g of Ca(OH)₂, 0.4 g of MgCl₂, and a certain amount of BaCl₂ and FeSO₄.

4. Conclusions

The elution concentrations of F, B, As, and Cr were successfully reduced from their maximum elution concentrations of 10 mg/L to below the environmental standards values with the additions of Ca(OH)₂, MgCl₂, BaCl₂, OPC, and CSP. Metal salts reduced the elution concentrations of F, B, As, and Cr by coprecipitation into insoluble inorganic salts. After this, OPC was added to the ion exchange and solidified with these hazardous ion-containing substances. The addition of CSP inhibited the elution of hazardous ions and improved the inhibition effect of OPC. A simultaneous inhibition method for the elution of F, B, As, and Cr from industrial wastes has been developed successfully and would be able to promote the reuse and recycling of industrial wastes.

Author Contributions: A.S. and X.K. performed the experiments; X.K. wrote the paper; and A.S. and M.E. reviewed and edited the manuscript. M.E. supervised the findings of this work. All authors discussed the results and contributed to the final manuscript.

Funding: This research received external funding.

Conflicts of Interest: The authors declare no conflicts of interest.

References

- 1. Environmental Quality Standards for Soil Pollution. Ministry of the Environment Government of Japan. Available online: https://www.env.go.jp/en/water/soil/sp.html (accessed on 18 August 2018).
- 2. Japan Industrial Waste Information Center. Available online: http://www.jwnet.or.jp/waste/knowledge/genjou.html (accessed on 18 August 2018).
- 3. Chrysochoou, M.; Dermatas, D. Evaluation of ettringite and hydrocalumite formation for heavy metal immobilization: Literature review and experimental study. *J. Hazard. Mater.* **2006**, *136*, 20–33. [CrossRef] [PubMed]
- Montañés, M.T.; Sánchez-Tovar, R.; Roux, M.S. The effectiveness of the stabilization/solidification process on the leachability and toxicity of the tannery sludge chromium. *J. Environ. Manag.* 2014, 143, 71–79. [CrossRef] [PubMed]
- 5. Kim, H.T.; Lee, T.G. A simultaneous stabilization and solidification of the top five most toxic heavy metals (Hg, Pb, As, Cr, and Cd). *Chemosphere* **2017**, *178*, 479–485. [CrossRef] [PubMed]
- Baek, J.W.; Choi, A.E.S.; Park, H.S. Solidification/stabilization of ASR fly ash using Thiomer material: Optimization of compressive strength and heavy metals leaching. *Waste Manag.* 2017, 70, 139–148. [CrossRef] [PubMed]
- Liu, S.J.; Jiang, J.Y.; Wang, S.; Guo, Y.P.; Ding, H. Assessment of water-soluble thiourea-formaldehyde (WTF) resin for stabilization/solidification (S/S) of heavy metal contaminated soils. *J. Environ. Manag.* 2018, 346, 167–173. [CrossRef] [PubMed]
- Al-Mashqbeh, A.; Abuali, S.; El-Eswed, B.; Khalili, F.I. Immobilization of toxic inorganic anions (Cr₂O₇²⁻, MnO₄⁻ and Fe(CN)₆³⁻) in metakaolin based geopolymers: A preliminary study. *Ceram. Int.* 2018, 44, 5613–5620. [CrossRef]
- 9. Kang, W.H.; Kim, E.I.; Park, J.Y. Fluoride removal capacity of cement paste. *Desalination* **2007**, 202, 38–44. [CrossRef]
- 10. Park, J.Y.; Byun, H.J.; Choi, W.H.; Kang, W.H. Cement paste column for simultaneous removal of fluoride, phosphate, and nitrate in acidic wastewater. *Chemosphere* **2008**, *70*, 1429–1437. [CrossRef] [PubMed]
- 11. Tsunashima, Y.; Iizuka, A.; Akimoto, J.; Hongo, T.; Yamasaki, A. Preparation of sorbents containing ettringite phase from concrete sludge and their performance in removing borate and fluoride ions from waste water. *Chem. Eng. J.* **2012**, 200–202, 338–343. [CrossRef]
- 12. Zhang, M.; Reardon, E.J. Removal of B, Cr, Mo, and Se from wastewater by incorporation into hydrocalumite and ettringite. *Environ. Sci. Technol.* 2003, *37*, 2947–2952. [CrossRef] [PubMed]
- 13. Hiraga, Y.; Shigemoto, N. Boron uptake behavior during ettringite synthesis in the presence of H₃BO₃ and in a suspension of ettringite in H₃BO₃. *J. Chem. Eng. Jpn.* **2010**, *43*, 865–871. [CrossRef]
- 14. Hongo, T.; Tsunashima, Y.; Sakai, Y.; Iizuka, A.; Yamasaki, A. A comparative borate adsorption study of ettringite and metaettringite. *Chem. Lett.* **2011**, *40*, 1269–1271. [CrossRef]
- 15. Sasaki, T.; Sakai, Y.; Hongo, T.; Iizuka, A.; Yamasaki, A. Preparation of a solid adsorbent derived from concrete sludge and its boron removal performance. *Ind. Eng. Chem. Res.* **2012**, *51*, 5813–5817. [CrossRef]
- 16. Myneni, S.C.B.; Traina, S.J.; Logan, T.J.; Waychunas, G.A. Oxyanion behavior in alkaline environments: Sorption and desorption of arsenate in ettringite. *Environ. Sci. Technol.* **1997**, *31*, 1761–1768. [CrossRef]
- 17. Tolonen, E.T.; Hu, T.; Rämö, J.; Lassi, U. The removal of sulphate from mine water by precipitation as ettringite and the utilisation of the precipitate as a sorbent for arsenate removal. *J. Environ. Manag.* **2016**, *181*, 856–862. [CrossRef] [PubMed]
- Karamalidis, A.K.; Voudrias, E.A. Release of Zn, Ni Cu, SO₄²⁻ and CrO₄²⁻ as a function of pH fromcement-based stabilized/solidified refinery oily sludge and ash from incineration of oily sludge. *J. Hazard. Mater.* 2007, 141, 591–606. [CrossRef] [PubMed]

- Peyronnard, O.; Benzaazoua, M.; Blanc, D.; Moszkowicz, P. Study of mineralogy and leaching behavior of stabilized/solidified sludge using differential acid neutralization analysis, Part I: Experimental study. *Cem. Concr. Res.* 2009, 39, 600–609. [CrossRef]
- 20. Leisinger, S.M.; Bhatnagar, A.; Lothenbach, B.; Johnson, C.A. Solubility of chromate in a hydrated OPC. *Appl. Geochem.* **2014**, *48*, 132–140. [CrossRef]
- 21. Zhang, M.; Yang, C.; Zhao, M.; Yu, L.; Yang, K.; Zhu, X.; Jiang, X. Immobilization of Cr(VI) by hydrated Portland cement pastes with and without calcium sulfate. *J. Hazard. Mater.* **2018**, *342*, 242–251. [CrossRef] [PubMed]
- 22. Kuang, X.; Sasaki, A.; Endo, M. The inhibition of fluoride elution from industrial wastes with Portland cement, calcium and magnesium salts in alkaline region. *J. Ion Exc.* **2018**, in press.
- 23. Yang, D.; Sasaki, A.; Endo, M. Solidification/stabilization of arsenic in red mud upon addition of Fe(III) or Fe(III) and Al(III) dissolved in H₂SO₄. *J. Water Environ. Technol.* **2018**, *16*, 115–126. [CrossRef]
- 24. Yang, D.; Sasaki, A.; Endo, M. Reclamation of a waste arsenic-bearing gypsum as a soil conditioner via acid treatment and subsequent Fe(II)-As stabilization. *J. Clean. Prod.* **2018**. submitted.
- 25. Langmuir, D.; Mahoney, J.; Rowson, J. Solubility products of amorphous ferric arsenate and crystalline scorodite (FeAsO₄·2H₂O) and their application to arsenic behavior in buried mine tailings. *Geochim. Cosmochim. Acta* 2006, *70*, 2942–2956. [CrossRef]
- 26. Bluteau, M.C.; Demopoulos, G.P. The incongruent dissolution of scorodite–solubility, kinetics and mechanism. *Hydrometallurgy* **2007**, *87*, 163–177. [CrossRef]
- 27. Daenzer, R.; Xu, L.; Doerfelt, C.; Jia, Y.; Demopoulos, G.P. Precipitation behaviour of As(V) during neutralization of acidic Fe(II)–As(V) solutions in batch and continuous modes. *Hydrometallurgy* **2014**, 146, 40–47. [CrossRef]
- Yuan, Z.; Zhang, D.; Wang, S.; Xu, L.; Wang, K.; Song, Y.; Xiao, F.; Jia, Y. Effect of hydroquinone-induced iron reduction on the stability of scorodite and arsenic mobilization. *Hydrometallurgy* 2016, 164, 228–237. [CrossRef]
- 29. Sato, M.; Saeki, T.; Inoshita, I. Characteristics of crushed stone sludge collected as admixture by wet process method. *P. Jpn. Concr. Inst.* **2002**, *24*, 1335–1340. (In Japanese)
- 30. Fukuyama, T.; Fumoto, T.; Ishino, R.; Yamada, M. Study on the utilization of crushed stone powder as admixture for high fluidity concrete. *Jpn. Concr. Inst.* **2003**, *25*, 982–997. (In Japanese)
- 31. Zichella, L.; Bellopede, R.; Spriano, S.; Marini, P. Preliminary investigations on stone cutting sludge processing for a future recovery. *J. Clean. Prod.* **2018**, *178*, 866–876. [CrossRef]
- 32. Çelik, M.Y.; Sabah, E. Geological and technical characterisation of Iscehisar (Afyon-Turkey) marble deposits and the impact of marble waste on environmental pollution. *J. Environ. Manag.* **2008**, *87*, 106–116. [CrossRef] [PubMed]
- 33. Rana, A.; Kalla, P.; Verma, H.K.; Mohnot, J.K. Recycling of dimensional stone waste in concrete: A review. *J. Clean. Prod.* **2016**, 135, 312–331. [CrossRef]
- 34. Chang, F.C.; Lee, M.Y.; Lo, S.L.; Lin, J.D. Artificial aggregate made from waste stone sludge and waste silt. *J. Environ. Manag.* **2010**, *91*, 2289–2294. [CrossRef] [PubMed]
- 35. De'Gennaro, R.; Graziano, S.F.; Cappelletti, P.; Colella, A.; Dondi, M.; Langella, A. Structural concretes with waste-based lightweight aggregates: From landfill to engineered materials. *Environ. Sci. Technol.* **2009**, *43*, 7123–7129. [CrossRef] [PubMed]
- 36. Al-Zboon, K.; Tahat, M.; Abu-Hamatteh, Z.S.; Al-Harahsheh, M.S. Recycling of stone cutting sludge in formulations of bricks and terrazzo tiles. *Waste Manag. Res.* **2010**, *28*, 568–574. [CrossRef] [PubMed]
- 37. Song, T.H.; Lee, S.H.; Kim, B. Recycling of crushed stone powder as a partial replacement for silica powder in extruded cement panels. *Constr. Build. Mater.* **2014**, *52*, 105–115. [CrossRef]
- Park, H.; Jeong, Y.; Jun, Y.; Oh, J.E. Production of price-competitive bricks using a high volume of stone powder sludge waste and blast furnace slag through cementless CaO activation. *Constr. Build. Mater.* 2016, 122, 343–353. [CrossRef]
- 39. Davraz, M.; Ceylan, H.; Topçu, İ.B.; Uygunoğlu, T. Pozzolanic effect of andesite waste powder on mechanical properties of high strength concrete. *Constr. Build. Mater.* **2018**, *165*, 494–503. [CrossRef]
- 40. Japanese Industrial Standard, Japanese Standards Association. JIS K0102: 2016 Testing Methods for Industrial Wastewater. Available online: https://webdesk.jsa.or.jp/books/W11M0090/?bunsyo_id=JIS%20K%200102:2016 (accessed on 18 August 2018).

- 41. Goto, I.O.; Muramoto, J.J.; Ninaki, M. Application of inductively coupled plasma atomic emission spectrometry (ICP-AES) to soil analysis, 3: Total analysis of major elements in soils by lithium metaborate fusion ICP-AES. *Jpn. J. Soil Sci. Plant Nutr.* **1991**, *62*, 521–528.
- 42. Luukkonen, T.; Runtti, H.; Niskanen, M.; Tolonen, E.T.; Sarkkinen, M.; Kemppainen, K.; Rämö, J.; Lassi, U. Simultaneous removal of Ni(II), As(III), and Sb(III) from spiked mine effluent with metakaolin and blast-furnace-slag geopolymers. *J. Environ. Manag.* **2016**, *166*, 579–588. [CrossRef] [PubMed]
- 43. Sun, S.; Lin, J.; Zhang, P.; Fang, L.; Ma, R.; Quan, Z.; Song, X. Geopolymer synthetized from sludge residue pretreated by thewet alkalinizing method: Compressive strength and immobilization efficiency of heavy metal. *Constr. Build. Mater.* **2018**, *170*, 619–626. [CrossRef]
- 44. Masonnave, J.M.C. Immobilization of borates and phosphates with saturated lime solutions. *Solid State Ion*. **1993**, *56*, 133–139.
- 45. Hernández, S.; Guerrero, A.; Gonñi, S. Leaching of borate waste cement matrices: Pore solution and solid phase characterization. *Adv. Cem. Res.* **2000**, *12*, 1–8. [CrossRef]
- 46. Coumes, C.C.D.; Dhoury, M.; Champenois, J.B.; Mercier, C.; Damidot, D. Combined effects of lithium and borate ions on the hydration of calcium sulfoaluminate cement. *Cem. Concr. Res.* **2017**, *97*, 50–60. [CrossRef]
- Wada, H.; Shimizu, K.; Kuroda, Y.; Higuchi, M. Advanced wastewater treatment of tetrafluoroboric acid-hexavalent chromium containing effluent using the ettringite. *J. Surf. Finish. Soc. Jpn.* 2016, 67, 111–117. (In Japanese) [CrossRef]
- 48. Zhu, Y.; Zhang, H.; Liang, Y.; Liu, H.; Zhang, X. Dependence of solubility and stability of calcium arsenates on pH value. *Acta Sci. Circumst.* **2005**, *25*, 1652–1660. (In Chinese)
- 49. Sasaki, T.; Iizuka, A.; Watanabe, M.; Hongo, T.; Yamasaki, A. Preparation and performance of arsenate (V) adsorbents derived from concrete wastes. *Waste Manag.* **2014**, *34*, 1829–1835. [CrossRef] [PubMed]
- 50. Lei, J.; Peng, B.; Min, X.; Liang, Y.; You, Y.; Chai, L. Modeling and optimization of lime-based stabilization in high alkaline arsenic-bearing sludges with a central composite design. *J. Environ. Sci. Health A Tox. Hazard. Subst. Environ. Eng.* **2017**, *52*, 449–458. [CrossRef] [PubMed]
- 51. Lei, J.; Peng, B.; Liang, Y.; Min, X.; Chai, L.; Ke, Y.; You, Y. Effects of anions on calcium arsenate crystalline structure and arsenic stability. *Hydrometallurgy* **2018**, *177*, 123–131. [CrossRef]
- 52. Smedley, P.L. Kinniburgh, D.G. A review of the source, behaviour and distribution of arsenic in natural waters. *Appl. Geochem.* **2002**, *17*, 517–568. [CrossRef]
- 53. Wang, S.; Vipulanandan, C. Solidification/stabilization of Cr(VI) with cement Leachability and XRD analyses. *Cem. Concr. Res.* 2000, *30*, 385–389. [CrossRef]
- 54. Jain, N.; Garg, M. Effect of Cr(VI) on the hydration behavior of marble dust blended cement: Solidification, leachability and XRD analyses. *Constr. Build. Mater.* **2008**, *22*, 1851–1856. [CrossRef]
- Lasheras-Zubiate, M.; Navarro-Blasco, I.; Fernández, J.M.; Álvarez, J.I. Encapsulation, solid-phases identification and leaching of toxic metals in cement systems modified by natural biodegradable polymers. *J. Hazard. Mater.* 2012, 233–234, 7–17. [CrossRef] [PubMed]
- 56. Omotoso, O.E.; Ivey, D.G.; Mikula, R. Characterization of chromium doped tricalcium silicate using SEM/EDS, XRD and FTIR. *J. Hazard. Mater.* **1995**, *42*, 87–102. [CrossRef]
- 57. He, H.; Suito, H. Immobilization of hexavalent chromium in aqueous solution through the formation of 3CaO·(Al, Fe)₂O₃·Ca(OH)₂·*x*H₂O phase, ettringite and C–S–H gel. *ISIJ Int.* **2002**, *42*, 139–145. [CrossRef]
- Lin, Y.P.; Singer, P.C. Effect of Mg²⁺ on the kinetics of calcite crystal growth. J. Cryst. Growth 2009, 312, 136–140. [CrossRef]
- 59. Hong, M.; Xu, J.; Teng, H.H. Evolution of calcite growth morphology in the presence of magnesium: Implications for the dolomite problem. *Geochim. Cosmochim. Acta* **2016**, *172*, 55–64. [CrossRef]
- Kim, E.; Spooren, J.; Broos, K.; Nielsen, P.; Horckmans, L.; Vrancken, K.C.; Quaghebeur, M. New method for selective Cr recovery from stainless steel slag by NaOCl assisted alkaline leaching and consecutive BaCrO₄ precipitation. *Chem. Eng. J.* 2016, 295, 542–551. [CrossRef]
- 61. Zhu, Y.; Zhang, X.; Xie, Q.; Cheng, G.; Wang, D.; Liang, Y.; Lu, J. Solubility and stability of barium arsenate and barium hydrogen arsenate at 25 °C. *J. Hazard. Mater.* **2005**, *120*, 37–44. [CrossRef] [PubMed]
- 62. Chen, D.; Yuan, Y.; Christensen, T.H. Reductive effect of ferrous iron on chromate in alkaline system and its application to controlling chromium leaching from incineration fly ashes. *Acta Sci. Circumst.* **2005**, *25*, 1202–1210. (In Chinese)

- 63. Utton, C.A.; Gallucci, E.; Hill, J.; Milestone, N.B. Interaction between BaCO₃ and OPC/BFS composite cements at 20 °C and 60 °C. *Cem. Concr. Res.* **2011**, *41*, 236–243. [CrossRef]
- 64. Zezulová, A.; Staněk, T.; Opravil, T. The influence of barium sulphate and barium carbonate on the Portland cement. *Procedia Eng.* **2016**, *151*, 42–49. [CrossRef]



 \odot 2018 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (http://creativecommons.org/licenses/by/4.0/).