Article

Sensitive Electrochemical Detection of Tryptophan Using a Hemin/G-Quadruplex Aptasensor

Ayemeh Bagheri Hashkavayi ¹, Jahan Bakhsh Raoof ² and Ki Soo Park ^{1,*}

¹ Department of Biological Engineering, College of Engineering, Konkuk University, Seoul 05029, Korea; elnazbagheri@konkuk.ac.kr

² Electroanalytical Chemistry Research Laboratory, Department of Analytical Chemistry, Faculty of Chemistry, University of Mazandaran, Babolsar 47416-95447, Iran; j.raoof@umz.ac.ir

* Correspondence: akdong486@konkuk.ac.kr

Received: 13 September 2020; Accepted: 12 October 2020; Published: 15 October 2020

Abstract: In this study, we design an electrochemical aptasensor with an enzyme-free amplification method to detect tryptophan (Trp). For the amplified electrochemical signal, the screen-printed electrode was modified with dendritic gold nanostructures (DGNs)/magnetic double-charged diazoniabicyclo [2.2.2] octane dichloride silica hybrid (Fe₃O₄@SiO₂/DABCO) to increase the surface area as well as electrical conductivity, and the hemin/G-quadruplex aptamer was immobilized. The presence of Trp improved the catalytic characteristic of hemin/G-quadruplex structure, which resulted in the efficient catalysis of the H₂O₂ reduction. As the concentration of Trp increased, the intensity of H₂O₂ reduction signal increased, and Trp was measured in the range of 0.007–200 nM with a detection limit of 0.002 nM. Compared with previous models, our sensor displayed higher detection sensitivity and specificity for Trp. Furthermore, we demonstrated that the proposed aptasensor successfully determined Trp in human serum samples, thereby proving its practical applicability.

Keywords: magnetic nanocomposite; aptamer; tryptophan; G-quadruplex; electrochemical sensor; dendritic gold nanostructures

1. Introduction

Tryptophan (Trp), an essential amino acid for humans, serves as a precursor for some biological molecules and structural component in proteins [1,2]. So far, different methods have been reported for measuring Trp, such as high-performance liquid chromatography (HPLC) [3], spectroscopy [4,5], and chemiluminescence [6]. As alternatives, many innovative approaches have been developed. For example, Eser et al. used ultra-HPLC coupled to electrospray ionization triple–quadrupole mass spectrometry to detect Trp [7]. In another study, Hazra et al. used resonance energy transfer between Ce³⁺ and Tb³⁺ ions in Ce³⁺/Tb³⁺-doped CaMoO₄ nanocrystals to detect Trp [8]. However, these methods have the limitations such as complicated sample preparation, long periods of time to acquire measurements, and the need for advanced and costly laboratory tools. Therefore, electrochemical methods are highly regarded as the simple and low-cost alternative that provides sensitive measurements of Trp in samples [9–13].

Recently, aptamers along with antibodies have been used to probe and selectively measure many biological and pharmaceutical compounds [14–18]. Aptamers have many advantages over antibodies. Namely, aptamers have high stability in the presence of different parameters such as pressure, temperature, pH, in vitro synthesis, and labeling with different groups during synthesis [19]. It has been shown that some aptamers catalyze reactions similar to peroxidases [20–23]. For example,

the guanine-rich aptamer that forms a G-quadruplex structure in the presence of hemin catalyzes the reduction of H_2O_2 , which has been used in a wide range of applications [24].

When generating new electrochemical sensors, great attention has been paid to using various nanomaterials to immobilize the aptamer on the electrode surface, which subsequently alters the effective surface area, the electron transfer kinetics, and the sensitivity of the sensor [25–27]. Notably, magnetic nanoparticles have been favorably considered in many studies because of their high surface area, super paramagnetic properties, biocompatibility, and low toxicity [28–31]. However, magnetic nanoparticles have a strong tendency to oxidize and aggregate when exposed to air, which requires them to be coated with other materials. Covering the magnetic nanoparticles with a silica layer increases the stability of the nanoparticles and facilitates surface modification with different functional groups [32–35].

In this study, we first prepared the magnetic nanocomposite as an ionic liquid core-shell structure by sol-gel method in order to improve its conductivity and make it a suitable modifier for the preparation of electrochemical biosensors [31]. Next, dendritic gold nanostructures (DGNs) were electrochemically synthesized on the magnetic double-charged diazoniabicyclo [2.2.2] octane dichloride silica hybrid ($\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}$)-modified screen-printed electrode (SPE) to not only increase the effective surface area and electrical conductivity, but also immobilize guanine-rich Trp aptamer. The presence of Trp allowed Trp aptamer to form hemin/G-quadruplex structure, enabling the efficient catalysis of the H_2O_2 reduction. Because of the dual amplification strategy based on DGNs/ $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}$ and Trp aptamer-hemin-mediated catalysis of H_2O_2 reduction, our sensor showed higher sensitivity than other electrochemical sensors for determining Trp levels. Notably, we discovered that the Trp aptamer-hemin has significantly improved the peroxidase-mimicking activity after binding to Trp, which is successfully utilized for the detection of Trp levels even in human serum.

2. Materials and Methods

2.1. Reagents and Instruments

Hexaammineruthenium (III) ($[\text{Ru}(\text{NH}_3)_6]^{3+}$), 1,4-diazabicyclo[2.2.2]octane, $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$, and $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$, Tetraethyl orthosilicate, tryptophan, tyrosine, histidine, arginine, lysine, valine, and methionine were purchased from Sigma Aldrich (Seoul, Korea). All other chemicals were of analytical grade and supplied from Sigma Aldrich Company. Trp aptamer sequences (5'-SH-(CH_2)₆-AGCAC GTTGGTTAGGTCAGGTTTGGGTTTCGTGC-3') were purchased from Bioneer Corp., Daejeon, Korea. The stock solution of Trp aptamer (0.1 mM) was prepared in Tris-EDTA buffer solution (5 mM tris(2-carboxyethyl) phosphine (TCEP), 50 mM Tris-HCl, 1.0 mM EDTA, pH 8.0) and kept at room temperature for 1 h to reduce the disulfide bonds of Trp aptamer. The Trp aptamer was diluted in Tris-HCl buffer solution (50 mM Tris-HCl and 10 mM KCl, pH 7.2). All the electrochemical evaluations were performed at room temperature. The auto-lab PGSTAT 30 electrochemical analysis system was controlled using GPES 4.9 and FRA 4.9 software packages (EcoChemie, Utrecht, The Netherlands) was used for electrochemical measurements. Graphite screen-printed electrodes (SPEs) were purchased from Ecobioservices & Researches (Florence, Italy). Electrochemical impedance spectroscopy (EIS) and cyclic voltammetry (CV) were recorded in 50 mM Tris-HCl buffer solutions (pH 7.4), containing 0.01 M $[\text{Fe}(\text{CN})_6]^{3-/4-}$ and 100 mM KCl, at a scan rate of 100 mV/s and the frequency ranged from 100 kHz to 0.05 Hz at open circuit potential (0.23 V). Field emission scanning electron microscopy (FE-SEM) images of modified electrode surface at each step were recorded using Mira 3-XMU FE-SEM (TESCAN, Brno, Czech Republic).

2.2. Synthesis of the $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}$

The $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}$ nanocomposite was synthesized in three steps according to the method described by Bagheri et al. [36]. In the first step, magnetic nanoparticles (MNPs) were prepared by a co-precipitation method from the reaction of $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ and $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$, which were then

dried under vacuum at 60 °C. In the second step, bis(n-propyl trimethoxysilane)-1,4-diazoniabicyclo [2.2.2] octane chloride (BPTDABCOCl) was prepared by the reaction of 1,4-diazabicyclo [2.2.2] octane (DABCO) and 3-chloropropyl trimethoxysilane (CPTMS) in DMF and the resulting product was dried in an electrical oven. Finally, $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}$ nanocomposite was synthesized using MNPs, BPTDABCOCl, and tetraethyl orthosilicate (TEOS) by sol-gel method.

2.3. Preparation of Trp Aptasensor

Figure 1 shows a schematic of the different steps for constructing the Trp aptasensor. First, we synthesized $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}$ as a biocompatible nanocomposite to modify the electrode surface as described in Section 2.2. Next, the dendritic gold nanostructures (DGNs) were prepared through the electrodeposition of gold solution (HAuCl_4 ; 0.5 mM) on $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ under the potential of -0.23 V for a duration of 300 s, and Trp aptamer (3.0×10^{-6} M) was then immobilized on the electrode surface overnight at room temperature. Finally, the hemin solution (20 μM) was dropped onto the electrode, which was incubated for 15 min. The state was then ready for analysis of the samples containing Trp. After each step, the modified electrode was thoroughly washed using distilled water. The differential pulse voltammetry (DPV) was performed with the potential range from 0 to -0.6 V in HEPES buffer (20 mM HEPES, pH 7.4, 100 mM NaCl, and 50 mM KCl), and H_2O_2 (20 μM). The error bars in all of the figures indicate the standard deviation among three replicates.

Figure 1. Schematic illustration for the construction of electrochemical Trp aptasensor.

2.4. Determination of Trp in Human Serum

To prevent protein adsorption on the electrode surface and the related interference with the measurement, the human serum was first de-proteinized using trichloroacetic acid and subjected to the centrifugation. After removing the precipitates, the supernatant was then diluted three-fold using 0.1 M PBS (pH 7.0) and different concentrations of Trp was spiked into diluted human serum. These samples were finally analyzed using the same procedures described in Section 2.3.

3. Results

3.1. Characterization of Sensing Interface

The surface morphologies of the bare SPE, $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$, and DGNs/ $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ were first characterized using FE-SEM (Figure 2). As shown in Figure 2B, $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ displayed a uniform spherical structure with an average size of 23 nm, which is different from the SPE (Figure 2A). In addition to the benefits of the ionic liquid framework,

the presence of functional groups on magnetic nanocomposites leads to greater deposition of gold nanostructures and prevents the agglomeration of nanoparticles on the magnetic nanocomposite surface [36]. Furthermore, AuNPs with an average size of 13.5 nm were successfully deposited on the $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ surface as demonstrated by a dendritic structure, which was achieved by the specific interaction with the functional groups of the magnetic nanocomposite (Figure 2C). To prove that the dendritic structure is only formed with the help of magnetic nanocomposites, we obtained the SEM image of gold nanoparticles (AuNPs) electrodeposited on the surface of bare SPE without magnetic nanocomposites (Figure S1). We assumed that the deposition of AuNPs with a dendritic structure enabled the signal amplification as well as the immobilization of thiolated Trp aptamer on the electrode surface.

Figure 2. Characterization of sensing interface. FE-SEM images of (A) bare SPE, (B) $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$, and (C) $\text{DGNs}/\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$. The measured particle size is indicated in yellow color. The scale bars in the high (inset) and low magnification are 200 nm and 1 μm , respectively.

Next, EIS and CV were recorded to investigate the fabrication process of the Trp aptasensor. Recently, there has been an escalating interest in using EIS for biological measurements since this technique can be performed within a narrow range of small potentials and have no detrimental effects on biological interactions [37]. Figure 3A shows Nyquist plots of different electrode surfaces in the presence of $[\text{Fe}(\text{CN})_6]^{3-/4-}$ redox couples. The bare SPE (a) exhibited a semicircle in the high frequency region with charge transfer resistance (R_{ct}) of 1375 Ω , but the R_{ct} decreased to 556 Ω for $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ (b), which indicates an improvement in the electron transfer ability of electrode surface. Furthermore, the deposition of AuNPs on the $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ led to a significant decrease of R_{ct} down to 190 Ω (c). These data imply that DGNs have excellent electrochemical conductivity and facilitate the electron transfer between the modified electrode surface and the redox couple. However, after the immobilization of the Trp aptamer on the surface of $\text{DGNs}/\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$, the negative charge of the aptamer repelled the $[\text{Fe}(\text{CN})_6]^{3-/4-}$ redox couple, which resulted in increased R_{ct} of 14,100 Ω (d). Finally, the addition of Trp (0.9 nM) and hemin further increased R_{ct} up to 38,455 Ω (e), which indicated that the diffusion rate between the $[\text{Fe}(\text{CN})_6]^{3-/4-}$ redox couple and the electrode surface was reduced by non-effective electron transfer. These results confirmed the formation of the Trp-aptamer complex at the electrode surface. The EIS results were also supported using the CV measurements. As shown in Figure 3B, the changes in CVs of the $[\text{Fe}(\text{CN})_6]^{3-/4-}$ redox couple confirmed that each preparation step was successfully carried out on the electrodes surface, and the results are in good agreement with EIS experiments.

Figure 3. Characterization of different modification steps by (A) EIS and (B) CV in 0.01 M $[\text{Fe}(\text{CN})_6]^{3-}$ and 0.1 KCl solution at a scan rate of 100 mV s^{-1} : bare SPE (a), $\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ (b), $\text{DGNs}/\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ (c), $\text{Apt}/\text{DGNs}/\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ (d), and $\text{Trp}/\text{hemin}/\text{Apt}/\text{DGNs}/\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ (e). The concentration of Trp was 0.9 nM.

3.2. Aptamer Surface Density and Detection Feasibility of Trp Aptasensor

The aptamer surface density on the modified electrode surface was investigated using the Tarlov equation (Equation (1)) [38]:

$$\Gamma_{\text{apt}} = \Gamma_0 (Z/M) (N_A) \quad (1)$$

where Γ_{apt} is the aptamer surface density ($\text{molecules}/\text{cm}^2$), Γ_0 is the quantity of adsorbed redox marker $[\text{Ru}(\text{NH}_3)_6]^{3+}$, M is the number of aptamer bases, and Z is the charge of $[\text{Ru}(\text{NH}_3)_6]^{3+}$. After immobilizing the Trp aptamer on the modified electrode surface, chronocoulometric curves were recorded in the presence or absence of $200 \mu\text{M}$ $[\text{Ru}(\text{NH}_3)_6]^{3+}$ with 0.05 M KCl solution at a potential of -0.3 V . As shown in Figure 4A, the Γ_{apt} was calculated to be $2.6 \times 10^{18} (\pm 1.2\%) \text{ molecules}/\text{cm}^2$ using the Tarlov equation.

Figure 4. Aptamer surface density and detection feasibility of Trp aptasensor (A) Chronocoulometric curves at $\text{Apt}/\text{DGNs}/\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ in a solution of composed of $200 \mu\text{M}$ $[\text{Ru}(\text{NH}_3)_6]^{3+}$ and 0.05 M KCl (a), and containing 0.05 M KCl only (b). (B) CV signals of hemin/ $\text{Apt}/\text{DGNs}/\text{Fe}_3\text{O}_4@\text{SiO}_2/\text{DABCO}/\text{SPE}$ in the absence of Trp (a), and in the presence of 3 nM Trp (b), and 100 nM Trp (c).

Next, to demonstrate the detection feasibility of Trp aptasensor, the CV method was used to measure reduction signals of H_2O_2 in the absence of Trp (a) and presence of Trp at 3 nM (b) and 100 nM (c) (Figure 4B). The Trp aptamer with hemin was not strong enough to form an active G-quadruplex structure for the effective catalysis of H_2O_2 reduction as indicated by the weak H_2O_2 current intensity (Figure 4B, a). On the other hand, the presence of Trp at 3 nM (b) and 100 nM (c) significantly

increased the reduction signal of H_2O_2 . These data confirm that the Trp aptamer forms a stable G-quadruplex structure only in the presence of Trp, and serves as an effective catalyst for the amplified electrochemical signal.

3.3. Optimization of the Proposed Aptasensor

To obtain the optimal condition for the proposed aptasensor, different concentrations of the aptamer (1.0–6.0 μM) were applied onto the surface of the modified electrode and the EIS spectra were recorded. As the concentration of the aptamer increased up to 3 μM , the R_{ct} increased, whereas the aptamer concentration beyond 4 μM led to a decrease in the R_{ct} (Figure S2A). At higher aptamer concentrations, the intermolecular hybridization of the complementary regions may lead to a decrease in the immobilization of the aptamer on the modified electrode surface. Additionally, we investigated the effect of Trp incubation time on the prepared sensor. EIS spectra results showed that the optimal time for trapping Trp molecules on the sensor surface is 40 min and incubating for longer did not have a significant effect (Figure S2B).

3.4. Sensitivity of the Prepared Aptasensor

As the Trp aptamer is rich in guanine, we assumed that in the presence of Trp, a stable G-quadruplex structure could form to effectively catalyze H_2O_2 reduction [39] (QGRS Mapper software, Table S1) [40,41]. By measuring the reduction signals of H_2O_2 using DPV technique, the performance of the designed sensor to detect different concentrations of Trp was evaluated. Figure 5A shows the DPV signals of H_2O_2 in the absence or presence of different concentrations of Trp. Figure 5B shows the calibration plots of H_2O_2 reduction signals versus Trp concentrations in three linear ranges. We observed that with increasing Trp concentrations, H_2O_2 reduction was more efficiently catalyzed because of the formation of stable G-quadruplex structure on the electrode surface. It is assumed that Trp induces the conformational change of aptamer, mediating the formation of stable G-quadruplex, and accordingly improves the peroxidase-like activity of hemin/G-quadruplex structure. As seen in the calibration plot (Figure 5B), the intensity of the current is proportional to the Trp concentration in the three ranges (0.007–0.1 nM, 0.1–10 nM, and 10–200 nM). The detection limit was estimated to be 0.002 nM ($\text{LOD} = 3S_b/m$, where S_b is the standard deviation of the blank signal ($n = 7$), and m is slope of the linear calibration range) [42,43], which is superior to that of other electrochemical detection methods (Table 1).

Figure 5. Sensitivity of the prepared aptasensor. (A) DPV signals of hemin/Apt/DGNs/ Fe_3O_4 @ SiO_2 /DABCO/SPE with different Trp concentrations: (a) 0, (b) 0.007, (c) 0.01, (d) 0.04, (e) 0.08, (f) 0.1, (g) 0.3, (h) 0.9, (i) 3, (j) 7, (k) 10, (l) 30, (m) 70, (n) 100, (o) 130, (p) 170, and (q) 200 nM. (B) The calibration plots of I vs. Trp concentration.

Table 1. Comparison of the analytical performance between the proposed aptasensor and other detection methods for Trp.

Sensing Surface	Electrochemical Method	Linear Range	Limit of Detection	Ref.
GNP/CILE	SWV	5×10^{-3} – 9×10^{-1} M	4×10^{-3} M	[44]
poly(<i>p</i> -ABSA) film/GCE	LSV	1×10^{-7} – 10^{-5} M	7×10^{-8} M	[45]
SiO ₂ nanoparticles/CPE	LSV	1×10^{-7} – 5×10^{-5} M	3.6×10^{-8} M	[46]
CuCoHCF/graphite electrode	Amperometry	1×10^{-5} – 9×10^{-4} M	6×10^{-6} M	[47]
SWNT/GCE	DPV	4×10^{-8} – 1×10^{-5} M	1×10^{-8} M	[48]
PGE/GND	CV	1×10^{-8} – 4×10^{-6} M	3×10^{-9} M	[49]
MWCNTs/SGE	DPV	2×10^{-7} – 15×10^{-6} M	14×10^{-8} M	[50]
OPPy/CPE	ASV	1×10^{-2} – 1×10^{-1} M	1×10^{-2} M	[51]
MIP-MWCNTs/GCE	CV	2×10^{-6} – 1×10^{-4} M	1×10^{-9} M	[9]
PVP-GR/GCE	LSV	6×10^{-8} – 1×10^{-4} M	1×10^{-8} M	[11]
BiF/BDDE	DPV	1×10^{-7} – 75×10^{-6} M	3×10^{-8} M	[52]
AuNPs/FSN/SPE	DPV	0.06 – 250×10^{-9} M	1×10^{-11} M	[12]
DGNs/Fe ₃ O ₄ @SiO ₂ -DABCO/SPE	DPV	0.007 – 0.1 , 0.1 – 10 , and 10 – 200×10^{-9} M	2×10^{-12} M	This study

Carbon ionic liquid electrode (CILE) modified with gold nanoparticle (GNP), poly(*p*-aminobenzene sulfonic acid) [Poly(*p*-ABSA)] modified glassy carbon electrode (GCE), carbon paste electrode (CPE), mixed metal (copper and cobalt) hexacyanoferrate (CuCoHCF), single-wall carbon nanotubes (SWNT), pyrolytic graphite electrode (PGE) modified with graphite/nanodiamond film (GND), multi-walled carbon nanotubes modified sol-gel electrode (MWCNTs/SGE), overoxidized polypyrrole film modified carbon paste electrode (OPPy/CPE), molecularly imprinted polymers (MIP), Polyvinylpyrrolidone functionalized graphene (PVP-GR), boron-doped diamond electrode modified in situ with bismuth film (BiF/BDDE).

3.5. Selectivity, Real Sample, Reproducibility, and Stability

Finally, the selectivity of this sensor was examined by measuring the reduction signals of H₂O₂ using DPV technique in the presence of 7 nM of Trp (a), and 20 nM of either tyrosine (b), histidine (c), arginine (d), lysine (e), valine (f), or methionine (g), and a blank control (h) (Figure 6). The H₂O₂ reduction signal in the presence of Trp was higher than other amino acids that showed negligible responses comparable to the blank control. To demonstrate the potential clinical application for this sensor, three concentrations of Trp were spiked in diluted human blood serum (33%), which were analyzed using our proposed method. The results in Table S2 showed that the prepared aptasensor analyzes Trp in the human blood serum samples with excellent reproducibility and precision as evidenced by the coefficient of variation (<2%) and accuracy (<10%). Regarding the reproducibility between samples, we prepared the five different aptasensors and measured the signal in the presence of Trp (7 nM). The new results show that the relative standard deviation is 2.8%, indicating that the fabricated sensor has an excellent reproducibility. Furthermore, the prepared aptasensors were stored at 4 °C in wet chamber for 3 weeks to investigate the stability of the developed aptasensor. As shown in Figure S3, 94% of the initial electrochemical signal in the presence of Trp (7 nM) was maintained at 21 days after the preparation of sensors, proving the high stability of the prepared aptasensor.

Figure 6. DPV responses in the presence of different amino acids (a) Trp and (b) tyrosine, (c) histidine, (d) arginine, (e) lysine, (f) valine, (g) methionine, and (h) blank. The concentration of Trp was 7 nM and other amino acids were 20 nM.

4. Conclusions

We have developed a sensitive and selective electrochemical aptasensor for the detection of Trp using a hemin/G-quadruplex structure to amplify the H_2O_2 reduction signal. The fabricated aptasensor showed a low detection limit, wide linear range, and excellent reproducibility to measure Trp levels. The high sensitivity and reliable performance of this aptasensor are attributed to the dual approach for signal amplification. First, the modified electrode with DGNs/ Fe_3O_4 @ SiO_2 /DABCO/SPE led to an increase in the effective surface area, electron transfer, and electrochemical signal. Second, the hemin/G-quadruplex structure served as a catalyst to enhance the H_2O_2 reduction signal. Furthermore, the prepared aptasensor exhibited high selectivity toward Trp and detected Trp in human blood serum with high levels of accuracy, which suggests the potential application of this sensor for clinical use.

Supplementary Materials: The following are available online at <http://www.mdpi.com/2227-9040/8/4/100/s1>, Figure S1: FE-SEM images of AuNPs/SPE, Figure S2: Optimization of the prepared aptasensor (Apt/DGNs/ Fe_3O_4 @ SiO_2 /DABCO/SPE). (A) Optimization of aptamer concentration for preparation of aptasensor: 1 μ M (a), 2 μ M (b), 3 μ M (c), 4 μ M (d), 5 μ M (e), and 6 μ M (f). (B) Optimization of incubation time for the interaction of aptamer (3 μ M) with Trp (0.9 nM), Figure S3: Stability of the prepared aptasensor, Table S1: Analysis of Trp aptamer sequence by QGRS Mapper software, Table S2: Analysis of human serum samples with Trp at different concentrations.

Author Contributions: Carrying out experimental work, discussion of the results, and writing the text A.B.H.; editing of the text and supervision J.B.R. and K.S.P. All authors have read and agreed to the published version of the manuscript.

Funding: This work was supported by Konkuk University in 2019.

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Friedman, M. Analysis, Nutrition, and Health Benefits of Tryptophan. *Int. J. Tryptophan Res.* **2018**, *11*. [CrossRef] [PubMed]
2. Palego, L.; Betti, L.; Rossi, A.; Giannaccini, G. Tryptophan Biochemistry: Structural, Nutritional, Metabolic, and Medical Aspects in Humans. *J. Amino Acids* **2016**, *2016*, 1–13. [CrossRef] [PubMed]
3. Xu, D.; Sánchez-López, E.; Wang, Q.; Jiang, Z.; Marina, M.L. Determination of L-Norvaline and L-Tryptophan in Dietary Supplements by Nano-LC Using an O-[2-(Methacryloyloxy)-Ethylcarbamoyl]-10,11-Dihydroquinidine-Silica Hybrid Monolithic Column. *J. Pharm. Anal.* **2019**, *10*, 70–77. [CrossRef]

4. Delgado-Andrade, C.; Rufián-Henares, J.; Jiménez, S.; Morales, F.J. Tryptophan determination in milk-based ingredients and dried sport supplements by liquid chromatography with fluorescence detection. *Food Chem.* **2006**, *98*, 580–585. [[CrossRef](#)]
5. Ren, J.; Zhao, M.; Wang, J.; Cui, C.; Yang, B. Spectrophotometric Method for Determination of Tryptophan in Protein Hydrolysates. *J. Food Tech. Biotech.* **2007**, *45*, 360–366.
6. Lin, Z.; Chen, X.; Cai, Z.; Li, P.; Chen, X.; Wang, X. Chemiluminescence of Tryptophan and Histidine in $\text{Ru}(\text{Bpy})_3^{2+}$ -KMnO₄ Aqueous Solution. *Talanta* **2008**, *75*, 544–550. [[CrossRef](#)] [[PubMed](#)]
7. Eser, B.; Özkan, Y.; Dinçel, A.S. Determination of Tryptophan and Kynurenine by LC-MS/MS by Using Amlodipine as an Internal Standard. *J. Am. Soc. Mass Spectrom.* **2020**, *31*, 379–385. [[CrossRef](#)]
8. Hazra, C.; Samanta, T.; Mahalingam, V. A resonance energy transfer approach for the selective detection of aromatic amino acids. *J. Mater. Chem. C* **2014**, *2*, 10157–10163. [[CrossRef](#)]
9. Wu, Y.; Deng, P.; Tian, Y.; Ding, Z.; Li, G.; Liu, J.; Zuberi, Z.; He, Q. Rapid recognition and determination of tryptophan by carbon nanotubes and molecularly imprinted polymer-modified glassy carbon electrode. *Bioelectrochemistry* **2020**, *131*, 107393. [[CrossRef](#)]
10. Idili, A.; Gerson, J.; Parolo, C.; Kippin, T.; Plaxco, K.W. An electrochemical aptamer-based sensor for the rapid and convenient measurement of l-tryptophan. *Anal. Bioanal. Chem.* **2019**, *411*, 4629–4635. [[CrossRef](#)]
11. He, Q.; Liu, J.; Feng, J.; Wu, Y.; Tian, Y.; Li, G.; Chen, D. Sensitive Voltammetric Sensor for Tryptophan Detection by Using Polyvinylpyrrolidone Functionalized Graphene/GCE. *Nanomaterials* **2020**, *10*, 125. [[CrossRef](#)] [[PubMed](#)]
12. Hashkavayi, A.B.; Raoof, J.-B.; Ojani, R. Construction of a highly sensitive signal-on aptasensor based on gold nanoparticles/functionalized silica nanoparticles for selective detection of tryptophan. *Anal. Bioanal. Chem.* **2017**, *409*, 6429–6438. [[CrossRef](#)]
13. Hashkavayi, A.B.; Raoof, J.-B. Ultrasensitive and reusable electrochemical aptasensor for detection of tryptophan using of $[\text{Fe}(\text{bpy})_3](\text{p-CH}_3\text{C}_6\text{H}_4\text{SO}_2)_2$ as an electroactive indicator. *J. Pharm. Biomed. Anal.* **2019**, *163*, 180–187. [[CrossRef](#)] [[PubMed](#)]
14. Hashkavayi, A.B.; Raoof, J.-B.; Ojani, R.; Asl, E.H. Label-Free Electrochemical Aptasensor for Determination of Chloramphenicol Based on Gold Nanocubes-Modified Screen-Printed Gold Electrode. *Electroanalysis* **2015**, *27*, 1449–1456. [[CrossRef](#)]
15. Hashkavayi, A.B.; Raoof, J.B.; Azimi, R.; Ojani, R. Label-free and sensitive aptasensor based on dendritic gold nanostructures on functionalized SBA-15 for determination of chloramphenicol. *Anal. Bioanal. Chem.* **2016**, *408*, 2557–2565. [[CrossRef](#)]
16. Hashkavayi, A.B.; Raoof, J.-B.; Ojani, R.; Kavosian, S. Ultrasensitive electrochemical aptasensor based on sandwich architecture for selective label-free detection of colorectal cancer (CT26) cells. *Biosens. Bioelectron.* **2017**, *92*, 630–637. [[CrossRef](#)]
17. Park, K.S. Nucleic acid aptamer-based methods for diagnosis of infections. *Biosens. Bioelectron.* **2018**, *102*, 179–188. [[CrossRef](#)]
18. Park, K.S.; Lee, C.Y.; Kang, K.S.; Park, H.G. Aptamer-mediated universal enzyme assay based on target-triggered DNA polymerase activity. *Biosens. Bioelectron.* **2017**, *88*, 48–54. [[CrossRef](#)]
19. Hashkavayi, A.B.; Raoof, J.-B.; Ojani, R. Preparation of Epirubicin Aptasensor Using Curcumin as Hybridization Indicator: Competitive Binding Assay between Complementary Strand of Aptamer and Epirubicin. *Electroanalysis* **2018**, *30*, 378–385. [[CrossRef](#)]
20. Yu, X.; Lin, Y.; Wang, X.; Xu, L.; Wang, Z.; Fu, F. Exonuclease-assisted multicolor aptasensor for visual detection of ochratoxin A based on G-quadruplex-hemin DNAzyme-mediated etching of gold nanorod. *J. Microchim. Acta* **2018**, *185*, 259. [[CrossRef](#)]
21. Golub, E.; Albada, H.B.; Liao, W.-C.; Biniuri, Y.; Willner, I.; Albada, B. Nucleoapzymes: Hemin/G-Quadruplex DNAzyme—Aptamer Binding Site Conjugates with Superior Enzyme-like Catalytic Functions. *J. Am. Chem. Soc.* **2016**, *138*. [[CrossRef](#)] [[PubMed](#)]
22. Shi, L.; Yu, Y.; Chen, Z.; Zhang, L.; He, S.; Shi, Q.; Yang, H. A label-free hemin/G-quadruplex DNAzyme biosensor developed on electrochemically modified electrodes for detection of a HBV DNA segment. *RSC Adv.* **2015**, *5*, 11541–11548. [[CrossRef](#)]
23. Wu, S.-H.; Tang, Y.; Chen, L.; Ma, X.-G.; Tian, S.-M.; Sun, J.-J. Amplified electrochemical hydrogen peroxide reduction based on hemin/G-quadruplex DNAzyme as electrocatalyst at gold particles modified heated copper disk electrode. *Biosens. Bioelectron.* **2015**, *73*, 41–46. [[CrossRef](#)] [[PubMed](#)]

24. Shen, B.; Wang, Q.; Zhu, D.; Luo, J.; Cheng, G.; He, P.; Fang, Y. G-Quadruplex-Based DNAzymes Aptasensor for the Amplified Electrochemical Detection of Thrombin. *Electroanalysis* **2010**, *22*, 2985–2990. [[CrossRef](#)]
25. Hashkavayi, A.B.; Hashemnia, S.; Osfouri, S.; Zarei, S. Electrochemical Study of Antioxidant Capacity of Gracilaria Pygmaea Macro-Algae Based on the Green Synthesis of Gold Nanoparticles: Assessment of Its Cytotoxic Effect on Four Cancer Cell Lines. *J. Electrochem. Soc.* **2019**, *166*, B969–B977. [[CrossRef](#)]
26. Raoof, J.-B.; Bagheryan, Z.; Hashkavayi, A.B. Development of a DNA biosensor based on MCM41 modified screen-printed graphite electrode for the study of the short sequence of the p53 tumor suppressor gene in hybridization and its interaction with the flutamide drug using hemin as the electrochemical label. *New J. Chem.* **2020**, *44*, 2016–2021.
27. Rahimi-Mohseni, M.; Raoof, J.B.; Ojani, R.; Aghajanzadeh, T.A.; Hashkavayi, A.B. Development of a new paper based nano-biosensor using the co-catalytic effect of tyrosinase from banana peel tissue (Musa Cavendish) and functionalized silica nanoparticles for voltammetric determination of l-tyrosine. *Int. J. Biol. Macromol.* **2018**, *113*, 648–654. [[CrossRef](#)]
28. Li, F.; Huang, Y.; Huang, K.; Lin, J.; Huang, P. Functional Magnetic Graphene Composites for Biosensing. *Int. J. Mol. Sci.* **2020**, *21*, 390. [[CrossRef](#)]
29. Doaga, R.; McCormac, T.; Dempsey, E. Functionalized magnetic nanomaterials for electrochemical biosensing of cholesterol and cholesteryl palmitate. *J. Microchim. Acta* **2020**, *187*, 1–10. [[CrossRef](#)]
30. Rajeev, G.; Cowin, A.J.; Voelcker, N.H.; Simon, B.P. Magnetic Nanoparticles Enhance Pore Blockage-Based Electrochemical Detection of a Wound Biomarker. *Front. Chem.* **2019**, *7*, 438. [[CrossRef](#)]
31. Cho, I.-H.; Kim, D.H.; Park, S. Electrochemical biosensors: Perspective on functional nanomaterials for on-site analysis. *J. Biomater. Res.* **2020**, *24*, 1–12. [[CrossRef](#)]
32. Silva, S.M.; Tavallaie, R.; Sandiford, L.; Tilley, R.D.; Gooding, J.J. Gold Coated Magnetic Nanoparticles: From Preparation to Surface Modification for Analytical and Biomedical Applications. *Chemcomm* **2016**, *47*, 7528–7540.
33. Phama, X.-H.; Hahm, E.; Kim, H.-M.; Son, B.S.; Jo, A.; An, J.; Thi, T.A.T.; Nguyen, D.Q.; Jun, B.-H. Silica-Coated Magnetic Iron Oxide Nanoparticles Grafted onto Graphene Oxide for Protein Isolation. *Nanomaterials* **2020**, *10*, 117. [[CrossRef](#)] [[PubMed](#)]
34. Galaria, A.; Soulé, S.; Hallali, N.; Ojo, W.-S.; Mirjolet, M.; Fuks, G.; Cornejo, A.; Allouche, J.; Dupin, J.C.; Martinez, H.; et al. Silica coated iron nanoparticles: Synthesis, interface control, magnetic and hyperthermia properties. *RSC Adv.* **2018**, *8*, 32146–32156. [[CrossRef](#)]
35. Sharafi, Z.; Bakhshi, B.; Javidi, J.; Adrangi, S. Synthesis of Silica-coated Iron Oxide Nanoparticles: Preventing Aggregation without Using Additives or Seed Pretreatment. *Iran. J. Pharm. Res. IJPR* **2018**, *17*, 386–395.
36. Hashkavayi, A.B.; Raoof, J.B. Design an Aptasensor Based on Structure-Switching Aptamer on Dendritic Gold Nanostructures/Fe₃O₄@ SiO₂/DabCO Modified Screen Printed Electrode for Highly Selective Detection of Epirubicin. *Biosens. Bioelectron.* **2017**, *91*, 650–657. [[CrossRef](#)]
37. Pajkossy, T. Voltammetry Coupled with Impedance Spectroscopy. *J. Solid State Electrochem.* **2020**, *24*, 2157–2159. [[CrossRef](#)]
38. Steel, A.B.; Herne, T.M.; Tarlov, M.J. Electrochemical Quantitation of DNA Immobilized on Gold. *J. Anal. Chem.* **1998**, *70*, 4670–4677. [[CrossRef](#)]
39. Yang, X.; Han, Q.; Zhang, Y.; Wu, J.; Tang, X.; Dong, C.; Liu, W. Determination of free tryptophan in serum with aptamer—Comparison of two aptasensors. *Talanta* **2015**, *131*, 672–677. [[CrossRef](#)]
40. Huang, H.; Zhang, J.; Harvey, S.E.; Hu, X.; Cheng, C. RNA G-quadruplex secondary structure promotes alternative splicing via the RNA-binding protein hnRNPF. *Genes Dev. Chang.* **2017**, *31*, 2296–2309. [[CrossRef](#)]
41. Kikin, O.; D’Antonio, L.; Bagga, P.S. QGRS Mapper: A web-based server for predicting G-quadruplexes in nucleotide sequences. *Nucleic Acids Res.* **2006**, *34*, W676–W682. [[CrossRef](#)] [[PubMed](#)]
42. Martínez-García, G.; Julián, E.P.; Agüí, L.; Cabré, N.; Joven, J.; Yáñez-Sedeño, P.; Pingarrón, J.M. An Electrochemical Enzyme Biosensor for 3-Hydroxybutyrate Detection Using Screen-Printed Electrodes Modified by Reduced Graphene Oxide and Thionine. *Biosensors* **2017**, *7*, 50. [[CrossRef](#)]
43. Dermiş, S.; Cay, H.Y. Electrochemical behaviour of sertraline hydrochloride at a glassy carbon electrode and its determination in pharmaceutical products using osteryoung square wave voltammetry. *Pharmazie* **2010**, *65*, 182–187. [[PubMed](#)]
44. Safavi, A.; Momeni, S. Electrocatalytic Oxidation of Tryptophan at Gold Nanoparticle-Modified Carbon Ionic Liquid Electrode. *Electroanalysis* **2010**, *22*, 2848–2855. [[CrossRef](#)]

45. Yu, Y.; Luo, D.; Zhan, G.; Li, C. Electrochemical Investigation of Tryptophan at a Poly (P-Aminobenzene Sulfonic Acid) Film Modified Glassy Carbon Electrode. *J. Bull. Korean Chem. Soc.* **2008**, *29*, 928.
46. Xu, M.; Ma, M.; Ma, Y. Electrochemical determination of tryptophan based on silicon dioxide nanoparticles modified carbon paste electrode. *Russ. J. Electrochem.* **2012**, *48*, 489–494. [[CrossRef](#)]
47. Liu, Y.; Xu, L. Electrochemical Sensor for Tryptophan Determination Based on Copper-cobalt Hexacyanoferrate Film Modified Graphite Electrode. *Sensors* **2007**, *7*, 2446–2457. [[CrossRef](#)]
48. Huang, W.; Mai, G.; Liu, Y.; Yang, C.; Qua, W. Voltammetric Determination of Tryptophan at a Single-Wall Carbon Nanotubes Modified Electrode. *J. Nanosci. Nanotechnol.* **2004**, *4*, 423–427. [[CrossRef](#)] [[PubMed](#)]
49. Shahrokhian, S.; Bayat, M. *Voltammetric Determination of Tryptophan and 5-Hydroxytryptophan Using Graphite Electrode Modified with a Thin Film of Graphite/Diamond Nano-Mixture and Determination of Omeprazole Using Graphite Electrode*; Department of Chemistry, Sharif University of Technology: Tehran, Iran, 2010.
50. Majidi, M.R.; Salimi, A.; Alipour, E. Development of Voltammetric Sensor for Determination of Tryptophan Using MWCNTs-Modified Sol-Gel Electrode. *J. Chin. Chem. Soc.* **2013**, *60*, 1473–1478. [[CrossRef](#)]
51. Chen, Z.-D.; Okamura, K.; Hanaki, M.; Nagaoka, T. Selective Determination of Tryptophan by Using a Carbon Paste Electrode Modified with an Overoxidized Polypyrrole Film. *Anal. Sci.* **2002**, *18*, 417–421. [[CrossRef](#)]
52. Sadok, I.; Tyszczyk-Rotko, K.; Mroczka, R.; Staniszewska, M. Simultaneous voltammetric analysis of tryptophan and kynurenine in culture medium from human cancer cells. *Talanta* **2020**, *209*, 120574. [[CrossRef](#)]

Publisher’s Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.

© 2020 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).