Controlled Preparation of Different Proportions of Metal Fe-Mn from Waste Mn Ferrite by Molten Salt Electrolysis

Shiyuan Liu ^{1,2} and Lijun Wang ^{1,*}

¹ Collaborative Innovation Center of Steel Technology, University of Science and Technology Beijing, Beijing 100083, China; shiyuanliu126@126.com

² National Engineering Laboratory for Hydrometallurgical Cleaner Production Technology, Institute of Process Engineering, Chinese Academy of Sciences, Beijing 100190, China

* Correspondence: lijunwang@ustb.edu.cn

Received: 5 November 2020; Accepted: 7 December 2020; Published: 14 December 2020

Abstract: A novel method for efficiently recovering Fe and Mn from waste Mn ferrite by molten salt electrolysis is firstly proposed. The electrolysis of molten salt (MnCl_2 (1.06 wt%)- FeCl_3 (2.69 wt%)- NaCl - KCl) was performed at 800 °C. The phase of product at 2.0 V was metal Fe while metal Fe and Mn were obtained by molten salt electrolysis at 2.3 V. The Fe/Mn mass ratio of electrodeposited products at 2.0 V and 2.3 V were 687 and 3.2, respectively. The different proportions of metal Fe-Mn were prepared by controlling the electrolytic voltages. This new method can realize direct transformation of waste Mn ferrite to Fe-Mn alloy.

Keywords: metallurgy; metals; waste Mn ferrite; molten salt electrolysis

1. Introduction

Ferrites are widely used in the electronics industry [1,2]. Since 2008, more than 250,000 tons of Mn-Zn ferrite have been produced annually in China [3]. A large amount of waste ferrite is generated in the manufacturing process of ferrite [3]. Traditional processes for treating waste ferrite included the following procedures: H_2SO_4 leaching, reducing, purification, co-precipitation, ball milling, sintering, etc. [4]. The reducing agent used in traditional processes is generally high-purity reduced iron powder [5]. The high price of high-purity iron powder severely affects the application of traditional processes [5]. The development of new processes is very necessary. Chlorination has received increasing attention in the treatment of solid waste and slag [6–10]. The crystal structure of Mn ferrite (MnFe_2O_4) is spinel [11]. In our previous work, we reported that molten salt chlorination destroyed the spinel structure of $(\text{Mn,Fe})(\text{Cr,V})_2\text{O}_4$ with AlCl_3 , and then MnCl_2 , CrCl_3 , FeCl_2 and VCl_3 were obtained [12,13]. In order to recover the Fe and Mn in waste ferrite, we propose that the new process includes the following two steps: chlorination of waste Mn ferrite with AlCl_3 and the separation of Fe and Mn by molten salt electrolysis. Figure 1 shows a flow diagram of a novel method for the utilization of waste Mn ferrite.

After chlorination, Fe and Mn in waste Mn ferrite were present in the form of FeCl_3 and MnCl_2 . The electrodeposition of Mn^{2+} in a NaCl - KCl system was studied by Xiao et al. [14]. Ye et al. reported the formation of Mg-Li-Mn alloys from MnCl_2 - MgCl_2 - LiCl - KCl salt [15]. Fe_2O_3 was chlorinated by AlCl_3 , and then metallic Fe was obtained from molten salt containing FeCl_3 by molten salt electrolysis [16]. However, the electrolysis and separation of FeCl_3 - MnCl_2 - NaCl - KCl systems has been not reported. In this work, as part of the foundational research on the recovery and separation of Fe and Mn from waste ferrite by a chlorination–electrolysis method, the electrolytic separation of Fe and Mn from FeCl_3 - MnCl_2 - NaCl - KCl molten salt has been studied.

Figure 1. Flow diagram of a novel method for the utilization of waste Mn ferrite.

2. Materials and Methods

Analytically pure NaCl, KCl, FeCl₃ and MnCl₂ are used in molten salt electrolysis. Equal molar NaCl and KCl were selected as the molten salt medium. The sample with MnCl₂ (1.06 wt%)-FeCl₃ (2.69 wt%)-NaCl-KCl was put in a high-temperature furnace, and heated to 800 °C under the protection of high-purity Ar gas. The electrolysis of Fe and Mn was conducted in a two-electrode cell. A tungsten wire and a graphite rod were used as the cathode material and anode material, respectively. After the electrolysis, the production of cathode surface was washed with deionized water to remove salt (NaCl, KCl, FeCl₃, and MnCl₂) from the molten salt medium. The morphology of production was analyzed with a scanning electron microscope (SEM, Zeiss Ultra 55, Oberkochen, Germany). X-ray diffraction (XRD, Rigaku Smartlab, Tokyo, Japan) with a Cu K α radiation source was used to identify the phase of the electrodeposited products. To accurately determine the content of Fe and Mn in the products, the products were dissolved with aqua regia. Then the contents of Fe and Mn in solution were measured by inductively couple plasma optical emission spectroscopy (ICP-OES, Optima 5300DV, Waltham, MA, USA).

3. Results and Discussion

The electrolysis of molten salt (MnCl₂ (1.06 wt%)-FeCl₃ (2.69 wt%)-NaCl-KCl) was performed at 800 °C. The decomposition voltages of FeCl₃ and MnCl₂ are calculated by the following Equations (1)–(4):

$$E_{\text{MnCl}_2} = E_{\text{MnCl}_2}^{\theta} - \frac{RT}{nF} \ln \frac{\alpha_{\text{MnCl}_2}}{\alpha_{\text{Cl}_2} \times \alpha_{\text{Mn}}} \quad (2)$$

$$E_{\text{FeCl}_3} = E_{\text{FeCl}_3}^{\theta} - \frac{RT}{nF} \ln \frac{\alpha_{\text{FeCl}_3}}{\alpha_{\text{Cl}_2}^{1.5} \times \alpha_{\text{Fe}}} \quad (4)$$

where E_{MnCl_2} and E_{FeCl_3} are the decomposition voltage of MnCl₂ and FeCl₃, respectively. $E_{\text{MnCl}_2}^{\theta}$ and $E_{\text{FeCl}_3}^{\theta}$ are the theoretical decomposition voltage of MnCl₂ and FeCl₃, respectively. R is the ideal gas constant. T is the temperature in K. n is the number of electrons transferred. F is the Faraday constant. α_{MnCl_2} and α_{FeCl_3} are the activity of MnCl₂ and the activity of FeCl₃, respectively. α_{Fe} and α_{Mn} are the activity of Fe and the activity of Mn, respectively. α_{Cl_2} is the activity of Cl₂.

The activity of Cl₂ is assumed to be 1 due to the high-purity Ar gas atmosphere in this experiment. The activity of both metallic Fe and metallic Mn are assumed to be 1. The concentrations of FeCl₃ and

MnCl_2 are used to calculate the decomposition voltages instead of activity, which are attributed to low concentrations of FeCl_3 and MnCl_2 in MnCl_2 (1.06 wt%)- FeCl_3 (2.69 wt%)- NaCl-KCl molten salt. The theoretical decomposition voltages of MnCl_2 and FeCl_3 at 800 °C are calculated by the Factsage 6.4 program. The theoretical decomposition voltages of MnCl_2 and FeCl_3 at 800 °C are 1.8 V and 0.8 V, respectively. The decomposition voltages of FeCl_3 and MnCl_2 are calculated by Equations (2) and (4). Thus, the decomposition voltages of MnCl_2 and FeCl_3 at 800 °C are 2.3 V and 1.1 V, respectively. Considering the concentration polarization and electro-chemical polarization, the electrolysis voltages of 2.0 V and 2.3 V are selected. The effect of electrolysis time at different voltages and 800 °C on current is shown in Figure 2. The current vs. time curve shows a similar shape. With a constant voltage of 2.0 V applied, the current dropped quickly from 1.60 A to 0.09 A in seconds, which indicated that the cell voltage achieved equilibrium. As the electrolysis time increased to 8 min, the current gradually increased from 0.09 A to 1.04 A. During this electrolysis, metal Fe is deposited on the W cathode, and the surface area of the W cathode increases. As the electrolysis time increases to 85 min, the current decreases to 0.09 A, which can be attributed to a decreased concentration of Fe^{3+} . Finally, the current drops to about 0.02 A within 85–125 min [17]. With a constant voltage of 2.3 V applied, the current dropped quickly from 2.05 A to 1.11 A in seconds. This may correspond to the electrolytic cell of molten salt achieving equilibrium. As the electrolysis time increased to 13 min, the current gradually increased from 1.11 A to 1.30 A. During this electrolysis, metal Fe and Mn are deposited on the W cathode, and the surface area of the W cathode increases. As the electrolysis time increases to 60 min, the current decreases to 0.27 A, which can be attributed to a decreased concentration of Fe^{3+} . Finally, the current drops to about 0.16 A within 60–95 min.

Figure 2. The current–time curve of electrolysis of molten salt (MnCl_2 (1.06 wt%)- FeCl_3 (2.69 wt%)- NaCl-KCl , 800 °C).

According to the calculated decomposition voltage, metal Fe was obtained when the electrolysis voltage exceeded 1.1 V. Meanwhile, metal Mn was obtained at voltages exceeding 2.3 V. The XRD in Figure 3 shows that the deposited products at 2.3 V are metal Fe and Mn. Meanwhile, the deposited product at 2.0 V is metal Fe. The electrolysis voltage is increased from 2.0 V to 2.3 V, and Mn^{2+} ions were electrolyzed to metal Mn. The SEM morphology of the deposited products is shown in Figure 4. The morphology of the product obtained at 2.0 V is dendritic. The morphology of metal Fe and Mn at 2.3 V exhibits a stick-like shape. The element contents of Fe and Mn in electrodeposited product were determined using ICP-OES. The Fe/Mn mass ratios of deposited product at 2 V and 2.3 V are 687 and 3.2, respectively. Thus, the different proportions of metal Fe-Mn were prepared by controlling the electrolytic voltages.

Figure 3. The XRD analysis of the electrodeposited products by electrolysis with different constant cell voltages (MnCl_2 (1.06 wt%)- FeCl_3 (2.69 wt%)- NaCl-KCl , 800 °C).

Figure 4. SEM analysis of electrodeposited products under different electrolysis voltages: (a) 2.0 V; (b) 2.3 V.

The economics of this process based on the production of 1 kg iron is discussed. Energy consumption and material costs were calculated as follows.

The conditions for the controlled preparation of different proportions of metal Fe-Mn by molten salt electrolysis were 2.0 V at 800 °C for 125 min. The energy consumption (Q , J) was obtained through Equation (5) [18].

$$Q = C \times m \times \Delta T + K \times A \times \Delta T \times t - Q_r + Q'_r + Q_e \quad (5)$$

where C is the specific heat of the material, J/(kg °C). m is the mass of the material, kg. ΔT is the temperature difference, °C. K is the heat conductivity coefficient, W/(m^2 °C). A is the superficial area of the reaction vessel, m^2 . T is the reaction time, h. Q_r is the reaction heat during the reaction process, J. Q'_r is the heat absorbed during the reduction process, J. Q_e is the energy consumption during the electro deposition, J.

Postulated conditions: the relationship of the specific heat of H_2O (C_H), NaCl (C_{NaCl}) and KCl (C_{KCl}) is described by Equation (6).

$$C_H = 4C_{\text{NaCl}} = 4C_{\text{KCl}} = 4.2 \times 10^3 \text{ J/(kg °C)}. \quad (6)$$

where C_H , C_{NaCl} , and C_{KCl} are the specific heat of H_2O , NaCl , and KCl , respectively.

According to the Equations (5) and (6), the Equation (7) can be obtained.

$$Q = 1050 \times 775 \times 129.5 + K \times A \times 775 \times 2.08 + 2 \times 1 \times 125 \times 60 \times 2 \times 1345 - Q_r + Q'_r = \frac{1.05 \times 10^8 + K \times A \times 775 \times 2.08 + 4.04 \times 10^7 - Q_r + Q'_r}{J} \quad (7)$$

where Q is the energy consumption in this process, J. K is the heat conductivity coefficient, $W/(M^2 \text{ } ^\circ\text{C})$. A is the superficial area of the reaction vessel, m^2 . Q_r is the reaction heat during the reaction process, J. Q'_r is the heat absorbed during the reduction process, J.

One kilogram of standard coal produces 2.92×10^7 J. Thus, about 4.8 kg standard coal (about 5.2 kg anthracite) was needed. Meanwhile, the price of anthracite is about RMB 900 per ton according to <http://www.mycoal.cn>. The price of energy consumption for producing 1 kg Fe is about RMB 4.7.

Molten salt electrolysis in this paper needs NaCl and KCl. The mass and the cost of materials required to produce 1 kg Fe is summarized in Table 1. The prices of the materials originate from <https://www.yhs518.com/archives/2956.html>. The cost of materials required to produce 1 kg Fe is about RMB 187. The price of 1 kg Fe and 0.5 kg Mn shown in Table 2 is RMB 9 according to <https://www.mysteel.com/>.

Table 1. The cost of materials required to produce 1 kg Fe.

Process	Raw Materials	Raw Material Amount/(g)	Cost (RMB)
Electrolysis	NaCl	57,056	57
	KCl	72,488	130

Table 2. The price of products.

Product	Product Amount/(g)	Price (RMB)
Fe	1000	4
Mn	500	5

Although the cost of producing 1 kg Fe is about RMB 191.7, NaCl and KCl can be reused. No other impurities are introduced during molten salt electrolysis. When the molten salt ratio is MnCl_2 (1.06 wt%)- FeCl_3 (2.69 wt%)-NaCl-KCl for electrolysis, NaCl and KCl molten salt can be recycled 22 times to achieve profitability. In fact, the number of cycles of molten salt can be far more than 22 times. At the same time, the content of MnCl_2 and FeCl_3 in the molten salt is relatively low. When the content of MnCl_2 and FeCl_3 increases, profits can also be realized. Thus, this process is very industrially promising.

4. Conclusions

In summary, the separation of Fe and Mn from waste Mn ferrite by molten salt electrolysis was investigated. The electrolysis of molten salt (MnCl_2 (1.06 wt%)- FeCl_3 (2.69 wt%)-NaCl-KCl) was performed at $800 \text{ } ^\circ\text{C}$. The phase of product at 2.0 V is metal Fe, while metal Fe and Mn are obtained by molten salt electrolysis at 2.3 V. The Fe/Mn mass ratio of deposited products at 2.0 V and 2.3 V are 687 and 3.2, respectively. Direct extraction of Fe and Mn from waste Mn ferrite was achieved by a chlorination–electrolysis process. This process is simple and effective for the usage of waste Mn ferrite. The chlorination mechanism for waste Mn ferrite and the electrolysis mechanism for FeCl_3 - MnCl_2 are the subject of further research.

Author Contributions: Conceptualization, S.L. and L.W.; methodology, S.L.; validation, S.L.; formal analysis, S.L.; investigation, S.L.; resources, S.L.; writing—original draft preparation, S.L.; writing—review and editing, L.W.; visualization, S.L.; supervision, L.W.; funding acquisition, S.L. and L.W. All authors have read and agreed to the published version of the manuscript.

Funding: This research was funded by National Natural Science Foundation of China (No. 51904286, 51922003, 51774027, 51734002) and China Postdoctoral Science Foundation (2019M650848).

Acknowledgments: The authors are grateful for the financial support of this work from the National Natural Science Foundation of China (No. 51904286, 51922003, 51774027, 51734002), and China Postdoctoral Science Foundation (2019M650848).

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Liu, S.Y.; Li, S.; Wu, S.; Wang, L.J.; Chou, K.C. A Novel Method for Vanadium Slag Comprehensive Utilization to Synthesize Zn-Mn Ferrite and Fe-V-Cr Alloy. *J. Hazard. Mater.* **2018**, *354*, 99–106. [\[CrossRef\]](#) [\[PubMed\]](#)
2. Bollero, A.; Rial, J.; Villanueva, M.; Golasinski, K.M.; Seoane, A.; Almunia, J.; Altimira, R. Recycling of Strontium Ferrite Waste in a Permanent Magnet Manufacturing Plant. *ACS Sustain. Chem. Eng.* **2017**, *5*, 3243–3249. [\[CrossRef\]](#)
3. Li, K.K.; Peng, C.H.; Jiang, K.Q. The Recycling of Mn–Zn Ferrite Wastes Through a Hydrometallurgical Route. *J. Hazard. Mater.* **2011**, *194*, 79–84. [\[CrossRef\]](#) [\[PubMed\]](#)
4. Bai, B.S. The Study on the Recycling of Waste MnZn Ferrite by Hydrometallurgy-method. Master's Thesis, Central South University, Hunan, China, 2007.
5. Zhu, Y. Study on the Preparation of High Peameability Ferrite Used for Anti-electro-magnetic-interference from MnZn Soft Ferrite Wastes. Master's Thesis, Central South University, Hunan, China, 2011.
6. Du, G.C.; Fan, C.L.; Yang, H.T.; Zhu, Q.S. Selective Extraction of Vanadium from Pre-oxidized Vanadium Slag by Carbochlorination in Fluidized Bed Reactor. *J. Clean. Prod.* **2019**, *237*, 117765. [\[CrossRef\]](#)
7. Liu, S.Y.; Wang, L.J.; Chou, K.C. Selective Chlorinated Extraction of Iron and Manganese from Vanadium Slag and Their Application to Hydrothermal Synthesis of MnFe_2O_4 . *ACS Sustain. Chem. Eng.* **2017**, *5*, 10588–10596. [\[CrossRef\]](#)
8. Ma, E.; Lu, R.X.; Xu, Z.M. An efficient rough vacuum chlorinated separation method for the recovery of indium from waste liquid crystal display panels. *Green Chem* **2012**, *14*, 3395–3401. [\[CrossRef\]](#)
9. Carbral-Pinto, M.M.S.; Inácio, M.; Neves, O.; Almeida, A.A.; Pinto, E.; Oliveiros, B.; Silva, E.A.F.D. Human Health Risk Assessment Due to Agricultural Activities and Crop Consumption in the Surroundings of an Industrial Area. *Expos. Health* **2020**, *12*, 629–640. [\[CrossRef\]](#)
10. Carbral-Pinto, M.M.S.; Marinho-Reis, P.; Almeida, A.; Pinto, E.; Neves, O.; Inácio, M.; Gerardo, B.; Freitas, S.; Simões, M.R.; Dinis, P.A.; et al. Links between Cognitive Status and Trace Element Levels in Hair for an Environmentally Exposed Population: A Case Study in the Surroundings of the Estarreja Industrial Area. *Int. J. Environ. Res. Public Health* **2019**, *16*, 4560. [\[CrossRef\]](#) [\[PubMed\]](#)
11. Liu, S.Y.; Wang, L.J.; Chou, K.C. Synthesis of Metal-Doped Mn-Zn Ferrite from the Leaching Solutions of Vanadium Slag Using Hydrothermal Method. *J. Magn. Magn. Mater.* **2018**, *449*, 49–54. [\[CrossRef\]](#)
12. Liu, S.Y.; Wang, L.J.; Chou, K.C. A Novel Process for Simultaneous Extraction of Iron, Vanadium, Manganese, Chromium, and Titanium from Vanadium Slag by Molten Salt Electrolysis. *Ind. Eng. Chem. Res.* **2016**, *55*, 12962–12969. [\[CrossRef\]](#)
13. Liu, S.Y.; Wang, L.J.; Chou, K.C.; Kumar, R.V. Electrolytic Preparation and Characterization of VCr Alloys in Molten Salt from Vanadium Slag. *J. Alloy. Comp.* **2019**, *803*, 875–881. [\[CrossRef\]](#)
14. Xiao, S.J.; Liu, W.; Gao, L. Cathodic Process of Manganese (II) in NaCl-KCl Melt. *Ionics* **2016**, *22*, 2387–2390. [\[CrossRef\]](#)
15. Ye, K.; Zhang, M.L.; Chen, Y.; Han, W.; Yan, Y.D.; Wei, S.Q.; Chen, L.J. Study on the Preparation of Mg–Li–Mn Alloys by Electrochemical Codeposition from $\text{LiCl-KCl-MgCl}_2\text{-MnCl}_2$ Molten Salt. *J. Appl. Electrochem.* **2010**, *40*, 1387–1393. [\[CrossRef\]](#)
16. Haarberg, G.; Kvalheim, M.E.; Rolseth, S.; Murakami, T.; Pietrzyk, S.; Wang, S.L. Electrodeposition of Iron from Molten Mixed Chloride/Fluoride Electrolytes. *ECS Trans.* **2007**, *3*, 341–345. [\[CrossRef\]](#)
17. Zou, X.L.; Lu, X.G.; Li, C.H.; Zhou, Z.F. A Direct Electrochemical Route from Oxides to Ti-Si Intermetallics. *Electrochim. Acta* **2010**, *55*, 5173–5179. [\[CrossRef\]](#)

18. Wang, H.G.; Zhang, M.; Guo, M. Utilization of Zn-Containing Electric Arc Furnace Dust for Multi-Metal Doped Ferrite with Enhanced Magnetic Property: From Hazardous Solid Waste to Green Product. *J. Hazard. Mater.* **2017**, *339*, 248–255. [[CrossRef](#)] [[PubMed](#)]

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.

© 2020 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).