

Supplementary Materials

Article

Surface Modification of *Bombyx mori* Silk Fibroin Film via Thiol-ene Click Chemistry

Xiaoning Zhang ^{1,*}, Jianwei Liang ¹, Zhenyu Chen ¹, Carrie Donley ², Xiaolin Zhang ¹ and Guotao Cheng ¹

¹ State Key Laboratory of Silkworm Genome Biology, College of Biotechnology, Southwest University, Chongqing 400715, China; kubf@swu.edu.cn (J.L.); c618@swu.edu.cn (Z.C.); zx1362969@163.com (X.Z.); cheng_2001@swu.edu.cn (G.C.)

² Chapel Hill Analytical and Nanofabrication Laboratory, Department of Applied Physical Sciences, University of North Carolina at Chapel Hill, Chapel Hill, North Carolina 27599-3216, USA; cdonley@email.unc.edu

* Correspondence: xzhang@swu.edu.cn; Tel.: +86-159-2281-5612




Figure S1. Representative XP survey spectra of GSH-SF films exposed to neat BUD under 365 nm UV illumination for (a) 5 min and (b) 60 min.

Table S1. Bromine-to-carbon ratios of GSH-SF films covered with neat BUD and illuminated with 365 nm UV light for (a) 5 min and (b) 60 min.

Sample	Br/C ratio
UV illuminated 5 min	0.00164
UV illuminated 60 min	0.02060