processes

MDPI

Article

Effect of Regenerated Cellulose Fibers Derived from Black Oat on Functional Properties of PVA-based Biocomposite Film

Naresh Shahi[1], Gautam Joshi[2] and Byungjin Min[2,] *

[1] Integrative Biosciences Ph.D. Program, Tuskegee University, Tuskegee, AL, USA 36088; nshahi1164@tuskegee.edu

[2] Department of Food and Nutritional Sciences, Tuskegee University, Tuskegee, AL, USA 36088; gjoshi7156@tuskegee.edu

* Correspondence: bmin@tuskegee.edu; Tel.+01-334-727-8393




Figure S1. Moisture absorption (%) of neat PVA and composite films.

Table S1. Remaining weight (%) of neat PVA and composite films with increasing temperature.

Temperature (°C)	Weight (%)			
	PVA	PVA-RC1	PVA-RC3	PVA-RC5
120	95	93	97	97
200	90	86	93	93
250	84	80	88	89
300	64	56	72	76
500	5	5	6	6