

Supplementary Materials: Exploring High-Symmetry Lanthanide-Functionalized Polyoxopalladates as Molecular Nanomagnets for Quantum Computing

José J. Baldoví and Aleksandar Kondinski

Table of contents

1. Computational Details (DFT)	2
2. Choice of theoretical level for geometry calculations	2
3. Comparison with the Preyssler System	3
4. Structural and electronic properties of 1, 1-Na, 1-La, 1-Gd and 1-Lu	3
5. Ligand Field Analysis	6
6. Coordinates	8

1. Computational Details (DFT)

Density functional theory (DFT) calculations were performed using the Amsterdam Density Functional program (ADF2017) [31]. Numerical integration was performed using the Becke grid integration [42,43]. The computational screening of **1-Na** was performed within the local density approximation (LDA, VWN density functional)[44] and the GGA Becke exchange plus the Perdew 86 correlation (BP) functional [45,46]. We used all-electron Slater basis sets of triple-zeta quality with one or two polarization functions (TZP and TZ2P, resp.) [47]. Scalar relativistic effects were accounted for using the Zeroth-Order Regular Approximation (ZORA) [48]. Solvation effects were introduced using the COnductor-like Screening MOdel (COSMO) with the default parameters for water ($\epsilon = 78.39$; solvent radius = 1.93 Å) [49]. The spin-unrestricted (= U) formalism was used for the high-spin open-shell electronic system **1-Gd**. Next to geometry optimizations at BP86/TZ2P/ZORA-Scalar/COSMO, single-point calculations using the hybrid B3LYP functional [50] were performed to calculate different molecular properties (bonding energies, frontier molecular orbitals, and molecular electrostatic potentials) of the five models **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu**. To confirm energy minima, vibrational analysis was performed at the same theoretical level as the geometry optimization.

2. Choice of the theoretical level

The DFT level for the geometry and single point calculations is typically used when performing calculations on POMs [51] and has been already used/validated on polyoxopalladates [32–34,52]. B3LYP functional and scalar relativistic already provide good estimation of the electronic structure and gap energies [32–34,52,53], while the results on the electronic structure alone are comparable to those obtained using spin-orbit coupling relativistic effects [54]. All known polyoxopalladates are water soluble and isolated from water media [24], therefore, COSMO water was applied as part of the model.

In addition to this, the geometry optimization of polyanion **1-Na** using LDA and BP functionals and TZP or TZ2P basis sets is summarized in Table S1.

- Calculations at LDA level leads to more accurate estimation of the Se-O and the Pd-O bond lengths, however the dimensions of the inner cavity (Figure S1) and the Ln-O are over estimated.
- Calculations at BP level lead to more accurate estimation of the dimensions of the inner cavity and the Ln-O bond lengths.
- At both levels, the basis set only induces difference on pm scale (i.e. contraction in case of TZ2P).

Table S1: Characteristic bond lengths of polyanion **1-Na** system as calculated at different theoretical levels. All bond lengths and interatomic distances are compared to the reported crystal structure in reference [21]. Calculated values that are within the experimental ranges are colored green, while those that do not are in red.

Length/ distance	Experiment [Å] Ref. [21]	BP/TZP/ZSC/COSMO Length/distance [Å]	BP/TZ2P/ZSC/COSMO Length/distance [Å]	LDA/TZP/ZSC/COSMO Length/distance [Å]	LDA/TZ2P/ZSC/COSMO Length/distance [Å]
Se-O	1.655-1.718	1.745; 1.746	1.731	1.718	1.705; 1.713
Pd-O	1.960-2.038	2.009	1.998	1.961	1.953
Pd-O _{Se}	1.997-2.062	2.094	2.072	2.033	2.045
Na···O	2.642-2.786	2.650	2.644	2.568	2.574
$d_1(O\cdots O)$	2.699-2.811	2.707	2.701	2.631	2.643
$d_2(O\cdots O)$	2.666-2.803	2.678	2.672	2.592	2.596

3. Comparison with the Preyssler System

The structure of the Preyssler type polyoxoanions $[P_5W_{30}O_{110}]^{15-}$ (Figure S1) exhibits an ideal D_{5h} . This polyanion exhibits two pentagonal entrances $\{W_5O_5\}$ fragments which are comparable to the entrance site of the $\{Pd_5O_5\}$ fragment polyanion **1** (see Figure 1). The entrance is wide enough to allow permeation of a variety of cations (alkali, earth alkali, lanthanides, actinides etc.) [16,55]. However, it must be stressed that in the case of lanthanides, the inner cavity is not suitable for encapsulation due to its dimensions. Thus, the incorporated lanthanides are incorporated between the pentagonal entrance and the pentagonal face of the cavity prism. The lanthanide centers adopt pentagonal antiprism or capped pentagonal antiprism coordination geometry when in the latter case they additionally bind to an outer water molecule [16,55].






Figure S1: Combined ball-and-stick and polyhedral representation of the $[P_5W_{30}O_{110}]^{15-}$ polyanion shown in top (left) and side view (right). Color code: W = black, P = purple, O = red spheres. The inner cavity defined by the $\{O_{10}\}$ pentagonal prism is shown in blue prism, while the pentagonal entrance comprised of the five μ_2 -O atoms is shown in yellow color.

4. Structural and electronic properties of **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu**

The calculated bond distances and interatomic distances for systems **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu** are summarized in Table S2. The calculated Mulliken charge populations of the three inequivalent O centers (Figure S2) are summarized in Table S3. Spin density isosurface of polyanion **1-Gd** is depicted in Figures S3. The HOMO-LUMO gap energies and distribution of the frontier orbitals over different atoms are presented in Tables S4 and S5.

Table S2: Characteristic bond lengths and interatomic distances in polyanions **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu** as calculated at BP/TZ2P/ZSC/COSMO-water levels.

Bond/distance	Length/distance [Å]				
Polyanion	1	1-Na	1-La	1-Gd	1-Lu
Se-O	1.731	1.731	1.732; 1.733	1.731; 1.732	1.731; 1.732
Pd-O	1.994	1.998	2.008	2.001	1.999
Pd-O _{Se}	2.092	2.072	2.064	2.058	2.060
Na···O	-	2.644	2.642	2.592	2.559
<i>d</i> ₁ (O···O)	2.692	2.701	2.714	2.671	2.646
<i>d</i> ₂ (O···O)	2.673	2.672	2.665	2.611	2.575

**Figure S2.** Ball-and-stick representation depicting segment of the **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu** polyanions. The segment shows the three topologically inequivalent O atoms in the vicinity of the {SeO₃} groups. Color code: Pd= blue, O = red, and Se = yellow spheres.**Figure S3:** Spin density isosurface of **1-Gd** indicating accumulation of α spins at the Gd^{III} center as calculated at UB3LYP/TZ2P/ZSC/COSMO level. Color code: Pd = blue, O = red, and Se = yellow spheres.**Table S3:** Mulliken charge populations of **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu** obtained at (U)B3LYP/TZ2P/ZSC/ COSMO for different O atoms following the labeling in Figure S2.

Polyanion	Charge		
	O _a	O _b	O _c
1	-0.78	-0.78	-0.79
1-Na	-0.67	-0.67	-0.71
1-La	-0.75	-0.75	-0.96
1-Gd	-0.75	-0.75	-0.97
1-Lu	-0.75	-0.75	-0.95

Table S4: HOMO, LUMO and HOMO-LUMO gap (Δ LUMO-HOMO) energies in eV of **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu**, calculated at (U)B3LYP/TZ2P/ZSC/COSMO.

	Polyanion				
	1	1-Na	1-La	1-Gd	1-Lu
HOMO [eV]	-4.1	-4.5	-5.2	-5.2	-5.2
LUMO [eV]	-0.7	-1.0	-1.6	-1.6	-1.6
Δ LUMO-HOMO [eV]	3.5	3.5	3.6	3.5	3.6

Table S5: Contributions (in %) of the Kohn-Sham orbitals centered on palladium, oxygen, selenium and the incorporated cations to the HOMO and the LUMO orbitals of **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu**.

Polyanion	Distribution [%]			
1	Pd	O	Se	NA
HOMO	41.4	48.5	1.5	-
LUMO	53.6	31.5	6.7	-
$\Delta_{\text{LUMO-HOMO}}$	12.1	-17.0	5.3	-
1-Na	Pd	O	Se	Na
HOMO	70.2	20.6	0.0	0
LUMO	55.0	30.0	8.1	0
$\Delta_{\text{LUMO-HOMO}}$	-15.3	9.5	8.1	0
1-La	Pd	O	Se	La
HOMO	70.6	18.7	0.0	0.0
LUMO	55.5	26.8	6.4	3.6
$\Delta_{\text{LUMO-HOMO}}$	-15.2	8.1	6.4	3.6
1-Gd	Pd	O	Se	Gd
HOMO	70.3	18.8	0.0	0.0
LUMO	55.1	26.4	6.2	5.0
$\Delta_{\text{LUMO-HOMO}}$	-15.2	7.6	6.2	5.0
1-Lu	Pd	O	Se	Lu
HOMO	69.5%	18.8%	0.0	0.0
LUMO	55.2%	27.1%	6.2	4.4
$\Delta_{\text{LUMO-HOMO}}$	-14.3%	8.3%	6.2	4.4

The calculated IR of **1-La** in water solution is shown in figure S4. From previous calculations on polyoxopalladates at similar theoretical level [32,34,52], the position of the absorption corresponding to stretching modes involving bonds at the exterior of the cluster are likely to underestimate the corresponding positions in any future recorded experimental spectrum of an isolated salt. This is because our current model is limited to a single molecule and not a bulk crystal structure.




Figure S4. Calculated spectrum of bare **1-La** on BP/TZ2P/ZSC/COSMO-water levels. Main absorptions at 747 cm^{-1} and 671 cm^{-1} correspond to Se-O stretch, while combination of stretch and bending modes corresponds to the absorption at 535 cm^{-1} .

5. Ligand Field Analysis

The model that we have applied in order to predict the magnetic states and the ground state wave function is the Radial Effective Charge (REC) model. Such a model is an electrostatic *semi-empirical* crystal field approach commonly used in molecular magnetism, which provides a computationally inexpensive estimation of the crystal field parameters (CFPs) and permit to rationalize the magnetic properties of a particular *f*-block coordination complex [37]. From the calculated CFPs, the model estimates the ground-*J* multiplet energy levels and their corresponding wave functions, composed by the different M_J microstates. This kind of calculations use the atomic coordinates of the first coordination sphere around the magnetic centre as an input. The software code that has this model implemented is the SIMPRE computational package [38], which parameterizes the electric field effect produced by the surrounding ligands by using the following Crystal Field Hamiltonian expressed in terms of the Extended Stevens Operators (ESOs) [56–58]:

$$\hat{H}_{cf}(J) = \sum_{k=2,4,6} \sum_{q=-k}^k B_k^q O_k^q = \sum_{k=2,4,6} \sum_{q=-k}^k a_k(1-\sigma_k) A_k^q \langle r^k \rangle O_k^q \quad (1)$$

where k is the order (also called rank or degree) and q is the operator range, that varies between k and $-k$, of the Stevens operator equivalents O_k^q as defined by Ryabov in terms of the angular momentum operators J_{\pm} and J_z ,ⁱ where the components $O_k^q(c)$ and $O_k^q(s)$ correspond to the ESOs with $q \geq 0$ and $q < 0$ respectively [59]. Note that all the Stevens CF parameters B_k^q are real, whereas the matrix elements of O_k^q ($q < 0$) are imaginary. a_k are the α , β and γ Stevens coefficients [60] for $k = 2, 4, 6$, respectively, which are tabulated and depend on the number of *f* electrons. σ_k are the Sternheimer shielding parameters [61] of the *4f* electronic shell, and $\langle r^k \rangle$ are the expectation values of the radius.⁶

In the code, the A_k^q CF parameters are calculated through the following expressions:

$$A_k^0 = \frac{4\pi}{2k+1} \sum_{i=1}^N \frac{Z_i e^2}{R_i^{k+1}} Z_{k0}(\theta_i, \varphi_i) p_{kq} \quad (2.a)$$

(2.b)

$$A_k^q = \frac{4\pi}{2k+1} \sum_{i=1}^N \frac{Z_i e^2}{R_i^{k+1}} Z_{kq}^c(\theta_i, \varphi_i) p_{kq} \quad (2.c)$$

$$A_k^q = \frac{4\pi}{2k+1} \sum_{i=1}^N \frac{Z_i e^2}{R_i^{k+1}} Z_{k|q|}^s(\theta_i, \varphi_i) p_{k|q|}$$

and the effect of the ligand is modeled through an effective point charge situated between the lanthanoid and the coordinated atom at a distance R_i from the magnetic center, which is smaller than the real metal-ligand distance (r_i). To account for the effect of covalent electron sharing, a radial displacement vector (D_r) is defined, in which the polar coordinate r of each coordinated atom is varied, $R_i = r_i - D_r$. The usual procedure is to obtain the D_r parameter of each kind of donor atom fitting an observable (e.g. energy levels or magnetic properties). At the same time, the charge value (Z_i) is scanned in order to achieve the minimum deviation between calculated and experimental data, whereas θ and φ remain constant. This allows to inexpensively correlate the chemical structure with ligand field effects.

In this work, we have used the REC parameters $D_r = 0.8$ Å and $Z_i = 0.197$ determined by Baldoví *et al.* in the study of the $[\text{LnPd}_{12}(\text{AsPh})_8\text{O}_{32}]^{5-}$ series as a starting point [20]. Due to the different coordination environment between that family of lanthanide-based polyoxopalladates and $[\text{LnPd}_{15}\text{Se}_{10}\text{O}_{40}]^{7-}$, the parameter D_r have been scanned between 0.6 and 1.2 Å (step 0.1 Å) to explore a wider range of possibilities, while keeping fixed the relation $f = D_r \cdot Z_i = 0.1576$. As an illustrative example, the resulting set of CFPs, energy levels and compositions of the wave functions for $D_r = 1.0$ Å and $Z_i = 0.1576$ are reported in Tables S6 and S7.

Table S6. Crystal-field parameters ($A_k^q < r^k >$; Stevens notation) in cm⁻¹ calculated for **1-Tb**, **1-Dy**, **1-Ho** and **1-Er**.

k	q	1-Tb	1-Dy	1-Ho	1-Er
2	0	-274.50	-258.78	-243.24	-227.15
4	0	-120.00	-110.68	-102.74	-95.99
6	0	36.72	32.62	29.19	26.33

Table S7. Ground multiplet energy level scheme (cm⁻¹) and main $|M_J>$ contributions to the wave function calculated for **1-Tb**, **1-Dy**, **1-Ho** and **1-Er**.

1-Tb		1-Dy		1-Ho		1-Er	
0	100% $ 0>$	0	$ \pm 1/2>$	0	50% $ +4> + 50% -4>$	0	$ \pm 13/2>$
20	50% $ +1> + 50% -1>$	4	$ \pm 11/2>$	26	50% $ +5> + 50% -5>$	20	$ \pm 15/2>$
78	50% $ +2> + 50% -2>$	8	$ \pm 9/2>$	37	50% $ +3> + 50% -3>$	33	$ \pm 1/2>$
171	50% $ +3> + 50% -3>$	10	$ \pm 3/2>$	105	50% $ +2> + 50% -2>$	82	$ \pm 3/2>$
267	65% $ +6> + 35% -6>$	20	$ \pm 5/2>$	119	50% $ +6> + 50% -6>$	113	$ \pm 11/2>$
278	50% $ +4> + 50% -4>$	21	$ \pm 7/2>$	166	50% $ +1> + 50% -1>$	156	$ \pm 5/2>$
345	50% $ +5> + 50% -5>$	77	$ \pm 13/2>$	190	100% $ 0>$	199	$ \pm 9/2>$
		375	$ \pm 15/2>$	200	50% $ +8> + 50% -8>$	209	$ \pm 7/2>$
				225	50% $ +7> + 50% -7>$		

6. Coordinates

Cartesian coordinates (in Å) of **1**, **1-Na**, **1-La**, **1-Gd** and **1-Lu** as calculated on (U)BP/TZ2P/ZSC/COSMO level.

1: [Pd ₁₅ O ₁₀ (SeO ₃) ₁₀] ¹⁰⁻ (D _{5h})	1-Na: [NaPd ₁₅ O ₁₀ (SeO ₃) ₁₀] ⁹⁻ (D _{5h})		
Se -5.15109846 -0.00000000 -3.06712817	Na -0.00000022 -0.00000000 0.00000000		
O 1.83943972 1.33643106 1.34607842	O 1.83907834 1.33616879 1.35062860		
O 1.83943972 1.33643106 -1.34607842	O 1.83907834 1.33616879 -1.35062860		
O 1.83943972 -1.33643106 1.34607842	O 1.83907834 -1.33616879 1.35062860		
O 1.83943972 -1.33643106 -1.34607842	O 1.83907834 -1.33616879 -1.35062860		
O -0.70260321 -2.16239087 1.34607842	O -0.70246572 -2.16196652 1.35062860		
O -0.70260321 -2.16239087 -1.34607842	O -0.70246572 -2.16196652 -1.35062860		
O -2.27367215 -0.00000000 1.34607842	O -2.27322634 -0.00000000 1.35062860		
O -2.27367215 -0.00000000 -1.34607842	O -2.27322634 -0.00000000 -1.35062860		
O -0.70260321 2.16239087 1.34607842	O -0.70246572 2.16196652 1.35062860		
O -0.70260321 2.16239087 -1.34607842	O -0.70246572 2.16196652 -1.35062860		
Pd 2.93600505 -0.00000000 2.34029563	Pd 2.93954442 -0.00000000 2.34866493		
Pd 3.02529806 2.19800757 0.00000000	Pd 3.02941268 2.20099731 0.00000000		
Pd 0.90727557 2.79230657 2.34029563	Pd 0.90836903 2.79567308 2.34866493		
Pd 2.93600505 -0.00000000 -2.34029563	Pd 2.93954442 -0.00000000 -2.34866493		
Pd 0.90727557 2.79230657 -2.34029563	Pd 0.90836903 2.79567308 -2.34866493		
Pd 3.02529806 -2.19800757 0.00000000	Pd 3.02941268 -2.20099731 0.00000000		
Pd 0.90727557 -2.79230657 2.34029563	Pd 0.90836903 -2.79567308 2.34866493		
Pd 0.90727557 -2.79230657 -2.34029563	Pd 0.90836903 -2.79567308 -2.34866493		
Pd -2.37527767 -1.72574037 2.34029563	Pd -2.37814179 -1.72782099 2.34866493		
Pd -1.15556080 -3.55645096 0.00000000	Pd -1.15713298 -3.56128845 0.00000000		
Pd -2.37527767 -1.72574037 -2.34029563	Pd -2.37814179 -1.72782099 -2.34866493		
Pd -2.37527767 1.72574037 2.34029563	Pd -2.37814179 1.72782099 2.34866493		
Pd -3.73947367 -0.00000000 0.00000000	Pd -3.74456049 -0.00000000 0.00000000		
Pd -2.37527767 1.72574037 -2.34029563	Pd -2.37814179 1.72782099 -2.34866493		
Pd -1.15556080 3.55645096 0.00000000	Pd -1.15713298 3.56128845 0.00000000		
O 4.15895319 1.32875260 3.39607708	O 4.15486389 1.32530168 3.39303064		
O 4.15895319 -1.32875260 3.39607708	O 4.15486389 -1.32530168 3.39303064		
O 4.33215972 3.14749815 1.34784654	O 4.32569517 3.14280166 1.34206175		
O 4.33215972 3.14749815 -1.34784654	O 4.32569517 3.14280166 -1.34206175		
O 0.02146851 4.36600650 3.39607708	O 0.02348660 4.36105132 3.39303064		
O 2.54890616 3.54479223 3.39607708	O 2.54436020 3.54196984 3.39303064		
O 4.15895319 1.32875260 -3.39607708	O 4.15486389 1.32530168 -3.39303064		
O 4.15895319 -1.32875260 -3.39607708	O 4.15486389 -1.32530168 -3.39303064		
O 0.02146851 4.36600650 -3.39607708	O 0.02348660 4.36105132 -3.39303064		
O 2.54890616 3.54479223 -3.39607708	O 2.54436020 3.54196984 -3.39303064		
O 4.33215972 -3.14749815 1.34784654	O 4.32569517 -3.14280166 -1.34206175		
O 4.33215972 -3.14749815 1.34784654	O 4.32569517 -3.14280166 1.34206175		
O 0.02146851 -4.36600650 3.39607708	O 0.02348660 -4.36105132 3.39303064		
O 2.54890616 -3.54479223 3.39607708	O 2.54436020 -3.54196984 3.39303064		
O 4.33215972 -3.14749815 -1.34784654	O 4.32569517 -3.14280166 -1.34206175		
O 4.33215972 -3.14749815 1.34784654	O 4.32569517 -3.14280166 1.34206175		
O 0.02146851 -4.36600650 -3.39607708	O 0.02348660 -4.36105132 -3.39303064		
O 2.54890616 -3.54479223 -3.39607708	O 2.54436020 -3.54196984 -3.39303064		
O -2.58364231 -3.51955469 3.39607708	O -2.58236310 -3.51435943 3.39303064		
O -4.14568468 -1.36958781 3.39607708	O -4.14034867 -1.36997626 3.39303064		
O -1.65473753 -5.09275898 1.34784654	O -1.65226883 -5.08515991 1.34206175		
O -1.65473753 -5.09275898 -1.34784654	O -1.65226883 -5.08515991 -1.34206175		
O -2.58364231 -3.51955469 -3.39607708	O -2.58236310 -3.51435943 -3.39303064		
O -4.14568468 -1.36958781 -3.39607708	O -4.14034867 -1.36997626 -3.39303064		
O -4.14568468 1.36958781 3.39607708	O -4.14034867 1.36997626 3.39303064		
O -2.58364231 3.51955469 3.39607708	O -2.58236310 3.51435943 3.39303064		
O -5.35484351 -0.00000000 1.34784654	O -5.34685376 -0.00000000 1.34206175		
O -5.35484351 -0.00000000 -1.34784654	O -5.34685376 -0.00000000 -1.34206175		
O -4.14568468 1.36958781 -3.39607708	O -4.14034867 1.36997626 -3.39303064		
O -2.58364231 3.51955469 -3.39607708	O -2.58236310 3.51435943 -3.39303064		
O -1.65473753 5.09275898 1.34784654	O -1.65226883 5.08515991 1.34206175		
O -1.65473753 5.09275898 -1.34784654	O -1.65226883 5.08515991 -1.34206175		
Se 4.16732651 3.02773981 3.06712817	Se 4.16243300 3.02418476 3.06120924		
Se 4.16732651 -3.02773981 3.06712817	Se 4.16243300 -3.02418476 3.06120924		
Se 4.16732651 3.02773981 -3.06712817	Se 4.16243300 3.02418476 -3.06120924		
Se -1.59177685 4.89898592 3.06712817	Se -1.58990823 4.89323372 3.06120924		
Se -1.59177685 4.89898592 -3.06712817	Se -1.58990823 4.89323372 -3.06120924		
Se -1.59177685 -4.89898592 3.06712817	Se -5.14505063 -0.00000000 3.06120924		
Se -1.59177685 -4.89898592 -3.06712817	Se -5.14505063 -0.00000000 -3.06120924		
Se -5.15109846 -0.00000000 3.06712817	Se -5.14505063 -0.00000000 -3.06120924		

1-La: [LaPd ₁₅ O ₁₀ (SeO ₃) ₁₀] ⁷⁻ (D_{5h})				1: Gd [GdPd ₁₅ O ₁₀ (SeO ₃) ₁₀] ⁷⁻ (D_{5h})			
La	0.00000099	0.00000000	0.00000000	Gd	-0.00000007	-0.00000000	0.00000000
O	1.83422520	1.33264189	1.35708367	O	1.79670793	1.30538477	1.33565068
O	1.83422520	1.33264189	-1.35708367	O	1.79670793	1.30538477	-1.33565068
O	1.83422520	-1.33264189	1.35708367	O	1.79670793	-1.30538477	1.33565068
O	-0.70061031	-2.15625988	1.35708367	O	-0.68628146	-2.11215692	1.33565068
O	-0.70061031	-2.15625988	-1.35708367	O	-0.68628146	-2.11215692	-1.33565068
O	-2.26722481	0.00000000	1.35708367	O	-2.22085329	-0.00000000	1.33565068
O	-2.26722481	0.00000000	-1.35708367	O	-2.22085329	-0.00000000	-1.33565068
O	-0.70061031	2.15625988	1.35708367	O	-0.68628146	2.11215692	1.33565068
O	-0.70061031	2.15625988	-1.35708367	O	-0.68628146	2.11215692	-1.33565068
Pd	2.94500870	0.00000000	2.36771485	Pd	2.92198025	-0.00000000	2.35246027
Pd	3.03766881	2.20699486	0.00000000	Pd	3.01050042	2.18725664	0.00000000
Pd	0.91005842	2.80086878	2.36771485	Pd	0.90294151	2.77896842	2.35246027
Pd	2.94500870	0.00000000	-2.36771485	Pd	2.92198025	-0.00000000	-2.35246027
Pd	0.91005842	2.80086878	-2.36771485	Pd	0.90294151	2.77896842	-2.35246027
Pd	3.03766881	-2.20699486	0.00000000	Pd	3.01050042	-2.18725664	0.00000000
Pd	0.91005842	-2.80086878	2.36771485	Pd	0.90294151	-2.77896842	2.35246027
Pd	0.91005842	-2.80086878	-2.36771485	Pd	0.90294151	-2.77896842	-2.35246027
Pd	-2.38256030	-1.73103210	2.36771485	Pd	-2.36393180	-1.71749694	2.35246027
Pd	-1.16028487	-3.57099269	0.00000000	Pd	-1.14990893	-3.53905558	0.00000000
Pd	-2.38256030	-1.73103210	-2.36771485	Pd	-2.36393180	-1.71749694	-2.35246027
Pd	-2.38256030	1.73103210	2.36771485	Pd	-2.36393180	1.71749694	2.35246027
Pd	-3.75476293	0.00000000	0.00000000	Pd	-3.72118332	-0.00000000	0.00000000
Pd	-2.38256030	1.73103210	-2.36771485	Pd	-2.36393180	1.71749694	-2.35246027
Pd	-1.16028487	3.57099269	0.00000000	Pd	-1.14990893	3.53905558	0.00000000
O	4.14572285	1.31697252	3.39047711	O	4.13201501	1.30991421	3.38036484
O	4.14572285	-1.31697252	3.39047711	O	4.13201501	-1.30991421	3.38036484
O	4.31228607	3.13305850	1.33347614	O	4.29475890	3.12032504	1.32393561
O	4.31228607	3.13305850	-1.33347614	O	4.29475890	3.12032504	-1.32393561
O	0.02858420	4.34978268	3.39047711	O	0.03106037	4.33456562	3.38036484
O	2.53361480	3.53584890	3.39047711	O	2.52266526	3.52499412	3.38036484
O	4.14572285	1.31697252	-3.39047711	O	4.13201501	1.30991421	-3.38036484
O	4.14572285	-1.31697252	-3.39047711	O	4.13201501	-1.30991421	-3.38036484
O	0.02858420	4.34978268	-3.39047711	O	0.03106037	4.33456562	-3.38036484
O	2.53361480	3.53584890	-3.39047711	O	2.52266526	3.52499412	-3.38036484
O	4.31228607	-3.13305850	-1.33347614	O	4.29475890	-3.12032504	-1.32393561
O	4.31228607	-3.13305850	1.33347614	O	4.29475890	-3.12032504	1.32393561
O	0.02858420	-4.34978268	3.39047711	O	0.03106037	-4.33456562	3.38036484
O	2.53361480	-3.53584890	-3.39047711	O	2.52266526	-3.52499412	-3.38036484
O	4.31228607	-3.13305850	-1.33347614	O	4.29475890	-3.12032504	-1.32393561
O	4.31228607	-3.13305850	1.33347614	O	4.29475890	-3.12032504	1.32393561
O	0.02858420	-4.34978268	-3.39047711	O	0.03106037	-4.33456562	-3.38036484
O	2.53361480	-3.53584890	-3.39047711	O	2.52266526	-3.52499412	-3.38036484
O	-2.57986142	-3.50224732	3.39047711	O	-2.57292224	-3.48848038	3.38036484
O	-4.12805547	-1.37134102	3.39047711	O	-4.11281875	-1.36899467	3.38036484
O	-1.64714534	-5.06939514	1.33347614	O	-1.64045202	-5.04879197	1.32393561
O	-1.64714534	-5.06939514	-1.33347614	O	-1.64045202	-5.04879197	-1.32393561
O	-2.57986142	-3.50224732	-3.39047711	O	-2.57292224	-3.48848038	-3.38036484
O	-4.12805547	-1.37134102	-3.39047711	O	-4.11281875	-1.36899467	-3.38036484
O	-4.12805547	1.37134102	3.39047711	O	-4.11281875	1.36899467	3.38036484
O	-2.57986142	3.50224732	3.39047711	O	-2.57292224	3.48848038	3.38036484
O	-5.33027650	0.00000000	1.33347614	O	-5.30861411	-0.00000000	1.32393561
O	-5.33027650	0.00000000	-1.33347614	O	-5.30861411	-0.00000000	-1.32393561
O	-4.12805547	1.37134102	-3.39047711	O	-4.11281875	1.36899467	-3.38036484
O	-4.12805547	1.37134102	3.39047711	O	-4.11281875	1.36899467	3.38036484
O	-2.57986142	3.50224732	-3.39047711	O	-2.57292224	3.48848038	-3.38036484
O	-1.64714534	5.06939514	1.33347614	O	-1.64045202	5.04879197	1.32393561
O	-1.64714534	5.06939514	-1.33347614	O	-1.64045202	5.04879197	-1.32393561
Se	4.15185527	3.01649871	3.05498473	Se	4.14140800	3.00890909	3.04494858
Se	4.15185527	-3.01649871	3.05498473	Se	4.14140800	-3.00890909	3.04494858
Se	4.15185527	3.01649871	-3.05498473	Se	4.14140800	3.00890909	-3.04494858
Se	-1.58586623	4.88079743	3.05498473	Se	-1.58187719	4.86851718	3.04494858
Se	4.15185527	-3.01649871	-3.05498473	Se	4.14140800	-3.00890909	-3.04494858
Se	-1.58586623	4.88079743	-3.05498473	Se	-1.58187719	4.86851718	-3.04494858
Se	-1.58586623	-4.88079743	3.05498473	Se	-1.58187719	-4.86851718	3.04494858
Se	-1.58586623	-4.88079743	-3.05498473	Se	-1.58187719	-4.86851718	-3.04494858
Se	-5.13197313	0.00000000	3.05498473	Se	-5.11906197	-0.00000000	3.04494858
Se	-5.13197313	0.00000000	-3.05498473	Se	-5.11906197	-0.00000000	-3.04494858

1-Lu: [LuPd ₁₅ O ₁₀ (SeO ₃) ₁₀] ⁷⁻ (D_{5h})			
Lu	-0.00000007	-0.00000000	0.00000000
O	1.77181341	1.28729785	1.32315721
O	1.77181341	1.28729785	-1.32315721
O	1.77181341	-1.28729785	1.32315721
O	1.77181341	-1.28729785	-1.32315721
O	-0.67677260	-2.08289167	1.32315721
O	-0.67677260	-2.08289167	-1.32315721
O	-2.19008198	-0.00000000	1.32315721
O	-2.19008198	-0.00000000	-1.32315721
O	-0.67677260	2.08289167	1.32315721
O	-0.67677260	2.08289167	-1.32315721
Pd	2.90737343	-0.00000000	2.34496041
Pd	2.99248011	2.17416411	0.00000000
Pd	0.89842775	2.76507651	2.34496041
Pd	2.90737343	-0.00000000	-2.34496041
Pd	0.89842775	2.76507651	-2.34496041
Pd	2.99248011	-2.17416411	0.00000000
Pd	0.89842775	-2.76507651	2.34496041
Pd	0.89842775	-2.76507651	-2.34496041
Pd	-2.35211464	-1.70891126	2.34496041
Pd	-1.14302579	-3.51787143	0.00000000
Pd	-2.35211464	-1.70891126	-2.34496041
Pd	-2.35211464	1.70891126	2.34496041
Pd	-3.69890899	-0.00000000	0.00000000
Pd	-2.35211464	1.70891126	-2.34496041
Pd	-1.14302579	3.51787143	0.00000000
O	4.12321339	1.30506327	3.37494130
O	4.12321339	-1.30506327	3.37494130
O	4.28215247	3.11116593	1.31789213
O	4.28215247	3.11116593	-1.31789213
O	0.03295404	4.32469576	3.37494130
O	2.51533189	3.51812230	3.37494130
O	4.12321339	1.30506327	-3.37494130
O	4.12321339	-1.30506327	-3.37494130
O	0.03295404	4.32469576	-3.37494130
O	2.51533189	3.51812230	-3.37494130
O	4.28215247	-3.11116593	-1.31789213
O	4.28215247	-3.11116593	1.31789213
O	0.03295404	-4.32469576	3.37494130
O	2.51533189	-3.51812230	3.37494130
O	0.03295404	-4.32469576	-3.37494130
O	2.51533189	-3.51812230	-3.37494130
O	0.03295404	-4.32469576	-3.37494130
O	2.51533189	-3.51812230	-3.37494130
O	-2.56865289	-3.47938242	3.37494130
O	-4.10284677	-1.36774570	3.37494130
O	-1.63563680	-5.03397223	1.31789213
O	-1.63563680	-5.03397223	-1.31789213
O	-2.56865289	-3.47938242	-3.37494130
O	-4.10284677	-1.36774570	-3.37494130
O	-4.10284677	1.36774570	3.37494130
O	-2.56865289	3.47938242	3.37494130
O	-5.29303170	-0.00000000	1.31789213
O	-5.29303170	-0.00000000	-1.31789213
O	-4.10284677	1.36774570	-3.37494130
O	-2.56865289	3.47938242	-3.37494130
O	-1.63563680	5.03397223	1.31789213
O	-1.63563680	5.03397223	-1.31789213
Se	4.13429078	3.00373812	3.03928453
Se	4.13429078	-3.00373812	3.03928453
Se	4.13429078	3.00373812	-3.03928453
Se	-1.57915865	4.86015038	3.03928453
Se	4.13429078	-3.00373812	-3.03928453
Se	-1.57915865	4.86015038	-3.03928453
Se	-1.57915865	-4.86015038	3.03928453
Se	-1.57915865	-4.86015038	-3.03928453
Se	-5.11026459	-0.00000000	3.03928453
Se	-5.11026459	-0.00000000	-3.03928453