gels

MDPI

Article

A Natural Antioxidant-Rich Hydrogel Formulation with *Laurus nobilis* Hydrosol: Physicochemical and Cosmeceutical Evaluation

Lea Juretić [1], Radwan Joukhadar [2], Emerik Galić [2], Renata Jurišić Grubešić [1] and Mario Jug [2,*]

[1] Faculty of Medicine, University of Rijeka, Braće Branchetta 20, HR-51000 Rijeka, Croatia; lea.juretic@medri.uniri.hr (L.J.); renatajg@medri.uniri.hr (R.J.G.)
[2] Faculty of Pharmacy and Biochemistry, University of Zagreb, A. Kovačića 1, HR-10000 Zagreb, Croatia; radwan.joukhadar@gmail.com (R.J.); emerik.galic@pharma.unizg.hr (E.G.)
* Correspondence: mario.jug@pharma.unizg.hr; Tel.: +385-1-6394-764

Abstract

Laurus nobilis hydrosol (HyLN), a water-soluble byproduct of essential oil extraction, containing beneficial antioxidants and antimicrobial compounds, was used as a sustainable ingredient in the development of a natural antioxidant-rich hydrogel formulation. Hydrogels were formulated using sodium hyaluronate and xanthan gum, natural ingredients with beneficial effects on the skin, while β-cyclodextrin (βCD) was added to enhance the stability of antioxidants in HyLN. Extensive rheological and textural analyses were employed to optimize the hydrogel formulation for dermal administration, while stability studies assessed the chemical and physical stability of developed formulations. A combination of sodium hyaluronate and xanthan gum provided several HyLN hydrogel formulations with tunable rheological and textural properties, presenting adequate physical and microbiological stability over 6 months of storage. The use of βCD failed to stabilize inherently unstable antioxidants in HyLN hydrogels, yet their residual antioxidant activity remained notable. An in vitro scratch test using a human keratinocyte cell line showed that the developed HyLN gel does not interfere with wound healing. HyLN hydrogels showed a pronounced occlusive effect in vitro, reaching up to 80% of that measured for Vaseline, which helps maintain skin hydration and appearance.

Keywords: *Laurus nobilis* L.; hydrosol; sodium hyaluronate; xanthan; rheology; textural analysis; antioxidants; wound healing; in vitro occlusive effect

Check for updates

Academic Editor: Charalampos Proestos

Received: 14 January 2026
Revised: 12 February 2026
Accepted: 12 February 2026
Published: 14 February 2026

Copyright: © 2026 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license.

1. Introduction

Laurus nobilis L. (Lauraceae), commonly referred to as bay laurel, is an evergreen tree or shrub indigenous to the Mediterranean basin and parts of Asia. The species is primarily valued for its leaves (Lauri folium), which represent the principal medicinal raw material. In classical antiquity, it was also ascribed symbolic significance, particularly as an emblem of wealth, honour, and distinction in Greek and Roman culture [1,2]. A hydrosol is a by-product of steam distillation used to produce essential oils, capturing water-soluble plant components and a small amount of essential oil during the process, creating an aromatic, diluted form of the plant's essence [3,4]. *L. nobilis* hydrosols were studied for their antimicrobial, antioxidant, and cytotoxic properties, demonstrating significant potential for further medicinal and cosmeceutical applications, providing better tolerability compared to the essential oils [5,6]. In line with green and sustainability principles, this research has focused on using bay leaf hydrosols as a secondary raw material to develop

natural, antioxidant-rich cosmeceuticals and dermopharmaceutical skin preparations [4]. The natural plant antioxidants, biosynthesized as a defence mechanism against oxidative stress-induced cell damage, are suitable ingredients for protecting human skin from aging-related deterioration. This process is often accelerated by sunlight and other external factors, such as weather, pollutants, and lifestyle habits, which together accelerate skin aging, leading to wrinkles, spots, freckles, dehydration, reduced healing ability, and other signs of aging [7]. *Laurus nobilis* hydrosols (HyLN), a water-soluble byproduct of essential oil extraction, contain beneficial compounds, including oxygenated monoterpenes, with 1,8-cineole as the predominant component, which act as antioxidants and antimicrobials and show mild wound-healing potential [6], positioning them as a sustainable ingredient for cosmeceutical and dermopharmaceutical applications. This approach enhances the value of plant byproducts, creating environmentally friendly alternatives to synthetic ingredients for skin health and rejuvenation [8].

In accordance with this, we selected sodium hyaluronate and xanthan gum as natural ingredients with beneficial effects on the skin to develop antioxidant-rich hydrogel formulations. Hyaluronic acid is a naturally occurring linear, unbranched polysaccharide built of repeating units of disaccharide, containing D-glucuronic acid and N-acetyl-D-glucosamine linked by alternating β-1,3 and β-1,4-glycosidic bonds [9]. It is commonly used in the sodium salt form, which is more stable, more soluble in water over a wider pH range, and more resistant to microbial degradation and oxidation, thus providing a better shelf life. Hyaluronic acid is a key component of the extracellular matrix, playing multiple roles in biological processes, including skin repair, wound healing, tissue regeneration, and modulation of inflammatory and immune responses. Due to its exceptional biocompatibility, hydration capacity, and regenerative properties, hyaluronic acid is widely utilized in (dermo)cosmetic formulations as an essential ingredient for skin health and anti-aging applications [10,11]. Furthermore, hyaluronic acid has excellent potential as an excipient for the development of various (dermo)cosmetic and drug-delivery formulations due to its biocompatibility, biodegradability, and non-immunogenicity [9]. It is frequently incorporated into hydrogels that provide sustained and prolonged release of entrapped bioactive molecules [12,13]. To achieve this, it is often necessary to modify the textural and rheological properties of hyaluronic acid by simply adding another synthetic or natural polymer. In this context, xanthan gum, a polysaccharide secreted by the bacterium *Xanthomonas campestris*, was introduced into the formulation. Xanthan gum is made of pentasaccharide repeating units that include glucose, mannose, and glucuronic acid in a molar ratio of 2:2:1 and is used as a rheology modifier in cosmetic products. It is soluble in both hot and cold water, producing neutral, pseudoplastic solutions that remain stable across a wide range of temperatures and pH values [14].

In this paper, extensive rheological and textural analyses were conducted to optimize the hydrogel formulation for dermal administration and to assess the impact of selected technological parameters on the gel's physicochemical properties and microstructure. Given the literature evidence that β-cyclodextrin (βCD), a cyclic oligosaccharide, can form inclusion complexes with key HyLN constituents (1,8-cineole, γ-terpinene, α-pinene, terpinene-4-ol), we incorporated βCD to investigate whether such complexation might translate into improved stability of these antioxidants [15–18]. Stability studies were conducted, monitoring the pH, rheological, textural, and antioxidative properties of the developed gel formulations to select the formulation with the highest potential for further development. Finally, the (dermo)cosmetic potential of the formulations was evaluated using an in vitro scratch test on a human keratinocyte cell line to assess their wound-healing capabilities, followed by an in vitro occlusion test to assess their ability to enhance skin hydration.

2. Results and Discussion

2.1. Preparation and Rheological Characterization of HyLN Hydrogels

The hydrogels were prepared with high-molecular-mass cosmetic-grade sodium hyaluronate at 0.5% (*w*/*w*), a typical concentration used in cosmetic skin products for hydration and skin barrier support [19]. The xanthan gum was incorporated at 1% and 2% to adjust the consistency and viscosity of the hydrogels to levels suitable for topical application. Pentylene glycol was added as a multifunctional excipient, serving as a humectant, solvent, and mild preservative [20]. Its ability to provide efficient antimicrobial preservation of hydrogels with a similar polymeric composition was previously demonstrated [21]. βCD was added to enhance the stability of antioxidants in HyLN through inclusion complexation [22]. The composition of the prepared hydrogels is presented in Table 1. In addition to hydrogels prepared using HyLN, hydrogel samples containing purified water as the continuous phase (blank gels) were also prepared to examine the influence of HyLN on the rheological and textural properties of the prepared formulations. All hydrogels exhibited a uniform, translucent appearance with a faint off-white coloration.

Table 1. Composition of the prepared HyLN hydrogels.

Sample Code	Sodium Hyaluronate (%, *w*/*w*)	Xanthan Gum (%, *w*/*w*)	β-Cyclodextrin (%, *w*/*w*)	Pentylene Glycol (%, *w*/*w*)	HyLN [1] (%, *w*/*w*)
F1 HyLN gel	0.5	1.0	-	5.0	ad 100
F1/βCD HyLN gel	0.5	1.0	1.0	5.0	ad 100
F2 HyLN gel	0.5	2.0	-	5.0	ad 100
F2/βCD HyLN gel	0.5	2.0	1.0	5.0	ad 100

[1] Blank hydrogel samples were prepared by omitting the HyLN and replacing it with the same quantity of purified water.

The rheological characterization of hydrogel formulations provides valuable insights into key aspects affecting their development and functionality, including flow through pipes, behavior during stirring, removal from packaging, and skin application [19]. Moreover, rheology plays a crucial role in tailoring the properties of (dermo)cosmetic products to meet specific functional and sensory requirements [20]. In this study, we conducted various rotational and oscillatory rheological tests to evaluate the developed hydrogels and identify the most appropriate for intended use.

The shear viscosity profiles of the prepared blank and HyLN hydrogels are presented in Figure 1, showing non-Newtonian shear thinning behavior typical of polysaccharide hydrogels, where high-molecular-weight, flexible chains of hyaluronate and xanthan interact via hydrogen bonding and physical entanglement. These interactions are disrupted under shear, leading to non-Newtonian, pseudoplastic (shear-thinning) behavior. Similar behavior was also observed for composite xanthan/hyaluronic acid eutectogels [23]. The viscosity of the hydrogels was primarily dependent on the xanthan gum concentration in the formulations, with samples containing 2% (*w*/*w*) xanthan gum exhibiting greater viscosity. Interestingly, there is a slight difference between the viscosity of blank and HyLN-loaded hydrogels of the same composition (Figure 1).

Considering the relatively acidic pH of HyLN observed previously [6], the pH of the prepared hydrogels was measured to help explain the observed viscosity difference and assess their suitability for dermal application. The results of pH measurements of blank and HyLN hydrogels are presented in Figure 2.

Blank hydrogels prepared with purified water as the continuous phase had a more neutral pH, ranging from 6.29 to 5.97, while samples containing βCD showed slightly lower pH values, but the difference with respect to the samples with the same polymeric content but without βCD was not statistically significant ($p > 0.05$). The pH of HyLN-based

hydrogels was around 4.7, close to the skin's natural pH [24] and consistent across gel compositions. In fact, the observed pH difference between the blank and HyLN-loaded hydrogels may explain the differences in gel viscosity. Namely, the viscosity of sodium hyaluronate solutions is strongly dependent on pH [25]. At neutral pH, polymer chains are fully ionized, resulting in maximum electrostatic repulsion and enhanced hydration, which, in turn, leads to higher viscosity. A decrease in pH leads to protonation of the carboxyl groups, reducing electrostatic repulsion, causing the polymer chains to collapse and adopt a double left-handed helical structure, thereby lowering viscosity [26]. However, protonation of HA may increase its tendency to interact with xanthan gum through hydrogen bonding and physical entanglement due to decreased charge repulsion, thus enhancing the viscosity of the formed gel. Furthermore, experimental data show that xanthan gum exhibits a viscosity increase between pH 3.6 and 4.4, likely due to protonation effects and helix-coil transitions that enhance intermolecular hydrogen bonding [27]. This structural ordering can synergize with sodium hyaluronate (which partially loses charge at low pH), leading to stronger network formation, consistent with general polyelectrolyte behavior and supported by formulation practices [28].




Figure 1. Shear viscosity profiles of the prepared blank and HyLN hydrogels without (**left**) and with βCD (**right**) at 32 °C. For formulation compositions, please refer to Table 1.




Figure 2. The pH of blank (left) and HyLN-loaded (right) hydrogels. Asterisk (*) denotes a statistically significant difference compared to the corresponding blank hydrogel ($p < 0.05$). For formulation compositions, please refer to Table 1.

The observed shear-thinning profiles, primarily governed by xanthan gum concentration, provide a tunable handle for formulation design. Increasing xanthan gum from 1%

to 2% (*w*/*w*) elevates low-shear viscosity (Figure 1), which is beneficial for sag-resistance during storage and on-skin residence after application (reduced dripping), while maintaining sufficient shear-thinning to enable dosing through standard dispensers. In HyLN gels, the slightly lower viscosity compared with blanks of the same polymer content (consistent with the pH-dependent hydration/ionization of hyaluronan) is advantageous for spreading (lower force at application shear rates) without compromising small-amplitude elasticity (see oscillatory data), thus supporting comfortable application while preserving film integrity on the skin [29]. The negligible effect of βCD on viscosity indicates that its use for inclusion complexation can be implemented without penalizing flow during manufacturing, filling, or end-use spreading.

Shear-thinning systems that are highly sensitive to applied shear stress are generally undesirable for topical application, as they may leak off from the skin after administration, leading to limited retention at the application site or drip from the container during dispensing. In this sense, formulations that temporarily reduce viscosity upon application and subsequently recover their original structure over time (i.e., thixotropic systems) can provide improved retention on the skin and potentially better biopharmaceutical performance. Accordingly, the thixotropic properties of the developed HyLN hydrogels were evaluated using a three-interval thixotropy (3-ITT) test, and the results are shown in Figure 3.




Figure 3. Time-dependent viscosity changes in blank (**left panel**) and HyLN-loaded gels (**right panel**) observed through a 3-interval thixotropy test at 32 °C. For formulation compositions, please refer to Table 1.

Figure 3 shows the time-dependent viscosity changes in hydrogels during the 3-interval thixotropy test (3-ITT). In all samples, viscosity sharply decreased at the high shear rate of 1000 s^{-1}, indicating a temporary structural breakdown of the polymer network. Upon returning to the initial shear rate, different levels of structural recovery were observed within 60 s, depending on the xanthan gum content. In blank hydrogels containing 1% (*w*/*w*) xanthan gum, recovery was rapid, reaching 91.7–94.8% for F1-blank and F1/βCD blank gels, respectively. For HyLN gels of the same composition, recovery even exceeded 100% (108.3% and 107.3%), a phenomenon previously reported in other hydrogel systems [30,31]. This over-recovery likely reflects shear-induced structural reorganization during the high-shear phase, resulting in a more compact polymer network reinforced by hydrogen bonding. The influence of pH on hyaluronan/xanthan interactions, as discussed earlier, may further contribute to this behaviour. In contrast, hydrogels with higher xanthan gum concentrations exhibited lower recovery, probably due to reduced polymer chain mobility associated with higher viscosity. Recovery levels for these samples ranged from 72.0–75.1%, similar for both blank and HyLN hydrogels. Overall, practical experience and rheological studies suggest that a recovery of 70–80% is suitable for topical hydrogels, ensuring adequate structural rebuilding after shear, preventing dripping or sagging, and

maintaining controlled release of incorporated bioactive compounds without excessive rigidity. The addition of βCD did not significantly affect the thixotropic behaviour of the prepared gels (Figure 3).

The observed viscosity recovery translates directly to on-skin behavior: rapid and high structural rebuilding (≈92–95% for F1 blank gel and >100% for F1 HyLN gel) indicates that, after the high-shear event of rubbing, the gels promptly regain their structure, limiting flow-off and supporting uniform film formation. The observed over-recovery suggests shear-induced microstructural reorganization (e.g., enhanced hydrogen-bond-assisted associations at lower pH) that may further strengthen post-application structure. In contrast, the lower recovery (≈72–75%) at 2% (*w*/*w*) of xanthan gum is consistent with higher base viscosity and reduced chain mobility: while still within a practical range for topical gels, this behavior favors applications where maximal on-site retention and a "body-richer" sensorial profile are desired, at the expense of higher extrusion/spreading force [29].

To further investigate the viscoelastic properties and microstructure of the prepared hydrogels, a frequency sweep test was performed under strain conditions previously confirmed to lie within the linear viscoelastic region, as determined by the amplitude sweep test [32]. The results are presented in Figure 4.




Figure 4. Dependence of storage (G′) and loss (G″) moduli on the angular frequency for blank and HyLN-loaded hydrogels in the linear viscoelastic region. For formulation compositions, please refer to Table 1.

The viscoelastic behaviour of the hydrogels was strongly influenced by xanthan gum concentration. As expected for physically crosslinked gels, for all samples, both G′ and G″ exhibited frequency dependence [32]. For hydrogels containing 1% xanthan gum, at low frequencies, G′ exceeded G″, indicating gel-like behaviour with pronounced elastic dominance and suggesting a well-developed network capable of gradual relaxation. At intermediate frequencies (around 1 rad·s^{-1}), the difference between G′ and G″ was minimal, placing the material near the transition between elastic and viscous responses. This reflects a network that is not highly rigid but retains some fluid-like characteristics, consistent with previous findings [21]. At high frequencies, the difference between G′ and G″ increased

again, with G′ dominating, as rapid oscillations limit polymer chain rearrangement and favour elastic response [32]. The hydrogels prepared with 2% xanthan gum exhibited $G' \gg G''$ across the entire frequency range, indicating the formation of a strongly elastic gel, regardless of βCD addition, showing that xanthan gum concentration is the main factor contributing to the gel formation. The presence of βCD did not significantly alter the viscoelastic properties of the gels. βCD is a cyclic oligosaccharide that mainly forms host–guest inclusion complexes with hydrophobic molecules and not with the hydrophilic backbones of hyaluronan or xanthan gum [33]. Therefore, βCD does not significantly interfere with the physical crosslinking or chain entanglement that governs gel elasticity.

Surprisingly, for all tested samples, the G′ and G″ values of blank and HyLN-loaded hydrogels were comparable (Figure 4), despite notable differences in viscosity caused by pH variations (Figure 1). This apparent discrepancy can be explained by the fundamental distinction between the two rheological methods: rotational viscosity can differ with pH due to changes in the material's structure that affect its resistance to flow, while oscillatory moduli might remain similar because pH changes may not significantly alter the material's internal elastic properties or energy dissipation under small, oscillatory deformations [34]. Practically, this means that HyLN enables skin-compatible pH (~4.7) and facilitates spreading, while preserving the elastic backbone required for film integrity and residence.

2.2. Textural Analysis of HyLN Hydrogels

In (dermo)cosmetic and semisolid pharmaceutical formulations, texture encompasses a set of mechanical and structural properties perceived primarily through tactile and visual senses. Key textural parameters include firmness, consistency, cohesiveness, and spreadability, which define the sensory experience during product application. These attributes are critical for consumer and patient adherence, as favourable textural characteristics can enhance product acceptance and sustained use [35]. Instrumental textural analysis provides an objective means to quantify these parameters, enabling a systematic evaluation of product performance and its alignment with sensory expectations. Although correlating subjective sensory impressions with instrumental measurements remains complex, such analysis offers valuable insights for optimizing formulations and predicting consumer acceptability [35,36].

In this study, we used the backward extrusion test to evaluate the firmness, consistency, and cohesiveness of the prepared hydrogels, while the spreadability test was used to measure the work of shear required to spread the sample into a thin layer. The values obtained for the blank and HyLN-loaded gels are shown in Figure 5. The measured textural properties were primarily influenced by the concentration of xanthan, whereas the incorporation of βCD did not produce significant variations. In some cases, hydrogels containing HyLN exhibited higher values for the evaluated textural parameters than their corresponding blank formulations, consistent with the increased viscosity observed in rheological measurements (Figure 1).

One of the main limitations of textural analysis for (dermo)cosmetic and semisolid pharmaceutical products is the lack of standardized protocols for measuring individual parameters and the absence of universally accepted reference values [36]. In the scientific literature, researchers often use different probes and operational settings, which introduces considerable variability and makes it difficult to compare results across studies. To our knowledge, the only published dataset generated using this specific back-extrusion and spreadability methodology pertains to sunscreen products [35], providing a relevant quantitative benchmark for interpreting consumer-acceptability ranges despite differences in formulation type. In their study, the authors analysed the textural properties of 39 sunscreen

formulations marketed in Asia, North America, Latin America, and Europe, providing ranges for firmness, consistency, cohesiveness, and work of shear using the same methodology applied in this work. For products available on the European market, the reported ranges were as follows: firmness, 74.1–490.5 g; consistency, 35.9–484.7 g·s; cohesiveness, 26.9–141.6 g·s; and work of shear, 33.9–479.4 g·s [35]. Based on these values, the firmness of the prepared hydrogels (Figure 5) falls below or at the lower end of the range for European-market products. The consistency and cohesiveness of formulations containing 1% (*w*/*w*) xanthan gum (F1 and F1/βCD) are within acceptable limits, whereas those prepared with 2% (*w*/*w*) xanthan gum (F2 and F2/βCD) exceed the upper limit reported for commercial products (Figure 5). Nevertheless, even the 2% (*w*/*w*) xanthan gum formulations exhibited favourable spreading behaviour, requiring work of shear values at the lower end of the reported range, likely due to the shear-thinning characteristics of the physically crosslinked hyaluronic acid/xanthan gels. Taken together, these results consolidate a design trade-off already apparent from rheology: higher xanthan gum content (2% *w*/*w*) shifts the product toward maximal residence, richer texture, and strong film cohesion, at the expense of increased application force relative to 1% XG (i.e., higher 'brush/drag' under mid/high shear). On the other side, lower xanthan (1% *w*/*w*) prioritizes ease of spreading and comfort while preserving sufficient cohesion and rapid post-shear recovery to avoid dripping/sagging.




Figure 5. Parameters of the textural analysis obtained by backward extrusion and spreadability tests of prepared blank and HyLN-loaded hydrogels. One asterisk (*) represents a statistically significant difference ($p < 0.05$) with respect to the corresponding sample containing 1% (*w*/*w*) of xanthan gum. Two asterisks (**) represent a statistically significant difference ($p < 0.05$) with respect to the corresponding blank gel. For formulation compositions, please refer to Table 1.

2.3. Stability Studies of HyLN Hydrogels

Stability is a key quality attribute of any (dermo)cosmetic and pharmaceutical product, ensuring its safety and efficiency. It encompasses several aspects, including the chemical, physical, and microbial stability of the developed product [37]. In this study, we monitored formulation pH and antioxidative activity as indicators of chemical stability of the developed HyLN-loaded hydrogels. The physical stability of hydrogels was assessed by monitoring hydrogel viscosity at a shear of 1 s^{-1}, relevant to spreading the formulation on the skin [20], loss factor (tan δ) at 1 rad s^{-1}, a midpoint of the examined range, as well as consistency, and spreadability as a function of storage time. Finally, the microbial stability of the developed formulation was assessed visually. The samples were stored in a refrigerator at 4 °C for 6 months, in line with the general recommendations for hydrosol storage in cold, dark places [4].

The changes in pH values and the antioxidant activity of the prepared HyLN hydrogels during storage are presented in Figure 6. Here, the antioxidant activity of HyLN, the starting ingredient for the gel preparation, is also provided for comparison. The pH of the prepared HyLN-loaded hydrogels was stable over the examined period (Figure 6). Antioxidative activity of HyLN and its hydrogels was determined by Trolox equivalent antioxidant capacity (TEAC) assay. TEAC uses the ABTS (2,2′-azobis-(3-ethylbenzothiazoline-6-sulphonic acid) radical cation (ABTS$\bullet^{+}$), which reacts with both hydrophilic and lipophilic antioxidants, making TEAC more versatile than the DPPH (2,2-diphenyl-1-picrylhydrazyl) radical-scavenging method, which primarily measures lipophilic antioxidants. TEAC can be performed over a wide pH range, unlike the FRAP (Ferric Reducing Antioxidant Power) assay, which is limited to acidic conditions (pH ~3.6). The results are expressed as Trolox equivalents, providing a standardized and straightforward comparison across different samples. TEAC is sensitive to a wide range of antioxidants and is mainly based on electron transfer, with some contribution from hydrogen atom transfer, making it more representative of antioxidant behaviour in biological systems, although it does not fully mimic in vivo conditions [38]. The antioxidant activity of HyLN decreased by 31.4% over six months of storage, reflecting the inherent instability of the bioactive compounds present in the hydrosol, despite refrigeration. A similar level of degradation (i.e., 31.4% and 30.3%) was also observed for F1 and F1/βCD HyLN gel, while for samples prepared with 2% (*w*/*w*) of xanthan gum, the level of degradation was higher, reaching 35.1 and 44.8% for F2 and F2/βCD HyLN gel, respectively. Increasing the xanthan gum content in hydrogel formulations appears to further destabilize the antioxidative compounds in HyLN or to cause their binding to xanthan, as observed with polyphenols [39].

Additionally, adding βCD did not stabilize the antioxidants in HyLN (Figure 6). CDs have a dual effect on the chemical stability of guest molecules, which mainly depends on the structure of the inclusion complex. Encapsulation of the drug's reactive functional group within the hydrophobic cavity of the CD generally protects it from degradation by reducing its exposure to external reactants. Conversely, when the reactive group remains outside the cavity, CDs can promote degradation processes, as shown for β-lactam antibiotics and proton pump inhibitors [22]. In this context, to ensure adequate stability of antioxidants in HyLN, their interactions with CDs should be studied to identify the structures of the formed complexes, which may help select a more effective CD derivative, with the focus on chemically modified βCD derivatives. Derivatization of the parent βCD molecule can eliminate its negative impact on drug stability, as demonstrated for prostaglandin inclusion complexes involving parent βCD and its methylated derivative [22]. Although βCD could not stabilize the antioxidants in HyLN, the hydrogels still exhibited significant residual antioxidant activity (Figure 6).




Figure 6. Variation in pH and antioxidative activity determined by Trolox equivalent antioxidant capacity assay of the HyLN hydrogels as a function of time during storage at 4 °C. Antioxidative activity of HyLN, the principal ingredient of the hydrogels, was added for comparison. The asterisk (*) represents a statistically significant difference with respect to the initial value of the same sample. For formulation compositions, please refer to Table 1.

The viscosity of the hydrogels remained stable over the 6-month storage period, with only insignificant variation, indicating physical stability of the prepared gels (Figure 7). Further information on the hydrogel's physical stability was obtained by monitoring the loss factor (tan δ), calculated as G″/G′. The loss factor represents the rate of dissipated and stored energy during the deformation cycle and indicates the gel strength. In general, gels with tan $\delta \approx 1$ are classified as weak; the ones with values in the interval $0.1 < \tan \delta < 0.5$ are considered to have medium strength, while values $\leq$ indicate the formation of a strong gel [40]. In this sense, samples prepared with 1% (w/w) of xanthan (F1 and F1/βCD HyLN gels) can be considered weak gels, where formulation F1 exhibited a slight decrease in tan δ during storage, indicating some reorganization and hydrogel network stabilization, while such an effect was not observed for the sample containing βCD (Figure 7). The hydrogels formulated with 2% (w/w) xanthan gum (F2 and F2/βCD HyLN gels, respectively) presented tan δ values typical of medium-strength gels and remained constant during storage. In general, a tan δ constant over time is an indication of the long-term stability of the formulation [41]. The physical stability of HyLN hydrogels was further supported by the examined textural parameters—the consistency and, consequently, the spreadability of the samples remained constant during storage, while only samples formulated with 2% (w/w) xanthan showed a slight, insignificant decrease in these parameters (Figure 7).




Figure 7. Selected rheological and textural parameters as indicators of hydrogels' physical stability: viscosity at 10 s^{-1} ($\eta(10\ s^{-1})$), loss factor (tan δ) at 1 rad s^{-1}, consistency and spreadability as a function of the storage time at 4 °C. For formulation compositions, please refer to Table 1.

No visible signs of microbial growth were observed during storage, whereas in preliminary hydrogels prepared without pentylene glycol, molding was observed after a few days, regardless of refrigeration. However, to fully investigate the preservative efficiency of pentylene glycol in the developed hydrogels, a microbial challenge test is required.

2.4. Functional Characterisation of HyLN Hydrogels

The selected HyLN formulations were further evaluated to assess their (dermo)cosmeceutical potential. In this context, an in vitro scratch test was performed on a human keratinocyte cell line to assess wound-healing capabilities, followed by an in vitro occlusion test to evaluate the formulation's ability to enhance skin hydration.

In vitro wound healing models are essential tools for advancing the understanding of tissue repair by providing a simplified and controlled environment that is suitable for the systematic evaluation of therapeutic interventions under reproducible conditions [42]. The in vitro scratch assay is an easy, fast, low-cost, and standardised method widely used to measure cell migration in vitro after a uniform "wound" is introduced by mechanically disrupting a confluent monolayer of cells, typically fibroblasts or keratinocytes. Cell migration into the wound area is tracked over time to assess wound closure [42,43]. For this study, we selected F1 and F1/βCD HyLN hydrogels because they demonstrated higher antioxidative potential than those formulated with 2% (*w*/*w*) xanthan gum. The results are presented in Figure 8 and Table 2.

The percentage of wound closure observed with the tested HyLN hydrogels is slightly lower than that of the control (Table 2), but the difference is not statistically significant ($p > 0.05$). This suggests that the developed formulations do not actively promote wound healing in the tested model, even though HyLN alone demonstrated a mildly positive effect

in previous research [6]. Additionally, the expected positive impact of sodium hyaluronate was not observed. Many studies have shown that sodium hyaluronate actively participates in all stages of wound healing. However, its effect is highly dependent on the molecular weight. For example, low-molecular-weight hyaluronan (10–250 kDa) supports the epidermalization phase but increases the expression of TGF-β1 and TGF-β2, which are responsible for scar formation. On the other hand, high-molecular-weight hyaluronan (>1000 kDa), such as that used in this study, increases TGF-β3 expression, thereby suppressing the scarring process [11]. In this regard, further development of formulations should focus on combining low- and high-molecular-weight hyaluronans and on evaluating the formulations using in vivo wound-healing models in animal subjects [37].




Figure 8. Microphotographs of the wound healing assay at timepoints of 0 h, 24 h, 48 h, and 72 h, respectively. The microscope magnification and scale bar are the same for all subfigures (4100×). For formulation compositions, please refer to Table 1.

Table 2. Wound healing rate at 24 h, 48 h, and 72 h after treatment with HyLN hydrogels.

Sample Code	Wound Healing Rate at 24 h (%)	Wound Healing Rate at 48 h (%)	Wound Healing Rate at 72 h (%)
F1 HyLN gel	18.94 ± 3.94	48.17 ± 5.11	60.83 ± 5.85
F1/βCD HyLN gel	23.46 ± 1.96	51.43 ± 2.89	69.72 ± 3.25
Control	32.09 ± 1.57	66.65 ± 5.10	80.56 ± 7.52

The occlusive effect, characteristic of some topical formulations, helps maintain skin hydration by reducing transepidermal water loss and supporting the skin barrier. This increased hydration can improve skin appearance, enhance the penetration of bioactive compounds, and provide optimal conditions for wound healing [42,44]. In this study, the occlusive effect of selected hydrogels was evaluated gravimetrically and compared with that of Vaseline, a well-known occlusive compound (Figure 9). In the test, Vaseline presented almost complete occlusion, aligned with its clinical performance [45]. The examined hydrogels (F1 and F2 HyLN gel, respectively) showed a notable occlusive effect, reaching up to 80% of the occlusive effect measured for Vaseline. Such a prominent occlusive effect may be attributed to the use of high molecular weight sodium hyaluronate, which binds large amounts of water, forming a cohesive gel layer that prevents water loss through evaporation [11]. This is further supported by the presence of pentylene glycol,

which exhibits reduced volatility and enhances the cohesion of the gel layer [46]. Also, the presence of xanthan gum, another anionic polysaccharide, contributes to this effect, as F2 HyLN gel shows a slightly more pronounced occlusive effect than F1 HyLN gel. However, this difference is not statistically significant ($p > 0.05$, Figure 9).




Figure 9. In vitro occlusion factor (OF) of selected HyLN hydrogels compared to that of Vaseline (**left**) and water retention capacity (WRC) for the gel layer at 32 °C and 50% RH (**right**) as a function of time. One asterisk represents a statistically significant difference compared to Vaseline at the same time ($p < 0.05$). For formulation compositions, please refer to Table 1.

The susceptibility of gels to drying in air leads to collapse and loss of their network structure, resulting in reduced flexibility, elasticity, and overall functionality, causing a tightening sensation on the skin, negatively affecting patient compliance [46]. The water retention capacity of the selected HyLN hydrogels was measured gravimetrically using the same setup as for in vitro occlusion factor determination, and the results are presented in Figure 9. Analysed samples with higher xanthan gum content (i.e., F2 HyLN gel) showed greater water retention capacity than F1 HyLN gel, and this difference grew over time. Within the hydrogel, water molecules interact with the polymers (xanthan and hyaluronate), forming hydrates. While free water molecules in the gel evaporate spontaneously, water molecules bound to polymers must be released first. Both sodium hyaluronate and xanthan gum demonstrate a strong water-binding capacity [10,25]. For this bonded water to evaporate, the bonds with polymers need to be broken. In this sense, increasing the xanthan gum content in the formulation increased its water-binding capacity, which may have contributed to the slightly increased occlusivity observed for this formulation (Figure 9). Furthermore, polyols like pentylene glycol exhibit lower volatility, providing additional hydroxyl groups for interaction with free water in the hydrogel, converting it to bound water and reducing evaporation [46].

3. Conclusions

The results showed that a combination of sodium hyaluronate and xanthan gum in an appropriate ratio can provide a range of HyLN hydrogel formulations with tunable rheological and textural properties, suitable for skin application. These formulations presented adequate physical stability, maintaining their original rheological and textural properties during 6 months of storage. The use of βCD failed to stabilize inherently unstable antioxidants in HyLN, requiring the examination of other CD derivatives and stabilization approaches in future investigations. Despite that, the residual antioxidant activity after 6 months of storage remained notable. Although the wound-healing activity of the tested formulations was not demonstrated, the HyLN hydrogels showed a pronounced occlusive effect, attributed to the use of high-molecular-weight hyaluronan and its enhanced water-

retention capacity. Future studies should explore the combined use of both low- and high-molecular-weight hyaluronan to enhance the formulation's wound-healing potential.

4. Materials and Methods

4.1. Materials

Sodium hyaluronate (CAS No. 9067-32-7, MW of 1.5–2.0 × 10^6 Da) and xanthan gum (CAS No. 11138-66-2) were obtained from Fagron, Zagreb, Croatia, while pentylene glycol (CAS No. 5343-92-0) was purchased from Cosmaderm, Wuppertal, Germany. β-cyclodextrin (βCD, CAS No. 7585-39-9) was kindly donated by Roqette, Lestrem, France.

Dulbecco's Modified Eagle's Medium (DMEM; PAN-Biotech, Aidenbach, Germany), foetal bovine serum (FBS; PAN-Biotech, Aidenbach, Germany), antibiotics (100 U/mL penicillin and 100 µg/mL streptomycin; Sigma-Aldrich, St. Louis, MI, USA), Hank's Balanced Salt Solution (HBSS; PAN-Biotech, Aidenbach, Germany) were used in cell culture. 2,2′-azobis-(3-ethylbenzothiazoline-6-sulphonic acid (ABTS) was from Sigma (St. Louis, MO, USA). All other chemicals and solvents used in this study were of analytical grade.

4.2. Plant Material and Green Isolation of HyLN

Leaves of *Laurus nobilis* L. were collected in August 2023 in the Central Adriatic region of Croatia (Tisno; 43°47′59″ N, 15°38′32″ E; 10 m a.s.l.). Healthy, fully developed leaves without visible damage were harvested from approximately ten trees. The material was air-dried for ten days in a single layer, protected from direct sunlight, and subsequently stored in *labelled* paper bags in a dry, dark place until analysis. Voucher specimens were deposited at the Herbarium of the Botany Laboratory, Faculty of Science, University of Split, Croatia (Voucher No. CROLn-02-2023).

Prior to isolation, dried leaves were rehydrated for 1 h and subjected to microwave-assisted green isolation using an ETHOS X microwave system (Milestone™ Srl, Sorisole, Italy; 2.45 GHz, max. 1900 W). The process was conducted at atmospheric pressure for 30 min following a 10 min preheating phase at 800 W (98 °C). Hydrosols were stored in sealed dark glass bottles at −20 °C until analysis.

Hydrosol composition was determined by GC–FID and GC–MS (Varian 3900 GC and 2100 T MS, Varian Inc., Palo Alto, USA), following a previously described protocol [6]. The dominant constituents of HyLN were 1,8-cineole (80.73%), γ-terpinene (8.47%), α-pinene (2.68%), and terpinen-4-ol (2.32%).

4.3. Formulation of HyLN-Loaded Hydrogels

HyLN was loaded into the gel base consisting of sodium hyaluronate (0,5%, *w*/*w*) and xanthan gum at different concentration levels (i.e., 1.0% and 2.0%, *w*/*w*), with or without βCD, according to Table 1. The HyLN-loaded hydrogels were prepared using the FagronLab™ PRO unguator (Germany) by adding the required amount of HyLN into the FagronLab vessel, followed by the addition of pentylene glycol (5%, *w*/*w*) and other powdered compounds. Powders were dispersed by mixing for 26 min with alternating speed intervals (600 rpm vs. 1400 rpm) for 485 s, 30 s, 510 s, 30 s, 485 s, and 30 s, respectively.

Blank gels were prepared according to the same procedure but replacing the HyLN with purified water. Prepared gel samples were transferred into opaque, airtight containers and stored at 4 °C until further analysis.

4.4. pH Measurements

The pH of both the blank and HyLN-loaded hydrogels was recorded using a Mettler S47 SevenMulti™ dual pH/conductivity meter equipped with a pH InLab® Viscous

electrode (Greifensee, Switzerland). The measurements were performed in triplicate on undiluted gel samples.

4.5. Rheological Characterisation

Rheological measurements were performed using Modular Compact Rheometer MCR102 (Anton Paar GmbH, Austria) equipped with a cone (1°)-plate (diameter 50 mm, CP50-1) or parallel-plate (diameter 50 mm, PP50) measuring system and integrated air-cooled Peltier temperature control system. All data were processed using RheoCompassTM software Version 1.23.403-Release (Anton Paar GmbH, Graz, Austria).

4.5.1. Viscosity Curve

The viscosity curve was determined using a rotational test with the CP50-1 measuring system, with a gap set to 0.102 mm. All samples were equilibrated at 32 °C for 3 min. The viscosity profile was measured in triplicate for each sample over a shear rate range of 0.1–100 s^{-1}.

4.5.2. 3-Interval Thixotropy Test

The 3-interval thixotropy test (3-ITT) was used to assess the thixotropic behavior and structural recovery of the hydrogels. Tests were performed at 32 °C using an Anton Paar MCR102 rheometer with a CP50-1 measuring system and a 0.102 mm gap, in controlled shear rate mode. Initially, viscosity was measured at a shear rate of 1 s^{-1} for 10 s to determine the baseline structure. Then, a shear rate of 1000 s^{-1} was applied for 5 s to cause structural breakdown. Finally, viscosity was recorded at 1 s^{-1} for 80 s to evaluate recovery. All tests were conducted in triplicate to ensure reproducibility.

4.5.3. Amplitude Sweep Test

An amplitude sweep test was performed in oscillatory mode using a PP50 measuring system with a gap set to 0.500 mm. The samples were equilibrated at 22 °C for 3 min before measurement. Storage (G′) and loss (G″) moduli were measured at a constant angular frequency of 1 rad s^{-1}, over an amplitude range from 0.1% to 100%. The measurement was performed in triplicate to ensure reproducibility.

4.5.4. Frequency Sweep Test

For the frequency sweep test, a PP50 measuring system was used with the gap set at 0.500 mm. The samples were kept on the lower measuring plate at 22 °C for 10 min before measurement. The dependence of storage (G′) and loss (G″) modulus on angular frequency in the range from 0.1 rad s^{-1} to 100 rad s^{-1} was measured at an amplitude 1% (from the linear viscoelastic range).

4.6. Texture Analysis

A texture analyzer TA.XT Plus (Stable Micro Systems Ltd., Godalming, UK), equipped with a 5 kg load cell, was used to study the texture properties and spreadability of the hydrogels prepared following the previously described procedure [21]. The measurements were performed at ambient temperature.

Texture analysis was performed using a 40 mm diameter back extrusion rig. About 75 g of hydrogel was placed into a standard back extrusion container with a 50 mm diameter, ensuring no air bubbles were introduced. The rig was then immersed in the gel to a depth of 20 mm at a speed of 2 mm s^{-1} and withdrawn at a return velocity of 20 mm s^{-1}. Three separate measurements were taken for each formulation. The texture parameters of the gels were derived from the force-time curve. The maximum compression force (in g) indicated the gel's firmness. Consistency was defined as the work required to deform the gel during

the probe's downward movement and was calculated from the area under the force-time curve. The surface of the negative part of the curve, recorded during the probe retraction, represented the hydrogel's cohesiveness [35].

The spreadability of the hydrogels was measured using the TTC spreadability fixture. During the test, the conical probe was lowered over a distance of 23 mm at a speed of 5 mm s^{-1} to the surface of the gel in the support, penetrating the sample and forcing it to flow outward at 45° between the surfaces of the two cones (male and female). The force (in g) required for the penetration of the male-type conical probe into the sample from the female-type conical support was measured as a function of time. The work of shear was determined from the area under the force-time curve in the region with positive force values [47] and was used as an indicator of product spreadability. Three separate replicates were measured for each formulation.

4.7. Antioxidative Potential

The Trolox equivalent antioxidant capacity (TEAC) of the infusions was determined using the ABTS radical cation decolorization method as described by Re et al. [48]. ABTS solution was prepared the day before the experiment by mixing ABTS radical and potassium persulfate. It was diluted immediately before the experiment to obtain an absorbance of approximately 0.70 at 750 nm. On the day of analysis, the hydrogels were centrifuged at 4000 rpm for 15 min using Technica Centric 322 A (Domel, Slovenia). Aliquots were then pipetted using ViscoTip (Eppendorf, Hamburg, Germany) and diluted 4× in distilled water. 20 µL of the diluted hydrogel sample was mixed with 200 µL of the ABTS solution in 96 well plate. The mixture was thoroughly resuspended using the pipette, and absorbance was measured at 750 nm using SpectraMax i3x (Molecular devices, San Jose, USA). Blank sample contained 20 µL of distilled water instead of hydrogels. All measurements were carried out in quadruplicate. The results were quantified using Trolox standard curve (10–100 mg/L, R^2 = 0.998). The results were expressed as Trolox equivalents (mg/L).

4.8. Functional Characterization of HyLN-Based Hydrogels

4.8.1. Wound Healing Assay

The in vitro scratch assay was performed using the Human epidermal keratinocyte cell line (HaCaT, CLS Cell Lines Service, Cat. No. 300493, CVCL_0038). HaCaT cells were cultured in DMEM supplemented with 10% FBS and a 1% antibiotic–antimycotic solution containing penicillin, streptomycin, and amphotericin B. Cells were seeded at a density of 1×10^5 cells per well in standard six-well plates and incubated at 37 °C in a humidified atmosphere with 5% CO_2 until reaching 80–90% confluence.

Before the experiment, cells were starved for 24 h in serum-free DMEM to inhibit proliferation. A straight scratch was created on the monolayer of HaCaT cells using a sterile 200 µL pipette tip, leaving a cell-free area. Following the scratch, the culture medium was removed, and the cell monolayer was gently washed with HBSS to eliminate detached cells and debris. 500 µL of HyLN gel formulation in serum-free medium was added to each well, and the cells were incubated for 72 h [6,49].

The scratched area was photographed immediately after wounding (0 h) and subsequently at 24, 48, and 72 h using an inverted microscope (Olympus IX73, Olympus, Tokyo, Japan) equipped with a digital camera with 100× magnification. The total wound area was determined using ImageJ software (version 1.54d, NIH, Bethesda, MD, USA).

Negative control wells received serum-free growth medium without LnHY gel formulation. Wound closure was quantified and expressed as a percentage of the initial wound area (at 0 h) calculated using the following Equation (1):

$$\text{Wound healing rate} = (A_0 - A_t)/A_0 \times 100 \quad (1)$$

where A_0 is the scratch area at time 0 and A_t is the corresponding scratch area at 24, 48, or 72 h. At least three independent experiments were performed for each sample, using three wells per treatment.

4.8.2. In Vitro Occlusion Test

An in vitro occlusion test was conducted following a previously reported procedure with slight modifications [21,50], using PTFE immersion cells with adjustable volume and an exposure area of 4 cm^2 (Agilent Technologies, Santa Clara, CA, USA). The reservoir of the immersion cells was filled with 1 mL of purified water and covered with a regenerated cellulose filter (pore size 0.2 µm, Sartorius, Göttingen, Germany). The cell was then assembled, and 1 g of the hydrogel sample was applied onto the membrane and evenly spread with a spatula, creating a thin surface layer. The cells were incubated in an ICH 110 eco Climate Chamber (Memmert GmbH, Schwabach, Germany) set to 32 °C and 50% RH to mimic skin surface conditions. At specific time points, the residual water in the reservoir was measured gravimetrically using a Mettler Toledo ML204T analytical balance (Gießen, Germany) to evaluate water loss due to evaporation through the membrane/gel layer. Each experiment was performed in triplicate. Cells without the gel sample served as a negative control, while Vaseline was used as a positive control. The occlusion factor (OF) for each time point was calculated according to the equation:

$$\text{OF (\%)} = 100 \times (A - B)/A \quad (2)$$

where A and B are the observed water loss values for the cells without and with the sample applied, respectively. An occlusion factor of zero indicates no occlusive effect compared to the reference, and 100 represents the maximum OF [50].

The same experimental setup enabled monitoring of the water retention capacity (WRC) of the hydrogel layer [46]. For this, the entire immersion cell with the applied gel layer was weighed at regular time intervals, and the change in mass of the gel layer on the membrane was calculated by subtracting the amount of evaporated water from the reservoir, as determined above. The water retention capacity was calculated as:

$$\text{WRC (\%)} = 100 \times (W_0 - W_t)/W_0 \quad (3)$$

where W_t represents the weight of the gel at the given time, while W_0 is the amount of water in the gel layer at the beginning of the test.

4.9. Statistical Evaluation

All results are expressed as mean ± standard deviation (SD) of three independent measurements. The statistical calculations were performed using GraphPad Prism 8 for Windows (GraphPad Software, USA). A one-way ANOVA was used to compare the means of different groups with a single independent variable (i.e., wound healing rate), followed by Tukey's multiple-comparison test. To compare means across groups with two independent variables (i.e., pH of the gel, textural parameters, physical stability parameters, TEAC, and in vitro occlusion data), a two-way ANOVA was employed, followed by Tukey's multiple comparisons test. A p-value ≤ 0.05 was considered statistically significant.

Author Contributions: Conceptualization, M.J., L.J. and R.J.G.; methodology, M.J., L.J. and E.G., formal analysis, L.J. and M.J.; investigation, R.J., L.J., E.G. and M.J.; resources, M.J. and R.J.G.; data curation, L.J. and M.J.; writing—original draft preparation, M.J.; writing—review and editing, R.J., R.J., E.G. and R.J.G.; visualization, M.J.; supervision, M.J. and R.J.G.; project administration, R.J.G. and M.J.; funding acquisition, M.J. and R.J.G. All authors have read and agreed to the published version of the manuscript.

Funding: This research was funded by the University of Rijeka (UNIRI-IZ-25-53), basic financing for the scientific and artistic activities of the University of Zagreb in the academic year 2024/2025, and by the FarmInova project (KK.01.1.1.02.0021) funded by the European Regional Development Fund.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: The original contributions presented in the study are included in the article. Further inquiries can be directed to the corresponding author.

Acknowledgments: During the preparation of this manuscript, the authors used Grammarly Pro (Grammarly Inc., San Francisco, CA, USA) solely for English language editing—specifically, for corrections of grammar and spelling. No content generation or structural revisions were performed using this tool. All intellectual content, analyses, and interpretations remained entirely the authors' responsibility.

Conflicts of Interest: The authors declare no conflicts of interest.

Abbreviations

The following abbreviations are used in this manuscript:

HyLN	*Laurus nobilis* hydrosols
βCD	β-cyclodextrin
3-ITT	Three-interval thixotropy test
G′	Viscoelastic storage modulus
G″	Viscoelastic loss modulus
tan δ	Loss factor
TEAC	Trolox equivalent antioxidant capacity
ABTS	2,2′-azobis-(3-ethylbenzothiazoline-6-sulphonic acid
DPPH	2,2-diphenyl-1-picrylhydrazyl
FRAP	Ferric Reducing Antioxidant Power
TGF-β1	Transforming Growth Factor Beta 1
TGF-β2	Transforming Growth Factor Beta 2
TGF-β3	Transforming Growth Factor Beta 3
OF	In vitro occlusion factor
WRC	Water retention capacity
DMEM	Dulbecco's Modified Eagle's Medium
FSB	Foetal bovine serum
HBSS	Hank's Balanced Salt Solution
HaCaT	Human epidermal keratinocyte cell line
ANOVA	Analysis of Variance

References

1. Dinsmore, S.; Grams, M.-K.; Couris, R.R. Bay Leaf: Leaf of the European Laurel. *Nutr. Today* **2018**, *53*, 47–55. [CrossRef]
2. Paparella, A.; Nawade, B.; Shaltiel-Harpaz, L.; Ibdah, M. A Review of the Botany, Volatile Composition, Biochemical and Molecular Aspects, and Traditional Uses of Laurus Nobilis. *Plants* **2022**, *11*, 1209. [CrossRef] [PubMed]
3. Jakubczyk, K.; Tuchowska, A.; Janda-Milczarek, K. Plant Hydrolates—Antioxidant Properties, Chemical Composition and Potential Applications. *Biomed. Pharmacother.* **2021**, *142*, 112033. [CrossRef] [PubMed]
4. Almeida, H.H.S.; Fernandes, I.P.; Amaral, J.S.; Rodrigues, A.E.; Barreiro, M.-F. Unlocking the Potential of Hydrosols: Transforming Essential Oil Byproducts into Valuable Resources. *Molecules* **2024**, *29*, 4660. [CrossRef]
5. Šilha, D.; Švarcová, K.; Bajer, T.; Královec, K.; Tesařová, E.; Moučková, K.; Pejchalová, M.; Bajerová, P. Chemical Composition of Natural Hydrolates and Their Antimicrobial Activity on Arcobacter-Like Cells in Comparison with Other Microorganisms. *Molecules* **2020**, *25*, 5654. [CrossRef]
6. Juretić, L.; Dunkić, V.; Gobin, I.; Inić, S.; Kremer, D.; Nazlić, M.; Pollak, L.; Mežnarić, S.; Barbarić, A.; Jurišić Grubešić, R. Chemical Composition, Quality, and Bioactivity of Laurus Nobilis L. Hydrosols from the Adriatic Regions of Croatia: Implications for Dermatological Applications. *Antioxidants* **2025**, *14*, 688. [CrossRef]

7. Olivero-Verbel, J.; Quintero-Rincón, P.; Caballero-Gallardo, K. Aromatic Plants as Cosmeceuticals: Benefits and Applications for Skin Health. *Planta* **2024**, *260*, 132. [CrossRef]
8. Machado, M.; Silva, S.; Costa, E.M. Byproducts as a Sustainable Source of Cosmetic Ingredients. *Appl. Sci.* **2024**, *14*, 10241. [CrossRef]
9. Harrer, D.; Sanchez Armengol, E.; Friedl, J.D.; Jalil, A.; Jelkmann, M.; Leichner, C.; Laffleur, F. Is Hyaluronic Acid the Perfect Excipient for the Pharmaceutical Need? *Int. J. Pharm.* **2021**, *601*, 120589. [CrossRef]
10. Bukhari, S.N.A.; Roswandi, N.L.; Waqas, M.; Habib, H.; Hussain, F.; Khan, S.; Sohail, M.; Ramli, N.A.; Thu, H.E.; Hussain, Z. Hyaluronic Acid, a Promising Skin Rejuvenating Biomedicine: A Review of Recent Updates and Pre-Clinical and Clinical Investigations on Cosmetic and Nutricosmetic Effects. *Int. J. Biol. Macromol.* **2018**, *120*, 1682–1695. [CrossRef]
11. Badri Narayanan, K.; Bhaskar, R.; Chylínska, N.; Maciejczyk, M. Hyaluronic Acid and Skin: Its Role in Aging and Wound-Healing Processes. *Gels* **2025**, *11*, 281. [CrossRef] [PubMed]
12. Sallustio, V.; Marto, J.; Escribano-Ferrer, E.; Gonçalves, L.M.; Rossi, M.; Cappadone, C.; Mandrone, M.; Chiocchio, I.; Rossello, S.; Ribeiro, H.; et al. Development and Characterization of Multifunctional Phytonanoemulgels Based on Licorice Extract and Biocompatible Polymers. *Int. J. Biol. Macromol.* **2025**, *319*, 145241. [CrossRef] [PubMed]
13. Bartos, C.; Ambrus, R.; Sipos, P.; Budai-Szűcs, M.; Csányi, E.; Gáspár, R.; Márki, Á.; Seres, A.B.; Sztojkov-Ivanov, A.; Horváth, T.; et al. Study of Sodium Hyaluronate-Based Intranasal Formulations Containing Micro- or Nanosized Meloxicam Particles. *Int. J. Pharm.* **2015**, *491*, 198–207. [CrossRef] [PubMed]
14. Kulkarni, V.S.; Shaw, C. Use of Polymers and Thickeners in Semisolid and Liquid Formulations. In *Essential Chemistry for Formulators of Semisolid and Liquid Dosages*; Elsevier: Amsterdam, The Netherlands, 2016; pp. 43–69.
15. Manaprasersak, A.; Karpkird, T. Selectivity Encapsulation of *Zingiber cassumunar* Roxb. Oil by Beta-Cyclodextrin Derivatives. *Mater. Today Proc.* **2020**, *23*, 659–665. [CrossRef]
16. Li, Z.; Ding, Y.; Huang, H.; Wang, K.; Wu, J.; Zhu, L.; Liao, Z.; Ming, L. Study of β-Cyclodextrin Differential Encapsulation of Essential Oil Components by Using Mixture Design and NIR: Encapsulation of α-Pinene, Myrcene, and 3-Carene as an Example. *J. Chin. Pharm. Sci.* **2021**, *30*, 524. [CrossRef]
17. Pina, L.T.S.; Rabelo, T.K.; Borges, L.P.; Gonçalves, V.S.S.; Silva, A.S.; Oliveira, M.A.; Quintans, J.S.S.; Quintans Júnior, L.J.; Scotti, L.; Scotti, M.T.; et al. Antihyperalgesic Effect of γ-Terpinene Complexed in β-Cyclodextrin on Neuropathic Pain Model Induced by Tumor Cells. *Int. J. Pharm.* **2024**, *662*, 124538. [CrossRef]
18. Tan, X.; Xu, R.; Li, A.P.; Li, D.; Wang, Y.; Zhao, Q.; Long, L.P.; Fan, Y.Z.; Zhao, C.X.; Liu, Y.; et al. Antioxidant and Anti-Alzheimer's Disease Activities of 1,8-Cineole and Its Cyclodextrin Inclusion Complex. *Biomed. Pharmacother.* **2024**, *175*, 116784. [CrossRef]
19. Becker, L.C.; Bergfeld, W.F.; Belsito, D.V.; Klaassen, C.D.; Marks, J.G.; Shank, R.C.; Slaga, T.J.; Snyder, P.W.; Andersen, F.A. Final Report of the Safety Assessment of Hyaluronic Acid, Potassium Hyaluronate, and Sodium Hyaluronate. *Int. J. Toxicol.* **2009**, *28*, 5–67. [CrossRef]
20. Chen, T.; Chang, H. Deciphering Trends in Replacing Preservatives in Cosmetics Intended for Infants and Sensitive Population. *Sci. Rep.* **2024**, *14*, 19053. [CrossRef]
21. Joukhadar, R.; Nižić Nodilo, L.; Lovrić, J.; Hafner, A.; Pepić, I.; Jug, M. Functional Nanostructured Lipid Carrier-Enriched Hydrogels Tailored to Repair Damaged Epidermal Barrier. *Gels* **2024**, *10*, 466. [CrossRef]
22. Aiassa, V.; Garnero, C.; Zoppi, A.; Longhi, M.R. Cyclodextrins and Their Derivatives as Drug Stability Modifiers. *Pharmaceuticals* **2023**, *16*, 1074. [CrossRef]
23. Anuța, V.; Nica, M.A.; Prisada, R.M.; Popa, L.; Velescu, B.Ș.; Marinas, I.C.; Gaboreanu, D.M.; Ghica, M.V.; Cocoș, F.I.; Nicolae, C.A.; et al. Novel Buccal Xanthan Gum–Hyaluronic Acid Eutectogels with Dual Anti-Inflammatory and Antimicrobial Properties. *Gels* **2025**, *11*, 208. [CrossRef] [PubMed]
24. Dejeu, I.L.; Vicaș, L.G.; Vlaia, L.L.; Jurca, T.; Mureșan, M.E.; Pallag, A.; Coneac, G.H.; Olariu, I.V.; Muț, A.M.; Bodea, A.S.; et al. Study for Evaluation of Hydrogels after the Incorporation of Liposomes Embedded with Caffeic Acid. *Pharmaceuticals* **2022**, *15*, 175. [CrossRef] [PubMed]
25. Carmo, F.J.R.; Salote, E.P.Z.; Valente, A.J.M.; Ribeiro, A.C.F.; Nicolau, P.M.G.; Fangaia, S.I.G. Diffusion of Sodium Hyaluronate in Artificial Saliva to Optimize Its Topical Application. *Molecules* **2025**, *30*, 2140. [CrossRef] [PubMed]
26. Kupská, I.; Lapčík, L.; Lapčíková, B.; Žáková, K.; Juříková, J. The Viscometric Behaviour of Sodium Hyaluronate in Aqueous and KCl Solutions. *Colloids Surf. A Physicochem. Eng. Asp.* **2014**, *454*, 32–37. [CrossRef]
27. Brunchi, C.E.; Bercea, M.; Morariu, S.; Dascalu, M. Some Properties of Xanthan Gum in Aqueous Solutions: Effect of Temperature and PH. *J. Polym. Res.* **2016**, *23*, 123. [CrossRef]
28. Falusi, F.; Berkó, S.; Kovács, A.; Budai-Szűcs, M. Application of Xanthan Gum and Hyaluronic Acid as Dermal Foam Stabilizers. *Gels* **2022**, *8*, 413. [CrossRef]
29. Ali, A.; Skedung, L.; Burleigh, S.; Lavant, E.; Ringstad, L.; Anderson, C.D.; Wahlgren, M.; Engblom, J. Relationship between Sensorial and Physical Characteristics of Topical Creams: A Comparative Study on Effects of Excipients. *Int. J. Pharm.* **2022**, *613*, 121370. [CrossRef]

30. Fragal, E.H.; Poirier, A.; Bleses, D.; Faria Guimarães Silva, Y.; Baccile, N.; Rharbi, Y. Microbial Biosurfactant Hydrogels with Tunable Rheology for Precision 3D Printing of Soft Scaffolds. *Soft Matter* **2025**, *21*, 4476–4487. [CrossRef]
31. Vergilio, M.M.; da Fonsêca, J.H.L.; d'Ávila, M.A.; Leonardi, G.R. Evaluation of the Influence of Niacinamide and Saccharide Isomerate on the Rheological Behavior of a Hydrogel for Topical Use. *Biotribology* **2023**, *35–36*, 100243. [CrossRef]
32. Stojkov, G.; Niyazov, Z.; Picchioni, F.; Bose, R.K. Relationship between Structure and Rheology of Hydrogels for Various Applications. *Gels* **2021**, *7*, 255. [CrossRef]
33. Hnin, H.M.; Tun, T.; Loftsson, T.; Jansook, P. A Recent Update of Water-Soluble Polymers in Cyclodextrin-Based Formulations for Mucosal Drug Delivery. *Carbohydr. Polym.* **2025**, *358*, 123539. [CrossRef] [PubMed]
34. Budai, L.; Budai, M.; Fülöpné Pápay, Z.E.; Vilimi, Z.; Antal, I. Rheological Considerations of Pharmaceutical Formulations: Focus on Viscoelasticity. *Gels* **2023**, *9*, 469. [CrossRef] [PubMed]
35. Franzol, A.; Banin, T.M.; Brazil, T.R.; Rezende, M.C. Textural Analyses and Artificial Neural Network as Optimization Tools to Predict the Sensory Perception of Cosmetic Emulsions. *J. Sens. Stud.* **2022**, *37*, e12776. [CrossRef]
36. AL-Smadi, K.; Ali, M.; Zhu, J.; Abdoh, A.; Phan, K.; Mohammed, Y. Advances in Characterization of Transdermal and Topical Products Using Texture Analyzer Systems. *AAPS PharmSciTech* **2025**, *26*, 157. [CrossRef]
37. Rico, F.; Mazabel, A.; Egurrola, G.; Pulido, J.; Barrios, N.; Marquez, R.; García, J. Meta-Analysis and Analytical Methods in Cosmetics Formulation: A Review. *Cosmetics* **2024**, *11*, 1. [CrossRef]
38. Schaich, K.M.; Tian, X.; Xie, J. Hurdles and Pitfalls in Measuring Antioxidant Efficacy: A Critical Evaluation of ABTS, DPPH, and ORAC Assays. *J. Funct. Foods* **2015**, *14*, 111–125. [CrossRef]
39. Widelska, G.; Wójtowicz, A.; Kasprzak, K.; Dib, A.; Oniszczuk, T.; Olech, M.; Wojtunik-Kulesza, K.; Nowak, R.; Sujak, A.; Dobrzański, B.; et al. Impact of Xanthan Gum Addition on Phenolic Acids Composition and Selected Properties of New Gluten-Free Maize-Field Bean Pasta. *Open Chem.* **2019**, *17*, 587–598. [CrossRef]
40. Amaral, C.N.R.; Oliveira, P.F.; Pedroni, L.G.; Mansur, C.R.E. Viscoelastic Behavior of Hydrogel-based Xanthan Gum/Aluminum Lactate with Potential Applicability for Conformance Control. *J. Appl. Polym. Sci.* **2021**, *138*, 50640. [CrossRef]
41. Herbig, M.E.; Evers, D.-H.; Gorissen, S.; Köllmer, M. Rational Design of Topical Semi-Solid Dosage Forms—How Far Are We? *Pharmaceutics* **2023**, *15*, 1822. [CrossRef]
42. Baldea, I.; Grosu, I.G.; Ghafury, S.; Golat, C.; Doubali, D.; Vestemean, A.M.; Cedorge, A.N.; Florian, I.; Yiannoulatos, M.; Wajahat, M.M.; et al. Biological Models for Evaluating Hydrogel-Based Formulations in Wound Healing. *Gels* **2025**, *11*, 705. [CrossRef]
43. Liang, C.C.; Park, A.Y.; Guan, J.L. In Vitro Scratch Assay: A Convenient and Inexpensive Method for Analysis of Cell Migration in Vitro. *Nat. Protoc.* **2007**, *2*, 329–333. [CrossRef] [PubMed]
44. Rajkumar, J.; Chandan, N.; Lio, P.; Shi, V. The Skin Barrier and Moisturization: Function, Disruption, and Mechanisms of Repair. *Skin Pharmacol. Physiol.* **2023**, *36*, 174–185. [CrossRef] [PubMed]
45. Kamrani, P.; Hedrick, J.; Marks, J.G.; Zaenglein, A.L. Petroleum Jelly: A Comprehensive Review of Its History, Uses, and Safety. *J. Am. Acad. Dermatol.* **2024**, *90*, 807–813. [CrossRef] [PubMed]
46. Huang, Y.; Zhu, T.; Yuan, H.; Tan, L.; Zhu, Z.; Yao, P.; Zhu, C.; Xu, J. An in Situ Encapsulation Strategy for Enhancing the Stability of Hydrogels in Both Air and Water through Surface-Confined Copolymerization. *Chem. Eng. J.* **2024**, *485*, 149847. [CrossRef]
47. Tomić, I.; Miočić, S.; Pepić, I.; Šimić, D.; Filipović-Grčić, J. Efficacy and Safety of Azelaic Acid Nanocrystal-Loaded in Situ Hydrogel in the Treatment of Acne Vulgaris. *Pharmaceutics* **2021**, *13*, 567. [CrossRef]
48. Re, R.; Pellegrini, N.; Proteggente, A.; Pannala, A.; Yang, M.; Rice-Evans, C. Antioxidant Activity Applying an Improved ABTS Radical Cation Decolorization Assay. *Free Radic. Biol. Med.* **1999**, *26*, 1231–1237. [CrossRef]
49. Blažević, F.; Milekić, T.; Romić, M.D.; Juretić, M.; Pepić, I.; Filipović-Grčić, J.; Lovrić, J.; Hafner, A. Nanoparticle-Mediated Interplay of Chitosan and Melatonin for Improved Wound Epithelialisation. *Carbohydr. Polym.* **2016**, *146*, 445–454. [CrossRef]
50. Na, Y.-G.; Huh, H.W.; Kim, M.-K.; Byeon, J.-J.; Han, M.-G.; Lee, H.-K.; Cho, C.-W. Development and Evaluation of a Film-Forming System Hybridized with Econazole-Loaded Nanostructured Lipid Carriers for Enhanced Antifungal Activity against Dermatophytes. *Acta Biomater.* **2020**, *101*, 507–518. [CrossRef]

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.