

---


# **Enhancing Conductivity and Self-Healing Properties of PVA/GEL/OSA Composite Hydrogels by GO/SWNTs for Electronic Skin**

Xiaohu Chen <sup>1, 2</sup>, Haonan Zhang <sup>1,2</sup>, Jiashu Cui <sup>1,2</sup>, Yanen Wang <sup>1,2,\*</sup>, Mingyang Li <sup>1,2</sup>, Juan Zhang <sup>1,2</sup>, Changgeng Wang <sup>1,2</sup>, Zhisheng Liu <sup>1,2</sup> and Qinghua Wei <sup>1,2,\*</sup>

<sup>1</sup> Department of Industry and Engineering, School of Mechanical Engineering, Northwestern Polytechnical University, Xi'an 710072, China

<sup>2</sup> Bio-Additive Manufacturing University-Enterprise Joint Research Center of Shaanxi Province, Northwestern Polytechnical University, Xi'an, 710072, China

\* Correspondence: wangyanen@nwpu.edu.cn (Y.W.); weiqinghua@nwpu.edu.cn (Q.W.);  
Tel./Fax: +86-029-88493232



**Figure S1.** The swelling ratios of hydrogels.

**Table S1** The conductivity of hydrogels at different degrees of bending.

Sample name	Parameter	The distance between electric clamps (5, 3, and 1 cm from left to right)		
PGO	Resistance (k $\Omega$ )	52.33	53.12	53.40
	Conductivity (mS/m)	19.11	18.82	18.73
PGO-GS3	Resistance (k $\Omega$ )	34.32	36.28	37.59
	Conductivity (mS/m)	29.13	27.56	26.60