

Supplementary Materials: Investigation of the Effects of Multi-Wall and Single-Wall Carbon Nanotubes Concentration on the Properties of ABS Nanocomposites.

Brenda Janett Alonso Gutierrez, Sithiprumnea Dul, Alessandro Pegoretti, Jaime Alvarez-Quintana and Luca Fambri




Figure S1. Representative Vicat softening curves of ABS and nanocomposites at different content of SWCNT and MWCNT between 5 and 10 wt%. (CM - compression moulded samples).




Figure S2. Representative DSC thermograms of ABS/MWCNT and ABS/SWCNT nanocomposite filaments at different filler content between 5 and 10 wt%. First (a) and second (b) heating scan.

Table S1. Melt flow index (280°C, 10Kg) of neat ABS, ABS/MWCNT and ABS/SWCNT nanocomposites at 5, 7.5 and 10 wt% of filler content.

Samples	Melt flow index (g/10 min)
ABS	232 ± 19 *
M5-Filament	13.2 ± 4.0
M7.5-Filament	0.68 ± 0.10
M10-Filament	0.22 ± 0.07
S5-Filament	19.9 ± 4.3
S7.5-Filament	11.1 ± 3.5
S10-Filament	2.12 ± 0.54

*data from Reference [16] Dul, S.; Pegoretti, A.; Fambri, L. Effects of the nanofillers on physical properties of acrylonitrile-butadiene-styrene nanocomposites: Comparison of graphene nanoplatelets and multiwall carbon nanotubes. *Nanomaterials* 2018, 8, 674-693