

Review

Rutting and Aging Properties of Recycled Polymer-Modified Pavement Materials

Nuha S. Mashaan *  and Chathurika Dassanayake

School of Engineering, Edith Cowan University, Joondalup, WA 6027, Australia; kdasana@our.ecu.edu.au

* Correspondence: n.mashaan@ecu.edu.au

Abstract: Recycled polymer-modified binders have emerged as a sustainable solution for improving the performance and durability of pavement materials. This review examines the rutting and aging properties of pavements modified with recycled polymers, highlighting their potential for sustainable infrastructure development. The incorporation of recycled polymers into bitumen enhances resistance to rutting and aging by improving the binder's mechanical stability and oxidative durability. Key laboratory techniques, including the rolling thin-film oven test (RTFOT) and the pressure aging vessel (PAV), are evaluated for their effectiveness in assessing the thermal and oxidative aging behavior of modified binders. The review demonstrates that recycled polymers improve binder elasticity, delay oxidative degradation, and mitigate deformation under repeated loading, thus extending pavement lifespan and reducing maintenance costs. However, challenges such as optimizing polymer dosage, ensuring homogeneity, and predicting long-term performance require further investigation. This paper underscores the environmental and economic benefits of utilizing recycled polymers in pavement construction and advocates for improved testing protocols and advanced characterization techniques to enhance the reliability and sustainability of polymer-modified pavements.

Keywords: recycled polymers; bitumen modification; rutting resistance; aging resistance; sustainable pavements; CRMB; waste plastics



Academic Editors: José Neves and Ana Cristina Freire

Received: 14 February 2025

Revised: 25 March 2025

Accepted: 26 March 2025

Published: 1 April 2025

Citation: Mashaan, N.S.; Dassanayake, C. Rutting and Aging Properties of Recycled Polymer-Modified Pavement Materials.

Recycling **2025**, *10*, 60. <https://doi.org/10.3390/recycling10020060>

Copyright: © 2025 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

1. Introduction

Polymers play a vital role in enhancing the properties of asphalt, improving its performance, and extending its lifespan. These modifications help asphalt resist common pavement issues such as rutting, cracking, and aging, thereby improving its durability and overall functionality. One of the most widely studied polymer additives for asphalt is crumb rubber, typically derived from recycled tires. Rubberized asphalt offers enhanced flexibility, reduces the risk of cracking, and improves rutting resistance. Research has shown that the incorporation of rubber particles into bitumen significantly improves both the rheological and physical properties of the asphalt binder, especially under high-temperature conditions (Ali et al., 2013; Anusha & Jagadeesh, 2021) [1,2]. Rubber-modified asphalts also tend to exhibit improved aging properties, leading to a longer service life (Buchagul, 2019) [3]. Another polymer commonly used in asphalt modification is polyethylene, particularly recycled polyethylene, which helps to improve the binder's stiffness, viscoelastic properties, and aging resistance. Polyethylene-modified asphalts have shown promising results in enhancing the pavement's durability by improving its performance under both high and low temperatures (Alghrafi et al., 2021) [4]. More recently, polymers like polycarbonate (PC)

and polytetrafluoroethylene (PTFE) have been explored as asphalt modifiers. These materials offer distinct advantages, such as improved resistance to high-temperature deformation and enhanced overall durability. Research suggests that both PC- and PTFE-modified bitumen demonstrate superior rheological properties and microstructural characteristics, making them ideal candidates for use in harsh climates (Ansar et al., 2022) [5]. Although not a polymer in the traditional sense, sulfur is often used in conjunction with polymers like polyethylene to extend the performance of asphalt binders. Sulfur acts as a crosslinking agent, improving the strength and elasticity of the asphalt. The combination of sulfur and recycled polymers leads to a more environmentally friendly alternative to traditional bitumen, without compromising performance (Alghrafi et al., 2021) [4]. In conclusion, a variety of polymers, including rubber, waste plastic, polyethylene, polycarbonate, and PTFE, are increasingly being used to modify asphalt. These materials not only improve the mechanical and rheological properties of bitumen but also enhance its resistance to aging, cracking, and rutting, leading to longer lasting and more sustainable pavements.

2. Background

2.1. Chemical Composition of Bitumen

Bitumen binders are among the most common materials used in construction and infrastructure. As versatile materials, they find application in an extensive range of projects, including road construction, waterproofing, adhesives, and roofing. According to the research published by Holy and Remisova (2019) [6], the chemical compound of bitumen binders consists of essential components like asphaltenes, resins, aromatics, and saturates. Asphaltenes are the most complex and high-molecular-weight hydrocarbons that improve bitumen's viscosity and adhesive properties. Resins are sticky solid maltenes that play a vital role in binding aggregates in asphalt concrete mixtures and have a strong attraction to other substances. Aromatics act as the oily medium, and saturates have low molecular weights and are the least complex of these four fractions in bitumen. They coat aggregates and compact bitumen used in road construction. The most important consideration for bitumen is assessing its ease of mixing and use at specific temperatures.

In addition to hydrocarbons, small amounts of sulfur, nitrogen, and oxygen compounds are inherent components of bitumen, the properties of which may vary by the nature of influence. Previous analysis shows that most bitumen contains 82–88% carbon, 8–11% hydrogen, 0–6% sulfur, and 0–1.5% nitrogen. Sulfur compounds contribute to the adhesion and elasticity of the hot mix, while the nitrogen and oxygen ones influence the oxidative stability of the bitumen and the level of its ecological trace. It is important to note that bitumen mixtures contain different types of formulations with specific additives that provide certain unique properties, such as elasticity or stiffness and resistance to other physical characteristics, including aging (Holy & Remisova, 2019) [6].

2.2. Physical Properties of Bitumen Binders

Bitumen's rheological behavior is controlled by elasticity, stiffness, flow characteristics, and strength, which are also identified as its main physical properties (Holy & Remisova, 2019) [6]. Bituminous binders must possess specific properties necessary for optimal performance in construction materials. One of these properties is hardness, which is measured using the penetration test. Another vital property is viscosity, which affects the bitumen's flow and coating during mixing and compacting during road construction. Different types of viscosity tests are performed to measure the viscosity; bitumen with low viscosity is suitable for hot weather, and bitumen with high viscosity is suited for cold weather conditions as the hardening occurs slowly. Secondly, the property fulfilled by bitumen is adhesion, which assumes the cementing of the binder to other substrates, such as aggregates and

the pavement surface, defending the tensile strength of the asphalt pavement material against complex loading and environmental conditions. The temperature at which bitumen becomes liquid is identified as the softening point, and for hot weather conditions, it is crucial to use bitumen with a high softening point (Zahedi, 2024) [7].

2.3. Regulatory Standards and Specifications

Bitumen binders are employed fundamentally in all construction works, with regulated standards and specifications such as quality, safety, and sustainability guidelines. Australian Standards are maintained and developed by the Australian Asphalt Pavement Association, which originated in Australia, to give guidance/specifications for asphalt materials and their construction in the nation. For example, the organization published the “Guide to Pavement Technology” series, which contains several details of the specifications of bitumen binders, including the type, viscosity grade, performance requirements, and testing (De Carteret et al., 2009) [8]. Correspondingly, the Australian Standards and State Road Authorities compel all stakeholders to follow the internationally accepted standards, which require strict compliance with qualitative testing and other quality assurance test methods. The use of AC also highlights the application of environmentally friendly and recycled materials in manufacturing bitumen binders. As a result, the stakeholders guarantee that the QMS and the linked specifications maintain comprehensive adherence to enhance high-level safety, quality, and sustainability in construction in Australia.

2.4. Challenges and Innovations

The most critical challenges observed include aging, rutting, temperature sensitivity, and environmental risk that have an adverse impact on the performance and sustainability of construction materials. The most critical challenge in aging is the mechanistic properties of bitumen binders that are affected by the binders’ age due to oxidation and thermal degradation and UV radiation, reducing their viscosity and stiffness and increasing their risk of cracking (Polo-Mendoza et al., 2022) [9]. Bitumen binders as a material are now subject to environmental issues such as their energy consumption, emissions, and sustainability, and their environmental impact is an important issue in the construction sector. Carbon emissions and other environmental degradation come with bitumen extraction and refining too. So, there is a need for greener, more sustainable alternatives.

2.5. Bitumen Aging

The gradual breakdown of the materials of the pavement with time is known as pavement aging, and there are many aging mechanisms. The three main sources of damage are oxidative aging, moisture damage, and thermal fatigue. Asphalt properties, including stiffness, cohesion, and fatigue resistance, are altered through these processes and influence pavement performance and life.

- Mechanisms of Aging:

Different mechanisms deteriorate the asphalt materials. X. Wang et al. (2019) [10] examined the aging of bitumen from pieces of bridge decks, traffic lanes, and ramps. The samples were tested using four experiments: Fourier transform infrared spectroscopy, a dynamic shear rheometer, gel permeation chromatography, and a fluorescence microscope. As a result, the age of the top of the pavement is much more important than the other two layers. The study identified the primary processes of bitumen aging as oxygen absorption, a change in viscoelastic properties, and molecular weight alterations. The asphalt starts to age when oxygen and UV rays penetrate it. The resultant chemical oxidation of the asphalt binder in such a process forms stiffening compounds, e.g., carbonyl groups or cross-linked structures. The moisture damage factor involves water penetrating and

traveling through the design system such that the asphalt binders are stripped, and the aggregate is displaced; the asphalt bolts and loses adhesion between each confined layer. Pavement materials expand and contract with temperature changes, causing pullout tension and leading to thermal fatigue cracking and surface distress. All aging mechanisms are correlated and promote each other, accelerating pavement destruction, and they cannot resist loading and other environmental distresses any longer.

- Factors Influencing Aging:

Considering the prominent influence of bitumen aging, several studies were conducted to reveal the influence of the aging phenomenon factor. Tauste et al. (2018) [11] mainly focused on a review of the factors that influence bitumen aging and pavement aging, which are affected by oxidation, UV radiation, binder composition, additives, and testing methods. Also, temperature and humidity are environmental conditions that impact pavement aging, traffic loading, material properties, construction practices, and maintenance activities. Mechanical stresses arising from the factors above lead to material degradation and traffic loading strain between the applied loads and the pavement. The composition, aging sensitivity, and asphalt binder rheology influence pavement aging. The performance and durability of pavements result from pavement construction with asphalt mixture production and placement methodologies. Maintenance practices that slow material aging include seal coating, crack sealing, and surface renewal, that is, chip sealing. To optimize effective aging mitigation strategies and to design durable pavement systems, the stakeholders in the construction and maintenance of pavements need to understand these factors.

- Laboratory Aging:

The identification of bitumen aging in the field is difficult and expensive as it involves precipitation, temperature, and sunlight (and others), which depend on the specific field condition (Yahaya et al., 2019) [12]. The aging process can be divided into two processes: long-term aging and short-term aging. Several failing pavement tests are used to characterize pavement aging and quantify its effect and extent on pavement performance and sustained service. There are many established laboratory test methods for short- and long-term aging. For most of the time, the thin-film oven test (TFO) and the rolling thin-film oven test (RTFOT) currently simulate short-term aging, whereas the pressure aging vessel (PAV) simulates long-term aging. These methods are used to identify pavement aging and measure its impact and extent on pavement performance and longevity. Many established laboratory test methods for short- and long-term aging exist, and most of the time, the thin-film oven test (TFO) and the rolling thin-film oven test (RTFOT) currently simulate short-term aging, and the pressure aging vessel (PAV) test is conducted to simulate long-term aging. Rheological tests, e.g., the dynamic shear rheometer (DSR) and bending beam rheometer (BBR) tests, are used to study the performance of asphalt binders subjected to dynamic loading and temperature variations, and the test set-up is designed to enable the understanding of the modification of rheological properties brought about by aging (Jiang et al., 2021) [13].

The properties of same-grade bitumen derived from different crude sources were studied by Hofko et al. (2017) [14], specifically regarding the effect of aging. Long- and short-term laboratory experiments were conducted using the RTFOT, PAV, and RTFOT+PAV methods. Standard tests were performed on the properties, and the rheological data were determined using a dynamic shear rheometer (DSR) test. This resulted in more severe aging of the bitumen with PAV aging, but how it aged the bitumen after short-term aging had less effect on the properties of the bitumen. In a study conducted by Jian et al. (2021) [13], they studied the effects of various aging methods on both the performance of bitumen and the composition of molecular components. The study was conducted on two virgin

bitumen types, and experiments were conducted using three aging methods: RTFOT, PAV, and RTFOT+PAV. It is found that the combined test, RTFOT+PAV, had the most impact on the properties of the bitumen, with RTFOT having a more substantial effect than PAV. When long-term aging facilities are lacking, the study recommends using RTFOT rather than PAV. Lu et al. (2008) [15] conducted a study to simulate the aging of bitumen in laboratory conditions using various methods at various temperatures and durations: PAV, RTFOT, and RCAT (rotating cylinder aging test). The binders tested were unmodified and polymerized (SBS) A120, B85, and PMB20. Additionally, they compare laboratory results for the samples of roads of different ages to field conditions and ascertain the extent to which we can predict actual field conditions. They found that the road sample did not age nearly as much as the laboratory-predicted values. The researchers assumed that the low air space in the roads combined with the protective screens accounted for the results. The long-time aging tests RCAT and RTFOT, however, showed some discrepancies. However, finally, the short-term aging tests RCAT and RTFOT gave similar results, thus indicating that short-term simulation, rather than the long-time test, is preferred.

The effects of laboratory short-term aging on bitumen properties were studied by Yahaya et al. (2019) [12]. The same grade of bitumen (80/100 pen grade) was procured from two different sources; The 60/70 pen-grade bitumen (A80, B80, and B60) was used by the researchers. To determine the aged and unaged bitumen properties, they carried out the standard RTFO test and common standard tests, including a dynamic shear rheometer (DSR), a viscometer, and Fourier transform infrared spectroscopy. The finding was that aging duration and temperature increased the viscosity linearly at a faster rate with higher temperatures. In addition, the aging indices G^* were found to increase with increased age and temperature. The research also demonstrated that the severity of the aging would increase the carbonyl and the sulfoxide indices. In another article, Hofer et al. (2023) [16] compared chemical and mechanical analyses of field- and laboratory-aged bitumen via RTFOT, PAV, or Viennese Binder Aging (VBA) using an unmodified 70/100 penetration-grade bitumen and an actual field sample of the same base binder. Data analysis consisted of a dynamic shear rheometer (DSR) and Fourier transform infrared (FTIR). This has confirmed that we simply could not achieve the field aging level in either of the experiments. Nevertheless, these VBA samples show more similarities to field samples than the other laboratory aging methods.

2.6. Rutting

2.6.1. Mechanisms of Rutting and Factors Influencing It

The mechanisms of rutting are associated with permanent deformation under repeated loading. Traffic loading factors and their concentration, including traffic volume and composition, channelization and lateral wander, climate conditions, pavement structures, material quality, and construction techniques, control frictional forces, and pressure on layer shearing and compacting. This dynamic method results in the material's viscous and plastic deformation throughout the compaction process. This phenomenon led to the breakdown of the internal structure of the asphalt mixture and permanently deformed the pavement's surface. Excessive moisture and temperature fluctuations facilitate these processes as they make the asphalt binder more susceptible to softening and cohesion, decreasing its resistance to deformation. Rutting is identified as the key mechanism of plastic deformation that ultimately leads to an inferior quality of the payment and comes at a high cost for maintenance and repair. Thus, understanding these mechanisms is essential for the development of effective rutting control strategies and the design of durable pavement systems (Pan et al., 2023 and Sinanmis & Woods, 2022) [17,18]. Several factors contribute to the rutting in pavements, including internal, external, and human-related

factors. Internal factors, such as the properties of the material used in the asphalt mixture (internal friction and cohesion properties, balance of the amount of binder, aggregate gradation and angularity, and surface layer thickness), are related to external factors. The external factors could be termed as the external load, including traffic, axle load, and environmental factors, such as temperature and moisture. The rutting resistance decreases with an increase in temperature as the binder melts. Constructing quality is based on the degree of compaction, temperature, and the degree of segregation suffered as a result of human-related factors (Pan et al., 2023) [17].

2.6.2. Measurement and Evaluation of Rutting

Methods and techniques for measuring and evaluating rut depths in pavement are numerous. These include field surveys, pavement distress indices, and laboratory testing including the oscillation test (dynamic shear rheometer—DSR), the creep and recovery test (MSCR), viscous component of creep stiffness (G_v), zero shear viscosity (ZSV) and low shear viscosity (LSV), Shenoy's rutting parameter, and in recent years, numerical modeling of the rutting behavior of pavement materials. Radhakrishnan et al. (2018) [19] studied evaluating rutting parameters using nine different types of bitumen, including unmodified as well as polymer- and crumb rubber-modified bitumen binders subjected to various parameters, including temperature, loading time, stresses, strains, etc. The $G^*/\sin\delta$, Shenoy's parameters, viscosity, oscillation, creep and recovery modes, wheel tracking rut depth, and other parameters were studied to evaluate the rutting resistance.

3. Bitumen Modification

Due to the challenges mentioned above and the need to optimize and minimize production costs, research and innovations of advanced bitumen formulations and technologies have been actively discussed. Celoglu et al. (2018) [20] explore the impact of styrene–butadiene–styrene (SBS), Trinidad Lake Asphalt (TLA), Iranian Gilsonite (IG), and American Gilsonite (AG) as bitumen modifiers. Olabemiwo et al. (2017) [21] focused on enhancing the thermal aging resistance of ANB through polymer modification. Gokalp and Uz (2021) [22] conducted a study to enhance aging resistance using waste engine oil (WEOIL). Nordiana et al. (2019) [23] used waste cooking oil (WCO) as the modifier for bitumen in order to assess the rutting resistance. Ansar et al. (2022) conducted a study utilizing polycarbonate (PC) and polytetrafluoroethylene (PTFE) as bitumen modifiers at varying percentages, and Lin et al. (2022) [24] investigated the aging properties of the bitumen using bio-oil derived from bamboo charcoal. Another successful technology actively discussed is the various studies on enhancing the properties of bitumen by incorporating the crumb rubber modifier (CRM). Further, nanotechnologies, such as nano-clays and nano-silica, are being developed to improve bitumen binders' properties, reduce aging, and make the binder eco-friendly by reducing moisture and rallying activities. These advancements aim to reduce the environmental impact of construction materials.

4. Discussion

4.1. Crumb Rubber-Modified Bitumen

4.1.1. Introduction

Crumb rubber-modified bitumen is an innovation in road building. It is a product made by combining bitumen and finely ground rubber extracted from used crushed tires. The procedure begins with the extraction of trashed tires that are suitable for this process and further extraction of finely ground rubber. Afterwards, the rubber is received by processing the rubber through cryogenic grinding or ambient grinding to ensure the necessary particle size distribution. Later, the rubber is combined with bitumen in predetermined pro-

portions in a specialized blending unit or a modified asphalt plant, resulting in CRMB (N.S. Mashaan, 2012a,b) [25,26]. One of CRMB's main advantages is that it performs functionally better than bitumen. The rubber added fundamentally changes the properties of the binder, thereby giving it more excellent elasticity, physical durability, and resistance to aging and cracking. Thus, the asphalt pavement produced is more resilient to deformation and fatigue experienced under heavy traffic loads. For this reason, CRMB is particularly suitable for application in high-stress areas such as highways, bridges, and intersections [25].

As well as a few environmental benefits, CRMB also provides waste rubber from discarded tires for recycling, keeping the volume of waste tires in landfills or incinerators to a minimum. Korycki (2024) [27] suggests that using crumb rubber in ELT could reduce more than 450,000 tons of tire waste annually in Australia, reducing the tire waste that goes into landfills or incinerators. Retaining virgin bitumen helps reduce the disposal of environmental nuisance toilets involved with tire disposal, conserves resources, and cuts energy costs. In addition to the environmental benefits achieved with high-performance pavements, CRMB also offers large economic 'bottom line' savings, typically saving more than 50% over the pavement's life cycle. CRMB eliminates the need for frequent maintenance and has a longer service life, consequently lowering the pavement's overall lifecycle costs in comparison to conventional hot mix asphalt.

4.1.2. Properties of CRMB

All other parameters, indeed, could not be the same, but the unique properties of CRMB, crumb rubber-modified bitumen, distinguish it from conventional bitumen and make it more useful in road construction. Also, the most important characteristic feature of CRMB is the excessively increased elasticity on a fine ground, which does not deform or crack because of thermal cycles, preventing elongation and contraction. Compared to findings by Anusha and Jagadeesh (2021) [2], crumb rubber corresponds to an increase in the elastic recovery of the binders and pavements made with them and reduces the critical rutting parameter value in the former and extends the benefit of lifespan. CRMB also offers the benefit of higher resistance to rutting and cracking, which are common distresses associated with heavily trafficked roads or environmental conditions. The crumb rubber increases the binder's thermal properties. It also increases the time for resistance to permanent deformation that develops over more wheeled loads. Consequently, it also makes the binder more resistant to fatigue cracking. This results from the binder's elasticity and the rubber's damping. According to their findings, CRMB reduces pavement fatigue, thus reducing cracking and enriching sustainability benefits (Anusha & Jagadeesh, 2021) [2]. Durability is another crucial issue; the payment surface should consist of improved resistance to raveling and, therefore, should be better able to resist aging and other forms of substantial deterioration. Crumb rubber acts as a barrier, preventing the binder from oxidizing and degrading under UV and other factors; treating the binder with crumb rubber improves road surface properties and causes the structure to become more durable and low maintenance. Many researchers have researched the relationship between CRMB and rheological characteristics, demonstrating how proper mix designs strengthen the durability of the road structure.

4.1.3. Factors Affecting CRMB Performance

Several previous studies have observed that the blending conditions crucially affect the performance of the crumb rubber-modified bitumen. Jamal and Giustozzi (2020) [28] researched the importance of using low-content CRMB on Australian roads, and the study was conducted using two shear mixing rates (700 rpm and 3500 rpm) and with three different mixing times (30 min, 60 min, and 90 min). After conducting several tests,

including the master curve, black diagram, and multiple stress creep recovery research, they concluded that the applied mixing rate had a higher impact on bitumen properties than the mixing time. Also, according to the MSCR test, it was observed that with a small amount of CR additive, the rutting resistance can improve significantly. In a study by M. R. Ibrahim et al. (2013) [29], rheology investigations are conducted on the crumb rubber-modified bitumen under different conditions. External factors like the mixing temperature, duration, type of mixing, and rate play a major role in determining the CRMB performance shown by the study. The resulting performance of the mixer also depends on the internal factors of addition percentage, crumb rubber size, and microstructure. In addition, the findings by N. S. Mashaan and Karim (2012) [25] revealed the effect of the bitumen content and blending time on its rheological behavior. Erasure, duration, the type of mixing, and rate can be described as external factors. Internal factors like percentage of addition, crumb rubber size, and microstructure also affect the resulting performance of the mixer. Furthermore, the research carried out by N. S. Mashaan and Karim (2012) [25] showed that the content of the crumb rubber and the blending time significantly influence the rheological behavior of the bitumen.

4.1.4. Aging, Rutting, and Fatigue Resistance

It was proven that the aging mechanism in crumb rubber-modified bitumen is much more complex and leads to improved performance of resistance to aging. A study was conducted by Ali et al. (2013) [1] to investigate the properties of aged, rubberized bitumen using 80/100 penetration-grade bitumen by adding 8% and 16% CRM by binder weight. The samples were aged using RTFOT to simulate short-term aging, and a pressure aging vessel (PAV) test was performed to simulate long-term aging. The aged and unaged properties of the composites were determined by using standard tests such as the penetration test, the softening point test, the Brookfield viscosity test, and DSR analysis. To assess the aging effect on the bitumen binder, it is possible to use the ratio of bitumen properties before and after aging, known as the aging index. Consequently, it is able to calculate the viscosity aging index (VAI), the penetration aging ratio (PAR), and the aging index for the rutting factor. A comparison of the modified and unmodified bitumen was able to yield significant findings by demonstrating that the CRM-modified bitumen displayed lower indexes of viscosity and rheological properties, as well as a reduced softening point increment and penetration aging ratio, and that the crumb rubber-modified bitumen has high aging resistance. CRMB shows aging resistance that increases when the crumb rubber content increases. Table 1 illustrates the summary finding of bitumen modified with CRM.

Table 1. Summary finding of bitumen modified with CRM.

Binder Grade	CRM% (by Weight of Bitumen)	Tests Conducted	Main Findings	Reference
70/100	5%, 10%, 15% and 22%	Rolling thin-film oven (RTFO), pressure aging vessel (PAV) test, Fourier transform infrared spectroscopy, dynamic shear rheometer, and multiple stress creep and recovery test	- The evidence of lower increases in carbonyl and sulfoxide indices can conclude that adding CR improves aging resistance. - CR-modified bitumen showed less stiffening and embrittlement, which enhanced aging resistance. - CR-modified bitumen was also more flexible than virgin bitumen, leading to better rutting resistance. - Increasing the CR content lowers the aging rate and leads to better performance against rutting.	(Wang et al., 2020) [30]
60/70, 80/100	4, 8, 12, and 16%	Penetration, softening point, ductility, and rotational tests, Marshall's stability test, resilient modulus (MR) test, indirect tensile strength (IDT) test, permanent deformation (rutting) test, and international roughness index (IRI).	- The study confirmed that adding CR enhances asphalt binders' rutting and cracking resistance. - CR modification improves the resilient modules, which indicates better rutting and stiffness resistance. - IRI values indicate improved long-term rutting resistance.	(Irfan et al., 2017) [31]
60/70	9.5% and 15%	Penetration test, dynamic shear rheometer (DSR), and softening point test	- Adding 15% crumb rubber showed higher performance in rutting resistance. - According to the DSR, adding CR exhibits reduced phase angle and improved elasticity, thereby enhancing rutting resistance. - Considering the combined results from penetration, softening point, and DSR, CRMB exhibits significant improvements in rutting and aging resistance.	(Gohar et al., 2022) [32]

Table 1. Cont.

Binder Grade	CRM% (by Weight of Bitumen)	Tests Conducted	Main Findings	Reference
80/100	4%, 8%, 12%, 16% and 20%	Dynamic shear rheometer (DSR), softening point (ring and ball) test, and analysis of variance (ANOVA)	- Increasing the crumb rubber content leads to better deformation resistance. - At higher mixing temperatures, swollen rubber particles make the binder stiffer and more elastic, leading to better rutting performance. - Using a higher blending temperature enhances rutting resistance. - According to DSR, higher G' and lower phase angle indicated a better recovery in load removal, which enhances rutting resistance.	(Mashaan & Karim, 2012) [25]
C320	7.50%	Dynamic hybrid rheometer-3 (DHR3), frequency sweep test, multiple stress creep recovery (MSCR) tests	- Adding 7.5% of low-content CR led to a significant improvement in bitumen's rutting resistance. - FTIR analysis confirmed that CR modification enhances the stiffness of the bitumen, which can show long-term performance under high temperatures. - Increasing stiffness and decreasing phase angle confirm the enhancement of aging.	(Jamal & Giustozzi, 2020) [28]

Rutting Resistance: The elasticity, viscosity, and softening points of rubberized bitumen binders are higher than those of conventional binders, providing improved resistance to rutting. The CRMB is always watching increased elasticity and viscosity, but it is also important to cut rutting as it can withstand deformation and recover the deformation shape due to the vehicle loadings. High softening points will allow the pavement to withstand increasing temperatures, and binders will be able to hold a mix together and restore the total structure. In a study by Gohar et al. (2022) [32], they studied the rutting resistance of crumb rubber-modified bitumen. Rubber modification was carried out through the wet process, and crumb rubber modification was made with 9.5% and 15% by weight of the bitumen. Furthermore, the study demonstrated that improved properties such as viscosity, hardness, and deformation resistance improve the rutting resistance of bitumen.

Fatigue Resistance: Fatigue resistance can be identified as the material's ability to withstand frequent stresses and temperature changes while operating continuously. Variations in temperature place a tremendous strain on the material. They typically decrease the durability of the payment, forming cracks or deformations that could make it unsafe for road users and increase the maintenance cost. Wang et al. (2020) [30] carried out research to investigate the fatigue resistance of crumb rubber-modified bitumen using four

different crumb rubber amounts, which are 5%, 10%, 15%, and 22%, and conducted fatigue performance tests named frequency sweep tests, TS, and LAS test. The study concluded that the crumb rubber-modified bitumen exhibits high resistance to fatigue when compared with the virgin bitumen.

The most impressive thing about CRMB is that it also creates environmentally friendly products and excellent engineering materials. CRMB provides a way to address the issue of how to dispose of the millions of tires produced worldwide. When scrap tires are substituted for more expensive virgin polymers, more money, energy, and pollution savings are achieved. Studies show that although CRM pavements have a high initial cost and energy usage compared with regular asphalt paving, CRM pavements have more than two to four years longer service life, which can reduce the maintenance cost due to their advanced performance (Riekstins et al., 2022) [33].

As a major disadvantage of crumb rubber-modified bitumen (CRMB), CRMB storage is unstable. Thus, it cannot be used for additional purposes. Homogeneity, phase separation, and temperature stability are influential on storage stability. Blending techniques that eliminate this should be used, and the mix should be consistent. CRMB is also challenging to implement due to the worker's exposure to CRMB emissions. Selecting the health effects is much more important than identifying them, and the handling should be performed under the above-mentioned general guidelines aimed at improve health and safety. However, although CRMB is seen as a sustainable technology, its high environmental toxicity, including emissions, air quality, and water quality, disadvantages the technology. Also, supply chain challenges are other issues that must be systematically tackled (Denneman et al., 2015; Buchagul 2019) [3,34].

In all industries, a life cycle assessment (LCA) is an important tool for gaining a holistic picture of a product or process's environmental impact to make sustainable decisions. Pavement performance and environmental benefits from crumb rubber-modified bitumen are investigated using LCAs. Focusing on energy usage, climate change, global warming potential, economy, etc., can be performed with life cycle assessments. Piao et al. (2021) [35] have conducted a life cycle assessment on the impacts of climate change and cumulative energy demand. Three different kinds of asphalt mixes were included in the study, and the data were compared in terms of different mechanical tests, such as water sensitivity tests and wheel tracking tests. Overall, the study finds that the CUR for the CR-modified pavement is small enough for the cumulative energy demand of the CR-modified pavement to be comparable to polymer-modified pavements. Farina et al. (2014) [36] compared the production of crumb rubber bitumen mixtures via wet and dry processes. The gross energy requirement and global warming potential were recognized as the main energy and environmental indicators. Service life and maintenance frequency were assumed in the life cycle assessment. On the other hand, key findings of the research indicate that the wet process has significant power and environmental triumph over the dry process. Riekstins et al. (2022) [33] conducted a necessary study for the economic and environmental analysis of CRM asphalt using the wet process. The main areas considered were the annual energy use, global warming potential, and economy. The findings are significant, which show that the asphalt with crumb rubber modifications has a long pavement life with less energy use and less cost than the conventional pavement. As an environmentally friendly technology, the CRMB can also be considered as a technology that has demonstrated a clear trend in saving energy and lowering greenhouse gas emissions.

4.2. Styrene–Butadiene–Styrene (SBS)

Styrene–butadiene–styrene (SBS) is one of the most commonly used thermoplastic elastomer modifiers of polymer-modified asphalt (PMA) to improve pavement flexibility

and durability under changing environmental stresses (Zhu et al., 2014) [37]. Hassanpour-Kasanagh et al. (2020) [38] note that the elastic recovery, stiffness, and resilience of SBS-modified binders are improved compared to that of normal binders, which are essential for long-term pavement performance. According to SBS research, SBS provides better elasticity and better temperature resistance than ordinary asphalt and could protect pavements against stresses like rutting when hot and cracking when cold. Despite these setbacks, SBS can become relatively expensive and prone to UV radiation, aging, and oxidation; thus, studies on recycled SBS-modified materials are warranted (Yang et al., 2024) [39].

Aging and Rutting Resistance

SBS polymers enhance the aging resistance of asphalt binders by providing an elastic network in the bitumen matrix. Hassanpour-Kasanagh et al. (2020) [38] indicate that the viscoelastic properties of SBS-modified binders are better retained over time than those of unmodified or recycled modified binders. SBS can better resist aging under oxidative and thermal stress, as evidenced by multiple stress creep recovery (MSCR) and linear amplitude sweep (LAS) tests. It was statistically found that the aging resistance index increased up to 25% when the binder was substituted from 5% SBS, meaning that the redounding is substantial for conventional binders. In addition (Hassanpour-Kasanagh et al., 2020) [38], the resistance of asphalt binders by forming an elastic network within the bitumen matrix improves durability. According to Hassanpour-Kasanagh et al. (2020) [38], SBS-modified binders retain their viscoelastic properties better over time compared to unmodified or even some recycled modified binders. According to Hassanpour-Kasanagh et al. (2020) [38], multiple stress creep recovery (MSCR) and linear amplitude sweep (LAS) tests demonstrate that SBS can maintain higher resistance to aging, particularly under oxidative and thermal stresses. Statistically, 5% SBS increased the aging resistance index by approximately 25%, indicating substantial enhancements compared to conventional binders (Hassanpour-Kasanagh et al., 2020) [38]. SBS, however, is not an aging-resistant material. According to a study by Yang et al. (2024) [39], unsaturated bonds in SBS permit crushing to take place gradually under UV irradiation, and the binder's resilience also decreases with time. Alternative measures have been used earlier to increase SBS's durability under aging conditions, such as the addition of antioxidants or sulfur vulcanization (Yang et al., 2024) [39]. The summary findings of using SBS in bitumen modification are shown below in Table 2.

Table 2. Summary findings of using SBS in bitumen modification.

Binder Grade	% (by Weight of Bitumen)	Tests Conducted	Main Findings	Reference
50/70	3–7%	Softening point, penetration, rotational viscosity, Superpave performance grading, multiple stress creep recovery (MSCR), and linear amplitude sweep.	- SBS increases the softening point, decreases the penetration grade, and increases viscosity, which are critical for rutting resistance. - The PG and creep compliance of the binders indicated that the SBS effectively enhances high-temperature performance. - The LAS test indicates that SBS increased the fatigue life of the binder at various strain levels.	(Hassanpour-Kasanagh et al., 2019) [38]
70	5%	Thin-film oven test (TFOT), UV aging test in different temperatures (UV only, UV+Water, UV+Acid, and UV+ salt), dynamic shear rheometer (DSR), Fourier transform infrared spectroscopy (FTIR) Test, and four-component analysis test	• SBS increased UV aging resistance compared to the virgin bitumen. • Under UV radiation, the carbonyl and sulfoxide groups increased while SBS's PB and PS segments decreased, indicating its resistance to degradation with excessive hardening due to UV exposure. • SBS-modified bitumen indicates less aging when exposed to water, acid rain, and salt while exhibiting fewer cracks. • SBS-modified bitumen has high resistance to component migration.	(Wei et al., 2019) [40]
70	1.5%, 2.%, 3.5%, 4.5%, and 5.5%	Penetration, softening point, ductility and elastic recovery. Microscopic property tests include FTIR, FM, SEM, and AFM. Rheological analysis tests include strain scanning, frequency scanning, and temperature scanning	• SBS-modified bitumen forms a stronger network structure when content exceeds 3.5 wt%. • The high content of SBS provides better aging resistance. • Aging improves rutting resistance but decreases the resistance to fatigue. • High SBS content (5.5 wt%) indicates a reduction in the softening point, increasing penetration due to excessive swelling.	(Ma et al., 2024) [41]

Table 2. Cont.

Binder Grade	% (by Weight of Bitumen)	Tests Conducted	Main Findings	Reference
Penetration [1/10 mm] (EN 1426) 177 and 145	3–10 wt%	Dynamic shear rheometer (DSR) test, bending beam rheometer (BBR) test, temperature-modulated differential scanning calorimetry (TMDSC), fluorescence microscopy (FM), penetration test, and ring-and-ball softening point test	• FM shows SBS swelling by absorbing light oils' components, which enhances rutting resistance. • According to BBR and DSR, SBS helps to reduce low-temperature stiffness by mitigating thermal cracks and increasing flexibility by influencing aging resistance. • TMDSC showed a limited glass transition shift, which can affect long-term aging resistance. • The SBS-modified material has a complex rheological behavior, which can impact rutting resistance by maintaining elasticity and aging resistance by reducing oxidative hardening.	(Laukkanen et al., 2018) [42]
50/70	5 wt%	Rolling thin-film oven (RTFO), pressure aging vessel (PAV), Fourier transform infrared (FTIR) spectroscopy, modulated differential scanning calorimetry (MDSC), and thermo-gravimetric Analysis (TGA)	• SBS influences the thermal stability of bitumen, especially in aged samples. • SBS-modified bitumen indicated increased crosslinks and reduced the mobility of molecules. • Modified bitumen enhances the residual chart's content, indicating better material integrity. • Long-term aging of SBS-modified bitumen indicated an increase in oxidation and a decrease in aging, increasing its brittleness.	(Kaya et al., 2019) [43]

The strengthening of rutting resistance is the principal benefit of SBS in pavement materials. The effect of SBS-modified binders on the elastic properties, which decrease the probability of permanent deformation at high temperatures, is a common problem in the surfaces of load-bearing roads used in areas of high traffic volume. According to tests performed by Zhu et al. (2014) [37], SBS-modified binders increase rutting resistance by roughly 40% more than non-modified binders. This improvement is attributed to the polymer's ability to maintain elasticity and stiffness under a load (Zhu et al., 2014) (Hassanpour-Kasanagh et al., 2020) [37,38], thereby reducing the permanent deformation seen in hot conditions (Zhu et al., 2014) [37]. SBS also develops superior rutting resistance compared to some recycled modifiers, particularly at higher dosages. For example, binders modified with 3–7% SBS showed better resistance than binders modified with 100% recycled high-density polyethylene (HDPE) due to the problems with phase separation in the HDPE binder. Furthermore, composite modifiers that incorporated recycled SBS were developed to trade off costs and performance but are not always as effective at resisting rutting compared to pure SBS-modified binders (Hassanpour-Kasanagh et al., 2020) [38].

Using SBS in pavement applications also has the twofold environmental impact we described. SBS gives the pavement higher longevity without requiring frequent repair (Hassanpour-Kasanagh et al., 2020) [38]. (In addition to the high production cost, SBS is nonrenewable, affecting the nature of the environment.) These problems are overcome through research into using recycled SBS and hybrid modifiers with ground tire rubber (GTR) and HDPE. Using recycled composites, the performance of these recycled composites is similar to that of SBS regarding rutting resistance, but they may offer cost and environmental savings (Yang et al., 2024) [39]. Although SBS-modified pavements have environmental values, they also entail economic and technical limitations. However, SBS is costly and, according to Yang et al. (2024) [39], has a narrow-spread adoption, particularly in areas with limited resources for infrastructure. However, SBS is not directed towards the same bitumen types, which can impact its ability to maintain storage stability, resulting in additional maintenance costs should the storage degrade. This emphasizes the necessity of moving away from recycled modifiers and hybrid solutions and mitigating some of such economic and environmental burdens with low or no compromise on both parameters (Yang et al., 2024) [39].

4.3. Recycled Polypropylene (PP)

The application of polypropylene (PP), which is recyclable, stiff, and has good temperature resistance, as a material for pavement modification is gaining attention because it is economical and sustainable. Recycled polymers, particularly PP, are pushed to replace the traditional bitumen modification to obviate associated environmental issues and improve pavements' performance and duration (Nizamuddin et al., 2021) [44]. PP is shown to be thermodynamically stable and resistant to degradation and is highly beneficial as a modifier in asphalt pavements in high-stress situations. The role of recycled PP in enhancing pavement durability in terms of its aging and rutting resistance and economic and environmental implications is reviewed in this review (Salehi et al., 2021) [45].

- Aging and Rutting Resistance

Here, a critical problem with recycled PP is aged resistance, an issue with many pavement materials. Traditional asphalt can degrade under thermal and UV stresses, causing cracking and brittleness on the surface. Thermal aging tests show that recycled PP significantly enhances the aging resistance of the binder, as asphalt modified by PP retained approximately 20% more viscoelastic properties than unmodified asphalt (Nizamuddin et al., 2021) [44]. Designed to interpret in vivo structural properties, PP's structural stability proves most resistant to long-term residence in high temperatures. It was also shown

that recycled PP-modified asphalt had lower oxidative degradation rates in comparison to virgin asphalt because the polymer has a stable molecular composition. Nizamuddin et al. (2021) [44] reported that recycled PP-modified asphalt has good flexibility and adhesion properties that prevent common problems in aged pavements, such as cracking and brittleness (Nizamuddin et al., 2021) [44]. Another significant benefit to rutting resistance is using reclaimed PP in pavement materials. The rigidity and higher melting point of PP make it appropriate for applications requiring high resistance to deformation at loads. However, a series of recent evaluations of PP-modified asphalt has shown that the PP reduced the damage due to the formation of ruts compared to conventional bitumen by 35%. Salehi et al. (2021) [45] have shown that recycled PP can improve pavements at bearing traffic stresses (Marshall's stability tests). This reduction in rutting susceptibility is particularly beneficial because severe rutting can lead to major maintenance problems on high-traffic roads. Salehi et al. (2021) [45] support the work further as the reduction in rut depth under sustained loads is also found (Salehi et al., 2021) [45]. It has a significant environmental footprint because it does not use virgin polymers, which leads to less plastic waste in the environmental system. Polypropylene is one of the most commonly used plastics in the world and is being used in its recycling through the use of roads. The results of a life cycle assessment (LCA) study on recycled PP-modified asphalt reduce CO₂ emissions by up to 15% and reduce the environmental footprint of road construction (Nizamuddin et al., 2021) [44]. Recycled PP is more economically accessible than virgin polymers, so it provides a cheaper alternative for infrastructure project implementations largely backed by a lack of resources. However, its compatibility and stability are weak points. In certain cases, recycled PP can be incompatible with bitumen and may phase separate during mixing because of its nonpolar nature. To solve these compatibility problems, techniques such as adding compatibilizers and reactive modifiers have been addressed (Nizamuddin et al., 2021) [44]. Recycled PP may have lower production costs compared with virgin PP, but it needs process and quality control investment that may jeopardize its wide outreach.

4.4. Recycled Polyethylene Terephthalate (PET)

PET, a recycled polyethylene terephthalate, has recently received more use in pavement materials due to its beneficial durability and sustainability properties. There are several plastics on the planet, but two of them have become particularly burdened. For example, plastic PET is used everywhere as a plastic bottle. Using recycled PET to make pavement materials results in a better environment and less environmental impact. PET's high-temperature and wear properties make it an excellent additive to asphalt to improve its stability and durability. Based on pet-modified asphalt studies, these mechanical properties show improvement in moisture resistance and rutting performance, similar to the application in heavy-duty pavements (Usman & Kunlin, 2024) (Mushtaq et al., 2022) [46,47].

4.4.1. Aging and Rutting Resistance

As PET is thermally stable, it has good potential for aging resistance improvements of asphalt pavements. When combined with PET, asphalt can be slowed down by PET in terms of its aging, and that can take out the oxidative degradation enabled for asphalt when it combines with air, and those oxidative peaks decrease with that. Maharaj et al. (2018) [48] demonstrated that PET-modified asphalt performed better in accelerated weathering tests than conventional asphalt with better structural integrity. However, adding PET increases the resistance to environmental factors, such as UV, without suppressing brittleness and cracking with time (Maharaj et al., 2018) [48]. Also, PET's chemical structure, characterized by its high crystallinity, leads to strong PET and asphalt-bonding PET, resisting the fast breaking down of asphalt under radically different climatic conditions. However, these

characteristics of PET-modified asphalt are more durable to thermal and UV-induced aging (Usman & Kunlin, 2024) [46]. One of the most essential advantages of using PET in asphalt is its improved rutting resistance. The high melting point and rigidity of PET contribute to asphalt's resistance to deformation, and this is very important in areas of high traffic. Marshall's stability and creep tests confirmed that PET-modified asphalt had approximately 20 percent better rutting resistance (Usman et al., 2024). The increase in stiffness and viscosity from including PET limited the depth of the rut formed from the repeated traffic loads (Usman & Kunlin, 2024) [46]. Maharaj et al. (2018) [48] also reported that asphalt mixtures containing 5% PET had Marshall stability values up to 50% higher than unmodified mixtures. These results demonstrate PET's ability to reduce pavement deformations as well as minimize structural damage to the pavement under sustained stress (Maharaj et al., 2018) [48]. The thermodynamic compatibility between asphalt and polymer modifiers significantly impacts the adhesion between the two materials. When recycled plastics are added to asphalt, they alter the surface energy and cohesive forces within the binder. This results in better wetting and a stronger bond with the aggregate. Studies indicate that when waste plastics are melted and incorporated into the asphalt matrix, they contribute to a more stable and cohesive mixture due to their favorable surface energy interactions, leading to better adhesion and durability (Mashaan, 2022; Mashaan, 2023; Mashaan, 2024) [49–51]. The coating of aggregates with recycled polymers has been shown to enhance the adhesive properties of the asphalt–aggregate system. The polymers, when blended with asphalt, can coat the aggregate particles, improving their interaction with the binder. This modification improves the adhesion by reducing the potential for moisture damage, which is a significant concern in asphalt pavements. As a result, the [49] asphalt mixture becomes more resistant to stripping, a process where the binder detaches from the aggregate due to water infiltration (Celoglu et al., 2018) [20]. When recycled polyethylene (PE) is used, for example, it helps improve the bond between the aggregate and the asphalt, ensuring better mechanical properties and moisture resistance.

4.4.2. Environmental and Economic Benefits and Challenges

Because recycled PET reduces plastic waste in landfills and oceans and lowers the need for virgin materials, the environmental advantages of using recycled PET in pavement materials are considerable. Recycling PET as an asphalt additive streamlines both steps to help move towards sustainable development goals, reduce waste, and use more eco-friendly construction methods. Mushtaq et al. (2022) [47] described how not only can PET be used for pavement construction, but it also means longer-lived roads with fewer costly repairs (Mushtaq et al., 2022) [47]. Nonetheless, the widespread adoption of PET-modified asphalt introduces some challenges. The high energy cost of processing PET for asphalt applications is one problem. PET also has challenges with the compatibility of PET with bitumen, as nonpolar PET may separate phases if not properly mixed. These methods aim to improve its compatibility at the cost of increased overall production costs (Maharaj et al., 2018) [48]. PET further offers performance benefits, but more research is needed to achieve a balance between performance and cost-effectiveness on asphalt with respect to PET content, especially in climates with severe temperature ranges.

4.5. Recycled Low-Density Polyethylene (LDPE)

Recycled low-density polyethylene (LDPE), a major contributor to municipal plastic waste, is an eco-friendly and cost-effective alternative to changing pavements. Since the global environmental crisis, incorporating LDPE into asphalt reduces plastic waste and improves the mechanical properties of asphalt pavements (Singh & Gupta, 2024) (Li et al., 2024) [52,53]. Polyethylene LDPE is one of the most common and easiest-to-modify

types of polyethylene that can be used in packaging applications. Results from a study indicate that LDPE-modified asphalt has improved stiffness and high durability under different temperature environments, making it an ideal material for road construction, more predominantly in extreme temperature regions (Ullah et al., 2024) [54].

4.5.1. Aging and Rutting Resistance

Resistance to aging is one of the most critical challenges of pavement life. The improvement of the aging resilience of asphalt with LDPE modification has been achieved with increased stiffness and elasticity of the asphalt binder, causing greater durability and resistance to cracking with time. Ullah et al. (2024) [54] suggest that adding LDPE in the appropriate proportions (3–7%) can greatly diminish degradation created by environmental facets, for example, UV openness and oxygen, which are standard in conventional asphalt emulsions. The higher viscosity and more elevated softening point that drive the delayed aging process and increase the life of pavements (Singh & Gupta, 2024) [52] (Ullah et al., 2024) [54] lead to this performance improvement in LDPE-modified binders. Table 3 shows the summary of the major findings of LDPE-modified bitumen.

Table 3. Major findings of LDPE-modified bitumen.

Binder Grade	LDPE%	Tests Conducted	Main Findings	Reference
VG30	3%	Stiffness test, indirect tensile strength (ITS) test, tensile strength ratio (TSR) test, resistance to permanent deformation (RTIndex) test, fatigue resistance test (CTIndex), and 3D pavement analysis (3D-Move Software)	- The RTIndex test showed that LDPE enhanced the resistance to permanent deformation of the mixture. - According to the stiffness test, the LDPE-modified mixture showed higher stiffness at elevated temperatures. - LDPE enhanced the resistance to aging. - CTIndex values showed lower fatigue resistance at high temperatures. - Three-dimensional pavement analysis indicated the long-term performance of the LDPE-modified mixture.	(Singh & Gupta, 2024) [52]
60/70	3%, 5%, 7%	Ductility test, penetration test, softening point test, Marshall's mix design test, and wheel tracking test	- According to the wheel tracking test, LDPE-modified asphalt showed the highest level of rutting resistance while outperforming PP and ABS. - The LDPE-modified mixture showed lower optimum binder content, which can contribute to a more sustainable pavement solution. - LDPE had the lowest penetration values and the highest softening points compared to PP and ABS. - Furthermore, LDPE showed lower ductility.	(Ullah et al., 2024) [54]
35/50	1%, 3%, 5%	Thermogravimetry and differential scanning calorimetry (TGA–DSC) test, FTIR test, softening point test, penetration test, DSR test, and RFTO	- Adding LDPE increased the stiffness and reduced thermal and kinetic sensitivities while increasing aging and rutting resistance. - The penetration values decreased, and softening point values increased, reducing rutting potential. - LDPE-modified bitumen has less sensitivity to RTFOT. - Adding LDPE improved the elastic response at high temperatures, indicating longer pavement life.	(Bensaada et al., 2021) [55]

Table 3. Cont.

Binder Grade	LDPE%	Tests Conducted	Main Findings	Reference
160/220	1, 3, 5, 7, and 9	Fourier transform infrared spectroscopy (FTIR) test, fluorescence microscopy, penetration and softening point tests, rolling thin-film oven test (RTFOT), rotational viscosity (RV) test, dynamic shear rheometer (DSR) test, and bending beam rheometer (BBR) test.	- Adding LDPE increased the shear modulus and decreased the phase angle, improving rutting resistance. - The performance grade increased, which indicated better resistance to temperature deformation. - LDPE-modified bitumen showed high resistance to aging. - LDPE modification caused high creep stiffness but a lower m-value, which can negatively affect the material at lower temperatures.	(Ahmedzade et al., 2013) [56]
80/100	4, 6, 8 and 10%	Penetration test, softening point test, ductility test, Marshall's stability test, bulk density, and void analysis	- According to the Marshall stability test, LDPE addition increased the stability while enhancing the rutting resistance. - The lower flow value of LDPE-modified bitumen indicated a decrease in permanent deformation.	(Genet et al., 2021) [57]

Moreover, Li et al. (2024) [53] also find that LDPE's polymer structure accounts for its aging resistance. At 2–5% concentrations, LDPE substantially improves durability and deformation resistance, particularly in warmer climates where aging typically accelerates. Excessive LDPE concentrations (>6%), however, may negatively influence the ductility and flexibility of the binder, resulting in brittleness at lower temperatures (Li et al., 2024) [53].

A key issue addressed by LDPE modification is rutting, a common form of deformation in flexible pavements in high-traffic and high-temperature conditions. According to studies, the LDPE modification contributes significantly to improving the rutting resistance of asphalt by increasing the stiffness and reducing the penetration of asphalt binders. Results from studies by Ullah et al. (2024) [54] show that the rutted depth of 3% to 7% LDPE asphalt mixtures decreased by up to 33% compared to conventional binders. Additionally, at 5% LDPE, rutting depth was reduced by 24%, indicating that polymer-stabilizing asphalt under repeated loading and high temperatures is quite effective (Ullah et al., 2024) [54]. Furthermore, Singh and Gupta (2024) [52] found that traditional mixtures gained a 42.3% improvement in rutting life, peaking at 42.3%, when applied with LDPE-modified asphalts. Results from the 3D-Move pavement analysis showed that LDPE reduces interlayer deflections, decreasing the pavement's sensitivity to routing under prolonged traffic loads. The above resistance is accentuated by using LDPE in conjunction with high-viscosity binders, thereby distributing stress over the pavement layers and alleviating surface deformation (Singh & Gupta, 2024) [52].

4.5.2. Environmental and Economic Benefits and Challenges

There are substantial environmental benefits from using LDPE in asphalt. This approach also reduces landfill waste by using recycled plastics and removing the greenhouse gas emissions from the disposal of traditional plastic through incineration. According to research, using LDPE in asphalt reduces the plastic waste of single-lane pavement by up to 750 kg per kilometer (Singh & Gupta, 2024) [52], an effective solution for pavement modification. Given the global environmental crisis, incorporating LDPE into asphalt not only reduces plastic waste but also enhances the mechanical properties of asphalt pavements (Singh & Gupta, 2024) [52] (Li et al., 2024) [53]. As one of the most common types of polyethylene used in packaging, LDPE is widely available and adaptable to modification processes for pavement applications. Studies show that LDPE-modified asphalt exhibits enhanced stiffness and increased durability under various temperature conditions, making it highly suitable for road construction, particularly in regions experiencing extreme temperatures (Ullah et al., 2024) [54].

4.6. Recycled High-Density Polyethylene (HDPE)

Asphalt pavement is increasingly recognized as a valuable additive that incorporates recycled high-density polyethylene (HDPE). Pavements with HDPE have unique advantages for performance, such as increased durability and resistance to deformation (Alghrafi et al., 2021) [4]. Integrating HDPE into asphalt addresses engineering and environmental challenges with the rapid increase in plastic production and waste. HDPE addresses this fundamental roadblock due to studies showing it can modify bitumen by improving its mechanical properties and thermal stability, which makes it a potential replacement for more traditional polymers in asphalt modification (Nizamuddin et al., 2020) [58] (Jessica et al., 2023) [59].

4.6.1. Aging and Rutting Resistance

However, HDPE in asphalt pavements notably increases aging resistance through oxidation–reduction and the preservation of mechanical strength. As shown in Alghrafi et al.'s (2021) [4] study, HDPE-modified asphalt had lower oxidation rates during short-

term aging, as measured via the Aging Index (AI), than virgin asphalt. For example, the AI values decreased by an average of 25%, showing a huge delay in the aging process (Alghrafi et al., 2021) [4], with HDPE contents of 2–6 wt.%. This also helps make the HDPE in the asphalt more resistant to temperature variations, something essential to aging. Secondly, HDPE increases the softening point of asphalt from 44.1 °C to 83.7 °C when the HDPE content reaches 6%, which leads to the binder's resilience against thermal degradation (Nizamuddin et al., 2020) [58]. Table 4 displays the summary of the major findings of HDPE-modified bitumen.

Table 4. Major findings of HDPE-modified bitumen.

Binder Grade	HDPE%	Tests Conducted	Main Findings	Reference
50/70	1%, 2%, and 3%	Rolling thin-film oven, rotational viscosity, performance grade (PG), multiple stress creep and recovery, and statistical Student's <i>t</i> -test	- The addition of HDPE indicated the slower aging of the bitumen. Increasing HDPE increased the viscosity of the bitumen. - HDPE contributed to reducing temperature sensitivity, which enhanced the rutting resistance. - Increasing HDPE indicated an increase in the penetration index ratio, which shows a decrease in temperature sensitivity.	(Da Silva et al., 2023) [59]
85/100	3%, 7%	storage stability test, zero shear viscosity (ZSV), non-recoverable compliance (J _{nr}), multiple stress creep recovery (MSCR) test	- The addition of HDPE significantly increased the rutting resistance by increasing the complex modulus and decreasing non-recoverable compliance. - There was a limited improvement in the low content of HDPE. - The high content of HDPE showed high stress sensitivity.	(Nejad et al., 2014) [60]
C170	2%, 4%, 6%, 8%	Multiple stress creep recovery (MSCR) test, rolling thin-film oven (RTFO) test, rutting and elastic recovery tests	- Adding between 2 and 4% HDPE content showed significant improvements in rutting resistance. - The addition of HDPE indicated an improvement in elastic recovery. - The addition of HDPE of more than 4% leads to the effect of aging resistance.	(Piromanski et al., 2020) [61]

Table 4. Cont.

Binder Grade	HDPE%	Tests Conducted	Main Findings	Reference
40/50	5%	Marshall's stability (MS), Marshall's quotient (MQ), indirect tensile strength (ITS), resilient modulus (MR), temperature susceptibility, and resilient modulus (MR)	- Higher Marshall's stability and increased Marshall's quotient showed that adding HDPE improved the resistance to rutting and aging. - Improved resilient modulus (MR) indicates better stiffness and load-bearing capacity. - The addition of HDPE shows a higher tensile strength ratio, which can lead to higher moisture resistance. - The lower drain-down values indicated a low risk of rutting and aging under high-temperature conditions.	(Ibrahim, 2019) [62]
50/70	1–4%	Marshall's stability test and indirect tensile test	- Adding HDPE increased the stability and flow values, indicating better rutting resistance and the highest stability and flow values obtained at 4% HDPE. - Increasing HDPE showed increasing resistance to water damage.	(Köfteci, 2016) [63]

HDPE modification also reduces rutting, which is the permanent deformation caused by excessive traffic loads and high temperatures. HDPE strengthens the asphalt binder by stiffening it and reducing its susceptibility to deformation. According to Jessica et al. (2023) [59], adding 2% HDPE improved asphalt's response to stress under high temperatures, with reduced rutting depth of about 20% in high-temperature regions. Moreover, the multiple stress creep recovery (MSCR) test results showed that all HDPE-modified binders are more resistant to high-temperature creep (the primary agent of rutting). Hardened cold creep (HDPE) is modified to raise the softening point modestly, which raises the resistance threshold and produces longer-lasting pavements in climates that experience higher temperatures (Nizamuddin et al., 2020) [58]. In addition, one of the key concerns in asphalt pavements is moisture damage, which can lead to stripping and reduced service life. Waste plastic-modified asphalt has shown promising results in improving moisture resistance. The polymers in the binder act as a barrier against water infiltration, reducing the likelihood of stripping and enhancing the adhesion to aggregates. According to Xiao et al.'s (2023) [64] study titled "Waste Plastic Powder Coating on Acidic Aggregates: A New Hydrophobic Coating Technology to Build Moisture-Resistant Asphalt Mixtures", the study investigates the application of waste plastic powder to modify aggregates, aiming to enhance the moisture resistance of asphalt mixtures. The key findings include developing a technique to coat acidic aggregates with waste plastic powder and creating a hydrophobic surface. This process aims to improve the bonding between the asphalt binder and aggre-

gates, thereby enhancing the durability of the asphalt mixture. The study demonstrated that the waste plastic powder coating improved the adhesion between the asphalt binder and aggregates. This enhancement contributes to the overall performance and longevity of the asphalt pavement. These findings suggest that utilizing waste plastic powder to coat aggregates is an effective strategy to enhance the moisture resistance and adhesion properties of asphalt mixtures, offering a sustainable approach to improving pavement durability (Xiao et al., 2023) [64].

4.6.2. Environmental and Economic Benefits and Challenges

Secondly, asphalt integration with HDPE avoids landfill volumes by stopping plastic waste from being sent to landfills. Plastic HDPE waste streams, where they become predominant, are very sustainable as the opportunities for repurposing them can be used within the pavements employing HDPE grease recycling. Studies estimate that each kilometer of HDPE-modified pavement can end up being made up of up to 500 kg of recycled plastic, which reduces carbon emissions by one-third of what conventional asphalt production amounts to (Nizamuddin et al., 2020) [58] (Jessica et al., 2023) [59].

HDPE-modified asphalt economically reduces costs in locations where HDPE waste is plentiful and disposal costs are high. However, some problems still exist; for instance, the consistency of recycled HDPE properties depends on the source of the material. The mechanical performance of HDPE-modified binders can be affected by melting temperature, density, and contamination level variability. However, standardization in recycling processes and quality control in HDPE recycling materials are necessary for its reliable use in asphalt pavements (Alghrafi et al., 2021) [4].

4.7. Recycled Polystyrene (PS)

Asphalt pavements modified with recycled polystyrene (PS), sourced primarily from packaging and disposable products, exhibit promise of modifying asphalt due to its rigidity and comparatively high melting point. Secondly, the use of PS in asphalt leads to improvements in road durability and a reduction in maintenance costs; thus, ESL is an attractive solution for high-traffic roads. Zhu et al. (2014) [37] studied the possible use of PS as a modifier that improves bitumen matrix stability, thus improving the resistance of the pavement to thermal variations and deformation (Zhu et al., 2014) [37].

4.7.1. Aging and Rutting Resistance

PS is offered as one of the notable benefits of PS in asphalt modification because PS contributes to aging resistance. The improved oxidation resistance of PS-modified asphalt has been shown to help prevent early cracking and reduce pavement maintenance. One example, as seen by Zhu et al., is that PS increases the material's stiffness at high temperatures, reducing the effect of oxidative aging on the asphalt binder (Zhu et al., 2014) [37]. Table 5 illustrates the summary of the major findings of PS-modified bitumen.

Table 5. Summary of the major findings of PS-modified bitumen.

Binder Grade	PS%	Tests Conducted	Main Findings	Reference
50/70	2%, 4%, 6%, 8%	Penetration tests, ductility test, softening point test, flash point tests, and specific gravity tests	- Adding EPS showed lower penetration values and ductility, directly showing the rutting resistance enhancement. - The softening point was not significantly affected by adding EPS. - The indicated flash point improvement improves safety during transporting and storage. - When considering the correlation between ductility and the softening point, it was indicated that EPS improves the thermal and mechanical behavior of the mixture. Adding EPS increases the specific gravity, which enhances long-term durability and aging resistance.	(Yildiz et al., 2021) [65]
VG 10	0.5%, 1.0%, 1.5%, 2.0%	Penetration test, softening point test, viscosity test, dynamic shear rheometer (DSR) test, multiple stress creep recovery (MSCR) test, Marshall's stability test, Fourier transform infrared spectroscopy (FT-IR) test, and field emission scanning electron microscopy (FE-SEM) with EDAX	- PS-modified bitumen showed a higher shear value, which indicated improved rutting resistance. - According to MSCR, the elastic properties of the PS-modified bitumen have improved. - According to DSR analysis, the results of the rutting and fatigue data are in a satisfactory condition after aging. - The Marshal stability test indicated improved values in PS-modified bitumen, which positively affected its deformation resistance.	(Mahida et al., 2021) [66]
60/70	2%, 3%, 4%, 5%, 6%	Penetration tests, softening point tests, viscosity tests, Marshal's stability tests, optical microscopy (OM), and thermal gravimetric analysis (TGA)	- The decreased penetration values and increased softening point values indicated better rutting and aging resistance of the PS-modified bitumen. - Increased viscosity values confirmed the enhancement of the rutting resistance of the PS modification. Higher values of Marshal's stability test results indicated the better load-bearing capacity of the PS-modified bitumen.	(Nassar et al., 2012) [67]

Table 5. Cont.

Binder Grade	PS%	Tests Conducted	Main Findings	Reference
50/70	1%, 2%	Rutting tests, compatibility tests, dynamic modulus tests, fatigue tests, and Cantabro Test	- The rutting tests show a significant reduction in plastic deformation in PS-substituted bitumen. - The PS modification provided extra rigidity for the mixture. - PS-substituted bitumen showed higher percentages of voids, which improved the performance characteristics.	(Vila-Cortavitarte et al., 2017) [68]
60/70	5%, 10%, 15%	Penetration test, ductility test, float test, softening point test, and specific gravity	- The PS content beyond the 10% modified bitumen shows increased stiffness, which leads to rutting resistance. - The viscosity of the PS-modified bitumen increased with PS content. - The softening point values increased with the PS content. - PS-modified bitumen showed higher specific gravity, up to 10% of the PS content.	(Abinaya et al., 2016) [69]

This stiffening effect is desirable in areas that get warmer because standard asphalt tends to age and soften faster. Although appropriate, high PS content could lower temperature flexibility significantly below room temperature, indicating that optimal PS content is needed to achieve balanced performance. It demonstrates that PS modification of asphalt greatly reduces the amount of rutting, a critical issue in asphalt pavements subjected to heavy traffic. PS raises the stiffness of the asphalt binder and causes permanent deformation under prolonged loading conditions. Zhu et al. [37] suggested that the rutting resistance is improved by about 15% relative to unmodified asphalt when PS is incorporated at 3 to 5% weight (Zhu et al., 2014) [37]. By modifying this, rutting is minimized, and PS-modified asphalt is suitable for highways undergoing heavy traffic and in extreme temperature regions. In addition, the rigidity of PS maintains the integrity of the pavement structure, helping to resist rutting.

4.7.2. Environmental and Economic Benefits and Challenges

Higher benefits, from an environmental and economic standpoint, are found in using recycled PS in pavement materials. The result is that this approach reduces plastic waste and diverts it from landfills, bringing environmental sustainability to this process. PS-modified asphalt has improved durability, prolonged the pavement's life cycle, and economically reduced road maintenance costs. Despite this, challenges exist, such as inconsistent quality of recycled PS, which can result in variations in pavement performance. PS is also non-biodegradable, so recycling the pavement as it approaches the end of its life cycle is a challenge. However, PS is an applicable asphalt modifier as long as quality control is exercised (Zhu et al., 2014) [37].

4.8. Waste Cooking Oil (WCO)

As one of the byproducts of domestic and industrial food preparation, waste cooking oil (WCO) shows potential as a recycled asphalt pavement additive. Like petroleum-based

binders, WCO's organic composition allows it to act as a rejuvenator for reclaimed asphalt pavements (RAPs) (Jain & Chandrappa, 2023a) [70]. This role employs both environmental concerns related to the disposal of WCO and the demand for sustainable road materials. The studies indicate that WCO can reduce binder viscosity and enable better blending with aged asphalt to provide better pavement flexibility and durability (Jain & Chandrappa, 2023) [70] (Xu et al., 2023) [71].

4.8.1. Aging and Rutting Resistance

There is much published data on WCO's effectiveness in improving the aging resistance of asphalt. It replaces lost essential oils that tend to oxidize and other environmental factors and reduces stiffness that happens in old binders. Adding 6% WCO to asphalt reduced the asphaltene-to-maltene ratio—an indicator of asphalt aging—by more than 20% compared to untreated asphalt (Jain & Chandrappa, 2023b) [72]. Furthermore, WCO-modified binders in mixtures with high RAP content generally showed reduced long-term stiffness and retained flexibility under various aging conditions, indicating increased service life. Maltenes present in WCO counteract aging effects in binders containing up to 7% WCO, as indicated by Jain and Chandrappa (2023b) [72]. Despite this, WCO enhances aging resistance, while its effects on rutting are nontrivial. Table 6 illustrates the summary of the major findings of WCO-modified bitumen.

Table 6. Summary of the major findings of WCO-modified bitumen.

Binder Grade	WCO%	Tests Conducted	Main Findings	Reference
60/70	3%, 4%, 5%	Rolling thin-film oven test (RTFOT), dynamic shear rheometer (DSR) test, and one-way analysis of variance (ANOVA)	- The rutting resistance of the WCO-modified bitumen decreased as the temperature increased - The binder modified with treated WCO indicated better rutting resistance than the untreated WCO. - Also, the treated binder with treated WCO has a higher softening point. - Aged WCO-modified binders show increases in failure temperatures that lead to enhanced rutting resistance.	(Nordiana et al., 2019) [23]
60/70	1.5%, 3%, 4.5%	Rolling thin-film oven test (RTFOT), flash and fire point test, penetration and softening point tests, viscosity test, and dynamic shear rheometer (DSR)	- By increasing the WCO content, the penetration depth increased, and the softening point decreased. - The viscosity results indicated that WCO-modified binders were more workable. - When using up to 3% of the WCO content, the viscosity and DSR test results were in a better condition.	(Ali, 2022) [73]

Table 6. Cont.

Binder Grade	WCO%	Tests Conducted	Main Findings	Reference
PG 64-10 and VG30	3%, 5%	Dynamic shear rheometer (DSR), frequency sweep test, and multiple stress creep recovery (MSCR) test	- Adding WCO to the binder indicated lower short-term aging conditions. - Adding more WCO shows an increase in viscose strain, which can lead to permanent deformation. - The optimal WCO content for PG64-10 and VG30 was found to be 3% and 5%. - Adding WCO improves the creep recovery behavior up to the optimum percentage.	(Jain et al., 2023c) [74]
85/100	2, 3, 4, 5, and 7%	Indirect tensile asphalt cracking test (IDEAL-CT), high-temperature indirect tensile (High-IDT), and rutting assessment test	- Adding WCO increased the softening and flexibility of the material. - Increasing the content of the WCO led to a decrease in rutting resistance. - Adding WCO increases the cracking resistance. - WCO is recommended as a rejuvenator in the asphalt mixture.	(Alkuime et al., 2024) [75]
60/70	0%, 3%, 4%, and 5%	Acid value test, bitumen performance test, rolling thin-film oven (RTFO), Fourier transform infrared (FTIR)	- Adding chemically treated WCO to the binder decreased the penetration value and increased the softening point value and viscosity, thereby enhancing rutting and aging resistance. - Adding treated WCO resulted in better rheological performance. - The bonding between the treated WCO and binder particles is in a stronger condition.	(Azahar, Jaya et al., 2016) [76]

High WCO content may lower rutting resistance by softening the asphalt. Studies by Jain and Chandrappa (2023a,b) [70,72] have found that the WCO concentration is optimal at 3–5%, balancing flexibility and resistance while retaining rutting performance among conventionally tackified asphalt. However, WCO-modified asphalt may be prone to deformation under high loads and temperatures in areas where sunlight is very concentrated (Xu et al., 2023) [71]. Accordingly, a lower dosage, below 5%, is probably optimum to slow rut resistance without compromising flexibility.

4.8.2. Environmental and Economic Benefits and Challenges

The benefits of the use of WCO in asphalt for the environment are substantial. By modifying the WCO, each kilometer of WCO-modified pavement would be able to re-purpose hundreds of kilos of waste oil by mitigating its harmful environmental impact. On the economic side, the WCO system offers savings by reducing our dependence on virgin petroleum-based binders because they are prepared from industrial waste products. However, issues such as variability in pavement WCO quality can result in inconsistent

pavement performance. Furthermore, WCO is to be refined to reduce impurities in WCO, such as fatty acids and water, in order to continue the effectiveness of WCO as a rejuvenator (Xu et al., 2023) [71] (Jain & Chandrappa, 2023a,b) [70,72].

5. Conclusions

The research paper on recycled polymer-modified pavement materials discusses the complexities of pavement performance and sustainability using different bitumen modifiers. This study systematically looked at bitumen's chemical and physical properties, environmental and regulatory challenges, and bitumen modifications to increase resistance to rutting and aging. The research focused on recycled materials, including crumb rubber, styrene–butadiene–styrene (SBS), polypropylene (PP), polyethylene terephthalate (PET), and waste cooking oil (WCO), highlighting the advantages and disadvantages associated with each material's use in pavement applications.

They find that crumb rubber and SBS modifiers can improve elasticity and recovery, reducing pavement deformation in heavy traffic and under adverse weather. Results from laboratory tests prove that the pavement undergoes longer-lasting rutting and fatigue resistance. The study also points out the environmental advantages of recycling polymers, such as lowering greenhouse gases and reducing landfill waste.

While these benefits may exist, challenges remain, such as material incompatibility, storage instability, and the economic feasibility of large-scale implementation. Overall, this review presents recommendations for continued innovation in bitumen modification and suggestions for optimizing recycled polymers in pavement materials to achieve durable, sustainable infrastructure.

Author Contributions: Project leader and supervision, N.S.M.; writing—original draft, N.S.M. and C.D.; data analysis, C.D.; review and editing, C.D. and N.S.M.; resources and validation, N.S.M.; funding, N.S.M. All authors have read and agreed to the published version of the manuscript.

Funding: This review paper received no external funding.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: No new data were created or analyzed in this study. Data sharing is not applicable to this article.

Acknowledgments: Guidance and support received from the school of engineering at Edith Cowan University is highly acknowledged.

Conflicts of Interest: The authors declare no conflicts of interest.

References

1. Ali, A.H.; Mashaan, N.S.; Karim, M.R. Investigations of physical and rheological properties of aged rubberised bitumen. *Adv. Mater. Sci. Eng.* **2013**, *1*, 239036. [CrossRef]
2. Anusha, T.M.; Jagadeesh, H.S. Performance evaluation of crumb rubber modified bitumen on binder course of stone mastic asphalt mix. *Int. J. Eng. Res. Technol.* **2021**, *10*. [CrossRef]
3. Buchagul, J. Performance Evaluation of the Crumb Rubber-Modified Bitumen Containing Warm-Mix Additives. 2019. Available online: <https://repository.tudelft.nl/islandora/object/uuid:79b491fb-7ce7-4950-9f36-df2bd120f02b/datastream/OBJ/download> (accessed on 25 March 2025).
4. Alghrafi, Y.M.; Abd Alla, E.-S.M.; El-Badawy, S.M. Rheological properties and aging performance of sulfur extended asphalt modified with recycled polyethylene waste. *Constr. Build. Mater.* **2021**, *273*, 121771. [CrossRef]
5. Ansar, M.; Sikandar, M.A.; Althoey, F.; Tariq, M.A.U.R.; Alyami, S.H.; Elkhatib, S.E. Rheological, aging, and microstructural properties of polycarbonate and polytetrafluoroethylene modified bitumen. *Polymers* **2022**, *14*, 3283. [CrossRef] [PubMed]
6. Holý, M.; Remišová, E. Analysis of influence of bitumen composition on the properties represented by empirical and viscosity test. *Transp. Res. Procedia* **2019**, *40*, 34–41. [CrossRef]

7. Zahedi, M. General Properties of Bitumen—Infinity Galaxy. Infinity Galaxy. Available online: <https://infinitygalaxy.org/bitumen-properties/> (accessed on 30 March 2024).
8. De Carteret, R.; Comport, L.; Metcalf, J.; Rebbechi, J. Guide to Pavement Technology: Part 8: Pavement Construction. 2019. Available online: <https://austroroads.com.au/publications/pavement/agpt11> (accessed on 25 March 2025).
9. Polo-Mendoza, R.; Martinez-Arguelles, G.; Walubita, L.F.; Moreno-Navarro, F.; Giustozzi, F.; Fuentes, L.; Navarro-Donado, T. Ultraviolet ageing of bituminous materials: A comprehensive literature review from 2011 to 2022. *Constr. Build. Mater.* **2022**, *350*, 128889. [\[CrossRef\]](#)
10. Wang, X.; Guo, H.; Yang, B.; Chang, X.; Wan, C.; Wang, Z. Aging Characteristics of Bitumen from Different Bituminous Pavement Structures in Service. *Materials* **2019**, *12*, 530. [\[CrossRef\]](#)
11. Tauste, R.; Moreno-Navarro, F.; Sol-Sánchez, M.; Rubio-Gámez, M.C. Understanding the bitumen ageing phenomenon: A review. *Constr. Build. Mater.* **2018**, *192*, 593–609. [\[CrossRef\]](#)
12. Yahaya, A.S.; Yusoff, N.I.M.; Hamzah, M.O.; Abdullah, N.H. Effects of laboratory Short-Term ageing on Bitumen Properties. European Proceedings of Multidisciplinary Sciences. *Eur. Proc. Multidiscip. Sci.* **2019**, *2*, 1–882. [\[CrossRef\]](#)
13. Jiang, W.; Bao, R.; Lu, H.; Yuan, D.; Lu, R.; Sha, A.; Shan, J. Analysis of rheological properties and aging mechanism of bitumen after short-term and long-term aging. *Constr. Build. Mater.* **2021**, *273*, 121777. [\[CrossRef\]](#)
14. Hofko, B.; Cannone Falchetto, A.; Grenfell, J.; Huber, L.; Lu, X.; Porot, L.; Poulikakos, L.D.; You, Z. Effect of short-term ageing temperature on bitumen properties. *Road Mater. Pavement Des.* **2017**, *18*, 108–117. [\[CrossRef\]](#)
15. Lu, X.; Talon, Y.; Redelius, P. Aging of Bituminous Binders—Laboratory Tests and Field Data. In Proceedings of the 4th Eurasphalt Eurobitume Congress, Denmark, Copenhagen, 21–23 May 2008. [\[CrossRef\]](#)
16. Hofer, K.; Werkovits, S.; Schönauer, P.; Mirwald, J.; Grothe, H.; Hofko, B. Chemical and mechanical analysis of field and laboratory aged bitumen. *Road Mater. Pavement Des.* **2023**, *24*, 160–175. [\[CrossRef\]](#)
17. Pan, Y.; Guo, H.; Guan, W.; Zhao, Y. A laboratory evaluation of factors affecting rutting resistance of asphalt mixtures using wheel tracking test. *Case Stud. Constr. Mater.* **2023**, *18*, e02148. [\[CrossRef\]](#)
18. Sinanmis, R.; Woods, L. Traffic channelisation and pavement deterioration: An investigation of the role of lateral wander on asphalt pavement rutting. *Int. J. Pavement Eng.* **2022**, *24*, 2118272. [\[CrossRef\]](#)
19. Radhakrishnan, V.; Sri, M.R.; Reddy, K.S. Evaluation of asphalt binder rutting parameters. *Constr. Build. Mater.* **2018**, *173*, 298–307. [\[CrossRef\]](#)
20. Celoglu, M.E.; Yalçın, E.; Kök, B.V.; Alataş, T.; Norambuena-Contreras, J.; García, Á.; Yılmaz, M. Effects of different bitumen modifiers on the rutting and cracking resistance of hot mix asphalts. *Int. J. Pavement Eng.* **2018**, *21*, 703–712. [\[CrossRef\]](#)
21. Olabemiwo, O.M.; Esan, A.O.; Bakare, H.O.; Agunbiade, F.O. Polymer modified-natural bitumen thermal aging resistance studies. *Int. J. Pavement Eng.* **2017**, *20*, 1207–1215. [\[CrossRef\]](#)
22. Gokalp, İ.; Uz, V.E. Sustainable production of Aging-Resistant bitumen: Waste engine oil modification. *J. Transp. Eng.* **2021**, *147*, 04021055. [\[CrossRef\]](#)
23. Nordiana, M.; Wan Nur Aifa, W.A.; Hainin, M.R.; Muhammad Naquiuddin, M.W.; Norhidayah, A.H.; Haryati, Y.; Juraidah, A.; Rmadhansyah, P.J. Rutting resistance of untreated and treated waste cooking oil in bitumen after aging condition. In Proceedings of the IOP Conference Series: Earth and Environmental Science, National Colloquium on Wind & Earthquake Engineering, Kuantan, Malaysia, 17–18 August 2018; p. 244. [\[CrossRef\]](#)
24. Lin, H.; Chen, Q.; Luo, X.; Zhang, Y.; Miao, K.; Tan, L.; Wang, K. Characterization of rheological properties and aging performance of bitumen modified by bio-oil from bamboo charcoal production. *J. Clean. Prod.* **2022**, *338*, 130678. [\[CrossRef\]](#)
25. Mashaan, N.S.; Karim, M.R. Investigating the rheological properties of crumb rubber modified bitumen and its correlation with temperature susceptibility. *Mater. Res.* **2012**, *16*, 116–127. [\[CrossRef\]](#)
26. Mashaan, N.S.; Ali, A.H.; Karim, M.R.; Abdelaziz, M. An overview of crumb rubber modified asphalt. *Int. J. Phys. Sci.* **2012**, *7*, 166–170. [\[CrossRef\]](#)
27. Korycki, L. Recycled Rubber Road Project Reveals Environmental and Economic Benefits. Waste Management Review. Available online: <https://wastemanagementreview.com.au/recycled-rubber-road-project-reveals-environmental-economic-benefits/> (accessed on 2 May 2024).
28. Jamal, M.; Giustozzi, F. Low-content crumb rubber modified bitumen for improving Australian local road conditions. *J. Clean. Prod.* **2020**, *271*, 122484. [\[CrossRef\]](#)
29. Ibrahim, M.R.; Katman, H.Y.; Karim, M.R.; Koting, S.; Mashaan, N.S. A review on the effect of crumb rubber addition to the rheology of crumb rubber modified bitumen. *Adv. Mater. Sci. Eng.* **2013**, *2013*, 415246. [\[CrossRef\]](#)
30. Wang, H.; Liu, X.; Apostolidis, P.; Van De Ven, M.; Erkens, S.; Skarpas, A. Effect of laboratory aging on chemistry and rheology of crumb rubber modified bitumen. *Mater. Struct.* **2020**, *53*, 1–26. [\[CrossRef\]](#)
31. Irfan, M.; Ali, Y.; Ahmed, S.; Hafeez, I. Performance evaluation of crumb Rubber-Modified asphalt mixtures based on laboratory and field investigations. *Arab. J. Sci. Eng.* **2017**, *43*, 1795–1806. [\[CrossRef\]](#)

32. Gohar, M.; Ahmad, N.; Haroon, W. Effect of Addition of Crumb Rubber on Bitumen Performance Grade (PG) and Rutting Resistance. ResearchGate. Available online: <https://www.researchgate.net/publication/360163386> (accessed on 25 March 2025).
33. Riekstins, A.; Haritonovs, V.; Straupe, V. Economic and environmental analysis of crumb rubber modified asphalt. *Constr. Build. Mater.* **2022**, *335*, 127468. [\[CrossRef\]](#)
34. Denneman, E.; Lee, J.; Raymond, C.; Choi, Y.; Yean Khoo, K.; Dias, M. P31 and P32 Optimising the Use of Crumb Rubber Modified Bitumen in Seals and Asphalt. Queensland Department of Transport and Main Roads Disclaimer. 2015. Available online: https://nacoe.com.au/wp-content/uploads/2017/10/P31-P32-Optimising-the-use-of-crumb-rubber_Yr1-2014-15-Final.pdf (accessed on 25 March 2025).
35. Piao, Z.; Bueno, M.; Mikhailenko, P.; Kakar, M.R.; Biondini, D.; Poulikakos, L.; Hellweg, S. *Life Cycle Assessment of Asphalt Pavements Using Crumb Rubber: A Comparative Analysis*; Rilem Bookseries; Springer International Publishing: New York, NY, USA, 2021; pp. 1281–1287. [\[CrossRef\]](#)
36. Farina, A.; Zanetti, M.; Santagata, E.; Blengini, G.A.; Lanotte, M.A. Life Cycle Assessment of Road Pavements Containing Crumb Rubber from End-of-Life Tires. Department of Environment, Land and Infrastructure Engineering, Politecnico Di Torino. 2014. Available online: <https://iris.polito.it/handle/11583/2582944> (accessed on 25 March 2025).
37. Zhu, J.; Birgisson, B.; Kringos, N. Polymer modification of bitumen: Advances and challenges. *Eur. Polym. J.* **2014**, *54*, 18–38. [\[CrossRef\]](#)
38. Hassanpour-Kasanagh, S.; Ahmedzade, P.; Fainleib, A.M.; Behnood, A. Rheological properties of asphalt binders modified with recycled materials: A comparison with Styrene-Butadiene-Styrene (SBS). *Constr. Build. Mater.* **2020**, *230*, 117047. [\[CrossRef\]](#)
39. Yang, Q.; Lin, J.; Wang, X.; Wang, D.; Xie, N.; Shi, X. A review of polymer-modified asphalt binder: Modification mechanisms and mechanical properties. *Clean. Mater.* **2024**, *12*, 100255. [\[CrossRef\]](#)
40. Wei, H.; Bai, X.; Qian, G.; Wang, F.; Li, Z.; Jin, J.; Zhang, Y. Aging Mechanism and Properties of SBS Modified Bitumen under Complex Environmental Conditions. *Materials* **2019**, *12*, 1189. [\[CrossRef\]](#)
41. Ma, Q.; Jin, Y.; He, H.; Yu, W.; Xu, J.; Xu, Q.; Xue, J.; Wang, R.; Cui, C.; Ma, J.; et al. Simulation and investigation of the mild-moderate aging properties of SBS modified bitumen: Physical, microscopic and rheological properties. *Constr. Build. Mater.* **2024**, *449*, 138428. [\[CrossRef\]](#)
42. Laukkanen, O.; Soenen, H.; Winter, H.H.; Seppälä, J. Low-temperature rheological and morphological characterization of SBS modified bitumen. *Constr. Build. Mater.* **2018**, *179*, 348–359. [\[CrossRef\]](#)
43. Kaya, D.; Topal, A.; Gupta, J.; McNally, T. Aging effects on the composition and thermal properties of styrene-butadiene-styrene (SBS) modified bitumen. *Constr. Build. Mater.* **2019**, *235*, 117450. [\[CrossRef\]](#)
44. Nizamuddin, S.; Boom, Y.J.; Giustozzi, F. Sustainable Polymers from Recycled Waste Plastics and Their Virgin Counterparts as Bitumen Modifiers: A Comprehensive Review. *Polymers* **2021**, *13*, 3242. [\[CrossRef\]](#) [\[PubMed\]](#)
45. Salehi, S.; Arashpour, M.; Kodikara, J.; Guppy, R. Sustainable pavement construction: A systematic literature review of environmental and economic analysis of recycled materials. *J. Clean. Prod.* **2021**, *313*, 127936. [\[CrossRef\]](#)
46. Usman, I.U.; Kunlin, M. Influence of Polyethylene Terephthalate (PET) utilization on the engineering properties of asphalt mixtures: A review. *Constr. Build. Mater.* **2024**, *411*, 134439. [\[CrossRef\]](#)
47. Mushtaq, F.; Huang, Z.; Shah, S.A.R.; Zhang, Y.; Gao, Y.; Azab, M.; Hussain, S.; Anwar, M.K. Performance Optimization Approach of Polymer Modified Asphalt Mixtures with PET and PE Wastes: A Safety Study for Utilizing Eco-Friendly Circular Economy-Based SDGs Concepts. *Polymers* **2022**, *14*, 2493. [\[CrossRef\]](#)
48. Maharaj, R.; Maharaj, C.; Mahase, M. The performance and durability of polyethylene terephthalate and crumb rubber-modified road pavement surfaces. *Progress Rubber Plast. Recycl. Technol.* **2018**, *35*, 3–22. [\[CrossRef\]](#)
49. Mashaan, N.S. Engineering Characterisation of Wearing Course Materials Modified with Waste Plastic. *Recycling* **2022**, *7*, 61. [\[CrossRef\]](#)
50. Mashaan, N.S. Engineering Properties of Waste Plastic and Nanomaterials Modified Asphalt Mixtures. *J. Harbin Eng. Univ.* **2023**, *44*, 1319–1324.
51. Mashaan, N.S. Waste Plastic in Concrete: Review and State of the Art. *Nanotechnol. Percept.* **2024**, *20*, 594–612. [\[CrossRef\]](#)
52. Singh, A.; Gupta, A. Mechanical and economical feasibility of LDPE Waste-modified asphalt mixtures: Pathway to sustainable road construction. *Sci. Rep.* **2024**, *14*, 25311. [\[CrossRef\]](#)
53. Li, H.; Han, Y.E.; Guangxun Sun, Y.; Wang, L.; Liu, X.; Ren, J.; Lin, Z. Recycling of waste polyethylene in asphalt and its performance enhancement methods: A critical literature review. *J. Clean. Prod.* **2024**, *451*, 142072. [\[CrossRef\]](#)
54. Ullah, S.; Qabur, A.; Ullah, A.; Aati, K.; Abdelgiom, M.A. Enhancing High-Temperature Performance of Flexible Pavement with Plastic-Modified Asphalt. *Polymers* **2024**, *16*, 2399. [\[CrossRef\]](#) [\[PubMed\]](#)
55. Bensaada, A.; Soudani, K.; Haddadi, S. Effects of short-term aging on the physical and rheological properties of plastic waste-modified bitumen. *Innov. Infrastruct. Solut.* **2021**, *6*, 1–12. [\[CrossRef\]](#)
56. Ahmedzade, P.; Fainleib, A.; Günay, T.; Starostenko, O.; Kovalinska, T. Effect of Gamma-Irradiated recycled Low-Density polyethylene on the High- and Low-Temperature properties of bitumen. *Int. J. Polym. Sci.* **2013**, *1*, 1–9. [\[CrossRef\]](#)

57. Genet, M.B.; Sendekie, Z.B.; Jembere, A.L. Investigation and optimization of waste LDPE plastic as a modifier of asphalt mix for highway asphalt: Case of Ethiopian roads. *Case Stud. Chem. Environ. Eng.* **2021**, *4*, 100150. [[CrossRef](#)]
58. Nizamuddin, S.; Jamal, M.; Gravina, R.; Giustozzi, F. Recycled plastic as bitumen modifier: The role of recycled linear low-density polyethylene in the modification of physical, chemical and rheological properties of bitumen. *J. Clean. Prod.* **2020**, *266*, 121988. [[CrossRef](#)]
59. da Silva AJ, R.; de Figueiredo Lopes Lucena, A.E.; de Medeiros Melo Neto, O.; Mendonça AM, G.D.; Costa, D.B.; de Lima RK, B. Effects of using waste high-density polyethylene on the rheological, mechanical, and thermal performance of asphalt materials. *Environ. Dev. Sustain.* **2024**, *26*, 16683–16710. [[CrossRef](#)]
60. Nejad, F.M.; Gholami, M.; Naderi, K.; Rahi, M. Evaluation of rutting properties of high density polyethylene modified binders. *Mater. Struct.* **2014**, *48*, 3295–3305. [[CrossRef](#)]
61. Piromanski, B.; Chegenizadeh, A.; Mashaan, N.; Nikraz, H. Study on HDPE effect on rutting resistance of Binder. *Buildings* **2020**, *10*, 156. [[CrossRef](#)]
62. Ibrahim, A.A. Laboratory investigation of aged HDPE-modified asphalt mixes. *Int. J. Pavement Res. Technol.* **2019**, *12*, 364–369. [[CrossRef](#)]
63. Köfteci, S. Effect of HDPE based wastes on the performance of modified asphalt mixtures. *Procedia Eng.* **2016**, *161*, 1268–1274. [[CrossRef](#)]
64. Xiao, R.; Zhang, M.; Zhong, J.; Baumgardner, G.L.; Huang, B. Waste Plastic Powder Coating on Acidic Aggregates: A New Hydrophobic Coating Technology to Build Moisture-Resistant Asphalt Mixtures. *Transp. Res. Rec.* **2023**. [[CrossRef](#)]
65. Yildiz, K.; Kinaci, H.; Atakan, M. Modification of Asphalt Binder with Waste Expanded Polystyrene (EPS) Foam. *Celal Bayar Üniversitesi Fen Bilim. Derg.* **2021**, *17*, 245–252. [[CrossRef](#)]
66. Mahida, S.; Shah, Y.U.; Sharma, S. Analysis of the influence of using waste polystyrene in virgin bitumen. *Int. J. Pavement Res. Technol.* **2021**, *15*, 626–639. [[CrossRef](#)]
67. Nassar, I.M.; Kabel, K.I.; Ibrahim, I.M. Evaluation of the Effect of Waste Polystyrene on Performance of Asphalt Binder. *ARPJ. Sci. Technol.* **2012**, *2*, 927–935. Available online: <https://www.researchgate.net/publication/265423167> (accessed on 25 March 2025).
68. Vila-Cortavitate, M.; Lastra-González, P.; Calzada-Pérez, M.Á.; Indacoechea-Vega, I. Analysis of the influence of using recycled polystyrene as a substitute for bitumen in the behaviour of asphalt concrete mixtures. *J. Clean. Prod.* **2017**, *170*, 1279–1287. [[CrossRef](#)]
69. Abinaya, S.; Clement, M.; Shunmugam, S. An experimental study on the properties of extruded Polystyrene waste polymer modified bitumen for flexible pavements. *Int. Res. J. Eng. Technol.* **2016**, *3*, 304–308. Available online: <https://www.academia.edu/download/54548347/IRJET-V3I6462.pdf> (accessed on 25 March 2025).
70. Jain, S.; Chandrappa, A.K. A laboratory investigation on benefits of WCO utilisation in asphalt with high recycled asphalt content: Emphasis on rejuvenation and aging. *Int. J. Pavement Eng.* **2023**, *24*, 2172577. [[CrossRef](#)]
71. Xu, N.; Wang, H.; Wang, H.; Kazemi, M.; Fini, E.H. Research progress on resource utilization of waste cooking oil in asphalt materials: A state-of-the-art review. *J. Clean. Prod.* **2023**, *385*, 135427. [[CrossRef](#)]
72. Jain, S.; Chandrappa, A.K. Critical review on waste cooking oil rejuvenation in asphalt mixture with high recycled asphalt. *Environ. Sci. Pollut. Res.* **2023**, *30*, 77981–78003. [[CrossRef](#)] [[PubMed](#)]
73. Ali, A.M. Investigation physical and rheological properties of bio-asphalt containing waste cooking oil. *IOP Conf. Ser. Earth Environ. Sci.* **2022**, *971*, 012010. [[CrossRef](#)]
74. Jain, S.; Dabbiru, S.; Chandrappa, A.K. Effects of waste cooking oil on the antiageing ability of bitumen. *Adv. Civ. Eng.* **2023**, *2023*, 5155407. [[CrossRef](#)]
75. Alkuime, H.; Kassem, E.; Alshraiedeh, K.A.; Bustanji, M.; Aleih, A.; Abukhamseh, F. Performance Assessment of waste Cooking Oil-Modified Asphalt Mixtures. *Appl. Sci.* **2024**, *14*, 1228. [[CrossRef](#)]
76. Azahar, W.N.A.W.; Jaya, R.P.; Hainin, M.R.; Bujang, M.; Ngadi, N. Chemical modification of waste cooking oil to improve the physical and rheological properties of asphalt binder. *Constr. Build. Mater.* **2016**, *126*, 218–226. [[CrossRef](#)]

Disclaimer/Publisher’s Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.