

Review

# Exigency for the Control and Upgradation of Indoor Air Quality—Forefront Advancements Using Nanomaterials

Ayesha Kausar <sup>1,2,3,\*</sup>, Ishaq Ahmad <sup>1,2,3</sup>, Tianle Zhu <sup>4</sup>, Hassan Shahzad <sup>3</sup> and M. H. Eisa <sup>5</sup>

<sup>1</sup> NPU-NCP Joint International Research Center on Advanced Nanomaterials and Defects Engineering, Northwestern Polytechnical University, Xi'an 710072, China

<sup>2</sup> UNESCO-UNISA Africa Chair in Nanosciences/Nanotechnology, iThemba LABS, Somerset West 7129, South Africa

<sup>3</sup> NPU-NCP Joint International Research Center on Advanced Nanomaterials and Defects Engineering, National Centre for Physics, Islamabad 44000, Pakistan

<sup>4</sup> School of Space and Environment, Beihang University, Beijing 100191, China

<sup>5</sup> Department of Physics, College of Science, Imam Mohammad Ibn Saud Islamic University (IMSIU), Riyadh 13318, Saudi Arabia

\* Correspondence: dr.ayeshakauser@yahoo.com

**Abstract:** Due to increasing health and environmental issues, indoor air quality (IAQ) has garnered much research attention with regard to incorporating advanced clean air technologies. Various physicochemical air treatments have been used to monitor, control, and manage air contaminants, such as monitoring devices (gas sensors and internet of things-based systems), filtration (mechanical and electrical), adsorption, UV disinfection, UV photocatalysts, a non-thermal plasma approach, air conditioning systems, and green technologies (green plants and algae). This article reviews presently viable technologies for cleaning indoor air and enhancing IAQ. However, regarding the integration of each technology, there are certain limitations to these methods, including the types of pollutants released. As a result, advanced nanomaterials have been applied to monitoring sensors, filtration and adsorption media, and UV photocatalysts to improve IAQ values. The most important nanomaterials used in this regard include polymeric nanofibrous membranes, nanoporous nanomaterials, nanocomposite hydrogels, polymer/nanocarbon nanocomposite, polymer/metal oxide nanocomposite, polymeric nanohybrids, etc. Accordingly, through the use of nanotechnology, optimal solutions linking IAQ regulation techniques to novel nanomaterials can be achieved to attain safe IAQ levels.

**Keywords:** indoor air quality; pollutants; filtration; sensors; UV disinfection; non-thermal plasma; nanomaterials; membranes; polymeric nanocomposite; nanohybrid

**Citation:** Kausar, A.; Ahmad, I.; Zhu, T.; Shahzad, H.; Eisa, M.H. Exigency for the Control and Upgradation of Indoor Air Quality—Forefront Advancements Using Nanomaterials. *Pollutants* **2023**, *3*, 123–148. <https://doi.org/10.3390/pollutants3010011>

Academic Editor: Pedro Branco

Received: 10 January 2023

Revised: 6 February 2023

Accepted: 8 February 2023

Published: 14 February 2023




**Copyright:** © 2023 by the author. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

## 1. Introduction

The indoor environmental conditions of buildings and houses greatly affect human health [1]. According to the World Health Organization (WHO), indoor air pollution may affect ~4–5 million people per year [2]. Most urban humans spend ~90% of their time indoors [3]. Therefore, the effect of indoor air environments on human health is obvious. Common sources of indoor air pollution include cooking, heating, smoking, garages, cleaning, electronic machines, outdoor air, and other human activities. Harmful indoor air pollutants include oxides of carbon, nitrogen, and sulfur; volatiles; particulates; aerosols; biological pollutants; and many more [4] (Figure 1). Indoor air pollution can lead to a range of physical illnesses, including cardiac, respiratory, nervous system, and even cancer-related diseases [5–7]. Consequently, indoor air quality (IAQ) monitoring, control, and management are considered important for preventing the related potential health risks [8]. The measurement of indoor pollutant concentration has been considered to be a crucial strategy for controlling and enhancing IAQ. It is also vital to determine the sources

of indoor air pollution to ensure total eradication. The relationships between indoor pollutants and health risks and health effects have been found to be significant enough to justify adopting suitable remediation strategies.



**Figure 1.** Common pollutants and sources in indoor air.

This paper presents a state-of-the-art review focusing on the essential indoor pollutants, the fundamentals of indispensable IAQ control and monitoring technologies, and the implementation of advanced nanomaterials in these technologies to develop a promising solution. To the best of our knowledge, such a comprehensive review linking indoor air control/management to advanced nanomaterials has not been reported before. Recent trending strategies for controlling and monitoring IAQ involve the use of an advanced nanomaterial in the sensing systems, filtration and adsorption media, and UV photocatalysts, as discussed in this review. The nanomaterials, nanofibrous membranes, nanoporous nanomaterials, hydrogels, nanohybrids, polymer/nanocarbon nanocomposite, polymer/metal oxide nanocomposite, etc. discussed here have been designed to reduce indoor pollutant concentrations for better IAQ. The future of IAQ control/monitoring relies on innovative, nanomaterial-based sensing systems, filtration/adsorption systems, and UV photocatalysts to eradicate indoor air pollutants. Thus, this novel review highlights the current situation regarding indoor pollutants, their health effects, and IAQ monitoring strategies. Consequently, the key pollutants, their health effects, and control techniques are here surveyed. Specifically, this article stresses the need for IAQ assessment, control, and monitoring technologies. Moreover, the involvement of academic/research institutes, government organizations, and stakeholders for long-term planned studies on indoor air pollution and linking indoor air control/management to appropriate policy interventions (as per WHO standards) are here found to be crucial.

## 2. Indoor Air Pollution: A Serious Threat to Human Health

### 2.1. Indoor Pollutants

IAQ is generally affected by factors such as outdoor air quality, building/construction materials, and human activity inside buildings [9]. Outdoor air pollutants directly influence IAQ due to the possible transfer of toxins from the outdoors to indoor atmosphere [10]. Outdoor pollutants result from industrial and transport activities [11]. Construction/building materials have been a source of indoor pollution due to the evolution of toxic organic compounds from paints, adhesives, coatings, poly(vinyl chloride) floor covers, rubber carpets, etc. [12]. Moreover, daily human activities (cooking, smoking, heating, cleaning, solvent uses, etc.) produce lots of indoor pollutants such as noxious gases, particulate matter, allergens, bacteria, viruses, insects, mites, etc. [13–15]. Major pollution-causing noxious gases include oxides of carbon (COx) such as carbon monoxide (CO) and carbon dioxide (CO<sub>2</sub>); oxides of sulfur (SOx) such as sulfur dioxide (SO<sub>2</sub>); oxides of nitrogen (NOx) as nitric oxide (NO), nitrogen dioxide (NO<sub>2</sub>), particulate matter (PM), and volatile organic matter (PM) [16]. All indoor human activities and building materials are a rich source of PM, VOC, NOx, COx, SOx, ozone, Radon, etc. The ozone (O<sub>3</sub>) is also a toxic indoor pollutant from computers, photocopying machines, printers, etc.

PM has varying size of <10 µm (large diameter coarse particles), fine particles of diameter <2.5 µm, and ultrafine particles of diameter <0.1 µm [17]. Inhalation of PM causes damaging effects to the lungs, heart, respiratory, and cardiovascular systems.

VOC consist of toxic gases and volatile chemicals from liquids or solids [18]. Formaldehyde is a toxic form of VOC emitted from building materials such as plywood, paints, coatings, coverings, etc. VOC are also penetrated in indoor environment from the outdoor air. The long term exposure to VOC can cause serious health risks like cancer [19].

NOx such as NO and NO<sub>2</sub> result from cooking, combustion, and other heating, and fire sources [20]. NO is a primary pollutant which is oxidized to form NO<sub>2</sub>. NO<sub>2</sub> can easily react with water to produce nitrous acid (HONO) which is a harmful indoor contaminant. Common health risks of NOx are asthmatic reactions and lung infections [21].

SOx, especially SO<sub>2</sub> is a harmful indoor pollutant originating from outdoor air, cooking, smoking, heaters, and coal/wood burning [22]. Human exposure to SOx harms respiratory and cardiac functions causing asthmatic, pulmonary, and cardiovascular diseases.

COx such as CO emerges from indoor combustion (tobacco, cooking, gas heaters, stoves, furnaces, chimneys, etc.) and comes from outdoor air [23]. Even at low concentrations, CO can harm the cardiovascular, respiratory, and nervous systems [24].

Ozone is generally produced in the indoor environment due to photochemical reactions of VOC, COx, NOx, etc. [25]. It arises from outdoor sources, indoor photocopying, the use of machines. O<sub>3</sub> can seriously affect lungs, DNA, and human organs causing asthmatic and respiratory diseases.

Radon is an indoor pollutant from building materials, soil, and tap water [26]. In indoor buildings, concentrations of radioactive radon (<sup>222</sup>Rn) gas can attain harmful levels [27]. Lethal dose LD50 for radon inhalation is ~1.0 g causing toxic effects such as lung cancer and respiratory diseases [28].

Pesticides are used in an indoor environment to prevent pests, bacteria, fungi, insects, etc. Pesticides cause irritating effects on eyes, nose, and throat. Moreover, these chemicals cause damaging effects to the central nervous system, kidneys, and cancer risks [29].

Aerosols originated in indoor environments from various outdoor sources and also result from indoor gas-to-particle conversion of VOC [30]. Aerosols can be of different types such as carbonaceous aerosols, biological aerosols, and gas-to-particle aerosols. Carbonaceous aerosols originate from combustion, while biological aerosols are formed from animals, bacteria, and microorganisms. Aerosols frequently affect the human heart and brain-related systems.

Indoor biological pollutants include biological allergens (pets' saliva, dust, cockroaches, mites, pollens, etc.) and microorganisms (bacteria, viruses, fungi, etc.) [31]. Biological pollutants emerge from outdoor air. The most common human health effects include respiratory and allergic diseases.

To control and monitor all the above-mentioned pollutants, precise techniques need to be developed. To some extent, IAQ depends on indoor ventilation rates and related systems.

## 2.2. Health Effects–Short and Long Term

Indoor air pollutants may cause short-term or long-term health effects. Short-term exposure involves interaction with low concentrations of indoor pollutants or contact with indoor pollutants for a short span of time. Short-term exposure to indoor pollutants such as particulate matter, volatile organic compounds, NO<sub>x</sub>, CO<sub>x</sub>, etc., does not cause serious health effects [32]. In some cases, short-term exposure to indoor pollutants may initiate headaches. Especially, NO<sub>x</sub> level of 28.97 µg/m<sup>3</sup>, PM<sub>2.5</sub> concentration of 21.51 µg/m<sup>3</sup>, PM<sub>10</sub> level of 37.79-µg/m<sup>3</sup>, and CO<sub>x</sub> concentration of 1.15-ppm were found to cause headaches in indoor inhabitants [33]. On the other hand, long-term exposure to indoor air pollutants has their serious health effects. Usually, exposure to indoor pollutants for more than one month results in serious health risks [34]. Consequently, daily exposure or long term exposure may lead to cancer-causing effects [35]. Other important effects include sick building syndrome [36,37], building-related illness [38,39], pulmonary diseases [40,41], cardiovascular diseases [42–44], and many more. Table 1 illustrates common indoor pollutants and resulting hazardous effects on human health.

**Table 1.** Common indoor pollutants and their effects on human health.

Pollutant	Source	Health Influence	Ref
Particulate matter	- Outdoor environment	- Heat and lung diseases - amplified respiratory symptoms	[45–47]
	- cigarette smoke		
	- cooking, burning/candles, fireplaces		
	- heaters		
	- cleaning events		
VOCs	- Paints/varnishes/polishes and dyes	- Headaches and nausea	[48,49]
	- pesticides from wood furniture	- irritation of nose/throat	
	- adhesives/lubricants	- impairment to the central nervous system	
	- tobacco use and smoking	- liver/kidney damage	
	- perfumes and air fresheners		
NO <sub>2</sub>	- printers, etc.		
	- Gas-fueled cooking	- Asthmatic reactions	[50,51]
O <sub>3</sub>	- heating appliances	- Disinfecting devices	[52,53]
	- Outdoor sources	- DNA damage	
	- Photocopying	- lung damage	
		- asthma and decreased respiratory rate	
SO <sub>2</sub>	- Outdoor air	- Impairment of respiratory function	[54,55]
	- cooking stoves	- asthma and chronic pulmonary disease	
	- fireplaces	- cardiovascular diseases	
CO <sub>x</sub>	- Outdoor air	- Fatigue and chest pain	[56–58]
	- cooking stoves and fireplaces	- impaired vision	
	- tobacco smoke	- reduced brain function	



	- gasoline powered gears		
Aerosol	- Tobacco smoke	- Cardiovascular diseases	[59,60]
	- cooking	- respiratory and lungs diseases	
	- cleaning	- allergies	
Radon	- Outdoor air		[61]
	- soil gas	- Lung cancer	
	- tap water		
Pesticides	- Outdoor air	- Eye, nose, and throat irritation	[62,63]
	- insecticides, disinfectants, and herbicides	- damage to the central nervous system	
	- textiles and cushioned furniture	- kidney damage - cancer risk	
Biological allergens	- House dust		[64]
	- pets	- Respiratory infections—asthma	
	- insects	- Allergies	
	- pollens		
Microorganism	- Bacteria and viruses from human, animals, and plants	- Infectious diseases such as fever - digestive problems - respiratory infections	[65,66]

According to literature reports, high indoor particulate matter PM<sub>1</sub>, PM<sub>2.5</sub>, and PM<sub>10</sub> concentration of up to 2000–9000 µg/m<sup>3</sup> (mainly due to indoor cooking and heating activities) cause pulmonary infections, lungs diseases, and cancer risks [67,68]. Moreover, PM and CO<sub>2</sub> emissions due to tobacco smoke instigated coughing, sneezing, and eye irritation in indoor inhabitants [69]. Presence of indoor gaseous pollutants such as CO, NO<sub>2</sub>, SO<sub>2</sub>, O<sub>3</sub> was found to be associated with asthma risks and nervous system issues [70]. High indoor dust ingestion of ~8.79–34.39 ng/g, containing polychlorinated biphenyl concentrations, had serious health effects such as cancer risks and loss of indoor working productivity [71]. Indoor inhalation of flame retardants (up to concentrations of 128,000 ng.g<sup>-1</sup>) revealed respiratory issues and loss of indoor working productivity [72]. Furthermore, high levels of indoor microflora and bacteria ~10,000–15,000 cfu m<sup>-3</sup> caused respiratory and cancer risks [73,74].


### 3. Monitoring of Indoor Air Quality (IAQ)

Indoor air quality (IAQ) is defined as air value inside and around the buildings [75]. IAQ is important for health and coziness of building inhabitants. Harmful air pollutants (volatile organic compounds, particulate matter, and physical, chemicals, and biological aspects) at high concentration levels in indoor air cause negative health effects on human body.

An analysis of air quality level of south-east Asian countries (Pakistan, India, Nepal, Sri Lanka, Bangladesh, and Bhutan) has been carried out [76]. Comparative evaluation was performed for indoor pollutants such as PM<sub>10</sub>, PM<sub>2.5</sub>, and CO. WHO standards were considered for comparison. The WHO standards set for indoor PM<sub>10</sub> level were 50 µg/m<sup>3</sup> and PM<sub>2.5</sub> was 25 µg/m<sup>3</sup>. Air quality level (200–5000 µg/m<sup>3</sup>) was attained much higher than the WHO standard value for safe IAQ [77]. Moreover, carbon monoxide level was found much higher (~29.4 ppm) than the WHO set standards (<5 ppm). The suggested reason was conventional indoor fuel burning sources, which affected >50% of indoor population. Consequently, employment of IAQ policies was found indispensable to safeguard public health in these countries [78]. Moreover, rising indoor pollutant levels pointed to increasing respiratory, nervous, and mortality rates in population [79].

Research, analysis, and monitoring for IAQ levels have arisen as a significant research field [80]. Purpose of supervising IAQ is to protect humans occupying non-industrial buildings from harmful pollutants. It is important to mention that IAQ assessments


are found to be affected by indoor conditions such as temperature, light, humidity, air flow, etc. [81]. Initially, indoor pollutants have been controlled through adjusting indoor temperature and humidity. Figure 2 demonstrates a flow chart for steps involved in monitoring, control, and management of indoor air quality.



**Figure 2.** Indoor air quality—Monitoring, control, and management.

### 3.1. Materials Based IAQ Sensors

For IAQ monitoring systems, sensors have gained considerable research interest [82]. Initially, two-dimensional nanostructured materials have been invented for gas sensing [83]. Later research attempts focused zero-, one-, and three-dimensional nanostructured materials for developing IAQ monitoring sensors. These nanomaterials have been used to develop gas sensors, light sensors, humidity sensors, and temperature sensors. For IAQ monitoring systems, manifold phases of data acquisition, processing, storage, and analysis have been used [84]. Figure 3 shows a conceptual architecture of IAQ monitoring system. The data processing phase is accomplished at hardware as well as software level. The data acquired is sent for storage and processing. The software was used for enhancing data analysis and visualization. Accuracy of sensors has been achieved through calibrations and maintenance procedures. Consequently, development of novel low-cost sensors offers precise output data for advanced IAQ monitoring systems.



**Figure 3.** General conceptual architecture of IAQ monitoring system.

### 3.2. Advanced Technologies for IAQ Monitoring IAQ—Internet of Things (IoT)-Based Systems

Advanced techniques have been developed for IAQ monitoring [85]. Most prominently, internet of things (IoT)-based systems and wireless sensor networks have been developed. The IoT has been used as most popular technique for industrial revolution for IAQ monitoring [86]. Portable IoT devices have been effectively used for IAQ monitoring and control [87]. Recently, *electronic noses* or *e-noses* have been used as IoT devices for IAQ monitoring [88]. An *e-nose* is made up of multi-sensors arrays, processing units, digital software, and artificial neural networks. The *e-nose* has ability to monitor, detect, and discriminate various gaseous molecules [89]. Moreover, *e-noses* have low-cost and compactness for developing efficient IAQ monitoring systems [90]. The *e-noses* can sense numerous air pollutants such as CO, CO<sub>2</sub>, NO<sub>2</sub>, and particulate matter [91].

## 4. Control and Management of IAQ for Enhancing Air Value

Air purification technologies such as optimized ventilation systems have been developed for improving IAQ. Innovative technologies have been researched to filter/purify indoor air pollutants [92]. Here, the control of air pollution emission sources has been considered.

### 4.1. Filtration

For eradicating gaseous pollutants, two types of filtration processes have been used namely mechanical filtration and electronic filtration [93]. In this regard, carbon-based filters have been used in filtration systems. Mechanical filtration is a commonly used technology for removing particulate matter and noxious gases from indoor air [94,95]. In this filtration technique, fiber-based membrane media has been used. For efficient removal of pollutants from indoor air, fiber diameter, surface area, and membrane pore size have been considered important [96]. Here, high filtration efficiency was achieved depending upon size of diffusing particles and gas molecules. In electronic filtration systems, static electrical charge is applied to filter media for enhancing removal of noxious gases/particle [93,97]. Electrically linked air-cleaning devices have been successfully used for air purification. Electronic filters of two types have been used i.e., electrostatic precipitators and ion generator/ionizers. Efficiency of electrostatic filtration systems is high, however, these techniques may cause health effects [98]. Electrostatic precipitators produce negative air ions and hazardous charged particles affecting the cardiorespiratory functions [99]. Moreover, clogging of these filters has been observed through repeated use [100].

#### 4.2. Adsorption Technologies

Adsorption means capturing air contaminants or impurities on adsorbent surfaces [101]. For controlling IAQ, adsorption of noxious gases, volatile organic compounds, harmful particles, and gaseous pollutants has been examined. Effective adsorbent materials investigated here include activated carbon, silica gel, zeolites, clays, and polymers [102]. Activated carbon and zeolites have large surface area and reported for high adsorption capacity [103]. The activated carbon has microporous structure for adsorbing high molecular weight volatiles [104]. Adsorbent materials can be easily applied in buildings without using extra energy sources and having no issues of byproduct development [105]. Passive removal materials have been used as common adsorbents for cleaning indoor environments [106,107]. Based on adsorption mechanisms, passive removal materials have been categorized as (i) sorptive materials [108] and (ii) photocatalytic oxidation materials [109]. For controlling IAQ, passive removal materials have been comprehensively explored in literature [110].

#### 4.3. Non-Thermal Plasma (NTP) Technologies

Non-thermal plasma (NTP) methods have been established for controlling and enhancing IAQ [111,112]. In NTP techniques, quasi-neutral environment with ions, electrons, radicals, UV photons, etc. have been generated [113]. Non-thermal discharge plasma methods have been adopted for eliminating corona discharge, CO<sub>x</sub>, NO<sub>x</sub>, SO<sub>x</sub>, and volatile compounds from indoor air [114]. Similar to electrostatic precipitators, NTP method has drawbacks of producing secondary harmful pollutants (such as CO, NO<sub>x</sub>, formaldehyde, etc.), humidity effects, and poor energy efficiency [115]. These disadvantages have restricted applications of NTP technologies in indoor air purification systems.

#### 4.4. UV Light Disinfection Systems

UV light disinfection system is a simple air decontamination technique [116]. Using UV light disinfection systems reduced microorganisms levels in indoor air [117]. The microorganisms are disinfected through covalent bond cleavage resulting in C, H, O and N of nucleotide chains [118]. Using UV light disinfection systems reveal better building ventilation avoiding health problems caused by microorganisms such as allergies and respiratory infections [119,120]. This technology needs to be further explored to broaden its perspectives for efficient air pollutant removal.

#### 4.5. UV Photocatalytic Oxidation

UV photocatalytic oxidation is emerged as an interesting air purification technology [121]. UV photocatalysts have been used for treating adsorbed gases and biological particles. Most commonly used UV photocatalysts include TiO<sub>2</sub>, ZnO, WO<sub>3</sub>, and iron and other metal oxides for controlling IAQ levels [122,123]. Research attempts are observed for designing UV photocatalysts nanomaterials for improving oxidation efficiency and pollutant removal [124]. UV photocatalytic degradation of indoor gaseous pollutants, particulates, and biological pollutants have been reported [125]. Consequently, UV photocatalysts are found effective to attain clean indoor environment and enhancing IAQ [126]. According to literature, using TiO<sub>2</sub> based UV photocatalytic resulted in 50% reduction in NO<sub>x</sub> and 5–54% decrease in aromatic compounds (benzene, toluene, ethylbenzene, xylene) levels in indoor air [127].

#### 4.6. Air-Conditioning (AC) Systems

Numerous AC systems have been reported for enhancing IAQ and indoor thermal comfort for indoor inhabitants [128–130]. AC systems have independent control of temperature and humidity for purifying indoor environment [131,132], outdoor air systems [133,134], and cooling ceiling and displacement ventilation systems [135,136]. The indoor air ventilation has been considered important for enhancing IAQ.


#### 4.7. Green Solution to IAQ

##### 4.7.1. Green Plants

The indoor green plants offer benefits of generating indoor oxygen, humidity, and natural ventilation system [137]. Using indoor green plants produce positive health effects by reducing stress levels and by improving work performance. Potential of green plants for cleansing and remediating indoor atmosphere has been established. According to studies, the indoor green plants have been used for air purification against SARS-CoV-2 (causing COVID-19). Mechanism of air purification relies on green plants capabilities for absorbing or degrading airborne pollutants. The green plants have ability to remove CO<sub>2</sub> through photosynthesis process and degrade PM and VOC through metabolic action of rhizospheric microbes [138]. The indoor plants species such as Aloe vera, *Chlorophytum comosum*, *Epipremnum aureum*, *Lagerstroemia macrocarpa*, *Dracaena sanderiana*, etc. have been studied [139].

##### 4.7.2. Microalgae in Air Purification

Microalgae (prokaryotic/eukaryotic microorganisms) are efficient photosynthetic organisms. It has high biomass yield and low nutrients need to grow in soil, seawater, freshwater, and even in harsh environmental conditions [140]. Microalgae has been used for improving IAQ through indoor oxygen production, CO<sub>2</sub> capture, and pollutants remediation. Biomass produced from microalgae can be transformed to chemicals/biofuels such as biohydrogen, biodiesel, biohydrocarbons, etc., for attaining ecological and economic values [141,142]. Figure 4 displays microalgae system to convert CO<sub>2</sub> to O<sub>2</sub> during photosynthesis and metabolism activities [143]. Using microalgae systems, indoor ventilation has been enhanced.




**Figure 4.** Microalgae cultivation system integrated into a building for indoor air treatment [144]. PBR = photobioreactor. Reproduced with permission from MDPI.

#### 5. Use of Advanced Nanomaterials for Enhancing IAQ

Figure 5 expresses the use of nanomaterials for IAQ control/management systems. Basically, advanced nanomaterials (nanocomposites, carbon-based material, polymeric

nanocomposites, nanohybrids, etc.) have been applied in the monitoring sensors, filtration systems, adsorption systems, and UV photocatalysts. IAQ techniques have efficiently clean the indoor air [145–147]. In Asian countries, the filters have been used to filter the dust from indoor air [148]. Moreover, the indoor adsorption systems have been used to remove the dust from air [149]. The indoor organochlorine pesticides concentration ~7.53–1272.87 ng/g was removed using filtration systems [150]. Removing indoor dust, PM, and gaseous pollutants have prevented the related lifetime cancer risks [151–153]. IAQ controlling systems have been used to protect indoor pollution in residential buildings, schools, and offices. Designing advanced equipment for enhancing IAQ can prevent indoor pollution issues by improving air quality [154].




**Figure 5.** Advanced nanomaterials for enhancing IAQ.

### 5.1. In Monitoring Sensors


Gaseous contaminants such as CO<sub>x</sub>, NO<sub>x</sub>, SO<sub>x</sub>, VOC, etc. from industries, automobiles, urbanization, households, and human activities are continuously contaminating our global ecosystems [155]. The WHO has reported human organs and systems (respiratory, immune, and nervous system) damages related to environmental contaminants [156]. As a result, there are increasing global demands for modern IAQ controlling and monitoring strategies [157]. The commercial sensors have low detection limits and poor selectivity for IAQ monitoring [158]. Here, the advanced nanomaterials have been used to develop high-tech sensors [159]. The air contamination sensing strategies are mentioned in Figure 6 [160]. However, high costs, sophisticated designs, and time-consuming functioning have limited the use of sensors. Organic and inorganic nanomaterials have been reported for designing advanced sensors.






**Figure 6.** Schematic of various air contaminant sensing strategies depending upon nature of transducing signals and diversified sensing materials with different dimensions for air monitoring and detection [160]. Reproduced with permission from Wiley.

Gas sensors were developed using metal oxides filled polymeric nanocomposites. Onthath et al. [161] designed a novel VOC gas sensing setup (Figure 7). For designing sensor, carbon nanotube/copper oxide nanocomposites were prepared through sol gel method. The sensors exhibited high sensitivity to detect VOC such as benzene. Benzene was detected at low concentration of 5 ppm. Chougule et al. [162] prepared sensors using polypyrrole and zinc oxide nanoparticles. In polymer matrix, nanofiller was introduced in 10–50 wt.% contents. The polypyrrole/zinc oxide nanocomposite was used to detect  $\text{NO}_2$  at low concentration of 10 ppm (Figure 8).



**Figure 7.** Schematic diagram of volatile organic compound (VOC) gas sensing setup [161]. Reproduced with permission from Wiley.



**Figure 8.** Sensitivity of neat polypyrrole (PPy) and polypyrrole/zinc oxide (PPy-ZnO) (50%) sensors [162]. Reproduced with permission from Elsevier.

Maximum NO<sub>2</sub> sensitivity of nanocomposite (100 ppm at room temperature) was ~38% higher than neat polypyrrole. Sensing mechanism of p-n junction formation was observed for polypyrrole/zinc oxide nanocomposites. Gas sensors were prepared using graphene and graphene derivative nanomaterials. Comparative gas sensing performance of polymer/graphene nanocomposites is illustrated in Table 2. Sensor designs, synthesis techniques, and desired gas pollutants are discussed here.

**Table 2.** Gas sensors based on polymer/graphene oxide nanocomposites with polymeric materials.

Materials for Sensors	Synthesis Methods	Target Gases	Concentration Range	Sensitivity	Ref.
Polyaniline/graphene oxide nanocomposite	Layer by layer method	RH	~0–97% RH	~20.0%	[163]
Polyaniline/graphene oxide/tin oxide nanocomposite	In situ polymerization	H <sub>2</sub> S	~50 ppb to 10 ppm	~76.3%	[164]
Polypyrrole/reduced graphene oxide nanocomposite	In situ oxidative polymerization	NH <sub>3</sub>	~3–500 ppm	~34.7%	[165]
Polypyrrole/reduced graphene oxide/copper nanoparticle nanocomposite	In situ chemical polymerization	NH <sub>3</sub>	~10–150 ppm	~12.4%	[166]
Poly(3,4-ethylenedioxythiophene)/reduced graphene oxide nanocomposite	In situ polymerization	NO <sub>2</sub>	~500 ppb–20 ppm	~41.7%	[167]
Poly(3,4-ethylenedioxythiophene); polystyrene sulfonate/graphene oxide nanocomposite	Solution processing	NH <sub>3</sub>	~1–1000 ppm	~100	[168]
Poly(diallyldimethyl-ammonium chloride)/graphene nanocomposite	Layer by layer method; self-assembly	RH	~11–97% RH	~97%	[169]

## 5.2. Filtration and Adsorption Media

The indoor gaseous pollutants and PM continuously affect human health [5]. Filtration is used as an effective method to maintain safe IAQ level [170]. In air filters, specific surface area, hydrophilicity, mechanical stability, recyclability, and filtration efficiency are important for IAQ level. In this concern, polymers, nanocomposites, and nonfibrous nanomaterials have been used for indoor air filtration systems [171]. Conventional polymer (polyethylene, polypropylene, etc.) based air filters have low specific surface areas and affinity for PM and gaseous molecules [172]. In synthetic or natural polymeric nanocomposites, nanofillers such as nanocarbons, inorganic nanoparticles, and metal oxides have been used for attaining high filtration efficiency [173,174]. Table 3 shows few commonly used materials for filtration media for maintaining IAQ levels. Filtration mechanisms involve diffusion, interception, and gravity effects for removing PM, VOC, or other noxious gases from indoor air [175,176]. Electrostatic interactions of pollutants or PM particles with membranes (under electrical field) enhance their filtration efficiency [177].

**Table 3.** General materials for filtration media for IAQ.

Material	Two-Dimensional Material	Three-Dimensional Material
- Polymer		
- Carbonaceous material	Papers	Foam or sponges
- Polymer	Fabrics	Hydrogels
- Polymer		
- Polymeric composite	nano-Fiber nets	Sponge-polymer networks
- Carbonaceous material		
- Polymeric composite	nano-Meshes	Sponge-paper layered structure

Carbon-based materials possess high specific surface areas leading to high filtration capacity [178]. Carbon nanotube has a high surface area and small diameter for increasing the filtration efficiency of air filters [179].


Graphene or graphene oxide aerogel/foam nanomaterials have been developed [180]. Resulting graphene-based aerogels (formed by freeze drying method) have large specific surface area (1019 m<sup>2</sup>/g) [181] and high PM<sub>2.5</sub> and PM<sub>10</sub> filtration efficiency ~99–100% [182].

Fiber-based air filtration media have been reported [183]. Electrospinning method was used to form polymer fibers [184]. The polymeric fibers have high surface-to-volume ratio, flexibility, and chemical and mechanical properties [185]. Common polymers used in air filters include polyacrylonitrile [186], poly(methyl methacrylate) [187], poly(vinyl pyrrolidone) [188], poly(vinylidene fluoride) [189], nylon [190], polyimide [191], chitosan [192], etc. The resulting polymeric nanofibrous membranes have a high filtration efficiency of 99.98% for PM removal.


Chitosan or cellulose-based green air filters for IAQ have been reported [193,194]. Kaang et al. [195] produced wastepaper-based cylindrical hollow air filter (CHAF). Figure 9 shows a schematic of an air filtration system having CHAF, flow meter, and PM detectors. Structures of numerous polymers used with chitosan are shown in Figure 9. Chitosan has higher polarity than blended polymer-based CHAF promoting air filtration. PM<sub>2.5</sub> having size of 2.5 µm and a concentration of 644,000 µg/m<sup>3</sup> were filtered by these membranes. The diameter of CHAF fibers was 1–2 mm. Thus, CHAF has high removal efficiency for PM<sub>2.5</sub> (~99.12%).

Non-woven fabric membranes have been used for IAQ monitoring [196]. Wang et al. [197] prepared halloysite nanotubes@chitosan/polyvinyl alcohol/non-woven fabric hybrid membrane. Figure 10 demonstrates the fabrication process of filtration

membranes. Uniform hierarchical porous air filters were prepared through the dip coating method. Fibrous composite membranes have a pore size of  $27.5\ \mu\text{m}$  and a porosity of 89.8%. Filtration efficiency for  $\text{PM}_{2.5}$  was found high i.e., ~96.8%. Moreover, membranes have high antibacterial activity for *E.coli* and *S. aureus* bacterial strains.



**Figure 9.** (a) Schematic of an air filtration system equipped with cylindrical hollow air filter (CHAF), flow meter, and PM detectors; (b) Structural formulas and dipole moments of various polymers [195]. Reproduced with permission from ACS.




**Figure 10.** Schematic diagram for fabrication of HNTs@CS/PVA/NWF membranes [197]. NIPS = nonsolvent induced phase separation; NWF = non-woven fabric; CS/PVA/NWF = chitosan/poly(vinyl alcohol)/non-woven fabric; HNTs@CS/PVA/NWF = halloysite nanotubes@chitosan/poly(vinyl alcohol)/non-woven fabric. Reproduced with permission from Elsevier.

Polymeric membranes and polymeric nanocomposite membranes have been effectively applied in air filters [198]. Polyacrylonitrile nanofiber-based air filters have been reported. Huang et al. [199] designed polyacrylonitrile nanofiber-based electrospun nanofibrous membranes for removing very fine indoor PM and preventing their lethal health effects. The diameter of polyacrylonitrile nanofiber was  $\sim 300\ \text{nm}$  enhancing PM filtration efficiency up to >99% for a safe IAQ level [200]. Here, efficient removal of  $\text{PM}_{2.5}$  (particle size  $< 2.5\ \mu\text{m}$ ) was achieved. Su et al. [201] prepared polyacrylonitrile nanofiber and  $\text{TiO}_2$  derived electrospun nanocomposite membranes. The nanoporous membranes have an average pore size of  $2.7\text{--}4.6\ \mu\text{m}$ . Hierarchical nanoporous membranes have enhanced




filtration efficiency of ~99–100 for  $PM_{2.5}$  with particle size  $< 2.5 \mu m$ . Hence, a safe IAQ level was attained [202]. Aydin-Aytekin et al. [203] developed polyamide 6/nanoclay/ $TiO_2$  derived electrospun nanofibrous membranes for maintaining IAQ. The nanofiber diameter was ~75.8–135.9 nm for filtration of VOC indoor pollutants. The membranes have an air permeability of 119.9–309.4  $g/m^2h$ . VOC removal efficacy of nanofibrous membranes was increased up to 44%, with increasing nanofiller loading (0 to 0.5 wt.%). Thus, IAQ was achieved through VOC removal [204]. Purwar et al. [205] designed the poly(vinyl alcohol)/Cloisite nanoclay-based electrospun nanofibrous membranes for maintaining IAQ. The diameter of electrospun nanofiber was in the range of 300–400 nm. The poly(vinyl alcohol)/Cloisite nanoclay membranes with 0.75% nanoclay were found promising for removing indoor  $PM_{2.5}$  (up to 90–100%). In this way, 100% PM removal ensures a safe IAQ level for a healthy indoor environment [206]. Li et al. [207] developed poly(vinyl alcohol)/silver nanoparticle-based electrospun membranes. The poly(vinyl alcohol) matrix was grafted with 3,3',4,4'-benzophenone tetracarboxylic acid to form electrospun membranes. Scheme for membrane formation is illustrated in Figure 11. The nanocomposite membranes were used for maintaining IAQ through the filtration of reactive oxygen species such as  $OH\cdot$  radical and  $H_2O_2$ . Moreover, nanocomposite membranes have antibacterial activity against *Staphylococcus aureus* and *Escherichia coli*. The  $1 \times 10^6$  cfu aerosol with bacterial strains was filtered. Filtration efficiencies were quite high i.e., ~99.98%. Removal of aerosol and bacteria from indoor air resulted in a safe IAQ level.

Recently, Bonfim et al. [208] produced polyethylene terephthalate-based electrospun nanofibrous membranes. In membranes, the fiber diameter was ~1.27  $\mu m$ . The membranes had high porosity of 96% and permeability of  $4.4 \times 10^{-8} m^2$ . PM and aerosol nanoparticles including bacteria, fungi, and virus of ~100 nm were removed using these membranes. Figure 12 shows the increasing efficiency of polyethylene terephthalate-based electrospun nanofibrous membranes with increasing particle diameter (70–100 nm). Minimal efficiency was observed for a particle size of 20 nm. Nanofibrous polyethylene terephthalate membranes were found effective to clean the indoor air of hospitals and food industries. Thus, reported nanocomposite membranes are found promising for maintaining high IAQ standards, due to structural stability, reusability, and filtration efficiency.



**Figure 11.** Polymer poly(vinyl alcohol)/silver nanoparticle-based nanocomposite membrane for air filtration [207]. PVA/AgNP = poly(vinyl alcohol)/silver nanoparticle; BPTA = 3,3',4,4'-benzophenone

tetracarboxylic acid; PVA/AgNP/BPTA = poly(vinyl alcohol)/silver nanoparticle/3,3',4,4'-benzophenone tetracarboxylic acid; ROS = reactive oxygen species. Reproduced with permission from Elsevier.



**Figure 12.** Fractional efficiency curves for samples with filtration velocity equal to 4.8 cm/s [208]. PET12\_0.8 = particle diameter 100 nm; PET12\_1.0 = particle diameter 70 nm; PET20\_0.8 = particle diameter 20 nm. Reproduced with permission from MDPI.


Adsorption has been used as an effective method for air purification [209,210]. Activated carbon-based adsorption method has been conventionally used. Adsorption media based on advanced nanomaterials has been developed for IAQ management. Nanomaterials with high surface area and high storage capacity have been preferred for adsorption materials [115]. Swamy [211] designed an adsorbent nanomaterial for CO<sub>2</sub> adsorption. Using this nanomaterial, the CO<sub>2</sub> level was reduced to 50%. Moreover, nanofibrous materials modified with adsorbent nanomaterials have been proposed for VOC adsorption [212]. In this way, adsorbents were used for controlling safe IAQ by removing VOC and toxic gases. Buyukada-Kesici et al. [213] prepared polyamide 6 and cellulose nanocrystal-based nanocomposite as adsorbent. The nanomaterial was capable of treating VOC, especially toluene. Kadam et al. [214] designed electrospun adsorbent material based on polyacrylonitrile/ $\beta$ -cyclodextrin nanofibers for VOC and indoor pollutants. The polyacrylonitrile/ $\beta$ -cyclodextrin nanofibers had an adsorption efficiency of >95% for formaldehyde and ~66% for xylene. Moreover, nanocomposite had no toxic effects on human systems. Hence, polymeric nanocomposite-based adsorbents were efficiently used to remove indoor pollutants.

### 5.3. UV Photocatalysts

UV photocatalytic oxidation has been focused on purifying indoor air [215]. UV photocatalysts cause redox reactions of toxic gases and biological particles adsorbed on its surface for removal [216]. The metal oxide-based UV photocatalysts have been used [217]. The physicochemical properties of nanomaterials have been modified to attain high-performance UV photocatalysts. The nanomaterials have the capability for removing VOC, PM, CO<sub>x</sub>, NO<sub>x</sub>, SO<sub>x</sub>, and other indoor environmental pollutants [218,219]. As a result, UV photocatalysts are proven promising for removing indoor pollutants and related diseases such as sick building syndrome [220]. Besides, UV photocatalysts have been used to prevent ozone depletion problem of the stratosphere. Arnawtee et al. [221] prepared lignin, carbon nanotube, and palladium nanoparticle-based UV photocatalyst through laser



ablation. UV photocatalyst was used to remove VOC and dye traces from indoor air. Zan et al. [222] designed a polystyrene grafted  $\text{TiO}_2$  nanocomposite for maintaining IAQ. Poly(vinylidene fluoride)/ $\text{TiO}_2$  nanocomposites have been developed (using solvothermal method) as a UV photocatalyst for removing indoor VOC [223]. Moreover, Boaretti et al. [224] formed a UV photocatalytic system based on electrospun nanofibers of poly(vinylidene fluoride)/graphene/ $\text{TiO}_2$  and poly(vinylidene fluoride)/graphene oxide/ $\text{TiO}_2$  nanocomposites. The nanomaterial was used for removing or degrading indoor air pollutants such as VOC, acetaldehyde, and methanol. The photocatalytic activity of  $\text{TiO}_2$ , graphene/ $\text{TiO}_2$ , and graphene oxide/ $\text{TiO}_2$  systems for removing acetaldehyde and methanol abatement was measured (Figure 13a,b). The resulting normalized data were analyzed (Figure 13c,d). In acetaldehyde degradation, the initial concentration was removed by using a catalyst in 15–20 min. On the other hand, neat  $\text{TiO}_2$  took 40 min for complete degradation. According to the results of moles reacted per gram of catalyst, better performance of nanocomposite systems was achieved. Better dispersion of graphene, graphene oxide, and  $\text{TiO}_2$  nanoparticles resulted in superior photocatalyst efficiency. In these UV photocatalysts, the inclusion of graphene and  $\text{TiO}_2$  nanoparticles decreased band-gap energy facilitating electron mobility and photocatalytic activity [225].



**Figure 13.** Acetaldehyde removal versus time (a) and normalized data on catalyst mass (c); Methanol removal versus time (b) and normalized data on catalyst mass (d) [224]. Reproduced with permission from MDPI.

## 6. Conclusions

As indoor air pollutants cause adverse human health effects, monitoring strategies/equipments have been developed for improving air quality by implementation in buildings and residences. An essential step to improve indoor air quality is the use of low-

emission products and materials causing pollution. In this regard, combustion/burning utilizations and building heating equipment need to be optimized for limiting pollutant emissions. Construction materials such as insulating materials, paints, coatings, covers, furniture, etc. must be developed using safe and inert materials causing low VOC emissions. Building indoor car garages must be avoided to eliminate the chances of indoor CO pollution. Moreover, indoor surfaces need to be kept clean and dry avoiding any moisture for growing germs, bacteria, molds, etc. Keeping indoor pets can be avoided to minimize chances of indoor pollution. An important control and management step to maintain IAQ must involve indoor air circulation and ventilation systems. Although, ventilation can only avoid indoor air pollutants to some extent, PM, VOC, noxious gases, and microorganisms still remain in an indoor environment. Outdoor air is a rich source of indoor pollutants and cannot be avoided. Advanced IAQ technologies such as filtration, adoption, UV disinfection, UV photocatalyst, NTP methods, green vegetation, etc. must be adopted to minimize indoor pollution. However, indoor pollution cannot be completely avoided. For IAQ monitoring, it is important to develop advanced sensors for sensing hazardous indoor pollutants. Current technical developments demonstrate the effectiveness of using advanced nanomaterials in monitoring sensors, filters, adsorbents, and photocatalysts. However, precise working mechanisms and design necessities of these nanomaterials for innovative systems need to be thoroughly explored. Moreover, the development of nanomaterials-based air purification systems on large-scale faces design challenges related to material type and final IAQ system. In other words, several challenges need to be overcome for using new materials and products for removing indoor pollutants. It is important to renovate existing buildings with equipment and devices supporting IAQ standards. It is important (i) to monitor IAQ on large scale; (ii) to properly educate people to avoid indoor pollution generation; and (iii) to take necessary action in case of indoor pollution. In the future safe IAQ level will be a performance indicator of our houses or buildings and society's foremost concern for health protection.

Briefly speaking, this review summarizes almost all possible indoor pollutants, their health effects, and required IAQ monitoring, control, and management technologies. The article presents the importance of using advanced nanomaterials in IAQ monitoring or management systems. The application of nanomaterials in IAQ systems opens future ways for a safe, healthy, and ecological indoor environment.

**Author Contributions:** Conceptualization, A.K.; data curation, A.K.; writing of original draft preparation, A.K.; Review and editing, A.K., I.A., T.Z., H.S. and M.H.E. All authors have read and agreed to the published version of the manuscript.

**Funding:** This research received no external funding.

**Data Availability Statement:** Not applicable.

**Conflicts of Interest:** The authors declare no conflict of interest.

## References

1. Pluschke, P.; Schleibinger, H. *Indoor Air Pollution*; Springer: Berlin/Heidelberg, Germany, 2018.
2. Amegah, A.K.; Jaakkola, J.J. Household air pollution and the sustainable development goals. *Bull. World Health Organ.* **2016**, *94*, 215.
3. Mendoza, D.L.; Benney, T.M.; Bares, R.; Fasoli, B.; Anderson, C.; Gonzales, S.A.; Crosman, E.T.; Hoch, S. Investigation of Indoor and Outdoor Fine Particulate Matter Concentrations in Schools in Salt Lake City, Utah. *Pollutants* **2022**, *2*, 82–97.
4. Kraft, M.; Rauchfuss, K.; Fromme, H.; Grün, L.; Sievering, S.; Köllner, B.; Chovolou, Y. Inhalation exposure to PCB from contaminated indoor air—How much is absorbed into the blood? *Pollutants* **2021**, *1*, 181–193.
5. Keswani, A.; Akselrod, H.; Anenberg, S.C. Health and clinical impacts of air pollution and linkages with climate change. *NEJM Evid.* **2022**, *1*, EVIDra2200068.
6. Zeng, Y.; Laguerre, A.; Gall, E.T.; Heidarinejad, M.; Stephens, B. Experimental Evaluations of the Impact of an Additive Oxidizing Electronic Air Cleaner on Particles and Gases. *Pollutants* **2022**, *2*, 98–134.
7. Bain-Reguis, N.; Smith, A.; Martin, C.H.; Currie, J. Indoor CO<sub>2</sub> and Thermal Conditions in Twenty Scottish Primary School Classrooms with Different Ventilation Systems during the COVID-19 Pandemic. *Pollutants* **2022**, *2*, 180–204.

8. Ciccioli, P.; Pallozzi, E.; Guerriero, E.; Iannelli, M.A.; Donati, E.; Lilla, L.; Rinaldi, C.; Svaldi, P.; Ciccioli, P.; Mabilia, R. A New Testing Facility to Investigate the Removal Processes of Indoor Air Contaminants with Different Cleaning Technologies and to Better Assess and Exploit Their Performances. *Environments* **2021**, *9*, 3.
9. Marć, M.; Śmiełowska, M.; Namieśnik, J.; Zabiegała, B. Indoor air quality of everyday use spaces dedicated to specific purposes—A review. *Environmental Science and Pollut. Res.* **2018**, *25*, 2065–2082.
10. Peng, Z.; Deng, W.; Tenorio, R. Investigation of indoor air quality and the identification of influential factors at primary schools in the North of China. *Sustainability* **2017**, *9*, 1180.
11. Liang, J. *Chemical Modeling for Air Resources: Fundamentals, Applications, and Corroborative Analysis*; Elsevier: Amsterdam, The Netherlands, 2013.
12. Gopalakrishnan, P.; Kavinraj, M.; Vivekanadhan; Jeevitha, N. Effect of indoor air quality on human health-A review. In Proceedings of the AIP Conference, Antalya, Turkey, 12–15 May 2021; AIP Publishing LLC: New York, NY, USA, 2021.
13. Wang, M.; Li, L.; Hou, C.; Guo, X.; Fu, H. Building and health: Mapping the knowledge development of sick building syndrome. *Buildings* **2022**, *12*, 287.
14. Li, C.; Zhu, Q.; Jin, X.; Cohen, R.C. Elucidating Contributions of Anthropogenic Volatile Organic Compounds and Particulate Matter to Ozone Trends over China. *Environ. Sci. Technol.* **2022**, *56*, 12906–12916.
15. Zhang, G.; Xu, H.; Qi, B.; Du, R.; Gui, K.; Wang, H.; Jiang, W.; Liang, L.; Xu, W. Characterization of atmospheric trace gases and particulate matter in Hangzhou, China. *Atmos. Chem. Phys.* **2018**, *18*, 1705–1728.
16. Mata, T.M.; Felgueiras, F.; Martins, A.A.; Monteiro, H.; Ferraz, M.P.; Oliveira, G.M.; Gabriel, M.F.; Silva, G.V. Indoor air quality in elderly centers: Pollutants emission and health effects. *Environments* **2022**, *9*, 86.
17. Zhai, Y.; Li, X.; Wang, T.; Wang, B.; Li, C.; Zeng, G. A review on airborne microorganisms in particulate matters: Composition, characteristics and influence factors. *Environ. Int.* **2018**, *113*, 74–90.
18. Ubando, A.T.; Africa, A.D.M.; Maniquiz-Redillas, M.C.; Culaba, A.B.; Chen, W.-H. Reduction of particulate matter and volatile organic compounds in biorefineries: A state-of-the-art review. *J. Hazard. Mater.* **2021**, *403*, 123955.
19. Cheng, L.; Wei, W.; Guo, A.; Zhang, C.; Sha, K.; Wang, R.; Wang, K.; Cheng, S. Health risk assessment of hazardous VOCs and its associations with exposure duration and protection measures for coking industry workers. *J. Clean. Prod.* **2022**, *379*, 134919.
20. Andersen, C.; Omelekhina, Y.; Rasmussen, B.B.; Nygaard Bennekov, M.; Skov, S.N.; Køcks, M.; Wang, K.; Strandberg, B.; Mattsson, F.; Bilde, M. Emissions of soot, PAHs, ultrafine particles, NO<sub>x</sub>, and other health relevant compounds from stressed burning of candles in indoor air. *Indoor Air* **2021**, *31*, 2033–2048.
21. Paciência, I.; Cavaleiro Rufo, J.; Moreira, A. Environmental inequality: Air pollution and asthma in children. *Pediatr. Allergy Immunol.* **2022**, *33*, 1–21.
22. Kureshi, R.R.; Thakker, D.; Mishra, B.K.; Ahmed, B. Use Case of Building an Indoor Air Quality Monitoring System. In Proceedings of the 2021 IEEE 7th World Forum on Internet of Things (WF-IoT), New Orleans, LA, USA, 14–31 July 2021.
23. Nair, A.N.; Anand, P.; George, A.; Mondal, N. A review of strategies and their effectiveness in reducing indoor airborne transmission and improving indoor air quality. *Environ. Res.* **2022**, *213*, 113579.
24. Sakai, H.; Yasuda, S.; Okuda, C.; Yamada, T.; Owaki, K.; Miwa, Y. Examination of central nervous system by functional observation battery after massive intravenous infusion of carbon monoxide-bound and oxygen-bound hemoglobin vesicles in rats. *Curr. Res. Pharmacol. Drug Discov.* **2022**, *3*, 100135.
25. Zhu, Y.; Wei, Z.; Yang, X.; Tao, S.; Zhang, Y.; Shangguan, W. Comprehensive control of PM 2.5 capture and ozone emission in two-stage electrostatic precipitators. *Sci. Total Environ.* **2022**, *858*, 159900.
26. Sá, J.P.; Branco, P.T.; Alvim-Ferraz, M.C.; Martins, F.G.; Sousa, S.I. Radon in Indoor Air: Towards Continuous Monitoring. *Sustainability* **2022**, *14*, 1529.
27. Stanley, F. *An Analysis of Human Exposure to Alpha Particle Radiation*; University of Calgary: Calgary, Canada, 2018.
28. Patocka, J. Human health and environmental uranium. *Mil. Med. Sci. Lett.* **2014**, *83*, 120–131.
29. Figueiredo, D.M.; Duyzer, J.; Huss, A.; Krop, E.J.; Gerritsen-Ebben, M.; Gooijer, Y.; Vermeulen, R.C. Spatio-temporal variation of outdoor and indoor pesticide air concentrations in homes near agricultural fields. *Atmos. Environ.* **2021**, *262*, 118612.
30. Mostafa, M.Y.A.; Khalaf, H.N.B.; Zhukovsky, M. Attachment rate characteristics of different wide used aerosol sources in indoor air. *J. Environ. Health Sci. Eng.* **2021**, *19*, 867–879.
31. López, A.; Yusà, V.; Villoldo, E.; Corpas-Burgos, F.; Coscollà, C. Indoor air pesticide in dwellings of breastfeeding mothers of the Valencian Region (Spain): Levels, exposure and risk assessment. *Atmos. Environ.* **2021**, *248*, 118231.
32. Błaszczuk, E.; Rogula-Kozłowska, W.; Klejnowski, K.; Kubiesa, P.; Fulara, I.; Mielżyńska-Śvach, D. Indoor air quality in urban and rural kindergartens: Short-term studies in Silesia, Poland. *Air Qual. Atmos. Health* **2017**, *10*, 1207–1220.
33. Dales, R.E.; Cakmak, S.; Vidal, C.B. Air pollution and hospitalization for headache in Chile. *Am. J. Epidemiol.* **2009**, *170*, 1057–1066.
34. Sun, S.; Zheng, X.; Villalba-Diez, J.; Ordieres-Meré, J. Indoor air-quality data-monitoring system: Long-term monitoring benefits. *Sensors* **2019**, *19*, 4157.
35. Maroni, M.; Seifert, B.; Lindvall, T. *Indoor Air Quality: A Comprehensive Reference Book*; Elsevier: Amsterdam, The Netherlands, 1995.
36. Sarkhosh, M.; Najafpoor, A.A.; Alidadi, H.; Shamsara, J.; Amiri, H.; Andrea, T.; Kariminejad, F. Indoor Air Quality associations with sick building syndrome: An application of decision tree technology. *Build. Environ.* **2021**, *188*, 107446.

37. Hou, J.; Sun, Y.; Dai, X.; Liu, J.; Shen, X.; Tan, H.; Yin, H.; Huang, K.; Gao, Y.; Lai, D. Associations of indoor carbon dioxide concentrations, air temperature, and humidity with perceived air quality and sick building syndrome symptoms in Chinese homes. *Indoor Air* **2021**, *31*, 1018–1028.
38. Fan, L.; Ding, Y. Research on risk scorecard of sick building syndrome based on machine learning. *Build. Environ.* **2022**, *211*, 108710.
39. Kalender-Smajlović, S.; Kuček, A.; Dovjak, M. The problem of indoor environmental quality at a general Slovenian hospital and its contribution to sick building syndrome. *Build. Environ.* **2022**, *214*, 108908.
40. Hansel, N.N.; Putcha, N.; Woo, H.; Peng, R.; Diette, G.B.; Fawzy, A.; Wise, R.A.; Romero, K.; Davis, M.F.; Rule, A.M. Randomized clinical trial of air cleaners to improve indoor air quality and chronic obstructive pulmonary disease health: Results of the CLEAN AIR study. *Am. J. Respir. Crit. Care Med.* **2022**, *205*, 421–430.
41. Kamal, R.; Srivastava, A.K.; Kesavachandran, C.N.; Bihari, V.; Singh, A. Chronic obstructive pulmonary disease (COPD) in women due to indoor biomass burning: A meta analysis. *Int. J. Environ. Health Res.* **2022**, *32*, 1403–1417.
42. Mannucci, P.M. An ecological alliance against air pollution and cardiovascular disease. *Bleeding Thromb. Vasc. Biol.* **2022**, *1*, 21. <https://doi.org/10.4081/btvb.2022.21>.
43. Münzel, T.; Sørensen, M.; Daiber, A. Transportation noise pollution and cardiovascular disease. *Nat. Rev. Cardiol.* **2021**, *18*, 619–636.
44. Zheng, C.; Tang, H.; Wang, X.; Chen, Z.; Zhang, L.; Kang, Y.; Yang, Y.; Chen, L.; Zhou, H.; Cai, J. Left ventricular diastolic dysfunction and cardiovascular disease in different ambient air pollution conditions: A prospective cohort study. *Sci. Total Environ.* **2022**, *831*, 154872.
45. Miller, M.R.; Shaw, C.A.; Langrish, J.P. From particles to patients: Oxidative stress and the cardiovascular effects of air pollution. *Future Cardiol.* **2012**, *8*, 577–602.
46. Brook, R.D.; Rajagopalan, S.; Pope, C.A., III; Brook, J.R.; Bhatnagar, A.; Diez-Roux, A.V.; Holguin, F.; Hong, Y.; Luepker, R.V.; Mittleman, M.A. Particulate matter air pollution and cardiovascular disease: An update to the scientific statement from the American Heart Association. *Circulation* **2010**, *121*, 2331–2378.
47. Al-Kindi, S.G.; Brook, R.D.; Biswal, S.; Rajagopalan, S. Environmental determinants of cardiovascular disease: Lessons learned from air pollution. *Nat. Rev. Cardiol.* **2020**, *17*, 656–672.
48. Tran, V.V.; Park, D.; Lee, Y.-C. Indoor air pollution, related human diseases, and recent trends in the control and improvement of indoor air quality. *Int. J. Environ. Res. Public Health* **2020**, *17*, 2927.
49. Weschler, C.J.; Nazaroff, W.W. Dermal uptake of organic vapors commonly found in indoor air. *Environ. Sci. Technol.* **2014**, *48*, 1230–1237.
50. Bernstein, J.A.; Alexis, N.; Bacchus, H.; Bernstein, I.L.; Fritz, P.; Horner, E.; Li, N.; Mason, S.; Nel, A.; Oullette, J. The health effects of nonindustrial indoor air pollution. *J. Allergy Clin. Immunol.* **2008**, *121*, 585–591.
51. Ghaffarianhoseini, A.; AlWaer, H.; Omrany, H.; Ghaffarianhoseini, A.; Alalouch, C.; Clements-Croome, D.; Tookey, J. Sick building syndrome: Are we doing enough? *Archit. Sci. Rev.* **2018**, *61*, 99–121.
52. Salonen, H.; Salthammer, T.; Morawska, L. Human exposure to ozone in school and office indoor environments. *Environ. Int.* **2018**, *119*, 503–514.
53. Huang, Y.; Yang, Z.; Gao, Z. Contributions of indoor and outdoor sources to ozone in residential buildings in nanjing. *Int. J. Environ. Res. Public Health* **2019**, *16*, 2587.
54. Seow, W.J.; Downward, G.S.; Wei, H.; Rothman, N.; Reiss, B.; Xu, J.; Bassig, B.A.; Li, J.; He, J.; Hosgood, H.D. Indoor concentrations of nitrogen dioxide and sulfur dioxide from burning solid fuels for cooking and heating in Yunnan Province, China. *Indoor Air* **2016**, *26*, 776–783.
55. Du, W.; Li, X.; Chen, Y.; Shen, G. Household air pollution and personal exposure to air pollutants in rural China—A review. *Environ. Pollut.* **2018**, *237*, 625–638.
56. Mattiuzzi, C.; Lippi, G. Worldwide epidemiology of carbon monoxide poisoning. *Hum. Exp. Toxicol.* **2020**, *39*, 387–392.
57. Hampson, N.B.; Weaver, L. Carbon monoxide poisoning: A new incidence for an old disease. *Undersea Hyperb. Med.* **2007**, *34*, 163–168.
58. Harper, A.; Croft-Baker, J. Carbon monoxide poisoning: Undetected by both patients and their doctors. *Age Ageing* **2004**, *33*, 105–109.
59. Oh, H.-J.; Jeong, N.-N.; Sohn, J.-R.; Kim, J. Personal exposure to indoor aerosols as actual concern: Perceived indoor and outdoor air quality, and health performances. *Build. Environ.* **2019**, *165*, 106403.
60. Cao, Q.; Li, F.; Zhang, T.T.; Wang, S. A ventilator that responds to outdoor conditions for ventilation and air filtration. *Energy Build.* **2020**, *229*, 110498.
61. Schabath, M.B.; Cote, M.L. Cancer progress and priorities: Lung cancer. *Cancer Epidemiol. Biomark. Prev.* **2019**, *28*, 1563–1579.
62. Hwang, H.-M.; Park, E.-K.; Young, T.M.; Hammock, B.D. Occurrence of endocrine-disrupting chemicals in indoor dust. *Sci. Total Environ.* **2008**, *404*, 26–35.
63. Lucattini, L.; Poma, G.; Covaci, A.; de Boer, J.; Lamoree, M.H.; Leonards, P.E. A review of semi-volatile organic compounds (SVOCs) in the indoor environment: Occurrence in consumer products, indoor air and dust. *Chemosphere* **2018**, *201*, 466–482.
64. Baldacci, S.; Maio, S.; Cerrai, S.; Sarno, G.; Baiz, N.; Simoni, M.; Annesi-Maesano, I.; Viegi, G.; Study, H. Allergy and asthma: Effects of the exposure to particulate matter and biological allergens. *Respir. Med.* **2015**, *109*, 1089–1104.

65. Hospodsky, D.; Qian, J.; Nazaroff, W.W.; Yamamoto, N.; Bibby, K.; Rismani-Yazdi, H. Human occupancy as a source of indoor airborne bacteria. *PLoS ONE* **2012**, *7*, e34867.
66. Adams, R.I.; Miletto, M.; Taylor, J.W.; Bruns, T.D. Dispersal in microbes: Fungi in indoor air are dominated by outdoor air and show dispersal limitation at short distances. *ISME J.* **2013**, *7*, 1262–1273.
67. Colbeck, I.; Nasir, Z.A.; Ali, Z. Characteristics of indoor/outdoor particulate pollution in urban and rural residential environment of Pakistan. *Indoor Air* **2010**, *20*, 40–51.
68. Junaid, M.; Syed, J.H.; Abbasi, N.A.; Hashmi, M.Z.; Malik, R.N.; Pei, D.-S. Status of indoor air pollution (IAP) through particulate matter (PM) emissions and associated health concerns in South Asia. *Chemosphere* **2018**, *191*, 651–663.
69. Naeem, A.; Rafiq, L.; Nazar, R.; Kashif, M.; Naqvi, S.H.Z. An assessment of Risk Factors and Health Impacts Associated with Indoor Air Pollution and Tobacco Smoke in Lahore, Pakistan. *J. Qual. Assur. Agric. Sci.* **2022**, *2*, 37–45.
70. Aslam, R.; Sharif, F.; Baqar, M.; Nizami, A.-S.; Ashraf, U. Role of ambient air pollution in asthma spread among various population groups of Lahore City: A case study. *Environ. Sci. Pollut. Res.* **2022**, *30*, 8682–8697.
71. Khalid, F.; Qadir, A.; Hashmi, M.Z.; Mehmood, A.; Aslam, I.; Zhang, G.; Ahmed, Z. Evaluation of ceiling fan dust as an indicator of indoor PCBs pollution in selected cities of Punjab, Pakistan: Implication on human health. *Arab. J. Geosci.* **2022**, *15*, 876.
72. Cao, Z.; Xu, F.; Covaci, A.; Wu, M.; Yu, G.; Wang, B.; Deng, S.; Huang, J. Differences in the seasonal variation of brominated and phosphorus flame retardants in office dust. *Environ. Int.* **2014**, *65*, 100–106.
73. Nasir, Z.A.; Colbeck, I.; Sultan, S.; Ahmed, S. Bioaerosols in residential micro-environments in low income countries: A case study from Pakistan. *Environ. Pollut.* **2012**, *168*, 15–22.
74. Sidra, S.; Ali, Z.; Sultan, S.; Ahmed, S.; Colbeck, I.; Nasir, Z.A. Assessment of airborne microflora in the indoor micro-environments of residential houses of Lahore, Pakistan. *Aerosol Air Qual. Res.* **2015**, *15*, 2385–2396.
75. Rajagopalan, P.; Goodman, N. Improving the indoor air quality of residential buildings during bushfire smoke events. *Climate* **2021**, *9*, 32.
76. Khwaja, M.A.; Shams, T. *Pakistan National Ambient Air Quality Standards: A comparative Assessment with Selected Asian Countries and World Health Organization (WHO)*; Sustainable Development Policy Institute: Islamabad, Pakistan, 2020.
77. Yasmin, N.; Grundmann, P. Home-cooked energy transitions: Women empowerment and biogas-based cooking technology in Pakistan. *Energy Policy* **2020**, *137*, 111074.
78. Shams, Z.I.; Javed, T.; Zubair, A.; Waqas, M.; Ali, S.; Ahmed, A. Carbon Monoxide Concentrations in Kitchens of Gas-fired Burners, Karachi, Pakistan: Carbon Monoxide in Karachi Bungalow and Apartment Kitchens. *Pak. J. Sci. Ind. Res. Ser. A Phys. Sci.* **2022**, *65*, 25–32.
79. Qayyum, F.; Mehmood, U.; Tariq, S.; Nawaz, H. Particulate matter (PM<sub>2.5</sub>) and diseases: An autoregressive distributed lag (ARDL) technique. *Environ. Sci. Pollut. Res.* **2021**, *28*, 67511–67518.
80. Argunhan, Z.; Avci, A.S. Statistical evaluation of indoor air quality parameters in classrooms of a university. *Adv. Meteorol.* **2018**, *2018*, 4391579.
81. Wolkoff, P. Indoor air humidity, air quality, and health—An overview. *Int. J. Hyg. Environ. Health* **2018**, *221*, 376–390.
82. Chojer, H.; Branco, P.; Martins, F.; Alvim-Ferraz, M.; Sousa, S. Development of low-cost indoor air quality monitoring devices: Recent advancements. *Sci. Total Environ.* **2020**, *727*, 138385.
83. Bag, A.; Lee, N.-E. Gas sensing with heterostructures based on two-dimensional nanostructured materials: A review. *J. Mater. Chem. C* **2019**, *7*, 13367–13383.
84. Hapsari, A.A.; Hajamydeen, A.I.; Abdullah, M.I. A review on indoor air quality monitoring using iot at campus environment. *Int. J. Eng. Technol.* **2018**, *7*, 55–60.
85. Saini, J.; Dutta, M.; Marques, G. A comprehensive review on indoor air quality monitoring systems for enhanced public health. *Sustain. Environ. Res.* **2020**, *30*, 6.
86. Saini, J.; Dutta, M.; Marques, G. Indoor air quality monitoring systems based on internet of things: A systematic review. *Int. J. Environ. Res. Public Health* **2020**, *17*, 4942.
87. Pitarma, R.; Marques, G.; Caetano, F. Monitoring indoor air quality to improve occupational health. In *New Advances in Information Systems and Technologies*; Springer: Berlin/Heidelberg, Germany, 2016; pp. 13–21.
88. Kim, J.-J.; Jung, S.K.; Kim, J.T. Wireless monitoring of indoor air quality by a sensor network. *Indoor Built Environ.* **2010**, *19*, 145–150.
89. Li, Z.; Askim, J.R.; Suslick, K.S. The optoelectronic nose: Colorimetric and fluorometric sensor arrays. *Chem. Rev.* **2018**, *119*, 231–292.
90. Taştan, M.; Gökozan, H. Real-time monitoring of indoor air quality with internet of things-based E-nose. *Appl. Sci.* **2019**, *9*, 3435.
91. Chen, K.; Gao, W.; Emaminejad, S.; Kiriya, D.; Ota, H.; Nyein, H.Y.Y.; Takei, K.; Javey, A. Printed carbon nanotube electronics and sensor systems. *Adv. Mater.* **2016**, *28*, 4397–4414.
92. Li, P.; Wang, C.; Zhang, Y.; Wei, F. Air filtration in the free molecular flow regime: A review of high-efficiency particulate air filters based on carbon nanotubes. *Small* **2014**, *10*, 4543–4561.
93. Liu, G.; Xiao, M.; Zhang, X.; Gal, C.; Chen, X.; Liu, L.; Pan, S.; Wu, J.; Tang, L.; Clements-Croome, D. A review of air filtration technologies for sustainable and healthy building ventilation. *Sustain. Cities Soc.* **2017**, *32*, 375–396.
94. Nazarenko, Y. Air filtration and severe acute respiratory syndrome Coronavirus 2. *Epidemiol. Health* **2020**, *42*, e2020049.
95. Martins, A.A.; Mata, T.M.; Callheiros, C.; Ventura, G.; Gabriel, M.; Alonso-Cuevilla, N.; Villanueva, F. Indoor Air Quality: A Review of Cleaning Technologies. *Environments* **2022**, *9*, 118.
96. Cao, J.; Cheng, Z.; Kang, L.; Lin, M.; Han, L. Patterned nanofiber air filters with high optical transparency, robust mechanical strength, and effective PM<sub>2.5</sub> capture capability. *RSC Adv.* **2020**, *10*, 20155–20161.

97. Gao, Y.; Tian, E.; Zhang, Y.; Mo, J. Utilizing electrostatic effect in fibrous filters for efficient airborne particles removal: Principles, fabrication, and material properties. *Appl. Mater. Today* **2022**, *26*, 101369.
98. Bliss, S. *Best Practices Guide to Residential Construction: Materials; Finishes and Details*, John Wiley & Sons: New York, NY, USA, 2006.
99. Liu, S.; Huang, Q.; Wu, Y.; Song, Y.; Dong, W.; Chu, M.; Yang, D.; Zhang, X.; Zhang, J.; Chen, C. Metabolic linkages between indoor negative air ions, particulate matter and cardiorespiratory function: A randomized, double-blind crossover study among children. *Environ. Int.* **2020**, *138*, 105663.
100. Tian, E.; Xia, F.; Wu, J.; Zhang, Y.; Li, J.; Wang, H.; Mo, J. Electrostatic air filtration by multifunctional dielectric heterocaking filters with ultralow pressure drop. *ACS Appl. Mater. Interfaces* **2020**, *12*, 29383–29392.
101. Yue, X.; Ma, N.L.; Sonne, C.; Guan, R.; Lam, S.S.; Van Le, Q.; Chen, X.; Yang, Y.; Gu, H.; Rinklebe, J. Mitigation of indoor air pollution: A review of recent advances in adsorption materials and catalytic oxidation. *J. Hazard. Mater.* **2021**, *405*, 124138.
102. Mobasser, S.; Wager, Y.; Dittrich, T.M. Indoor Air Purification of Volatile Organic Compounds (VOCs) Using Activated Carbon, Zeolite, and Organosilica Sorbents. *Ind. Eng. Chem. Res.* **2022**, *61*, 6791–6801.
103. Luengas, A.; Barona, A.; Hort, C.; Gallastegui, G.; Platel, V.; Elias, A. A review of indoor air treatment technologies. *Rev. Environ. Sci. Bio/Technol.* **2015**, *14*, 499–522.
104. Xie, T. Indoor air pollution and control technology. In *Proceedings of the IOP Conference Series: Earth and Environmental Science, Banda Aceh, Indonesia, 26–27 September 2018*; IOP Publishing: Bristol, UK, 2018.
105. Liang, X. Research on the Causes and Prevention Strategies of Air Environmental Pollution. In *Proceedings of the IOP Conference Series: Earth and Environmental Science, Jakarta, Indonesia, 25–26 September 2021*; IOP Publishing: Bristol, UK, 2021.
106. Darling, E.; Morrison, G.C.; Corsi, R.L. Passive removal materials for indoor ozone control. *Build. Environ.* **2016**, *106*, 33–44.
107. Gall, E.T.; Corsi, R.L.; Siegel, J.A. Barriers and opportunities for passive removal of indoor ozone. *Atmos. Environ.* **2011**, *45*, 3338–3341.
108. Bahri, M.; Schleibinger, H.; Render, W.; Naboka, O. Removal performance of formaldehyde by ceiling tiles as sorptive passive panels. *Build. Environ.* **2019**, *160*, 106172.
109. Zuraimi, M.; Magee, R.; Won, D.; Nong, G.; Arsenault, C.; Yang, W.; So, S.; Nilsson, G.; Abebe, L.; Alliston, C. Performance of sorption-and photocatalytic oxidation-based indoor passive panel technologies. *Build. Environ.* **2018**, *135*, 85–93.
110. Jing, L.; Wang, J. Study on indoor ozone removal by PRM under the influence of typical factors. In *Proceedings of the E3S Web of Conferences, Xi'an, China, 31 August 2022*; EDP Sciences: Les Ulis, France, 2022.
111. Hossaini, H.; Pirsaeheb, M.; Hossini, H.; Derakhshan, A.A.; Asadi, F. Improving the purification of aqueous solutions by controlling the production of reactive oxygen species in non-thermal plasma; a systematic review. *Rev. Environ. Health* **2022**, *ahead of print*.
112. Zhang, Z.; Fan, X.; Song, C.; Lu, W.; Li, H.; Wang, P. The effect of dual dielectric barrier discharge non-thermal plasma on the emission characteristics of diesel engine. *Environ. Chall.* **2022**, *9*, 100652.
113. Kim, H.H. Nonthermal plasma processing for air-pollution control: A historical review, current issues, and future prospects. *Plasma Process. Polym.* **2004**, *1*, 91–110.
114. Vandenbroucke, A.M.; Morent, R.; De Geyter, N.; Leys, C. Non-thermal plasmas for non-catalytic and catalytic VOC abatement. *J. Hazard. Mater.* **2011**, *195*, 30–54.
115. Bahri, M.; Haghighat, F. Plasma-B based Indoor Air Cleaning Technologies: The State of the Art-Review. *CLEAN—Soil Air Water* **2014**, *42*, 1667–1680.
116. Kowalski, W.; Moeller, R.; Walsh, T.J.; Petraitis, V.; Passman, F.J. Ultraviolet disinfection efficacy test method using bacteria monolayers. *J. Microbiol. Methods* **2022**, *200*, 106541.
117. Bern, Z.; Davies, S.; Dennen, T. Enhanced ultraviolet cancellations in  $N = 5$  supergravity at four loops. *Phys. Rev. D* **2014**, *90*, 105011.
118. Lee, L.D.; Delclos, G.; Berkheiser, M.L.; Barakat, M.T.; Jensen, P.A. Evaluation of multiple fixed in-room air cleaners with ultraviolet germicidal irradiation, in high-occupancy areas of selected commercial indoor environments. *J. Occup. Environ. Hyg.* **2022**, *19*, 67–77.
119. Atci, F.; Cetin, Y.E.; Avci, M.; Aydin, O. Evaluation of in-duct UV-C lamp array on air disinfection: A numerical analysis. *Sci. Technol. Built Environ.* **2020**, *27*, 98–108.
120. Luo, H.; Zhong, L. Ultraviolet germicidal irradiation (UVGI) for in-duct airborne bioaerosol disinfection: Review and analysis of design factors. *Build. Environ.* **2021**, *197*, 107852.
121. Weon, S.; He, F.; Choi, W. Status and challenges in photocatalytic nanotechnology for cleaning air polluted with volatile organic compounds: Visible light utilization and catalyst deactivation. *Environ. Sci. Nano* **2019**, *6*, 3185–3214.
122. Nassehinia, H.; Rahmani, A.; Ghaieny, G.; Mehdinia, S.M. Application of novel methods in environmental and health hazardous pollutants removal using nanophotocatalysts. *Koomesh* **2016**, *18*, 309–316.
123. Rafique, M.S.; Tahir, M.B.; Rafique, M.; Shakil, M. Photocatalytic nanomaterials for air purification and self-cleaning. In *Nanotechnology and Photocatalysis for Environmental Applications*; Elsevier: Amsterdam, The Netherlands, 2020; pp. 203–219.
124. Tai, X.H.; Lai, C.W.; Juan, J.C.; Lee, K.M. Nano-photocatalyst in photocatalytic oxidation processes. In *Nanomaterials for Air Remediation*; Elsevier: Amsterdam, The Netherlands, 2020; pp. 151–165.
125. Wang, H.; Li, X.; Zhao, X.; Li, C.; Song, X.; Zhang, P.; Huo, P. A review on heterogeneous photocatalysis for environmental remediation: From semiconductors to modification strategies. *Chin. J. Catal.* **2022**, *43*, 178–214.



126. Ren, H.; Koshy, P.; Chen, W.-F.; Qi, S.; Sorrell, C.C. Photocatalytic materials and technologies for air purification. *J. Hazard. Mater.* **2017**, *325*, 340–366.
127. Yu, C.W.; Kim, J.T. Photocatalytic oxidation for maintenance of indoor environmental quality. *Indoor Built Environ.* **2013**, *22*, 39–51.
128. Park, D.Y.; Chang, S. Effects of combined central air conditioning diffusers and window-integrated ventilation system on indoor air quality and thermal comfort in an office. *Sustain. Cities Soc.* **2020**, *61*, 102292.
129. Daghighi, R. Assessing the thermal comfort and ventilation in Malaysia and the surrounding regions. *Renew. Sustain. Energy Rev.* **2015**, *48*, 681–691.
130. Liu, S.; Cao, Q.; Zhao, X.; Lu, Z.; Deng, Z.; Dong, J.; Lin, X.; Qing, K.; Zhang, W.; Chen, Q. Improving indoor air quality and thermal comfort in residential kitchens with a new ventilation system. *Build. Environ.* **2020**, *180*, 107016.
131. Purwanto, F.H.; Utami, E.; Pramono, E. Design of server room temperature and humidity control system using fuzzy logic based on microcontroller. In Proceedings of the 2018 International Conference on Information and Communications Technology (ICOIAC), Yogyakarta, Indonesia, 6–7 March 2018; IEEE: Piscataway, USA, 2018.
132. Kaewwiset, T.; Yodkhad, P. Automatic temperature and humidity control system by using Fuzzy Logic algorithm for mushroom nursery. In Proceedings of the 2017 International Conference on Digital Arts, Media and Technology (ICDAMT), Chiang Mai, Thailand, 1–4 March 2017; IEEE: Piscataway, USA, 2017.
133. Yang, S.; Wan, M.P.; Ng, B.F.; Dubey, S.; Henze, G.P.; Chen, W.; Baskaran, K. Experimental study of model predictive control for an air-conditioning system with dedicated outdoor air system. *Appl. Energy* **2020**, *257*, 113920.
134. Cheon, S.-Y.; Cho, H.-J.; Jeong, J.-W. Energy saving potential of a vacuum-based membrane dehumidifier in a dedicated outdoor air system. *Energy Convers. Manag.* **2021**, *227*, 113618.
135. Schiavon, S.; Bauman, F.; Tully, B.; Rimmer, J. Room air stratification in combined chilled ceiling and displacement ventilation systems. *HVACR Res.* **2012**, *18*, 147–159.
136. Liu, Z.; Zhang, L.; Gong, G. Experimental evaluation of a solar thermoelectric cooled ceiling combined with displacement ventilation system. *Energy Convers. Manag.* **2014**, *87*, 559–565.
137. Moya, T.A.; van den Dobbelsteen, A.; Ottele, M.; Bluyssen, P.M. A review of green systems within the indoor environment. *Indoor Built Environ.* **2019**, *28*, 298–309.
138. Irga, P.; Pettit, T.; Torpy, F. The phytoremediation of indoor air pollution: A review on the technology development from the potted plant through to functional green wall biofilters. *Rev. Environ. Sci. Bio/Technol.* **2018**, *17*, 395–415.
139. Bandehali, S.; Miri, T.; Onyeaka, H.; Kumar, P. Current state of indoor air phytoremediation using potted plants and green walls. *Atmosphere* **2021**, *12*, 473.
140. Mata, T.M.; Martins, A.A.; Caetano, N.S. Microalgae for biodiesel production and other applications: A review. *Renew. Sustain. Energy Rev.* **2010**, *14*, 217–232.
141. Branco-Vieira, M.; San Martin, S.; Agurto, C.; Santos, M.A.d.; Freitas, M.A.; Mata, T.M.; Martins, A.A.; Caetano, N.S. Potential of *Phaeodactylum tricornutum* for biodiesel production under natural conditions in Chile. *Energies* **2017**, *11*, 54.
142. Salehizadeh, H.; Yan, N.; Farnood, R. Recent advances in microbial CO<sub>2</sub> fixation and conversion to value-added products. *Chem. Eng. J.* **2020**, *390*, 124584.
143. Acien Fernández, F.G.; González-López, C.; Fernández Sevilla, J.; Molina Grima, E. Conversion of CO<sub>2</sub> into biomass by microalgae: How realistic a contribution may it be to significant CO<sub>2</sub> removal? *Appl. Microbiol. Biotechnol.* **2012**, *96*, 577–586.
144. Mata, T.M.; Oliveira, G.M.; Monteiro, H.; Silva, G.V.; Caetano, N.S.; Martins, A.A. Indoor Air Quality Improvement Using Nature-Based Solutions: Design Proposals to Greener Cities. *Int. J. Environ. Res. Public Health* **2021**, *18*, 8472.
145. Singh, R.; Dewan, A. Implementation of the Right to Healthy Environment: Regulations for running air conditioners in public buildings and recognition of biological pollutants. *Authorea Prepr.* **2022**. <https://doi.org/10.22541/au.164269331.18559346/v1>.
146. Chen, Y.; Li, X.; Zhang, X.; Zhang, Y.; Gao, W.; Wang, R.; He, D. Air conditioner filters become sinks and sources of indoor microplastics fibers. *Environ. Pollut.* **2022**, *292*, 118465.
147. Yang, Z.; Xiao, H.; Sun, H.; Wang, B.; Lin, B.; Shi, W.; Huang, W. Performance analysis of room air conditioners via questionnaire and integrated field test. *Appl. Therm. Eng.* **2021**, *196*, 117243.
148. AlMulla, A.A.; Berekaa, M.; Dahlawi, S. Human Exposure Assessment to Air Pollutants in AC Filters from Agricultural, Industrial, and Residential Areas. *Atmosphere* **2022**, *13*, 1899.
149. Aslam, I.; Mumtaz, M.; Qadir, A.; Jamil, N.; Baqar, M.; Mahmood, A.; Ahmad, S.R.; Zhang, G. Organochlorine pesticides (OCPs) in air-conditioner filter dust of indoor urban setting: Implication for health risk in a developing country. *Indoor Air* **2021**, *31*, 807–817.
150. Arif, S.; Tabusum, S.; Gul, N. Pesticides residues in the human breast milk of primiparous and multiparous women of karachi, pakistan. *Feb-Fresenius Environ. Bull.* **2022**, *31*, 9494–9498.
151. Wang, Y.; Sun, M.; Yang, X.; Yuan, X. Public awareness and willingness to pay for tackling smog pollution in China: A case study. *J. Clean. Prod.* **2016**, *112*, 1627–1634.
152. Loewy, S.A.; Kelly, G.W.; Nathanson, M.D. Indoor Pollution in Commercial Buildings: Legal Requirements and Emerging Trends. *Temp. Environ. Law Technol. J.* **1992**, *11*, 239.
153. Kankaria, A.; Nongkynrih, B.; Gupta, S.K. Indoor air pollution in India: Implications on health and its control. *Indian J. Community Med. Off. Publ. Indian Assoc. Prev. Soc. Med.* **2014**, *39*, 203.
154. Shahid, M.A.K.; Ahmad, N.; Hussain, K.; Ahmad, N. Indoor, Out Door Air Pollution (Ioap), Cost Effective Methodologies And Potential Intervention Strategies. *Int. J. Core Eng. Manag.* **2015**, *1*, 11–25.

155. McKercher, G.R.; Salmond, J.A.; Vanos, J.K. Characteristics and applications of small, portable gaseous air pollution monitors. *Environ. Pollut.* **2017**, *223*, 102–110.
156. Manisalidis, I.; Stavropoulou, E.; Stavropoulos, A.; Bezirtzoglou, E. Environmental and health impacts of air pollution: A review. *Front. Public Health* **2020**, *8*, 14.
157. Fuller, G. *The Invisible Killer: The Rising Global Threat of Air Pollution-and How We Can Fight Back*; Melville House: NY, USA, 2019.
158. Ródenas García, M.; Spinazzé, A.; Branco, P.T.; Borghi, F.; Villena, G.; Cattaneo, A.; Di Gilio, A.; Mihucz, V.G.; Gómez Álvarez, E.; Lopes, S.I. Review of low-cost sensors for indoor air quality: Features and applications. *Appl. Spectrosc. Rev.* **2022**, *57*, 747–779.
159. Robin, Y.; Amann, J.; Baur, T.; Goodarzi, P.; Schultealbert, C.; Schneider, T.; Schütze, A. High-Performance VOC Quantification for IAQ Monitoring Using Advanced Sensor Systems and Deep Learning. *Atmosphere* **2021**, *12*, 1487.
160. Chaudhary, V.; Ashraf, N.; Khalid, M.; Walvekar, R.; Yang, Y.; Kaushik, A.; Mishra, Y.K. Emergence of MXene–polymer hybrid nanocomposites as high-performance next-generation chemiresistors for efficient air quality monitoring. *Adv. Funct. Mater.* **2022**, *32*, 2112913.
161. Onthath, H.; Maurya, M.R.; Bykkam, S.; Morsy, H.; Ibrahim, M.; Ahmed, A.E.; Riyaz, N.U.S.; Abuznad, R.; Alruwaili, A.; Kumar, B. Development and Fabrication of Carbon Nanotube (CNT)/CuO Nanocomposite for Volatile Organic Compounds (VOCs) Gas Sensor Application. In *Macromolecular Symposia*; Wiley Online Library: New York, NY, USA, 2021.
162. Chougule, M.; Dalavi, D.; Mali, S.; Patil, P.; Moholkar, A.; Agawane, G.; Kim, J.; Sen, S.; Patil, V. Novel method for fabrication of room temperature polypyrrole–ZnO nanocomposite NO<sub>2</sub> sensor. *Measurement* **2012**, *45*, 1989–1996.
163. Zhang, D.; Wang, D.; Li, P.; Zhou, X.; Zong, X.; Dong, G. Facile fabrication of high-performance QCM humidity sensor based on layer-by-layer self-assembled polyaniline/graphene oxide nanocomposite film. *Sens. Actuators B Chem.* **2018**, *255*, 1869–1877.
164. Zhang, D.; Wu, Z.; Zong, X. Flexible and highly sensitive H<sub>2</sub>S gas sensor based on in-situ polymerized SnO<sub>2</sub>/rGO/PANI ternary nanocomposite with application in halitosis diagnosis. *Sens. Actuators B Chem.* **2019**, *289*, 32–41.
165. Tiwari, D.C.; Atri, P.; Sharma, R. Sensitive detection of ammonia by reduced graphene oxide/polypyrrole nanocomposites. *Synth. Met.* **2015**, *203*, 228–234.
166. Yin, Y.; Zhang, H.; Huang, P.; Xiang, C.; Zou, Y.; Xu, F.; Sun, L. Inducement of nanoscale Cu–BTC on nanocomposite of PPy–rGO and its performance in ammonia sensing. *Mater. Res. Bull.* **2018**, *99*, 152–160.
167. Yang, Y.; Li, S.; Yang, W.; Yuan, W.; Xu, J.; Jiang, Y. In situ polymerization deposition of porous conducting polymer on reduced graphene oxide for gas sensor. *ACS Appl. Mater. Interfaces* **2014**, *6*, 13807–13814.
168. Hasani, A.; Sharifi Dehsari, H.; Asghari Lafmejani, M.; Salehi, A.; Afshar Taromi, F.; Asadi, K.; Kim, S.Y. Ammonia-Sensing Using a Composite of Graphene Oxide and Conducting Polymer. *Phys. Status Solidi (RRL)—Rapid Res. Lett.* **2018**, *12*, 1800037.
169. Zhang, D.; Tong, J.; Xia, B.; Xue, Q. Ultrahigh performance humidity sensor based on layer-by-layer self-assembly of graphene oxide/polyelectrolyte nanocomposite film. *Sens. Actuators B Chem.* **2014**, *203*, 263–270.
170. De Castro, B.J.C.; Sartim, R.; Guerra, V.G.; Aguiar, M.L. Hybrid air filters: A review of the main equipment configurations and results. *Process Saf. Environ. Prot.* **2020**, *144*, 193–207.
171. Henning, L.M.; Abdullayev, A.; Vakifahmetoglu, C.; Simon, U.; Bensalah, H.; Gurlo, A.; Bekheet, M.F. Review on polymeric, inorganic, and composite materials for air filters: From processing to properties. *Adv. Energy Sustain. Res.* **2021**, *2*, 2100005.
172. Liu, J.; Zhang, H.; Gong, H.; Zhang, X.; Wang, Y.; Jin, X. Polyethylene/polypropylene bicomponent spunbond air filtration materials containing magnesium stearate for efficient fine particle capture. *ACS Appl. Mater. Interfaces* **2019**, *11*, 40592–40601.
173. Lee, H.-J.; Choi, W.S. 2d and 3d bulk materials for environmental remediation: Air filtration and oil/water separation. *Materials* **2020**, *13*, 5714.
174. Bortolassi, A.C.C.; Nagarajan, S.; de Araújo Lima, B.; Guerra, V.G.; Aguiar, M.L.; Huon, V.; Soussan, L.; Cornu, D.; Miele, P.; Bechelany, M. Efficient nanoparticles removal and bactericidal action of electrospun nanofibers membranes for air filtration. *Mater. Sci. Eng. C* **2019**, *102*, 718–729.
175. Han, N.; Lee, Y.S.; Kaang, B.K.; Jang, W.; Koo, H.Y.; San Choi, W. A lottery draw machine-inspired movable air filter with high removal efficiency and low pressure drop at a high flow rate. *J. Mater. Chem. A* **2019**, *7*, 6001–6011.
176. Gong, G.; Zhou, C.; Wu, J.; Jin, X.; Jiang, L. Nanofibrous adhesion: The twin of gecko adhesion. *ACS Nano* **2015**, *9*, 3721–3727.
177. Jeong, S.; Cho, H.; Han, S.; Won, P.; Lee, H.; Hong, S.; Yeo, J.; Kwon, J.; Ko, S.H. High efficiency, transparent, reusable, and active PM<sub>2.5</sub> filters by hierarchical Ag nanowire percolation network. *Nano Lett.* **2017**, *17*, 4339–4346.
178. Wang, Z.; Yan, F.; Pei, H.; Li, J.; Cui, Z.; He, B. Antibacterial and environmentally friendly chitosan/polyvinyl alcohol blend membranes for air filtration. *Carbohydr. Polym.* **2018**, *198*, 241–248.
179. Liu, H.; Cao, C.; Huang, J.; Chen, Z.; Chen, G.; Lai, Y. Progress on particulate matter filtration technology: Basic concepts, advanced materials, and performances. *Nanoscale* **2020**, *12*, 437–453.
180. Li, J.; Wei, L.; Leng, W.; Hunt, J.F.; Cai, Z. Fabrication and characterization of cellulose nanofibrils/epoxy nanocomposite foam. *J. Mater. Sci.* **2018**, *53*, 4949–4960.
181. Qian, Y.; Ismail, I.M.; Stein, A. Ultralight, high-surface-area, multifunctional graphene-based aerogels from self-assembly of graphene oxide and resol. *Carbon* **2014**, *68*, 221–231.
182. Zhao, K.; Huang, J.; Mao, J.; Bao, Z.; Chen, Z.; Lai, Y. Charged graphene aerogel filter enabled superior particulate matter removal efficiency in harsh environment. *Chem. Eng. J.* **2020**, *395*, 125086.
183. Yu, X.; Li, C.; Tian, H.; Yuan, L.; Xiang, A.; Li, J.; Wang, C.; Rajulu, A.V. Hydrophobic cross-linked zein-based nanofibers with efficient air filtration and improved moisture stability. *Chem. Eng. J.* **2020**, *396*, 125373.

184. Yoon, J.; Yang, H.S.; Lee, B.S.; Yu, W.R. Recent progress in coaxial electrospinning: New parameters, various structures, and wide applications. *Adv. Mater.* **2018**, *30*, 1704765.
185. Lu, T.; Cui, J.; Qu, Q.; Wang, Y.; Zhang, J.; Xiong, R.; Ma, W.; Huang, C. Multistructured electrospun nanofibers for air filtration: A review. *ACS Appl. Mater. Interfaces* **2021**, *13*, 23293–23313.
186. Wang, N.; Si, Y.; Wang, N.; Sun, G.; El-Newehy, M.; Al-Deyab, S.S.; Ding, B. Multilevel structured polyacrylonitrile/silica nanofibrous membranes for high-performance air filtration. *Sep. Purif. Technol.* **2014**, *126*, 44–51.
187. Lv, S.; Zhao, X.; Shi, L.; Zhang, G.; Wang, S.; Kang, W.; Zhuang, X. Preparation and properties of sc-PLA/PMMA transparent nanofiber air filter. *Polymers* **2018**, *10*, 996.
188. Melike, G.; Calisir, M.D.; Akgul, Y.; Selcuk, S.; Ali, D.; Kilic, A. Submicron aerosol filtration performance of centrifugally spun nanofibrous polyvinylpyrrolidone media. *J. Ind. Text.* **2021**, *50*, 1545–1558.
189. Wang, L.-Y.; Liya, E.Y.; Lai, J.-Y.; Chung, T.-S. Developing ultra-high gas permeance PVDF hollow fibers for air filtration applications. *Sep. Purif. Technol.* **2018**, *205*, 184–195.
190. Shi, L.; Zhuang, X.; Tao, X.; Cheng, B.; Kang, W. Solution blowing nylon 6 nanofiber mats for air filtration. *Fibers Polym.* **2013**, *14*, 1485–1490.
191. Li, D.; Shen, Y.; Wang, L.; Liu, F.; Deng, B.; Liu, Q. Hierarchical structured polyimide–silica hybrid nano/microfiber filters welded by solvent vapor for air filtration. *Polymers* **2020**, *12*, 2494.
192. Li, H.; Wang, Z.; Zhang, H.; Pan, Z. Nanoporous PLA/(chitosan nanoparticle) composite fibrous membranes with excellent air filtration and antibacterial performance. *Polymers* **2018**, *10*, 1085.
193. Lippi, M.; Riva, L.; Caruso, M.; Punta, C. Cellulose for the Production of Air-Filtering Systems: A Critical Review. *Materials* **2022**, *15*, 976.
194. Rojas-Taboada, M.; García Betancourt, M.L. Nanocellulose Membranes for Air Filtration. In *Handbook of Nanocelluloses: Classification, Properties, Fabrication, and Emerging Applications*. Springer: Berlin/Heidelberg, Germany, 2022; pp. 1–32.
195. Kaang, B.K.; Lee, H.B.; Koo, H.Y.; Choi, W.S. Wastepaper-Based Cylindrical Hollow Air Filter Module for the Removal of Particulate Matter (PM10 and PM2.5) and HCHO. *ACS Sustain. Chem. Eng.* **2020**, *8*, 13984–13996.
196. Borojeni, I.A.; Gajewski, G.; Riahi, R.A. Application of Electrospun Nonwoven Fibers in Air Filters. *Fibers* **2022**, *10*, 15.
197. Wang, Z.; Yan, F.; Pei, H.; Yan, K.; Cui, Z.; He, B.; Fang, K.; Li, J. Environmentally-friendly halloysite nanotubes@chitosan/polyvinyl alcohol/non-woven fabric hybrid membranes with a uniform hierarchical porous structure for air filtration. *J. Membr. Sci.* **2020**, *594*, 117445.
198. Kim, H.-J.; Park, S.J.; Park, C.S.; Le, T.-H.; Lee, S.H.; Ha, T.H.; Kim, H.-i.; Kim, J.; Lee, C.-S.; Yoon, H. Surface-modified polymer nanofiber membrane for high-efficiency microdust capturing. *Chem. Eng. J.* **2018**, *339*, 204–213.
199. Huang, J.J.; Tian, Y.; Wang, R.; Tian, M.; Liao, Y. Fabrication of bead-on-string polyacrylonitrile nanofibrous air filters with superior filtration efficiency and ultralow pressure drop. *Sep. Purif. Technol.* **2020**, *237*, 116377.
200. Agarwal, N.; Meena, C.S.; Raj, B.P.; Saini, L.; Kumar, A.; Gopalakrishnan, N.; Kumar, A.; Balam, N.B.; Alam, T.; Kapoor, N.R. Indoor air quality improvement in COVID-19 pandemic. *Sustain. Cities Soc.* **2021**, *70*, 102942.
201. Su, J.; Yang, G.; Cheng, C.; Huang, C.; Xu, H.; Ke, Q. Hierarchically structured TiO<sub>2</sub>/PAN nanofibrous membranes for high-efficiency air filtration and toluene degradation. *J. Colloid Interface Sci.* **2017**, *507*, 386–396.
202. Branco, P.; Alvim-Ferraz, M.; Martins, F.; Sousa, S. Indoor air quality in urban nurseries at Porto city: Particulate matter assessment. *Atmos. Environ.* **2014**, *84*, 133–143.
203. Aydin-Aytenkin, D.; Gezmis-Yavuz, E.; Buyukada-Kesici, E.; Cansoy, C.E.; Alp, K.; Koseoglu-Imer, D.Y. Fabrication and characterization of multifunctional nanoclay and TiO<sub>2</sub> embedded polyamide electrospun nanofibers and their applications at indoor air filtration. *Mater. Sci. Eng. B* **2022**, *279*, 115675.
204. Sheng, Y.; Fang, L.; Nie, J. Experimental analysis of indoor air quality improvement achieved by using a Clean-Air Heat Pump (CAHP) air-cleaner in a ventilation system. *Build. Environ.* **2017**, *122*, 343–353.
205. Purwar, R.; Sai Goutham, K.; Srivastava, C.M. Electrospun Sericin/PVA/Clay nanofibrous mats for antimicrobial air filtration mask. *Fibers Polym.* **2016**, *17*, 1206–1216.
206. Wang, M.; Lu, T.; Li, Y. Optimizing air purification for household particulate matters using sensor-based and time-based intervention strategies. *Particuology* **2023**, *79*, 78–84.
207. Li, S.; Zhang, R.; Xie, J.; Sameen, D.E.; Ahmed, S.; Dai, J.; Qin, W.; Li, S.; Liu, Y. Electrospun antibacterial poly(vinyl alcohol)/Ag nanoparticles membrane grafted with 3, 3', 4, 4'-benzophenone tetracarboxylic acid for efficient air filtration. *Appl. Surf. Sci.* **2020**, *533*, 147516.
208. Bonfim, D.P.; Cruz, F.G.; Bretas, R.E.; Guerra, V.G.; Aguiar, M.L. A sustainable recycling alternative: Electrospun PET-membranes for air nanofiltration. *Polymers* **2021**, *13*, 1166.
209. Sidheswaran, M.A.; Destailhats, H.; Sullivan, D.P.; Cohn, S.; Fisk, W.J. Energy efficient indoor VOC air cleaning with activated carbon fiber (ACF) filters. *Build. Environ.* **2012**, *47*, 357–367.
210. Ligotski, R.; Sager, U.; Schneiderwind, U.; Asbach, C.; Schmidt, F. Prediction of VOC adsorption performance for estimation of service life of activated carbon based filter media for indoor air purification. *Build. Environ.* **2019**, *149*, 146–156.
211. Swamy, G. Development of an indoor air purification system to improve ventilation and air quality. *Heliyon* **2021**, *7*, e08153.
212. de Almeida, D.S.; Martins, L.D.; Aguiar, M.L. Air pollution control for indoor environments using nanofiber filters: A brief review and post-pandemic perspectives. *Chem. Eng. J. Adv.* **2022**, *11*, 100330.

213. Buyukada-Kesici, E.; Gezmis-Yavuz, E.; Aydin, D.; Cansoy, C.E.; Alp, K.; Koseoglu-Imer, D.Y. Design and fabrication of nano-engineered electrospun filter media with cellulose nanocrystal for toluene adsorption from indoor air. *Mater. Sci. Eng. B* **2021**, *264*, 114953.
214. Kadam, V.; Truong, Y.B.; Schutz, J.; Kyrtzis, I.L.; Padhye, R.; Wang, L. Gelatin/ $\beta$ -cyclodextrin bio-nanofibers as respiratory filter media for filtration of aerosols and volatile organic compounds at low air resistance. *J. Hazard. Mater.* **2021**, *403*, 123841.
215. Hodgson, A.; Destailats, H.; Sullivan, D.; Fisk, W. Performance of ultraviolet photocatalytic oxidation for indoor air cleaning applications. *Indoor Air* **2007**, *17*, 305–316.
216. Mo, J.; Zhang, Y.; Xu, Q.; Lamson, J.J.; Zhao, R. Photocatalytic purification of volatile organic compounds in indoor air: A literature review. *Atmos. Environ.* **2009**, *43*, 2229–2246.
217. Zhong, L.; Haghighat, F. Modeling and validation of a photocatalytic oxidation reactor for indoor environment applications. *Chem. Eng. Sci.* **2011**, *66*, 5945–5954.
218. Soni, V.; Singh, P.; Shree, V.; Goel, V. *Effects of VOCs on Human Health, in Air Pollution and Control*; Springer: Berlin/Heidelberg, Germany, 2018; pp. 119–142.
219. Maung, T.Z.; Bishop, J.E.; Holt, E.; Turner, A.M.; Pfrang, C. Indoor air pollution and the health of vulnerable groups: A systematic review focused on particulate matter (PM), volatile organic compounds (VOCs) and their effects on children and people with pre-existing lung disease. *Int. J. Environ. Res. Public Health* **2022**, *19*, 8752.
220. Boyjoo, Y.; Sun, H.; Liu, J.; Pareek, V.K.; Wang, S. A review on photocatalysis for air treatment: From catalyst development to reactor design. *Chem. Eng. J.* **2017**, *310*, 537–559.
221. Arnawtee, W.H.; Jaleh, B.; Nasrollahzadeh, M.; Bakhshali-Dehkordi, R.; Nasri, A.; Orooji, Y. Lignin valorization: Facile synthesis, characterization and catalytic activity of multiwalled carbon nanotubes/kraft lignin/Pd nanocomposite for environmental remediation. *Sep. Purif. Technol.* **2022**, *290*, 120793.
222. Zan, L.; Wang, S.; Fa, W.; Hu, Y.; Tian, L.; Deng, K. Solid-phase photocatalytic degradation of polystyrene with modified nano-TiO<sub>2</sub> catalyst. *Polymer* **2006**, *47*, 8155–8162.
223. Almaie, S.; Vatanpour, V.; Rasoulifard, M.H. and Koyuncu, I. Volatile organic compounds (VOCs) removal by photocatalysts: A review. *Chemosphere* **2022**, *306*, 135655. <https://doi.org/10.1016/j.chemosphere.2022.135655>.
224. Boaretti, C.; Vitiello, G.; Luciani, G.; Lorenzetti, A.; Modesti, M.; Roso, M. Electrospun Active Media Based on Polyvinylidene Fluoride (PVDF)-Graphene-TiO<sub>2</sub> Nanocomposite Materials for Methanol and Acetaldehyde Gas-Phase Abatement. *Catalysts* **2020**, *10*, 1017.
225. Rajendran, S.; Hoang, T.K.; Trudeau, M.L.; Jalil, A.; Naushad, M.; Awual, M.R. Generation of novel npn (CeO<sub>2</sub>-PPy-ZnO) heterojunction for photocatalytic degradation of micro-organic pollutants. *Environ. Pollut.* **2022**, *292*, 118375.

**Disclaimer/Publisher's Note:** The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.