

Supporting Information

Study on the Performance and Corrosion-failure Process of Po-rous-titanium-based Coated Electrode (lubricants-1959038)

Li Jiamin^{1,2}, Chang Linhui^{1,2}, Chen Bumng^{1,2,3,*}, Huang Hui^{1,2,3} and Guo Zhongcheng^{1,2,3}

1 Faculty of Metallurgical and Energy Engineering, Kunming University of Science and Technology, Kunming 650093, China;

2 Research Center of Metallurgical Electrode Materials Engineering Technology, Yunnan Province, Kunming 650106, China;

3 Kunming Hendera Science and Technology Co., Ltd., Kunming, 650106, China

* Correspondence: Author: Bumng Chen; bumchen@kust.edu.cn

Supplementary Figures and Tables




Figure S1. BET analysis of porous Ti-sheet.

According to the BET test results, the specific surface area of the porous titanium sheet is $2.863 \times 10^{-2} \text{ m}^2/\text{g}$.