

Supplementary materials

In Figure S1, both in Co-9-9-At and Co-9-9-At-Harmonic, can be clearly seen that W is concentrated on γ' . On the other hand, γ is enriched of Co but Al is homogeneously distributed throughout γ/γ' structure.




Figure S1. EDX-TEM analysis example of Co9-9-At sample after aged heat treatment. Down: harmonic treated materials.