

Efficient catalytic degradation of methyl orange by Various ZnO-doped lignin-based carbons

Zhihao Tang¹, Yonggang Yang² and Weiqi Wei^{1, 2,*}

¹ Jiangsu Co-Innovation Center of Efficient Processing and Utilization of Forest Resources,

Nanjing Forestry University, Nanjing 210037, China ; tangzhihao@njfu.edu.cn

² School of Environmental & Resource Science, Shanxi University, Taiyuan 030006,

China; m18352353192@163.com

* Correspondence: wqwei@njfu.edu.cn (Weiqi Wei)

Table S1. The specific surface area, total pore volume and average pore diameter of ZnO and LC_{AL}/ZnO, LC_{OL}/ZnO and LC_{SL}/ZnO.

Sample Name	BET surface area (m ² /g)	Total pore volume (cm ³ /g)	Average pore diameter (nm)
ZnO	24.8436	10.061295	28.2653
LC _{AL} /ZnO	52.5159	10.114030	16.3155
LC _{OL} /ZnO	64.4977	20.134970	17.4985
LC _{SL} /ZnO	79.6220	30.042036	6.8782




Figure S1. The effect of pH (a b & c) and catalyst dosage (d e & f) on MO photodegradation.