

# Microstructural Characterization and Magnetic, Dielectric, and Transport Properties of Hydrothermal La<sub>2</sub>FeCrO<sub>6</sub> Double Perovskites

## Section S1-Theoretical $M_S$ value of the LFCO powders and their ASD content determination

To assess the theoretical  $M_S$  value of the LFCO powders based on an intuitive ionic model, one should take into account of the different oxide states of Fe and Cr ions and their relative amount ratios, as revealed by the XPS spectra. Here, the molar percentage ratios of [Fe<sup>2+</sup>]/[Fe<sup>3+</sup>] and [Cr<sup>3+</sup>]/[Cr<sup>4+</sup>] were 18%:82% and 74%:26%, respectively. The  $M_S$  value of the LFCO powders is evaluated based on the following Equations (S1-S2) and the electronic configurations of Fe<sup>2+</sup> ( $3d^6$ ,  $t_{2g}^4 e_g^2$ ;  $\mu_{Fe^{2+}} = 4.90 \mu_B$ ), Fe<sup>3+</sup> ( $3d^5$ ,  $t_{2g}^3 e_g^2$ ;  $\mu_{Fe^{3+}} = 5.92 \mu_B$ ), Cr<sup>3+</sup> ( $3d^3$ ,  $t_{2g}^3 e_g^0$ ;  $\mu_{Cr^{3+}} = 3.87 \mu_B$ ), and Cr<sup>4+</sup> ions ( $3d^2$ ,  $t_{2g}^2 e_g^0$ ;  $\mu_{Cr^{4+}} = 2.83 \mu_B$ ). In addition, the AFM coupling between the Fe and Cr ions is considered and the molar ratio of Fe:Cr is 1:1 at the B-sites. Thus,

$$\langle m_{Fe} \rangle = 4.90 \times 18\% + 5.92 \times 82\% = 5.74 \mu_B/\text{f.u.} \quad (\text{S1})$$

$$\langle m_{Cr} \rangle = 3.87 \times 74\% + 2.83 \times 26\% = 3.60 \mu_B/\text{f.u.} \quad (\text{S2})$$

$$M_S = \langle m_{Fe} \rangle - \langle m_{Cr} \rangle = 2.14 \mu_B/\text{f.u.} \quad (\text{S3})$$

In comparison with the above theoretical  $M_S$  ( $= 2.14 \mu_B/\text{f.u.}$ ), the experimental  $M_S = 0.31 \mu_B/\text{f.u.}$  at 5 K, is much smaller due to the existence of large amounts of ASDs in the LFCO powders. The ASD content in the LFCO powders can be assessed by Equation (S4) [63]:

$$ASD = \frac{(1 - \frac{M_S^{exp}}{M_S^{cal}})}{2} \quad (\text{S4})$$

where  $M_S^{cal}$  is the theoretical  $M_S$  value, and  $M_S^{exp}$  the experimental one. The ASD content was calculated to 42.8%, which reflected that the B-site ordering degree ( $\eta$ ) of the LFCO powders was much smaller (14.4%), as described by Equation (S5) [64]:

$$\eta = 1 - 2 * ASD \quad (\text{S5})$$

## Section S2- Effective magnetic moments ( $\mu_{eff}$ ) and theoretical magnetic moment ( $\mu_{cal}$ )

By using the CW parameter  $C$  the effective magnetic moments ( $\mu_{eff}$ ) in the PM phase can be calculated as 6.64  $\mu_B/\text{f.u.}$  (@ 500 Oe) by the following Equation (S6) [65]:

$$\mu_{eff} = \sqrt{\frac{3k_B C}{N_A \mu_B^2}} = 2.828 \sqrt{C} \quad (\text{S6})$$

As compared with the  $\mu_{eff}$ , the theoretical magnetic moment,  $\mu_{cal}$  (per formula unit) of the La<sub>2</sub>Fe<sub>0.18</sub>Fe<sub>0.82</sub>Cr<sub>0.74</sub>Cr<sub>0.26</sub>O<sub>6</sub> is determined to be 6.80  $\mu_B/\text{f.u.}$  by using Equation (S7) [66]:

$$\mu_{cal} = \sqrt{0.18 \times \mu_{Fe^{2+}}^2 + 0.82 \times \mu_{Fe^{3+}}^2 + 0.74 \times \mu_{Cr^{3+}}^2 + 0.26 \times \mu_{Cr^{4+}}^2} \quad (\text{S7})$$

where the effective magnetic moments for the Fe<sup>2+</sup> ( $\mu_{Fe^{2+}} = 4.90 \mu_B$ ), Fe<sup>3+</sup> ( $\mu_{Fe^{3+}} = 5.92 \mu_B$ ), Cr<sup>3+</sup> ( $\mu_{Cr^{3+}} = 3.87 \mu_B$ ), and Cr<sup>4+</sup> ( $\mu_{Cr^{4+}} = 2.83 \mu_B$ ) ions are used [67].

**Table S1** Refined crystal structural parameters (space group, unit cell parameters, average bond lengths and bond angles), structural tolerance factor ( $t$ ), reliability factors, and average crystallite size as well as the magnetic data ( $M_s$ ,  $M_r$ ,  $H_C$ ,  $T_N$ , irreversibility temperature  $T_{irr}$ , Curie-Weiss constant  $C$  and paramagnetic Curie-Weiss temperature  $\theta_p$ , effective paramagnetic moment,  $\mu_{eff}$  calculated from Curie-Weiss constant  $C$ , and theoretically calculated magnetic moment,  $\mu_{cal}$  of the hydrothermal LFCO oxides.

Materials parameters		Measured data for the hydrothermal LFCO oxides									
Space group	<i>Pnma</i>										
Unit cell parameters	$a = 5.5293(6) \text{ \AA}$ , $b = 7.8192(0) \text{ \AA}$ , $c = 5.5408(9) \text{ \AA}$ , $\alpha = \beta = \gamma = 90^\circ$ , $V = 239.56(7) \text{ \AA}^3$										
Cr-O bond length ( $\text{\AA}$ )											
Cr <sub>1</sub> -O <sub>1</sub>	1.9928(2)										
Cr <sub>1</sub> -O <sub>2</sub>	1.9918(1)										
Cr <sub>1</sub> -O	1.9923(1)										
Fe-O bond length ( $\text{\AA}$ )											
Fe <sub>1</sub> -O <sub>1</sub>	1.9928(2)										
Fe <sub>1</sub> -O <sub>2</sub>	1.9918(1)										
Fe <sub>1</sub> -O	1.9923(1)										
< $\angle$ Fe-O <sub>i</sub> -Cr>											
bond angle ( $^\circ$ )	158.559(3)										
$\angle$ Fe <sub>1</sub> -O <sub>1</sub> -Cr <sub>1</sub>	157.529(2)										
$\angle$ Fe <sub>1</sub> -O <sub>2</sub> -Cr <sub>1</sub>	158.528(3)										
Structural tolerance factor ( $t$ )	0.961 calculated by $t = \frac{r_{La^{3+}} + r_{O^{2-}}}{\sqrt{2} \left( \frac{r_{Cr^{3+}} + r_{Fe^{3+}}}{2} + r_{O^{2-}} \right)}$										
Reliability factors	$R_{wp} = 6.03\%$ ; $R_p = 5.98\%$ ; $\chi^2 = 2.32$										
Average crystallite size (nm)	41 nm calculated by Scherrer formula (Eq. (1))										
Magnetic data	2 K			$T_N$	$T_B$	$T_C$	$\theta_p$	$T_{irr}$	$C @ 500 \text{ Oe}$	$\mu_{eff}$	$\mu_{cal}$
	$M_s$	$M_r$	$H_c$								
	( $\mu_B/\text{f.u.}$ )	( $\mu_B/\text{f.u.}$ )	(kOe)								
	0.31	0.021	8.0	10	113	200	-441	295	5.51	6.64	6.80

**Table S2** Species, peak positions and percentage molar ratios obtained from the peak fittings of Fe 2p<sub>3/2</sub>, Cr 2p<sub>3/2</sub> and O 1s XPS spectra of the hydrothermal LFCO powders and the effective oxidation states of the Fe and Cr elements.

XPS results		Hydrothermal LFCO powders		
		Species	Position (eV)	Percentage molar ratio
	Fe 2p <sub>3/2</sub>	Fe <sup>2+</sup>	710.15	[Fe <sup>2+</sup> ]/[Fe <sup>3+</sup> ] = 18%:82%
		Fe <sup>3+</sup>	711.41	
XPS spectra	Cr 2p <sub>3/2</sub>	Species	Position	Percentage molar ratio
		Cr <sup>3+</sup>	576.25	[Cr <sup>3+</sup> ]:[Cr <sup>4+</sup> ] = 74%:26%
		Cr <sup>4+</sup>	578.90	
	O 1s	Species	Position	Percentage molar ratio
		O <sub>α</sub>	529.42	[O <sub>α</sub> ]:[O <sub>β</sub> ] = 46%: 54%
		O <sub>β</sub>	531.70	
Effective oxide states of Fe and Cr elements				Fe element: + 2.82
				Cr element: + 3.26

## References

63. Pal, S.; Govinda, S.; Goyal, M.; Mukherjee, S.; Pal, B.; Saha, R.; Sundaresan, A.; Jana, S.; Karis, O.; Freeland, J.W.; et al. Effect of anti-site disorder on magnetism in La<sub>2</sub>NiMnO<sub>6</sub>. *Phys. Rev. B* **2018**, *97*, 165137.
64. Moritomo, Y.; Shimamoto, N.; Xu, S.; Machida, A.; Nishibori, E.; Takata, M.; Sakata, M.; Nakamura, A. Effects of B-site disorder in Sr<sub>2</sub>FeMoO<sub>6</sub> with double perovskite structure. *J. Appl. Phys.* **2001**, *40*, L672–L674.
65. Rogado, N.S.; Li, J.; Sleight, A.W.; Subramanian, M.A. Magnetocapacitance and magnetoresistance near room temperature in a ferromagnetic semiconductor: La<sub>2</sub>NiMnO<sub>6</sub>. *Adv. Mater.* **2005**, *17*, 2225–2227.
66. Taguchi, H. Relationship between crystal structure and electrical properties of Nd(Cr<sub>1-x</sub>Fe<sub>x</sub>)O<sub>3</sub>. *J. Solid State Chem.* **1997**, *131*, 108–114.
67. Buschow, K.H.J.; Boer, F.R. *Physics of Magnetism and Magnetic Materials*; Springer: Berlin/Heidelberg, Germany, 2003.