

Formulation and Characterization of Curcumin Niosomes: Antioxidant and Cytotoxicity Studies


Supplementary Figure-S1

A. Size

Results

	Size (d.nm):	% Intensity:	St Dev (d.n...
Z-Average (d.nm): 168.4	Peak 1: 146.0	100.0	55.08
Pdl: 0.150	Peak 2: 0.000	0.0	0.000
Intercept: 0.609	Peak 3: 0.000	0.0	0.000
Result quality : Good			

B. Surface charge



Results

	Mean (mV)	Area (%)	St Dev (mV)
Zeta Potential (mV): -50.6	Peak 1: -50.6	100.0	7.81
Zeta Deviation (mV): 7.81	Peak 2: 0.00	0.0	0.00
Conductivity (mS/cm): 0.740	Peak 3: 0.00	0.0	0.00
Result quality : Good			




Figure S1. (A) Size distribution; (B) Surface charge of curcunosomes