

Supplementary Materials:

Influence on elastic wave propagation behavior in polymers composites: An analysis of inflection phenomena

Guoqiang Luo^{1,2}, Pu Cheng², Yin Yu³, Xiangwei Geng², Yue Zhao², Yulong Xia², Ruizhi Zhang^{2,3,*}, Qiang Shen²

¹ Chaozhou Branch of Chemistry and Chemical Engineering Guangdong Laboratory, Chaozhou 521000, China

² State Key Lab of Advanced Technology for Materials Synthesis and Processing, Wuhan University of Technology, Wuhan 430070, China

³ National Key Laboratory of Shock Wave and Detonation Physics, Institute of Fluid Physics, China Academy of Engineering Physics, Mianyang 621900, China

* Correspondence: zhangrz1991@gmail.com; Tel.: +86-130-3514-9005




Figure S1. C.T. Scan results for Cu/PMMA composites

Table S1. Preparation and actual content of Cu/PMMA composites

Design content (vol. %)	Particle size (μm)	Mixing temperature ($^{\circ}\text{C}$)	Mixing Time (min)	Hot pressing temperature ($^{\circ}\text{C}$)	Hot pressing times (min)	Actual content (vol. %)	Error (%)
	1					29.27	2.43
30	10	210	20	200	70	29.77	0.77
	100					29.14	2.87
	1					40.12	-0.30
40	10	210	20	200	70	40.71	-1.78
	100					41.28	-3.20
	1					53.74	2.29
55	10	210	20	200	70	54.22	1.42
	100					53.76	2.25
	1					65.22	-0.34
65	10	220	20	210	100	66.78	-2.74
	100					67.01	-3.09