


Supporting Information

Sterically induced enhancement in electrochemical stability of salen type cathode materials

Julia V. Novoselova [1], Evgenii V. Beletskii [2], Daniil A. Lukyanov [1], Sofya S. Filippova[1], Uliana M. Rodionova[1], Vladimir V. Sizov [1], Elena V. Alekseeva [1,*], Oleg V. Levin [1]

Table S1. Contact angles of wetting polymers with H_2O.		
poly[Ni(Salen)]	poly[Ni(ketoSalen)]	poly[Ni(Salpn-1,2)]
35°	33°	31°
		
poly[Ni(Saldmen)]	poly[Ni(Saltmen)]	
28°	63°	
