

Table S1. CP characterization after organosolv treatment.

Run	Cellulose	Hemicellulose	Lignin
1	95.93%	0.00%	4.07%
2	78.05%	0.00%	21.95%
3	87.06%	0.06%	12.88%
4	77.82%	2.74%	19.44%
5	95.71%	0.03%	4.26%
6	92.67%	0.00%	7.33%
7	92.47%	0.03%	7.50%
8	90.38%	0.00%	9.62%
9	90.58%	0.00%	9.42%
10	91.09%	0.08%	8.83%
11	93.91%	0.01%	6.08%
12	93.33%	0.01%	6.66%
13	81.77%	8.20%	10.03%
14	94.09%	0.00%	5.91%
15	85.36%	2.29%	12.35%
17	92.79%	0.00%	7.21%
18	90.97%	0.00%	9.03%
19	97.50%	0.00%	2.50%
20	90.23%	0.00%	9.77%