Supplementary material

Modification of freezing point for hydrogel extinguishant and its effect on comprehensive properties in simulated forest fire rescue

Ziwei Han 1&, Peiyao Chen 4&, Meifang Hou 1*, Qianqian Li 2, 3*, Guijin Su 2, 3, Jing Meng 2, 3, Bin Shi 2, 3 and Jie Deng 4

1 College of Ecological Technology and Engineering, Shanghai Institute of Technology, Shanghai 201400, China; hanziwei2021@163.com (Z.H.)

2 Tianjin Fire Research Institute of MEM, Tianjin 300381, PR China; chenpeiyao@tfri.com.cn (P.L); 867146388@qq.com (J.D.)

3 Key Laboratory of Environmental Nanotechnology and Health Effects, Research center for Eco-Environmental Sciences, Chinese Academy of Sciences, Beijing 100085, China; gjsu@rcees.ac.cn (G.S.); jingm@rcees.ac.cn (J.M.); binshi@rcees.ac.cn (B.S.)

4 University of Chinese Academy of Sciences, Beijing 100049, China

* Correspondence: qqli@rcees.ac.cn (Q.L.); mfhou@sit.edu.cn (M.H.)

Supplementary materials

Table S1 The Characterization of the data of blank and 1# hydrogel extinguishant.

Sample	Adhesion mass (g)	Flame retardance time (s)	Viscosity (cP)	Freezing point (◦C)
Blank control	/	4.3s	/	/
1# extinguishant (0.5%)	3.15	62.8	541	-0.3