Supplementary Information

Tuning the Catalytic Water Oxidation Activity through Structural Modifications of High-Nuclearity Mn-oxo Clusters [$Mn_{18}M$] (M = Sr^{2+}, Mn^{2+})

Joaquín Soriano-López *, Rory Elliott, Amal C. Kathalikkattil, Ayuk M. Ako and Wolfgang Schmitt *

School of Chemistry & SFI AMBER Centre, Trinity College, University of Dublin, 999014 Dublin, Ireland; relliot@tcd.ie (R.E.); amalcherian@gmail.com (A.C.K.); akomana12@gmail.com (A.M.A.)

* Correspondence: sorianoj@tcd.ie (J.S.-L.); schmittw@tcd.ie (W.S.)

Index	**Page**
Figure S1. FT-IR spectra of the freshly prepared **Mn_{18}Sr** (**a**) and **Mn_{19}** (**b**) complexes.	S2
Figure S2. Comparison of the Raman spectra obtained for the freshly developed **Mn_{18}Sr** (**a**) and **Mn_{19}** (**c**) complexes, and that for the recovered decomposition products identified as a catalytically inactive amorphous manganese-potassium carbonate-phosphate species (**b**,**d**).	S3
Figure S3. Calculation of the onset overpotential employing 30% **Mn_{18}Sr**/CP working electrodes. The onset overpotential was estimated from the intersection point between the tangent line of the Faradaic current at 1 mA cm^{-2} and the extrapolated line arising from the non-Faradaic current.	S4
Figure S4. Long-term chronopotentiometry measurements at applied current densities of (**a**) 1 mA cm^{-2} (red) and (**b**) 10 mA cm^{-2} (orange). The experiments were performed in an H-cell using a 50 mM KP_i aqueous buffer at pH = 7.2 using KNO_3 (1 M) as electrolyte.	S5



Figure S1. FT-IR spectra of the freshly prepared **$Mn_{18}Sr$** (**a**) and **Mn_{19}** (**b**) complexes.



Figure S2. Comparison of the Raman spectra obtained for the freshly developed **Mn18Sr** (**a**) and **Mn19** (**c**) complexes, and that for the recovered decomposition products identified as a catalytically inactive amorphous manganese-potassium carbonate-phosphate species (**b**,**d**).



Figure S3. Calculation of the onset overpotential employing 30% **Mn_{18}Sr**/CP working electrodes. The onset overpotential was estimated from the intersection point between the tangent line of the Faradaic current at 1 mA cm^{-2} and the extrapolated line arising from the non-Faradaic current.



Figure S4. Long-term chronopotentiometry measurements at applied current densities of (**a**) 1 mA cm^{-2} (red) and (**b**) 10 mA cm^{-2} (orange). The experiments were performed in an H-cell using a 50 mM KP_i aqueous buffer at pH = 7.2 using KNO_3 (1 M) as electrolyte.